
Urine collection bags —
Part 2:
Requirements and test methods

Poches de recueil d'urine —

Partie 2: Prescriptions et méthodes d'essai

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8669-2:1996

<https://standards.iteh.ai/catalog/standards/sist/f18fef22-47ad-454c-94a6-712241cb7260/iso-8669-2-1996>



Contents

Page

1	Scope	1
2	Normative reference	1
3	Definitions	1
4	Requirements	2
5	General test conditions	2
6	Test methods.....	3
7	Test reports	13
Annex		
A	Dimensions of urine collection bags	14

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 8669-2:1996

<https://standards.iteh.ai/catalog/standards/sist/f18fef22-47ad-454c-94a6-712241cb7260/iso-8669-2-1996>

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization

Case postale 56 • CH-1211 Genève 20 • Switzerland

Internet: central@isocs.iso.ch

X.400: c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

iTeh STANDARD PREVIEW

International Standard ISO 8669-2 was prepared by Technical Committee ISO/TC 173, *Technical systems and aids for disabled or handicapped persons*, Subcommittee SC 3, *Aids for ostomy and incontinence*.

This second edition cancels and replaces the first editions of ISO 8669-2:1988, ISO 8669-3:1990 and ISO 8669-4:1990, which have been technically revised.

ISO 8669 consists of the following parts, under the general title *Urine collection bags*:

- *Part 1: Vocabulary*
- *Part 2: Requirements and test methods*

Annex A forms an integral part of this part of ISO 8669.

Introduction

Users of this part of ISO 8669 are advised to consider the desirability of third-party certification of product conformity with this part of ISO 8669, based on testing and continuing surveillance, which may be coupled with assessment of a supplier's quality system against the appropriate standards in the ISO 9000 series.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 8669-2:1996

<https://standards.iteh.ai/catalog/standards/sist/f18fef22-47ad-454c-94a6-712241cb7260/iso-8669-2-1996>

Urine collection bags —

Part 2: Requirements and test methods

1 Scope

This part of ISO 8669 specifies performance requirements and test methods for open-ended and closed-ended urine collection bags of the following types:

- a) urine collection bags intended to be worn on the body (body-worn bags);
- b) urine collection bags intended to be used with a hanger or a floor stand (non-body-worn bags).

It does not apply to urostomy bags, urimeters and urine bags intended specifically for paediatric use.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

2 Normative reference

ISO 8669-2:1996

<https://standards.iteh.ai/catalog/standards/sist/f18fe22-47ad-454c-94a6-7b1b10101010/iso-8669-2-1996>

The following standard contains provisions which, through reference in this text, constitute provisions of this part of ISO 8669. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this part of ISO 8669 are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 8669-1:1988, *Urine collection bags — Part 1: Vocabulary*.

3 Definitions

For the purposes of this part of ISO 8669, the definitions given in ISO 8669-1 and the following definitions apply.

3.1 closed-ended urine collection bag: Flexible container for collecting urine, without an opening for drainage of the contents.

3.2 open-ended urine collection bag: Flexible container for collecting urine, with an opening for drainage of the contents.

3.3 rated volume: Capacity of the bag, expressed in millilitres, as stated by the manufacturer.

3.4 test volume: That volume on which is based the volume of liquid added, or the force applied, to a urine collection bag when performing tests to verify the strength and leakage resistance of the bag assembly (see 6.1).

4 Requirements

4.1 Rated volume

When measured by the method given in 6.1, the bag shall have a rated volume not larger than the test volume.

4.2 Freedom from leakage without load

When tested by the method given in 6.2, the bag shall not leak.

4.3 Freedom from leakage under load

When tested by the method given in 6.3, the bag shall not leak.

4.4 Freedom from leakage under impact

When tested by the method given in 6.4, the bag shall not leak.

4.5 Nonreturn valve

If a nonreturn valve is fitted, when tested by the method given in 6.5, the reflux flowrate shall not exceed 10 ml/min.

4.6 Strength of the attachment system

When the attachment system of bags provided with cutouts is tested by the method given in 6.6, none of the attachment points shall fail to support the bag.

When the attachment system of bags provided with a button and buttonhole system is tested by the method given in 6.7, none of the buttons and buttonholes shall fail to support the bag.

When bags provided with integral suspensory systems are tested by the method given in 6.8, no part of the integral suspensory system shall fail to support the bag.

4.7 Strength of attachment of the inlet tubing

When tested by the method given in 6.9, the inlet tubing shall not become detached from the bag.

4.8 Pressure/time required to initiate flow into the bag and filling rate

When tested by the method given in 6.10, the water shall start flowing into the bag within 1 min and the average filling rate shall be not less than 10 ml/s.

4.9 Dimensions

If dimensions are given, they shall be measured in accordance with annex A.

5 General test conditions

5.1 Temperature

The standard temperature for testing (atmosphere and reagent) shall be $23\text{ °C} \pm 2\text{ °C}$.

5.2 Test samples

Testing shall be carried out on product samples as supplied to the end user.

6 Test methods

6.1 Test volume

6.1.1 Principle

The urine collection bag is filled with water and the volume of water within the bag is measured.

6.1.2 Reagent

6.1.2.1 Tap water

6.1.3 Apparatus

6.1.3.1 Graduated cylinders, of capacities to suit the bags being tested and having a measurement accuracy of $\pm 2\%$.

6.1.3.2 Filling system, of arrangement and dimensions shown in figure 1.

To maintain a constant hydrostatic head, the rate of flow into the reservoir of the filling system shall be higher than the rate of the filling of the bag.

6.1.3.3 Stopwatch, or similar timing device.

6.1.4 Procedure

6.1.4.1 Cut the inlet tubing so that the reservoir tap is positioned as close as possible to the bag.

NOTE — For bags having extensible tubing, these should be drawn out to their maximum length before cutting.

6.1.4.2 Remove as much air as possible from the bag. Close the drainage tap afterwards.

NOTE — Most bags have a drainage tap through which air can be squeezed out.

6.1.4.3 Measure the distance between bottom and top of the bag (l_4 in figure A.1) and mark a horizontal line at $0,75 l_4$, measuring from the bottom of the bag.

6.1.4.4 Suspend a non-body-worn bag using the manufacturer's recommended suspension system. Suspend a body-worn bag freely in a vertical position, so that the volume of the bag is not restricted.

6.1.4.5 Using the filling system (6.1.3.2), ensure that the reservoir tap is closed, turn on the water supply (6.1.2.1) and adjust the hydrostatic head to $500 \text{ mm} \pm 5 \text{ mm}$. Connect the reservoir tap to the inlet tubing of the bag.

6.1.4.6 Open the reservoir tap and allow water to enter the bag, ensuring that no air is entrained.

6.1.4.7 When the water level inside the bag has risen to the $0,75 l_4$ line, start the stopwatch (6.1.3.3).


6.1.4.8 After 1 min but before 1 min 10 s, close the reservoir tap.

6.1.4.9 Visually inspect the bag to determine whether or not leakage has occurred. If leakage has occurred, deem the test invalid and repeat it, using a fresh bag if necessary.

6.1.4.10 Clamp the inlet tubing as close to the filling top surface of the bag as possible. Remove the bag from the filling system and empty the water from the bag into a graduated cylinder (6.1.3.1). Measure the volume, in millilitres, and record it as the test volume to an accuracy of $\pm 2\%$.

6.1.5 Test report

The test report shall contain the general information specified in clause 7, together with the test volume.



NOTE — $d \geq$ largest internal diameter of inlet tubing of bag.

Figure 1 — Filling system for determination of test volume

6.2 Freedom from leakage without load

6.2.1 Principle

The urine collection bag is filled with coloured water, positioned horizontally and examined for leakage. It is then suspended vertically and again inspected visually for leakage.

6.2.2 Reagents

6.2.2.1 Tap water

6.2.2.2 Coloured water, comprising tap water coloured by the addition of 0,3 g/l of erythrosin (E 127).

6.2.2.3 Absorbent material, white.

6.2.3 Apparatus

6.2.3.1 Graduated cylinder, as specified in 6.1.3.1.

6.2.3.2 Filling system, of arrangement and dimensions shown in figure 2.

Dimensions in millimetres




Figure 2 — Filling system for freedom of leakage test (a) and measurement of filling rate (b)

6.2.4 Procedure

6.2.4.1 Suspend a non-body-worn bag using the manufacturer's recommended suspension system. Suspend a body-worn bag freely, so that the volume of the bag is not restricted.

6.2.4.2 If the bag is fitted with a drainage tap, add a small volume of the water (6.2.2.1) into the bag, open the drainage tap and allow the bag to drain, and then fully open and close the drainage tap ten times. Empty the bag and close the tap.

6.2.4.3 Using the graduated cylinder and the filling system in figure 2 with a distance of $500 \text{ mm} \pm 5 \text{ mm}$ between the top of the bag and the bottom of the reservoir, add to the bag a volume of coloured water (6.2.2.2) equal to 75 % of the test volume (6.1.4.10), ensuring that no air is entrained.

6.2.4.4 Seal the inlet tubing and, if present, the air vent.

6.2.4.5 Place the absorbent material (6.2.2.3) on a flat surface. Remove the bag from the suspension system and place it horizontally on the absorbent material.

6.2.4.6 Leave the bag undisturbed for $17 \text{ h} \pm 1 \text{ h}$ and then visually inspect the bag and absorbent material for staining caused by leakage. If staining is observed, the urine collection bag under test is deemed to have failed.

6.2.4.7 Reposition the bag under test in a vertical position, as described in 6.2.4.1, above absorbent material.

6.2.4.8 Leave the bag undisturbed for $4 \text{ h} \pm 1 \text{ h}$, then visually inspect the bag and absorbent material for staining caused by leakage. If staining is observed, the urine collection bag under test is deemed to have failed.

6.2.5 Test report

The test report shall contain the general information specified in clause 7, together with a statement as to whether or not leakage was observed and, if so, from where the leakage occurred and at which orientation of the bag.

6.3 Freedom from leakage under load

6.3.1 Principle

Coloured water is added to the uring collection bag under test, which is then subjected to a compressive load between two parallel plates. The bag is then visually inspected for leakage.

6.3.2 Reagent

ISO 8669-2:1996

6.3.2.1 Coloured water, as specified in 6.2.2.2.

<https://standards.iteh.ai/catalog/standards/sist/f18fef22-47ad-454c-94a6-712241cb7260/iso-8669-2-1996>

6.3.2.2 Absorbent material, white.

6.3.3 Apparatus

6.3.3.1 Graduated cylinder, as specified in 6.1.3.1.

6.3.3.2 Filling system, of arrangement and dimensions shown in figure 2.

6.3.3.3 Flat, rigid plate, of length and width not less than those of the bag being tested.

6.3.3.4 Restraints, capable of allowing the plate to move freely in a vertical direction whilst remaining horizontal within a tolerance of $\pm 5^\circ$.

6.3.3.5 Weights, or other means of loading the plate, to produce total downward force of $200 \text{ N} \pm 10 \text{ N}$ on the bag.

6.3.3.6 Stopwatch, or similar timing device.

6.3.4 Procedure

6.3.4.1 Add coloured water (6.3.2.1) to the bag, as specified in 6.2.4.3.

6.3.4.2 Seal the inlet tubing and, if present, the air vent.

6.3.4.3 Place the absorbent material (6.3.2.2) on a horizontal, flat rigid surface. Place the bag horizontally on the absorbent material.

6.3.4.4 Place the flat, rigid plate (6.3.3.3) on the top of the bag, position the restraints (6.3.3.4) and load the plate gently with the weights (6.3.3.5) so that a total force of $200 \text{ N} \pm 10 \text{ N}$ is imposed on the bag.

6.3.4.5 Allow the force to act on the bag at least 1 min but not longer than 1 min 10 s. Remove the force and visually inspect the bag and the white absorbent material for staining caused by leakage. If staining is observed, the urine collection bag under test is deemed to have failed.

6.3.5 Test report

The test report shall contain the general information specified in clause 7, together with a statement as to whether leakage was observed, and if so, from where.

6.4 Freedom from leakage under impact

6.4.1 Principle

Water is added to the urine collection bag, which is then dropped on to a smooth, rigid surface. The bag is then visually inspected for leakage.

6.4.2 Reagent

6.4.2.1 Tap water.

6.4.3 Apparatus

6.4.3.1 Graduated cylinder, as specified in 6.1.3.1.

6.4.3.2 Filling system, of arrangement and dimensions shown in figure 2.

6.4.3.3 Smooth, rigid surface, for instance a ceramic floor or a heavy steel plate.

<https://standards.iteh.ai/catalog/standards/sist/f18fe22-47ad-454c-94a6-712241cb7260/iso-8669-2-1996>

6.4.4 Procedure

6.4.4.1 Using the graduated cylinder (6.4.3.1) and the filling system in figure 2 with a distance of $500 \text{ mm} \pm 5 \text{ mm}$ between the top of the bag and the bottom of the reservoir, add to the bag a volume of water (6.4.2.1) equal to 50 % of the test volume (see 6.1.4.10), ensuring that no air is entrained.

6.4.4.2 Seal the inlet tubing and, if present, the air vent.

6.4.4.3 Hold the bag so that the lowest edge is a distance of $500 \text{ mm} \pm 10 \text{ mm}$ above the smooth, rigid surface (6.4.3.3), and then drop the bag so that it strikes the surface with the bottom of the bag.

6.4.4.4 Visually inspect the bag for leakage.

6.4.4.5 Repeat 6.4.4.1 to 6.4.4.4 twice more, using a fresh bag each time, dropping them so that one

a) strikes the surface with one face of the bag

and the other

b) strikes the surface with one side edge of the bag.

6.4.5 Test report

The test report shall contain the general information specified in clause 7, together with a statement as to whether leakage was observed on any bag, and if so, which drop attitude caused the damage and where the leakage occurred.