
**Petroleum and natural gas industries —
Steel pipes for use as casing or tubing for
wells**

*Industries du pétrole et du gaz naturel — Tubes d'acier utilisés comme
cuvelage ou tubes de production dans les puits*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 11960:2001

[https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-
f313d50e3896/iso-11960-2001](https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001)



Reference number
ISO 11960:2001(E)

© ISO 2001

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 11960:2001

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

© ISO 2001

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	vi
Introduction	vii
1 Scope	1
2 Conformance.....	2
2.1 Normative references	2
2.2 Units of measurement	2
2.3 Tables and figures	2
3 Normative references	2
4 Terms, definitions, symbols and abbreviated terms.....	4
4.1 Terms and definitions	4
4.2 Symbols and abbreviated terms	8
5 Information to be supplied by the purchaser	9
5.1 Casing	9
5.2 Tubing	10
6 Process of manufacture.....	12
6.1 General.....	12
6.2 Heat treatment.....	12
6.3 Straightening.....	13
6.4 Traceability.....	13
7 Material requirements.....	14
7.1 Chemical composition	14
7.2 Tensile properties	14
7.3 Charpy V-notch test properties — General requirements.....	15
7.4 Charpy V-notch (CVN) — Absorbed energy requirements for coupling stock, coupling blanks and couplings.....	16
7.5 Charpy V-notch — Absorbed energy requirements for pipe	17
7.6 Charpy V-notch test — Absorbed energy requirements for casing and tubing accessories.....	19
7.7 Hardness maxima	20
7.8 Hardness variation — Grades C90, T95 and Q125	20
7.9 Process control — Grades C90, T95 and Q125	20
7.10 Hardenability — Minimum percentage martensite for quenched and tempered products.....	21
7.11 Grain size — Grades C90 and T95	21
7.12 Surface condition — Grades L80 9Cr and L80 13Cr	21
7.13 Flattening — Electric-welded pipe	21
7.14 Sulfide stress corrosion cracking (SSCC) test — Grades C90 and T95	21
8 Dimensions, masses, tolerances, pipe ends and defects	23
8.1 Labels and sizes	23
8.2 Dimensions and masses.....	23
8.3 Diameter.....	23
8.4 Wall thickness	24
8.5 Mass.....	24
8.6 Length	24
8.7 Casing jointers.....	24
8.8 Height and trim of electric-weld flash.....	24
8.9 Straightness	25
8.10 Drift requirements.....	25
8.11 Tolerances on dimensions and masses.....	26
8.12 Pipe ends	27

8.13	Defects	28
8.14	Coupling make-up and thread protection	29
9	Couplings.....	29
9.1	General requirements.....	29
9.2	Alternative grades or heat treatments	29
9.3	Process of manufacture — Groups 1, 2 and 3	30
9.4	Process of manufacture — Grade Q125	30
9.5	Mechanical properties	30
9.6	Dimensions and tolerances	31
9.7	Regular couplings.....	31
9.8	Special-clearance couplings — Groups 1, 2 and 3	31
9.9	Combination couplings	31
9.10	Reducing couplings.....	31
9.11	Seal-ring couplings.....	31
9.12	Special-bevel couplings — Groups 1, 2 and 3	32
9.13	Threading.....	32
9.14	Surface inspection.....	32
9.15	Measurement of imperfections.....	33
9.16	Repair and removal of imperfections and defects	33
9.17	Thread surface treatment — Grade Q125.....	33
9.18	Couplings and coupling blank protection — Grade Q125.....	33
10	Inspection and testing.....	33
10.1	Test equipment	33
10.2	Lot definition for testing of mechanical properties.....	34
10.3	Testing of chemical composition.....	34
10.4	Tensile tests	35
10.5	Flattening test	37
10.6	Hardness test	38
10.7	Impact test	41
10.8	Grain size determination — Grades C90 and T95	43
10.9	Hardenability — Grades C90 and T95	43
10.10	Sulfide stress cracking test — Grades C90 and T95	43
10.11	Metallographic evaluation — EW Grades P110 and Q125	43
10.12	Hydrostatic test.....	43
10.13	Dimensional testing.....	45
10.14	Visual inspection	47
10.15	Non-destructive examination (NDE)	48
11	Marking	53
11.1	General.....	53
11.2	Stamp marking requirements	54
11.3	Stencil marking requirements	55
11.4	Colour identification	55
11.5	Thread and end-finish marking — All groups.....	56
11.6	Pipe-threader marking requirements — All groups	56
12	Coating and protection.....	57
12.1	Coatings — All groups	57
12.2	Thread protectors	57
13	Documents.....	58
13.1	Electronic media — All groups.....	58
13.2	Certification — Groups 1, 2 and 3	58
13.3	Certification requirements — Grade Q125	58
13.4	Retention of records.....	58
14	Minimum facility requirements for various categories of manufacturer	58
14.1	Pipe mill	58
14.2	Processor.....	59
14.3	Threader.....	59
14.4	Coupling, pup-joint, and accessory manufacturer.....	59

Annex A (normative) Supplementary requirements	60
Annex B (normative) Purchaser inspection	72
Annex C (normative) Tables in SI units	73
Annex D (normative) Figures in SI (USC) units	136
Annex E (normative) Tables in USC units	158
Annex F (informative) Marking instructions for API licensees	217
Annex G (informative) Procedures used to convert from USC units to SI units	221
Bibliography	234

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 11960:2001](https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001)

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 11960 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum and natural gas industries*, Subcommittee SC 5, *Casing, tubing and drill pipe*.

This second edition replaces the first edition (ISO 11960:1996) which has been technically revised. It is the intent of TC 67 that the first and second editions of ISO 11960 both be applicable, at the user's option, for a period of six months after the date of publication of this second edition, after which the first edition will no longer be applicable.

Annexes A to E form a normative part of this International Standard. Annexes F and G are for information only.

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

Introduction

This International Standard is based on API 5CT (Specification for Casing and Tubing).

Users of this International Standard should be aware that further or differing requirements may be needed for individual applications. This International Standard is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This may be particularly applicable where there is innovative or developing technology. Where an alternative is offered, the vendor should identify any variations from this International Standard and provide details.

This International Standard includes requirements of various nature. These are identified by the use of certain verbal forms:

- SHALL is used to indicate that a provision is MANDATORY;
- SHOULD is used to indicate that a provision is not mandatory, but RECOMMENDED as good practice;
- MAY is used to indicate that a provision is OPTIONAL.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 11960:2001

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 11960:2001

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

Petroleum and natural gas industries — Steel pipes for use as casing or tubing for wells

1 Scope

1.1 This International Standard specifies the technical delivery conditions for steel pipes (casing, tubing, plain end casing liners and pup-joints) and accessories. This International Standard is applicable to the following connections in accordance with ISO 10422 or API Spec 5B:

- short round thread casing (STC);
- long round thread casing (LC);
- buttress thread casing (BC);
- extreme-line casing (XC);
- non-upset tubing (NU);
- external upset tubing (EU);
- integral joint tubing (IJ).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

For such connections, this International Standard specifies the technical delivery conditions for couplings and thread protection.

For pipes covered by this International Standard, the sizes, masses, wall thicknesses, grades and applicable end finishes are defined.

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

This International Standard may also be applied to tubulars with connections not covered by ISO/API standards.

1.2 The four groups of products to which this International Standard is applicable include the following grades of pipe:

- Group 1: All casing and tubing in Grades H, J, K and N;
- Group 2: All casing and tubing in Grades C, L, M and T;
- Group 3: All casing and tubing in Grade P;
- Group 4: All casing in Grade Q.

1.3 Casing sizes larger than Label 1: 4-1/2 but smaller than Label 1: 10-3/4 may be specified by the purchaser to be used in tubing service, see Tables C.1, C.24, C.30 and C.31 or Tables E.1, E.24, E.30 and E.31.

1.4 Supplementary requirements that may optionally be agreed between purchaser and manufacturer, for non-destructive examination, coupling blanks, upset casing, electric-welded casing, impact testing, seal ring couplings and certificates are given in annex A.

1.5 This International Standard is not applicable to threading requirements.

NOTE Dimensional requirements on threads and thread gauges, stipulations on gauging practice, gauge specifications, as well as instruments and methods for inspection of threads are given in ISO 10422 or API Spec 5B. Connections machined to either of these specifications are the same for practical purposes and are totally interchangeable.

2 Conformance

2.1 Normative references

In the interests of worldwide application of this International Standard, ISO/TC 67 has decided, after detailed technical analysis, that certain of the normative documents listed in clause 3 and prepared by ISO/TC 67 or other ISO Technical Committee are interchangeable in the context of the relevant requirement with the relevant document prepared by the American Petroleum Institute (API), the American Society for Testing and Materials (ASTM) or the American National Standards Institute (ANSI). These latter documents are cited in the running text following the ISO reference and preceded by “or”, for example “ISO XXXX or API YYYY”. Application of an alternative normative document cited in this manner will lead to the same results as the use of the preceding ISO reference. These documents are thus considered interchangeable in practice.

2.2 Units of measurement

In this International Standard, data are expressed in both the International System (SI) of units and the United States Customary (USC) system of units. For a specific order item, it is intended that only one system of units be used, without combining data expressed in the other system.

Products manufactured to specifications expressed in either of these unit systems shall be considered equivalent and totally interchangeable. Consequently, compliance with the requirements of this International Standard as expressed in one system provides compliance with requirements expressed in the other system.

For data expressed in the SI, a comma is used as the decimal separator and a space as the thousands separator. For data expressed in the USC system, a dot (on the line) is used as the decimal separator and a space as the thousands separator.

In the text, data in SI units are followed by data in USC units in brackets.

2.3 Tables and figures

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

Separate tables for data expressed in SI units and USC units are given in annex C and annex E respectively. For a specific order item, only one unit system shall be used.

Figures are contained in annex D and express data in both SI and USC units.

3 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 31-0, *Quantities and units — Part 0: General principles*

ISO 643, *Steels — Micrographic determination of the ferritic or austenitic grain size*

ISO 6506-1, *Metallic materials — Brinell Hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell Hardness test — Part 1: Test method (Scales A, B, C, D, E, F, G, H, K, N, T)*

ISO 6892, *Metallic materials — Tensile testing at ambient temperature*

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tensile/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9303, *Seamless and welded (except submerged arc-welded) steel tubes for pressure purposes — Full peripheral ultrasonic testing for the detection of longitudinal imperfections*

ISO 9304, *Seamless and welded (except submerged arc-welded) steel tubes for pressure purposes — Eddy current testing for the detection of imperfections*

ISO 9305, *Seamless steel tubes for pressure purposes — Full peripheral ultrasonic testing for the detection of transverse imperfections*

ISO 9402, *Seamless and welded (except submerged arc-welded) steel tubes for pressure purposes — Full peripheral magnetic transducer/flux leakage testing of ferromagnetic steel tubes for the detection of longitudinal imperfections*

ISO 9598, *Seamless steel tubes for pressure purposes — Full peripheral magnetic transducer/flux leakage testing of ferromagnetic steel tubes for the detection of transverse imperfections*

ISO 9764, *Electric resistance and induction welded steel tubes for pressure purposes — Ultrasonic testing of the weld seam for the detection of longitudinal imperfections*

ISO 10400, *Petroleum and natural gas industries — Formulae and calculation for casing, tubing, drill pipe and line pipe properties*

ISO 10422, *Petroleum and natural gas industries — Threading, gauging and thread inspection of casing, tubing and line pipe threads — Specification*

ISO 10474, *Steel and steel products — Inspection documents*

ISO 11484, *Steel tubes for pressure purposes — Qualification and certification of non-destructive testing (NDT) personnel*

ISO 13665, *Seamless and welded steel tubes for pressure purposes — Magnetic particle inspection of the tube body for the detection of surface imperfections*

ISO 13678, *Petroleum and natural gas industries — Evaluation and testing of thread compounds for use with casing, tubing and line pipe*

ISO/TR 9769, *Steel and iron — Review of available methods of analysis*

ANSI-ASNT SNT-TC-1A:1984, *Personnel qualifications and certification in non-destructive testing*

ANSI-NACE TM0177:1996, *Laboratory testing of metals for resistance to sulfide stress cracking at ambient temperature in H₂S environment*

API Bul 5C2, *Bulletin on performance properties of casing, tubing and drill pipe*

API Bul 5C3, *Bulletin on formulas and calculations for casing, tubing, drill pipe and line pipe properties (plus Supplement 1)*

API RP 5A3, *Bulletin on thread compounds for casing, tubing and line pipe*

API Spec 5B, *Specification for threading, gauging and thread inspection of casing, tubing and line pipe threads*

API Std 5T1, *Imperfection technology*

ASTM A370, *Standard test methods and definitions for mechanical testing of steel products*

ASTM A751, *Methods, practices and definitions for chemical analysis of steel products*

ASTM A941, *Terminology relating to steel, stainless steel, related alloys and ferro-alloys*

ASTM E4, *Practices for load verification of testing machines*

ASTM E10, *Standard method of test for Brinell hardness of metallic materials*

ASTM E18, *Standard methods of test for Rockwell hardness and Rockwell superficial hardness of metallic materials*

ASTM E23, *Standard test methods for notched bar impact testing of metallic materials*

ASTM E29, *Practice for using significant digits in test data to determine conformance with specifications*

ASTM E83, *Standard practice for verification and classification of extensometers*

ASTM E112, *Methods for determining average grain size*

ASTM E213, *Standard practice for ultrasonic examination of metal pipe and tubing*

ASTM E273, *Standard practice for ultrasonic examination of longitudinal welded pipe and tubing*

ASTM E309, *Standard practice for eddy-current examination of steel tubular products using magnetic saturation*

ASTM E570, *Standard practice for flux leakage examination of ferro-magnetic steel tubular products*

ASTM E709, *Standard practice for magnetic particle examination*

iTech STANDARD PREVIEW
(standards.iteh.ai)

ISO 11960:2001

4 Terms, definitions, symbols and abbreviated terms

4.1 Terms and definitions

For the purposes of this International Standard, the terms and definitions in ASTM A941 for heat treatment operations and the following apply.

4.1.1

carload

quantity of pipe loaded on a railway car for shipment from the pipe-making facilities

4.1.2

casing

pipe run from the surface and intended to line the walls of a drilled well

4.1.3

casing and tubing accessory

one-piece tubular section used in a pipe string to provide mechanical and pressure integrity within the pipe string and facilitate the performance of some other function required of that pipe string

NOTE Examples of accessories are: crossover connectors, swages, nipples, flow couplings, blast joints, etc. Accessories exclude the other tubular products specifically defined in this International Standard or products included in other ISO (API) specifications.

4.1.4

connection

threaded assembly of tubular components

4.1.5**controlled cooling**

cooling from an elevated temperature in a pre-determined manner to avoid hardening, cracking or internal damage, or to produce a desired microstructure or mechanical properties

4.1.6**coupling**

internally threaded cylinder for joining two lengths of threaded pipe

4.1.7**coupling blank**

unthreaded material used to produce an individual coupling

4.1.8**coupling stock**

tubular used for the manufacture of coupling blanks

4.1.8**defect**

imperfection of sufficient magnitude to warrant rejection of the product based on criteria defined in this International Standard

4.1.9**electric-welded pipe**

pipe having one longitudinal seam formed by electric-resistance or electric-induction welding, without the addition of filler metal, wherein the edges to be welded are mechanically pressed together and the heat for welding is generated by the resistance to flow of electric current

4.1.10**handling tight**

sufficiently tight that the coupling cannot be removed except by the use of a wrench

4.1.11**heat**

metal produced by a single cycle of a batch melting process

4.1.12**heat analysis**

chemical analysis representative of a heat as reported by the metal producer

4.1.13**imperfection**

discontinuity in the product wall or on the product surface that can be detected by a NDE method included in Table C.61 or Table E.61 of this International Standard

4.1.14**inspection**

process of measuring, examining, testing, gauging or otherwise comparing a unit of product with the applicable requirements

4.1.15**inspection lot**

definite quantity of product manufactured under conditions that are considered uniform for the attribute to be inspected

4.1.16**inspection lot sample**

one or more units of product selected from an inspection lot to represent that inspection lot

4.1.17

inspection lot size

number of units of product in an inspection lot

4.1.18

interrupted quenching

quenching in which the pipe being quenched is removed from the quenching medium while the pipe is at a temperature substantially higher than that of the quenching medium

4.1.19

ISO/API threads

threads as specified in ISO 10422 or API Spec 5B

4.1.20

label 1

dimensionless designation for the size or specified outside diameter that may be used when ordering pipe

4.1.21

label 2

dimensionless designation for the mass per unit length or wall thickness that may be used when ordering pipe

4.1.22

length

piece of pipe that may be plain-end, threaded, or threaded and coupled, that is in accordance with the range requirements in Table C.30 or Table E.30 of this International Standard

4.1.23

linear imperfection

imperfection which includes, but is not limited to, seams, laps, cracks, plug scores, cuts and gouges

NOTE See API Std 5T1.

<https://standards.iteh.ai/catalog/standards/sist/3eee6ef3-090d-4dd3-b858-f313d50e3896/iso-11960-2001>

4.1.24

manufacturer

one or more of the following, depending on the context: pipe mill; processor; threader; coupling manufacturer, pup-joint manufacturer; accessory manufacturer

NOTE See clause 14.

4.1.25

non-linear imperfection

imperfection which includes, but is not limited to, pits and round bottom die stamping

NOTE See API Std 5T1.

4.1.26

pipe

casing, tubing, plain-end casing liners and pup-joints as a group

4.1.27

pipe mill

firm, company or corporation that operates pipe-making facilities

4.1.28

plain-end casing liner

casing provided unthreaded and with a wall thickness often greater than that specified for J55

4.1.29

processor

firm, company or corporation that operates facilities capable of heat-treating pipe made by a pipe mill

4.1.30 product

pipe, coupling, accessory, coupling stock or coupling blank, either individually or collectively as applicable

4.1.31 pup-joint

casing, tubing or plain-end casing liner of length shorter than Range 1

4.1.32 purchaser

party responsible for both the definition of requirements for a product order and for payment for that order

4.1.33 quench crack

crack in steel resulting from stresses produced during the transformation from austenite to martensite

NOTE This transformation is accompanied by an increase in volume.

4.1.34 seamless pipe

wrought steel tubular product made without a weld seam

NOTE It is manufactured by hot-working steel, and if necessary, by subsequently cold-working or heat-treating, or a combination of these operations, to produce the desired shape, dimensions and properties.

4.1.35 special end finish

threads with thread form and features, manufacturing specifications, dimensions, connection make-up and performance properties which are beyond the scope of this International Standard

4.1.36 special processes

final operations which are performed during pipe manufacturing that affect the attributes of product, except its chemistry and dimensions

NOTE These special processes are:

Manufacturing conditions	Special processes
Seamless, as-rolled	<ul style="list-style-type: none"> — Final re-heating practice and hot sizing or stretch-reducing. — If applicable, upsetting, coldfinishing. — Non-destructive examination
Seamless, heat-treated	<ul style="list-style-type: none"> — Heat treatment — Non-destructive examination
Electric-weld, as-rolled	<ul style="list-style-type: none"> — Sizing and seam welding — If applicable, seam heat treatment and upsetting — Non-destructive examination
Electric-weld, heat-treated	<ul style="list-style-type: none"> — Seam welding and full-body heat treatment — Non-destructive examination