
**Welding and allied processes —
Recommendations for joint
preparation —**

**Part 4:
Clad steels**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Soudage et techniques connexes — Recommandations pour la
préparation de joints —*

Partie 4: Aciers plaqués

ISO 9692-4:2003

[https://standards.iteh.ai/catalog/standards/sist/562d2878-1d47-43bf-b7ea-
2376ad185748/iso-9692-4-2003](https://standards.iteh.ai/catalog/standards/sist/562d2878-1d47-43bf-b7ea-2376ad185748/iso-9692-4-2003)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9692-4:2003

<https://standards.iteh.ai/catalog/standards/sist/562d2878-1d47-43bf-b7ea-2376ad185748/iso-9692-4-2003>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9692-4 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 7, *Representation and terms*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Throughout the text of this document, read "...this European Standard..." to mean "...this International Standard...".

[ISO 9692-4:2003](https://www.iso.org/standard/5628851.html)

ISO 9692 consists of the following parts, under the general title *Welding and allied processes — Recommendations for joint preparation*:

- *Part 1: Manual metal-arc welding, gas-shielded metal-arc welding, gas welding, TIG welding and beam welding of steels*
- *Part 2: Submerged arc welding of steels*
- *Part 3: Metal inert gas welding and tungsten inert gas welding of aluminium and its alloys*
- *Part 4: Clad steels*

The Bibliography provides a list of corresponding International and European Standards for which equivalents are not given in the text.

Contents

Foreword.....v

1 Scope1

2 Normative references1

3 Materials.....1

4 Types of joint preparation.....1

Table 1 — Joint preparation for clad steels welded from both sides.....2

Table 2 — Joint preparation for clad steels welded from both sides with cladding removal.....4

Table 3 — Joint preparation for clad steels welded from one side6

Table 4 – Joint preparation for clad steels incorporating a backing, insert or cover strip.....8

Bibliography10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 9692-4:2003](https://standards.iteh.ai/catalog/standards/sist/562d2878-1d47-43bf-b7ea-2376ad185748/iso-9692-4-2003)
<https://standards.iteh.ai/catalog/standards/sist/562d2878-1d47-43bf-b7ea-2376ad185748/iso-9692-4-2003>

Foreword

This document (EN ISO 9692-4:2003) has been prepared by Technical Committee CEN/TC 121, "Welding", the secretariat of which is held by DS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2004, and conflicting national standards shall be withdrawn at the latest by February 2004.

EN ISO 9692 "*Welding and allied processes – Recommendations for joint preparation*" consists of the following Parts:

- *Part 1: Manual metal-arc welding, gas-shielded metal-arc welding, gas welding, TIG Welding and beam welding of steels.*
- *Part 2: Submerged arc welding of steels.*
- *Part 3: Metal inert gas welding and tungsten inert gas welding of aluminium and its alloys.*
- *Part 4: Clad steels*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

ISO 9692-4:2003

<https://standards.iteh.ai/catalog/standards/sist/562d2878-1d47-43bf-b7ea-2376ad185748/iso-9692-4-2003>

1 Scope

This Part of this European Standard gives recommendations for types of joint preparation for clad steels.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revision of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1011-5, Welding – Recommendations for welding of metallic materials – Part 5: Welding of clad steels

3 Materials

Joint preparations recommended in this part of EN ISO 9692 are suitable for all types of weldable clad steels.

4 Types of joint preparation

The recommended types of joint preparation and dimensions are specified in Tables 1 to 4.

Details concerning welding recommendations for clad steels are given in EN 1011-5.

Figures showing the completed joint are given in Table 4 for clarity.

In certain cases, where the welding process may produce a brittle phase e.g. clad steels with cladding of titanium, zirconium and their alloys, a deviation from the weld preparations shown may be necessary.

<https://standards.iteh.ai/catalog/standards/sist/562d2878-1d47-43bf-b7ea-2376ad185748/iso-9692-4-2003>

Table 1 — Joint preparation for clad steels welded from both sides

Dimensions in millimetres





Ref. No.	Parent metal thickness t_1	Joint preparation	Cross section	Angle β	Gap b Radius R	Depth of root face c	Depth of preparation h	Cladding removal e	Remarks
1.1	$t_1 \leq 18$	Single V-butt weld With broad root face		$50^\circ < \alpha < 70^\circ$ $5^\circ < \beta < 15^\circ$	$4 < b < 8$ $b \leq 3$	$2 \leq c \leq 4$	—	—	Back grinding or machining from the clad side.
1.2		Single U-butt weld							

Table 1 — Joint preparation for clad steels welded from both sides (concluded)

Ref. No.	Parent metal thickness t_1	Joint preparation	Cross section	Angle β	Gap b Radius R	Depth of root face c	Depth of preparation h	Cladding removal e	Remarks
1.3	$t_1 > 18$	Double V-butt weld With broad root face		$50^\circ \leq \alpha \leq 70^\circ$ $5^\circ \leq \beta \leq 15^\circ$	$4 \leq R \leq 8$ $b \leq 3$	$2 \leq c \leq 6$	$h = 3$	—	
1.4		Single U-butt weld with V-root							
Key 1 Parent metal 2 Cladding t_2 Cladding thickness									