



SLOVENSKI STANDARD SIST EN ISO 2811-1:2011

01-november-2011

Nadomešča:

SIST EN ISO 2811-1:2002

SIST EN ISO 2811-1:2002/AC:2006

Barve in laki - Ugotavljanje gostote - 1. del: Metoda s piknometrom (ISO 2811-1:2011)

Paints and varnishes - Determination of density - Part 1: Pyknometer method (ISO 2811-1:2011)

Beschichtungsstoffe - Bestimmung der Dichte - Teil 1: Pyknometer-Verfahren (ISO 2811-1:2011)

Peintures et vernis - Détermination de la masse volumique - Partie 1: Méthode pycnométrique (ISO 2811-1:2011)

Ta slovenski standard je istoveten z: EN ISO 2811-1:2011

ICS:

87.040

Barve in laki

Paints and varnishes

SIST EN ISO 2811-1:2011

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 2811-1:2011](https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>

EUROPEAN STANDARD

EN ISO 2811-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2011

ICS 87.040

Supersedes EN ISO 2811-1:2001

English Version

Paints and varnishes - Determination of density - Part 1: Pyknometer method (ISO 2811-1:2011)

Peintures et vernis - Détermination de la masse volumique
- Partie 1: Méthode pycnométrique (ISO 2811-1:2011)

Beschichtungsstoffe - Bestimmung der Dichte - Teil 1:
Pyknometer-Verfahren (ISO 2811-1:2011)

This European Standard was approved by CEN on 19 February 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 2811-1:2011](https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST EN ISO 2811-1:2011](https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>

Foreword

This document (EN ISO 2811-1:2011) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2011, and conflicting national standards shall be withdrawn at the latest by September 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 2811-1:2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Endorsement notice

The text of ISO 2811-1:2011 has been approved by CEN as a EN ISO 2811-1:2011 without any modification.

[SIST EN ISO 2811-1:2011](https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 2811-1:2011](https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>

INTERNATIONAL STANDARD

ISO
2811-1

Second edition
2011-03-01

Paints and varnishes — Determination of density —

Part 1: Pyknometer method

Peintures et vernis — Détermination de la masse volumique —

Partie 1: Méthode pycnométrique

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 2811-1:2011](https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>



Reference number
ISO 2811-1:2011(E)

© ISO 2011

ISO 2811-1:2011(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 2811-1:2011](https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/700ad6ae-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2011

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

| | |
|-------------------------------------------------------------|----|
| Foreword | iv |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 4 Principle | 1 |
| 5 Temperature | 2 |
| 6 Apparatus | 2 |
| 7 Sampling | 2 |
| 8 Procedure | 2 |
| 8.1 General | 2 |
| 8.2 Determination | 3 |
| 9 Calculation | 4 |
| 10 Precision | 4 |
| 10.1 Repeatability limit, r | 4 |
| 10.2 Reproducibility limit, R | 4 |
| 11 Test report | 5 |
| Annex A (informative) Example of a calibration method | 6 |
| Annex B (informative) Temperature variation | 8 |
| Bibliography | 10 |

ISO 2811-1:2011(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 2811-1 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

This second edition cancels and replaces the first edition (ISO 2811-1:1997), which has been technically revised.

The main changes are the following.

- a) The unit for the density has been changed from grams per millilitre to grams per cubic centimetre, because this is the more common SI unit.
- b) The determination in duplicate has been changed to a single determination.
- c) The information on calibration procedure has been changed to an example only and the status of Annex B has been changed from normative to informative.
- d) The Hubbard pycnometer has been deleted because it is not used for paints and varnishes and their raw materials, but for bitumen and putty only (see ISO 3507).
- e) The dust-proof container has been deleted because it is not used in practice.
- f) The precision data has been updated by an interlaboratory test.
- g) The normative references have been updated.

ISO 2811 consists of the following parts, under the general title *Paints and varnishes — Determination of density*:

- *Part 1: Pycnometer method*
- *Part 2: Immersed body (plummet) method*
- *Part 3: Oscillation method*
- *Part 4: Pressure cup method*

Paints and varnishes — Determination of density —

Part 1: Pyknometer method

1 Scope

This part of ISO 2811 specifies a method for determining the density of paints, varnishes and related products using a metal or Gay-Lussac pyknometer.

The method is limited to materials of low or medium viscosity at the temperature of test. The Hubbard pyknometer (see ISO 3507) can be used for highly viscous materials.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1513, *Paints and varnishes — Examination and preparation of test samples*
<https://standards.iteh.ai/catalog/standards/sist/700ad6ac-3020-4888-bd1a-686a7136f18e/sist-en-iso-2811-1-2011>

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 density

ρ
mass divided by the volume of a portion of a material

NOTE It is expressed in grams per cubic centimetre.

4 Principle

A pyknometer is filled with the product under test. The density is calculated from the mass of the product in the pyknometer and the known volume of the pyknometer.