



Designation: D 912 – 81 (Reapproved 1999)

## Standard Specification for Cuprous Oxide for Use in Antifouling Paints<sup>1</sup>

This standard is issued under the fixed designation D 912; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last approval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This specification covers cuprous oxide for use in antifouling paints.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints<sup>2</sup>
- D 283 Test Methods for Chemical Analysis of Cuprous Oxide and Copper Pigments<sup>2</sup>

### 3. Composition

3.1 The pigment shall consist essentially of finely divided cuprous oxide and shall conform to the following requirements:

Cuprous oxide, min, %	97
Total copper, calculated as Cu, min, %	86
Total reducing power as Cu <sub>2</sub> O, min, %	97
Metals other than copper, max, %	0.5
Combined chlorides, calculated as Cl, and sulfates, calculated as SO <sub>4</sub> , max, %	0.5
Acetone-soluble matter, max, %	0.5
Stability: decrease in total reducing power after stability test, max, %	2.0

Coarse particles (total residue retained on a No. 325 (45- $\mu$ m) sieve), max, %	0.5
Total nitric acid insoluble residue on a No. 200 (75- $\mu$ m) sieve, max, %	0.1

### 4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples for each 10 000 lb (5000 kg), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities the samples from the same production unit to form a composite sample.

### 5. Test Methods

5.1 Tests shall be conducted in accordance with the following ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon between the purchaser and the seller.

5.2 *Coarse Particles*—Test Methods D 185.

5.3 *Cuprous Oxide Content, Total Copper, Reducing Power, Other Metals, Chlorides, Sulfates, Acetone, Soluble Matter, and Stability*—Methods D 283.

### 6. Keywords

6.1 antifouling paints; copper; cuprous oxide

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Oct. 30, 1981. Published December 1981. Originally published as D 912 – 47 T. Last previous edition D 912 – 65 (1975).

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.03.

*The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.*

*This standard is copyrighted by ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (http://www.astm.org).*