



SLOVENSKI STANDARD SIST EN ISO 6721-2:2008

01-september-2008

BUXca Yý U
SIST EN ISO 6721-2:1999

Dc`ja Yfb]a UHYf]U]!'8c`c Yj Ub^YX]bUa] b] `a Y Ubg_] `Ug]bcg]!'&"XY. `A YrcXU
g'rcfn]g_]a `b] Uca `fIGC`* +&/%& &\$\$, Ł

Plastics - Determination of dynamic mechanical properties - Part 2: Torsion-pendulum method (ISO 6721-2:2008)

Kunststoffe - Bestimmung dynamisch mechanischer Eigenschaften - Teil 2: Torsionspendel-Verfahren (ISO 6721-2:2008)

Plastiques - Détermination des propriétés mécaniques dynamiques - Partie 2: Méthode au pendule de torsion (ISO 6721-2:2008)

Ta slovenski standard je istoveten z: EN ISO 6721-2:2008

ICS:

83.080.01 Polimerni materiali na splošno Plastics in general

SIST EN ISO 6721-2:2008 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 6721-2:2008

<https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>

English Version

Plastics - Determination of dynamic mechanical properties - Part
2: Torsion-pendulum method (ISO 6721-2:2008)

Plastiques - Détermination des propriétés mécaniques
dynamiques - Partie 2: Méthode au pendule de torsion (ISO
6721-2:2008)

Kunststoffe - Bestimmung dynamisch mechanischer
Eigenschaften - Teil 2: Torsionspendel-Verfahren (ISO
6721-2:2008)

This European Standard was approved by CEN on 18 May 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 6721-2:2008](https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 6721-2:2008

<https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>

Foreword

This document (EN ISO 6721-2:2008) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2008, and conflicting national standards shall be withdrawn at the latest by December 2008.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6721-2:1996.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 6721-2:2008 has been approved by CEN as a EN ISO 6721-2:2008 without any modification.

[SIST EN ISO 6721-2:2008](https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 6721-2:2008

<https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>

**Plastics — Determination of dynamic
mechanical properties —**

**Part 2:
Torsion-pendulum method**

Plastiques — Détermination des propriétés mécaniques dynamiques —

Partie 2: Méthode au pendule de torsion

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 6721-2:2008

<https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 6721-2:2008](https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	1
4 Principle.....	1
5 Test apparatus	3
6 Test specimens	4
7 Number of specimens	5
8 Conditioning.....	5
9 Procedure	5
10 Expression of results	6
11 Precision.....	9
12 Test report	9
Annex A (normative) Influence of longitudinal force, W	10
Annex B (informative) Damping correction factor, F_d	11
Annex C (informative) Dimensional correction factor, F_c	12
Bibliography	14

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 6721-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical properties*.

This second edition cancels and replaces the first edition (ISO 6721-2:1994), of which it constitutes a minor revision. It also incorporates the Technical Corrigendum ISO 6721-2:1994/Cor.1:1995. Apart from the inclusion of the Corrigendum (which concerns the last sentence in the first paragraph in Annex C), the main changes are the updating of the references and the correction of ISO 6721-3 to ISO 6721-1 in Subclause 5.6.

ISO 6721 consists of the following parts, under the general title *Plastics — Determination of dynamic mechanical properties*:

- *Part 1: General principles*
- *Part 2: Torsion-pendulum method*
- *Part 3: Flexural vibration — Resonance-curve method*
- *Part 4: Tensile vibration — Non-resonance method*
- *Part 5: Flexural vibration — Non-resonance method*
- *Part 6: Shear vibration — Non-resonance method*
- *Part 7: Torsional vibration — Non-resonance method*
- *Part 8: Longitudinal and shear vibration — Wave-propagation method*
- *Part 9: Tensile vibration — Sonic-pulse propagation method*
- *Part 10: Complex shear viscosity using a parallel-plate oscillatory rheometer*

Plastics — Determination of dynamic mechanical properties —

Part 2: Torsion-pendulum method

1 Scope

This part of ISO 6721 specifies two methods (A and B) for determining the linear dynamic mechanical properties of plastics, i.e. the storage and loss components of the torsional modulus, as a function of temperature, for small deformations within the frequency range from 0,1 Hz to 10 Hz.

The temperature dependence of these properties, measured over a sufficiently broad range of temperatures (for example from -50 °C to $+150\text{ °C}$ for the majority of commercially available plastics), gives information on the transition regions (for example the glass transition and the melting transition) of the polymer. It also provides information concerning the onset of plastic flow. The two methods described are not applicable to non-symmetrical laminates (see ISO 6721-3, *Plastics — Determination of dynamic mechanical properties — Part 3: Flexural vibration — Resonance-curve method*). The methods are not suitable for testing rubbers, for which the user is referred to ISO 4664-2, *Rubber, vulcanized or thermoplastic — Determination of dynamic properties — Part 2: Torsion pendulum methods at low frequencies*.

SIST EN ISO 6721-2:2008

2 Normative references

<http://standards.iteh.ai/catalog/standards/sist/13b879a1-cfe9-434c-97da-33d7a3e4da1f/sist-en-iso-6721-2-2008>

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6721-1:2001, *Plastics — Determination of dynamic mechanical properties — Part 1: General principles*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 6721-1:2001, Clause 3, apply.

4 Principle

A test specimen of uniform cross-section is gripped by two clamps, one of them fixed and the other connected to a disc, which acts as an inertial member, by a rod. The end of the specimen connected to the disc is excited, together with the disc, to execute freely decaying torsional oscillations. The oscillation mode is that designated IV in ISO 6721-1:2001, Table 2, and the type of modulus is G_{t0} as defined in ISO 6721-1:2001, Table 3.

The inertial member is suspended either from the specimen (method A, see Figure 1) or from a wire (method B, see Figure 2). In the latter case, the wire is also part of the elastically oscillating system.