

SLOVENSKI STANDARD

SIST EN ISO 179-1:2010

01-september-2010

Nadomešča:

SIST EN ISO 179-1:2001

SIST EN ISO 179-1:2001/A1:2005

Polimerni materiali - Ugotavljanje udarne žilavosti pa Charpyju - 1. del: Preskus udarne žilavosti z neinstrumentalno metodo (ISO 179-1:2010)

Plastics - Determination of Charpy impact properties - Part 1: Non-instrumented impact test (ISO 179-1:2010)

Kunststoffe - Bestimmung der Charpy-Schlageigenschaften - Teil 1: Nicht instrumentierte Schlagzähigkeitsprüfung (ISO 179-1:2010)

Plastiques - Détermination des caractéristiques au choc Charpy - Partie 1: Essai de choc non instrumenté (ISO 179-1:2010)

Ta slovenski standard je istoveten z: EN ISO 179-1:2010

ICS:

83.080.01	Polimerni materiali na splošno	Plastics in general
-----------	--------------------------------	---------------------

SIST EN ISO 179-1:2010

en,fr

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 179-1:2010

<https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 179-1

June 2010

ICS 83.080.01

Supersedes EN ISO 179-1:2000

English Version

**Plastics - Determination of Charpy impact properties - Part 1:
Non-instrumented impact test (ISO 179-1:2010)**

Plastiques - Détermination des caractéristiques au choc
Charpy - Partie 1: Essai de choc non instrumenté (ISO 179-1:2010)

Kunststoffe - Bestimmung der Charpy-Schlageigenschaften - Teil 1: Nicht instrumentierte Schlagzähigkeitsprüfung (ISO 179-1:2010)

This European Standard was approved by CEN on 19 May 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 179-1:2010](https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
---------------	---

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 179-1:2010

<https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010>

Foreword

This document (EN ISO 179-1:2010) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2010, and conflicting national standards shall be withdrawn at the latest by December 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 179-1:2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 179-1:2010 has been approved by CEN as a EN ISO 179-1:2010 without any modification.

[SIST EN ISO 179-1:2010](https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010)
<https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 179-1:2010

<https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010>

INTERNATIONAL STANDARD

ISO
179-1

Second edition
2010-06-15

Plastics — Determination of Charpy impact properties —

Part 1: Non-instrumented impact test

Plastiques — Détermination des caractéristiques au choc Charpy —

Partie 1: Essai de choc non instrumenté

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 179-1:2010

<https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010>



Reference number
ISO 179-1:2010(E)

© ISO 2010

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 179-1:2010](https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/122b906b-91c0-4e39-b587-38d576d61834/sist-en-iso-179-1-2010>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2010

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Principle.....	3
5 Apparatus	3
5.1 Test machine.....	3
5.2 Micrometers and gauges	3
6 Test specimens.....	4
6.1 Preparation.....	4
6.1.1 Moulding and extrusion compounds	4
6.1.2 Sheets	4
6.1.3 Long-fibre-reinforced materials	4
6.1.4 Checking.....	7
6.1.5 Notching	7
6.2 Anisotropy.....	7
6.3 Shape and dimensions	8
6.3.1 Materials not exhibiting interlaminar shear fracture	8
6.3.2 Materials exhibiting interlaminar shear fracture (e.g. long-fibre-reinforced materials).....	9
6.4 Number of test specimens.....	9
6.5 Definition of span between specimen supports, L	10
6.6 Conditioning	11
7 Procedure	11
8 Calculation and expression of results	12
8.1 Unnotched specimens	12
8.2 Notched specimens.....	12
8.3 Statistical parameters	13
8.4 Significant figures	13
9 Precision.....	13
10 Test report.....	13
Annex A (informative) Additional methods for investigating the influence of surface effects.....	15
Annex B (informative) Precision data	17
Annex C (informative) Determining the notch tip radius using a CCD microscope	19
Bibliography.....	22

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 179-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 2, *Mechanical properties*.

This second edition cancels and replaces the first edition (ISO 179-1:2000), which has been technically revised. The main changes are as follows:

- a new subclause (6.5) has been added, defining the span between the specimen supports and indicating a convenient position at which it can be measured;
- a new annex, Annex C, has been added, giving a method of measuring the radius of the notch in a notched specimen.

This second edition also incorporates the Amendment ISO 179-1:2000/Amd.1:2005.

ISO 179 consists of the following parts, under the general title *Plastics — Determination of Charpy impact properties*:

- *Part 1: Non-instrumented impact test*
- *Part 2: Instrumented impact test*

Plastics — Determination of Charpy impact properties —

Part 1: Non-instrumented impact test

1 Scope

1.1 This part of ISO 179 specifies a method for determining the Charpy impact strength of plastics under defined conditions. A number of different types of specimen and test configurations are defined. Different test parameters are specified according to the type of material, the type of test specimen and the type of notch.

1.2 The method can be used to investigate the behaviour of specified types of specimen under the impact conditions defined and for estimating the brittleness or toughness of specimens within the limitations inherent in the test conditions. It can also be used for the determination of comparative data from similar types of material.

1.3 The method has a greater range of applicability than that given in ISO 180^[1] and is more suitable for the testing of materials showing interlaminar shear fracture or of materials exhibiting surface effects due to environmental factors.

1.4 The method is suitable for use with the following range of materials:

- rigid thermoplastic moulding and extrusion materials (including filled and reinforced compounds in addition to unfilled types) and rigid thermoplastics sheets;
- rigid thermosetting moulding materials (including filled and reinforced compounds) and rigid thermosetting sheets (including laminates);
- fibre-reinforced thermosetting and thermoplastic composites incorporating unidirectional or multi-directional reinforcements (such as mats, woven fabrics, woven rovings, chopped strands, combination and hybrid reinforcements, rovings and milled fibres) or incorporating sheets made from pre-impregnated materials (prepregs), including filled and reinforced compounds;
- thermotropic liquid-crystal polymers.

1.5 Notched samples are not normally suitable for use with rigid cellular materials, long-fibre-reinforced composites or thermotropic liquid-crystal polymers. In these cases, unnotched samples may be used.

1.6 The method is suited to the use of specimens moulded to the chosen dimensions, machined from the central portion of a standard multipurpose test specimen (see ISO 3167) or machined from finished or semifinished products such as mouldings, laminates and extruded or cast sheet.

1.7 The method specifies preferred dimensions for the test specimen. Tests which are carried out on specimens of different dimensions or with different notches, or specimens which are prepared under different conditions, might produce results which are not comparable. Other factors, such as the energy capacity of the apparatus, the impact velocity and the conditioning of the specimens can also influence the results. Consequently, when comparative data are required, these factors must be carefully controlled and recorded.

ISO 179-1:2010(E)

1.8 The method should not be used as a source of data for design calculations. Information on the typical behaviour of a material can be obtained, however, by testing at different temperatures, by varying the notch radius and/or the specimen thickness and by testing specimens prepared under different conditions.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing*

ISO 293, *Plastics — Compression moulding of test specimens of thermoplastic materials*

ISO 294-1, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 1: General principles, and moulding of multipurpose and bar test specimens*

ISO 294-3, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 3: Small plates*

ISO 295, *Plastics — Compression moulding of test specimens of thermosetting materials*

ISO 1268-11, *Fibre-reinforced plastics — Methods of producing test plates — Part 11: Injection moulding of BMC and other long-fibre moulding compounds — Small plates*

ISO 2602, *Statistical interpretation of test results — Estimation of the mean — Confidence interval*

ISO 2818, *Plastics — Preparation of test specimens by machining*

ISO 3167, *Plastics — Multipurpose test specimens*

ISO 10724-1, *Plastics — Injection moulding of test specimens of thermosetting powder moulding compounds (PMCs) — Part 1: General principles and moulding of multipurpose test specimens*

ISO 13802, *Plastics — Verification of pendulum impact-testing machines — Charpy, Izod and tensile impact-testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

Charpy unnotched impact strength

a_{cU}
impact energy absorbed in breaking an unnotched specimen, referred to the original cross-sectional area of the specimen

NOTE It is expressed in kilojoules per square metre (kJ/m²).

3.2

Charpy notched impact strength

a_{cN}
impact energy absorbed in breaking a notched specimen, referred to the original cross-sectional area of the specimen at the notch, where N = A, B or C, depending on the notch type (see 6.3.1.1.2)

NOTE It is expressed in kilojoules per square metre (kJ/m²).