



SLOVENSKI STANDARD

SIST EN 15771:2010

01-junij-2010

Steklasti in keramični emajli - Določevanje trdote površin na razenje po Mohsovi trdotni lestvici

Vitreous and porcelain enamels - Determination of scratch hardness of surface according to Mohs

Emails und Emailierungen - Bestimmung der Ritzhärte nach Mohs

Emaux vitrifiés - Détermination de la dureté superficielle suivant l'échelle de Mohs

Ta slovenski standard je istoveten z: EN 15771:2010

SIST EN 15771:2010
<https://standards.iteh.ai/catalog/standards/sist/fb59174-d74e-4af5-9544-7af976fb1771/sist-en-15771-2010>

ICS:

25.220.50 Emajlne prevleke Enamels

SIST EN 15771:2010

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15771:2010

<https://standards.iteh.ai/catalog/standards/sist/f4b59174-d74e-4af5-9544-7af976fb1771/sist-en-15771-2010>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 15771

March 2010

ICS 25.220.50

English Version

**Vitreous and porcelain enamels - Determination of surface
scratch hardness according to the Mohs scale**

Émaux vitrifiés - Détermination de la dureté superficielle
suivant l'échelle de Mohs

Emails und Emailierungen - Bestimmung der Ritzhärte
nach Mohs

This European Standard was approved by CEN on 13 February 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

SIST EN 15771:2010

<https://standards.iteh.ai/catalog/standards/sist/f4b59174-d74e-4af5-9544-7af976fb1771/sist-en-15771-2010>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle	4
5 Reference minerals	4
6 Test specimen	5
7 Procedure	5
8 Assessment of result	5
9 Test report	5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 15771:2010](https://standards.iteh.ai/catalog/standards/sist/f4b59174-d74e-4af5-9544-7af976fb1771/sist-en-15771-2010)

<https://standards.iteh.ai/catalog/standards/sist/f4b59174-d74e-4af5-9544-7af976fb1771/sist-en-15771-2010>

Foreword

This document (EN 15771:2010) has been prepared by Technical Committee CEN/TC 262 “Metallic and other inorganic coatings”, the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2010, and conflicting national standards shall be withdrawn at the latest by September 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 15771:2010

<https://standards.iteh.ai/catalog/standards/sist/f4b59174-d74e-4af5-9544-7af976fb1771/sist-en-15771-2010>

1 Scope

This European Standard specifies a method of test for determining the scratch hardness of the surface of vitreous and porcelain enamels.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 15206, *Vitreous and porcelain enamels — Production of specimens for testing enamel on sheet steel, sheet aluminium and cast iron*

3 Terms and definitions

For the purposes of this document, the following term and definition applies.

3.1
Mohs scale
hardness scale of minerals, characterising the scratch resistance of various minerals through the ability of a harder mineral to scratch a softer mineral

4 Principle

The scratch hardness on the Mohs scale of vitreous and porcelain enamels is determined by drawing certain minerals of defined hardness, on the Mohs scale, by hand over their surface.

5 Reference minerals

Reference minerals and their Mohs scale hardness are listed in Table 1.

Table 1 — Reference minerals and their Mohs scale hardness

Mineral	Mohs scale hardness
Talc	1
Gypsum	2
Calcite	3
Fluorspar	4
Apatite	5
Felspar	6
Quartz	7
Topaz	8
Corundum	9
Diamond	10

6 Test specimen

The test specimen shall be prepared in accordance with EN 15206.

7 Procedure

7.1 Place the test specimen of the enamel that is under test on a firm support with the vitreous and porcelain enamel coating uppermost.

7.2 By hand, draw across the surface of the test specimen a sharp edge of the reference mineral, starting with fluorspar, applying a uniform effort such that at the end of the test either the edge of the reference mineral or the surface of the test specimen is damaged. Scratch the surface of the test specimen two times with a sharp edge of the reference mineral.

7.3 Examine the test specimen visually for scratches.

7.4 If there are no scratches, repeat steps given in 7.1 to 7.3 with the reference mineral of the next highest Mohs scale hardness.

8 Assessment of result

For each test specimen note the mineral of highest Mohs scale hardness that produces no scratches.

In the case of a test specimen having variable scratch hardness, note the lowest Mohs scale hardness.

9 Test report

The test report shall include the following:

- a) all information necessary for identification of the test specimen;
- b) reference to this European Standard (EN 15771);
- c) reference minerals used;
- d) results of the test as specified in Clause 8, expressed as the Mohs scale hardness for each test specimen;
- e) any unusual features (anomalies) observed during the test;
- f) date of the test.