
Implants for surgery — Measurements of open-circuit potential to assess corrosion behaviour of metallic implantable materials and medical devices over extended time periods

Implants chirurgicaux — Mesurages sur de longues périodes du potentiel en circuit ouvert pour l'évaluation du comportement à la corrosion des matériaux métalliques et dispositifs médicaux implantables

(<https://standards.iteh.ai>)

Document Preview

ISO 16429:2004

<https://standards.iteh.ai/catalog/standards/iso/7b2973f4-6924-4ef7-81e6-282d0d88dc10/iso-16429-2004>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 16429:2004](https://standards.iteh.ai/catalog/standards/iso/7b2973f4-6924-4ef7-81e6-282d0d88dc10/iso-16429-2004)

<https://standards.iteh.ai/catalog/standards/iso/7b2973f4-6924-4ef7-81e6-282d0d88dc10/iso-16429-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Significance and application	2
4.1 Principle	2
4.2 Significance of the measurements	4
4.3 Application	4
5 Apparatus	5
6 Specimen preparation	5
6.1 Type of specimen	5
6.2 Surface preparation	6
6.3 Specimen mounting	6
7 Environmental conditions	6
7.1 General	6
7.2 Testing solution	6
7.3 Testing temperature	6
7.4 pH value	7
7.5 Aeration	7
7.6 Volume of testing solution	7
8 Test procedure	7
8.1 Set-up of test	7
8.2 Duration of test	7
8.3 Observations	7
9 Test report	8
Annex A (informative) Additional test solutions	9
Bibliography	10

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 16429 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[ISO 16429:2004](https://standards.iteh.ai/catalog/standards/iso/7b2973f4-6924-4ef7-81e6-282d0d88dc10/iso-16429-2004)

<https://standards.iteh.ai/catalog/standards/iso/7b2973f4-6924-4ef7-81e6-282d0d88dc10/iso-16429-2004>

Introduction

This International Standard was developed because, in contrast to polarization measurements which are well described in ASTM G5 [6] and literature, there is no standard available on typical open-circuit potential measurements over extended time periods.

Relating to corrosion behaviour of implant materials and surgical implant devices, the long-term electrochemical behaviour in the body environment is of interest.

Metal surfaces undergo spontaneous changes at their interface with an electrolytic environment to reach a state of equilibrium. Depending on the conditions, the corresponding physico-chemical and electrochemical reactions can be highly active and corrosive, or very sluggish and passive. For passivating metals such as those usually used for surgical implants, the formation and stability of the passive film is an important prerequisite for corrosion resistance of these materials, under given conditions.

With the measurement of the open-circuit potential over a longer time period, the spontaneous reaction to the environment (electrolyte) in the form of passivation or activation, the formation of a steady state potential and its stability can be assessed. Regarding surgical implant materials and devices, the measurements of these properties is of interest because they help to characterize implant material systems and to optimize processing, surface treatments and properties. Furthermore, measurements of the long-term open-circuit potential in combination with mechanical loading give information on the effect of mechanical, dynamic conditions on the electrochemical potential, passivity and corrosion behaviour.

This International Standard specifies conditions for the measurement of the open-circuit potential over extended periods of time. Isotonic 0,9 % NaCl (see 3.5) is used as the electrolyte (testing solution). This solution is related to body fluid in that it contains approximately the same concentration of Cl ions, and Cl ions are the most likely species in this solution to cause metal corrosion due to their aggressivity. For more stringent testing conditions, solutions with higher concentrations of Cl ions are given in Annex A.

[ISO 16429:2004](https://standards.iteh.ai/catalog/standards/iso/7b2973f4-6924-4ef7-81e6-282d0d88dc10/iso-16429-2004)

<https://standards.iteh.ai/catalog/standards/iso/7b2973f4-6924-4ef7-81e6-282d0d88dc10/iso-16429-2004>

