



Designation: G 110 – 92 (Reapproved 2003)^{ε1}

Standard Practice for Evaluating Intergranular Corrosion Resistance of Heat Treatable Aluminum Alloys by Immersion in Sodium Chloride + Hydrogen Peroxide Solution¹

This standard is issued under the fixed designation G 110; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Warning notes were editorially moved into main body text in October 2003.

1. Scope

1.1 This practice covers the procedures for immersion tests in sodium chloride + hydrogen peroxide solution. It is primarily for tests of wrought heat treatable aluminum alloys (2XXX and 7XXX) but may be used for other aluminum alloys, including castings. It sets forth the specimen preparation procedures and the environmental conditions of the test and the means for controlling them.

1.2 This practice is intended for evaluations during alloy development and for evaluating production where it may serve as a control test on the quality of successive lots of the same material (see MIL-H-6088 and U.S. Federal Test Method Std. 151b). Therefore strict test conditions are stipulated for maximum assurance that variations in results are attributable to lot-to-lot differences in the material being tested.

NOTE 1—This practice does not address sampling or interpretation or significance of results.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 1193 Specification for Reagent Water²

E 3 Methods of Preparation of Metallographic Specimens³

E 407 Test Methods for Microetching Metals and Alloys³

G 1 Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens⁴

G 15 Terminology Relating to Corrosion and Corrosion Testing⁴

G 67 Test Method for Determining the Susceptibility to Intergranular Corrosion of 5XXX Series Aluminum Alloys by Mass Loss After Exposure to Nitric Acid (NAMLT Test)⁴

G 69 Practice for Measurement of Corrosion Potentials of Aluminum Alloys⁴

2.2 Other Documents:

U.S. Military Specification MIL-H-6088, Heat Treatment of Aluminum Alloys⁵

U.S. Federal Test Method, Standard No. 151b, Method 822.1, Intergranular Corrosion Test for Aluminum Alloys⁵

3. Summary of Practice

3.1 This practice consists of immersing etched test specimens in a sodium chloride + hydrogen peroxide solution for 6 or more hours. After immersion, metallographic sections are examined to determine the extent of intergranular corrosion (see Terminology G 15).

4. Significance and Use

4.1 This practice is especially useful for evaluating the adequacy of quenching when performed on material in the as-quenched condition. The practice may also be used to study the effect of subsequent thermal processes (for example, paint or bonding cures) or of actual precipitation treatments on the inherent type of corrosion. Intergranular corrosion resistance of heat treatable aluminum alloys is often directly related to the quenching conditions applied after solution heat treatment and to the subsequent aging treatment.⁶

¹ This practice is under the jurisdiction of ASTM Committee G01 on Corrosion of Metals and is the direct responsibility of Subcommittee G01.05 on Laboratory Corrosion Tests.

Current edition approved October 1, 2003. Published October 2003. Originally approved in 1992. Last previous edition approved in 1997 as G 110 – 92 (1997).

² *Annual Book of ASTM Standards*, Vol 11.01.

³ *Annual Book of ASTM Standards*, Vol 03.01.

⁴ *Annual Book of ASTM Standards*, Vol 03.02.

⁵ Available from Standardization Documents Order Desk, Building 4, Section D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

⁶ Lifka, B. W., and Sprowls, D. O., "Significance of Intergranular Corrosion of High Strength Aluminum Alloy Products," *Localized Corrosion Cause of Metal Failure*, ASTM STP 516 (1972), pp. 120–144.