



Standard Test Method for Impact Strength of Adhesive Bonds¹

This standard is issued under the fixed designation D 950; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

INTRODUCTION

The accuracy of the results of strength tests of adhesive bonds will depend on the conditions under which the bonding process is carried out. Unless otherwise agreed upon between the manufacturer and the purchaser, the bonding conditions shall be prescribed by the manufacturer of the adhesive. In order to ensure that complete information is available to the individual conducting the tests, the manufacturer of the adhesive shall furnish numerical values and other specific information for each of the following variables:

(1) Procedure for preparation of surfaces prior to application of the adhesive, including the moisture content of wood, the cleaning and drying of metal surfaces, and special surface treatments such as sanding which are not specifically limited by the pertinent test method.

(2) Complete mixing directions for the adhesive.

(3) Conditions for application of the adhesive including the rate of spread or thickness of film, number of coats to be applied, whether to be applied to one or both surfaces, and the conditions of drying where more than one coat is required.

(4) Assembly conditions before application of pressure, including the room temperature, length of time, and whether open or closed assembly is to be used.

(5) Curing conditions, including the amount of pressure to be applied, the length of time under pressure and the temperature of the assembly when under pressure. It should be stated whether this temperature is that of the bond line, or of the atmosphere at which the assembly is to be maintained.

(6) Conditioning procedure before testing, unless a standard procedure is specified, including the length of time, temperature, and relative humidity.

A range may be prescribed for any variable by the manufacturer of the adhesive if it can be assumed by the test operator that any arbitrarily chosen value within such a range or any combination of such values for several variables will be acceptable to both the manufacturer and the purchaser of the adhesive.

1. Scope

1.1 This test method covers the determination of the comparative impact strength of adhesive bonds in shear, when tested on standard specimens under specified conditions of preparation, conditioning, and testing.

1.2 The values stated in SI units are to be regarded as the standard. The values in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applica-*

bility of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:

A 108 Specification for Steel Bars, Carbon, Cold-Finished, Standard Quality²

B 16 Specification for Free-Cutting Brass Rod, Bar, and Shapes for Use in Screw Machines³

B 107/B107 M Specification for Magnesium-Alloy Extruded Bars, Rods, Shapes, Tubes, and Wire⁴

B 133 Specification for Copper Rod, Bar, and Shapes³

B 139 Specification for Phosphor Bronze Rod, Bar, and Shapes³

¹ This test method is under the jurisdiction of ASTM Committee D-14 on Adhesives and is the direct responsibility of Subcommittee D14.30 on Wood Adhesives.

Current edition approved April 10, 1998. Published March 1999. Originally published as D 950 – 52 T. Last previous edition D 950 – 94.

² Annual Book of ASTM Standards, Vol 01.05.

³ Annual Book of ASTM Standards, Vol 02.01.

⁴ Annual Book of ASTM Standards, Vol 02.02.

 D 950

- B 151 Specification for Copper-Nickel-Zinc Alloy (Nickel Silver) and Copper-Nickel Rod and Bar³
- B 211 Specification for Aluminum and Aluminum-Alloy Bar, Rod, and Wire⁴
- D 143 Methods of Testing Small, Clear Specimens of Timber⁵
- D 905 Test Method for Strength Properties of Adhesive Bonds in Shear by Compression Loading⁶
- D 907 Terminology of Adhesives⁶
- E 23 Test Methods for Notched Bar Impact Testing of Metallic Materials⁷

3. Terminology

3.1 *Definitions*—Many terms in this test method are defined in Terminology D 907.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *impact strength, n*—the energy absorbed expressed in joules per square metre or foot-pounds-force (ft-lbf) per square inch, by a specimen of standard design when impacted to failure by a single blow of a testing-machine hammer. (Synonym *impact value*.)

3.2.2 *impact value, n*—Synonym for *impact strength*.

4. Significance and Use

4.1 Adhesives can fail under a sudden impact load and not under a slowly applied load of the same or greater force.

4.2 This test method can be used to compare the sensitivity of various adhesives to suddenly applied loads.

5. Apparatus

5.1 *Testing Machine:*

5.1.1 A pendulum-type impact machine with a hand velocity of 3.4 m/s (11 ft/s), comprising essentially the following:

5.1.1.1 *Impact Head* equipped with a flat striking face slightly wider than the test specimen, aligned to strike the specimen full-face.

5.1.1.2 *Jig* to hold the test specimen, as shown in Fig. 1. The jig illustrated is not suitable for use with all impact machines and vises. Vary the dimensions and design of the jig as required for adaptation to machines and vises available, provided the following general requirements are met: Machine the jig from a solid piece of steel and bolt it solidly to the base of the testing machine. Drill the corners to ensure that the test specimen sets flush against the retaining end of the jig. Minimize the dirt collection at the drilled corners which could hold the end of the specimen away from the face of the jig. Provide the jig with a screw to tighten the specimen in the jig, in order to minimize the tendency of the specimen to overturn when struck. To prevent the holding screw from splitting specimens of wood, place a metal plate between the end of the wood block and the end of the screw. Locate the jig so that the specimen will be struck at the point of maximum head velocity.

5.1.1.3 *Vise or Bolts* to hold the jig rigid and immobile under the stress of the testing machine hammer with the total

height of the vise, jig, and test specimen such that the lower edge of the striking face of the impact head strikes the specimen as near the adhesive line as possible, preferably within 0.79 mm ($\frac{1}{32}$ in.). Ordinarily the distance between the top of the jaws of the vise of the machine and the bottom of the striking face of the head is 22 mm (0.866 in.), and proper height of the specimen may be obtained by adjusting its height in the jig.

5.1.2 See Test Methods E 23 for additional information on impact testing machines and their calibration.

5.2 *Conditioning Room or Desiccators*—A conditioning room capable of maintaining a relative humidity of $50 \pm 2\%$ at $23 \pm 1.1^\circ\text{C}$ ($73.4 \pm 2^\circ\text{F}$), or desiccators filled with a saturated salt solution (Note 1) to give a relative humidity of $50 \pm 2\%$ at $23 \pm 1.1^\circ\text{C}$.

NOTE 1—A saturated salt solution of calcium nitrate will give approximately 51 % relative humidity at the test temperature.

6. Test Specimens

6.1 *Metal-to-Metal Specimens:*

6.1.1 *Material*—Metals conforming to the following specifications are recommended:

Metal	Designation
Brass	ASTM B16, C36000; half-hard temper
Copper	ASTM B133, C11000; hard temper
Aluminum	ASTM B211, A92024; G-3
Steel	AISI 1020, G10200; cold-finished bar
Phosphor bronze	ASTM B139, C54400
Magnesium	ASTM B107, AZ61A or M1A-F
Nickel silver	ASTM B151, C77000; quarter-hard

6.1.1.1 Run tests on adhesives with high-impact strength preferably on steel to minimize deformation. The reuse of specimens is allowed, provided that the face receiving the impact is not deformed.

6.1.2 *Specimen Size, Shape, and Assembly*—Use the test specimen dimensions for metal-to-metal adhesives given in Fig. 2(a), whenever possible. In cases where this specimen cannot be fractured in the testing machine available, the square dimensions of the 25.4 by 25.4-mm (1 by 1-in.) block may be reduced to a smaller square, keeping the dimensions of the 25.4 by 44.5-mm (1 by $1\frac{3}{4}$ -in.) block constant. Clearly state the dimensions of the specimen and bonded area in the report (Section 9). In any case, it is desirable that the specimen size be such as to give impact strengths that fall somewhere near the middle range of the testing machine, since readings in the highest and lowest ranges are often unreliable. Assemble the specimen so the face receiving the impact load is at the point of maximum velocity of the impact head. The impact face of the specimen is to be square and flat, perpendicular to the plane of the bond line, and parallel to the striking face of the pendulum.

6.1.3 *Bonding*—Apply adhesive and pressure in accordance with the procedure outlined by the manufacturer of the adhesive.

6.1.3.1 For metal-to-metal specimens, prepare areas that are to be bonded in accordance with the recommendations of the manufacturer of the adhesive.

6.1.4 *Conditioning*—Preconditioning is not required for metal-to-metal bonds. The adhesive is ready for test purposes when it has been applied in accordance with 6.1.3 unless

⁵ Annual Book of ASTM Standards, Vol 04.10.

⁶ Annual Book of ASTM Standards, Vol 15.06.

⁷ Annual Book of ASTM Standards, Vol 03.01.