



SLOVENSKI STANDARD
SIST EN 10245-3:2012

01-januar-2012

Nadomešča:
SIST EN 10245-3:2002

Jeklena žica in žični izdelki - Organske prevleke na jekleni žici - 3. del: Žica, prevlečena s PE

Steel wire and wire products - Organic coatings on steel wire - Part 3: PE coated wire

Stahldraht und Drahterzeugnisse - Organische Beschichtungen auf Draht - Teil 3: PE-beschichteter Draht

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Fils et produits tréfilés en acier - Revêtements organiques sur fils d'acier - Partie 3: Fils à revêtement de PE

[SIST EN 10245-3:2012](https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012)

<https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012>

Ta slovenski standard je istoveten z: EN 10245-3:2011

ICS:

25.220.60	Organske prevleke	Organic coatings
77.140.65	Jeklene žice, jeklene vrvi in verige	Steel wire, wire ropes and link chains

SIST EN 10245-3:2012

en,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 10245-3:2012](https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012)

<https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 10245-3

October 2011

ICS 25.220.60; 77.140.65

Supersedes EN 10245-3:2001

English Version

Steel wire and wire products - Organic coatings on steel wire - Part 3: PE coated wire

Fils et produits tréfilés en acier - Revêtements organiques
sur fils d'acier - Partie 3: Fils à revêtement de PE

Stahldraht und Drahterzeugnisse - Organische
Beschichtungen auf Stahldraht - Teil 3: PE-beschichteter
Draht

This European Standard was approved by CEN on 17 September 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 10245-3:2012](https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012)

<https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	4
2 Normative references	5
3 Terms and definitions	5
4 Types of PE coating materials.....	5
5 Requirements and test methods for PE coating material	6
5.1 Requirements	6
5.1.1 The composition and method of application	6
5.1.2 PE organic coating material consistency	6
5.1.3 Density	6
5.1.4 Melt flow index	6
5.1.5 Tensile strength	6
5.1.6 Elongation	7
5.2 Test methods.....	7
5.2.1 General.....	7
5.2.2 Melt flow index	7
6 Requirements and test methods for PE coating on wire.....	7
6.1 Requirements	7
6.1.1 General.....	7
6.1.2 Appearance	7
6.1.3 Colour-gloss and thickness.....	7
6.1.4 Elongation	7
6.1.5 Concentricity	8
6.1.6 Adherence	8
6.2 Test method.....	8
6.2.1 Appearance	8
6.2.2 Colour	8
6.2.3 Gloss	8
6.2.4 Thickness	8
6.2.5 Concentricity	8
6.2.6 Tensile strength and elongation	8
6.2.7 Adherence (where required)	8
6.2.8 Resistance to artificial light exposure	8
7 Performance of PE coating materials as the coating on wire.....	8
7.1 Requirement for colour stability (accelerated weathering).....	8
7.2 Test method for colour stability	9
8 Retests	9
9 Inspection and quality assurance	9
Bibliography	10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 10245-3:2012

[https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-](https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012)

[3732e56e80ac/sist-en-10245-3-2012](https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012)

Foreword

This document (EN 10245-3:2011) has been prepared by Technical Committee ECISS/TC 106 "Wire rod and wires", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2012, and conflicting national standards shall be withdrawn at the latest by April 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10245-3:2001.

This standard is made up of the following parts:

— *Part 1: General Rules;*

— *Part 2: PVC finished wire;*

— *Part 3: PE coated wire;*

— *Part 4: Polyester coated wire;*

— *Part 5: Polyamide coated wire.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

This European Standard for organic coatings for steel wire covers the requirements of a general nature and applies also to coatings for which no specific requirements have been established in the subsequent parts of this standard.

The subsequent parts of this standard deal more specifically with clearly defined coatings or groups of coatings. These coatings may have their own particular methods of application and their individual requirements which are specified in these parts of this standard, in other standards or in manufacturers data sheets.

Because the standard specifies requirements and tests not only for the coating but also for the coating material, it has proved not practical to put all the requirements in one clause and all the tests in another one. Following structure has been chosen in order to limit complexity and to facilitate the use.

In writing this series of standards consideration has been given to the nomenclature and transformation of organic coating materials as applied to steel wire products. These organic coating materials may, on application to wire and by their integration into the finished wire product, change their characteristics and properties.

This standard specifies characteristics and tests not only for the organic coating but also for the coating materials both before and after their application to steel wire and wire products. In addition it specifies the requirements for performance levels and testing methods on organic coating material which have become an integral and permanent part of the finished wire product. Therefore it has proven not to be practical to put all requirements in one clause and all the tests in another one.

To aid continuity and in order to limit complexity, the following structure has been chosen for this standard:

- **Clause 4** deals with the characteristics and testing methods of organic coating material as supplied by the manufacturer for the purposes of its application to the wire product.

Tests described in this section are intended to be carried out by the organic coating material manufacturer or the applicator **before** the coating operation.

- **Clause 5** relates to the characteristics and testing methods for the "organic coating" when the organic coating material has been applied to and has become an integral part of the finished wire. Consequently tests are intended to be in the main carried out by the coating "applicators".
- **Clause 6** defines the performance requirements and testing methods on the "organic coating" of the finished wire product, and where this is not possible, tests will be carried out on "coated" panels.

1 Scope

Complementary to EN 10245-1, this European Standard specifies the characteristics and requirements for steel wire and wire products coated with polyethylene (PE).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10021, *General technical delivery conditions for steel products*

EN 10204, *Metallic products — Types of inspection documents*

EN 10245-1:2008, *Steel wire and wire products — Organic coatings on steel wire — Part 1: General rules*

EN ISO 1133:2005, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics (ISO 1133:2005)*

EN ISO 3668, *Paints and varnishes — Visual comparison of the colour of paints (ISO 3668:1998)*

EN ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance (ISO 4892-1:1999)*

EN ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps (ISO 4892-2:2006)*

EN ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps (ISO 4892-3:2006)*

ISO 813, *Rubber, vulcanized or thermoplastic — Determination of adhesion to a rigid substrate — 90 degree peel method*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

iTeh STANDARD PREVIEW
(standards.iteh.ai)
SIST EN 10245-3:2012
<https://standards.iteh.ai/catalog/standards/sist/24de1061-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012>

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10245-1:2008 and the following apply.

3.1

PE coating

coating on steel wire or wire products made from organic coating material comprising a polymer base compound made up of at least 85 % ethylene (Ethene) which constitutes essentially the only monomer

4 Types of PE coating materials

Polyethylene coatings are classified into three types according to their density.

- Type 1 : low density (0,910 g/cm³ to 0,925 g/cm³)
- Type 2 : medium density (0,926 g/cm³ to 0,940 g/cm³)
- Type 3 : high density (0,941 g/cm³ to 0,965 g/cm³)

EN 10245-3:2011 (E)

5 Requirements and test methods for PE coating material

5.1 Requirements

5.1.1 The composition and method of application

The composition shall be agreed between manufacturer and the applicator and shall take account of the latter's method of application. However the PE coating material shall fulfil the requirements of this standard.

The processing of the PE coating material shall be at the manufacturer's discretion.

5.1.2 PE organic coating material consistency

The manufacturer shall ensure that the organic coating material composition and its characteristics remain constant from batch to batch and unchanged from that as agreed at the time of enquiry and order.

The manufacturer shall immediately notify the applicator of any subsequent change in the type and quantity of the constituent parts of the composition once this has been agreed between the two parties. At the request of the specifier/purchaser the presence of certain elements may be limited. In any case, the compound composition shall be cadmium free.

5.1.3 Density

The density at a temperature of 20 °C shall satisfy the values specified in Clause 4 of this standard.

5.1.4 Melt flow index

Polyethylene is classified in one of the following categories defined in Table 1 on the basis of the determined melt flow index:

<https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3f21e5c803/iso-10245-3:2012>

The melt flow index of the base material shall be $0,3 \pm 0,1$ g/10 min. According to Table 1, the material is category 5, unless otherwise specified at the time of enquiry and order.

Table 1 — Classification according to the melt flow index

Category	Nominal melt flow index of the base material g/10 min (at 190°C and 21,2 N load)
1	> 25
2	> 10 - 25
3	> 1,0 - 10
4	> 0,4 - 1,0
5	max 0,4

5.1.5 Tensile strength

Depending on the type of coating specified the minimum tensile strength shall satisfy the requirements of Table 2.

Table 2 — Tensile strength

Type of coating	Minimum tensile strength (MPa)
Type 1	8,5
Type 2	11,0
Type 3	17,0

5.1.6 Elongation

The minimum elongation of the coating material shall be 800 %.

However, for modified PE (cross linked), agreement should be taken at the time of order on elongation value, since no relevant official standard can be referred to.

5.2 Test methods

5.2.1 General

Unless otherwise specified the test methods shall be in accordance with EN 10245-1.

5.2.2 Melt flow index

The melt flow index shall be determined in accordance with EN ISO 1133:2005 condition E at 190 °C under a load of 21,2 N.

SIST EN 10245-3:2012

[https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-](https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012)

[3732e56e80ac/sist-en-10245-3-2012](https://standards.iteh.ai/catalog/standards/sist/2adef681-bfbc-42ee-a20d-3732e56e80ac/sist-en-10245-3-2012)

6 Requirements and test methods for PE coating on wire

6.1 Requirements

6.1.1 General

In addition to the general requirements of EN 10245-1, PE coatings shall satisfy following requirements.

6.1.2 Appearance

When examined by visual inspection, the surface of the PE coating shall be smooth, shiny, free from irregularities and uniform in colour.

Small dents, not affecting subsequent use and resulting from contact with adjacent turns shall not constitute a cause for rejection.

6.1.3 Colour-gloss and thickness

In the absence of a product specification, these requirements shall be agreed at the time of enquiry and order.

6.1.4 Elongation

The elongation of coating film on the wire product shall be not less than 300 %.