

---

**Jeklena žica in žični izdelki - Organske prevleke na jekleni žici - 5. del: S poliamidi prevlečena žica**

Steel wire and wire products - Organic coatings on steel wire - Part 5: Polyamide coated wire

Stahldraht und Drahterzeugnisse - Organische Beschichtungen auf Draht - Teil 5: Polyamid beschichteter Draht

Fils et produits tréfilés en acier - Revêtements organiques sur fils d'acier - Partie 5: Fils à revêtement de polyamide

[SIST EN 10245-5:2012](https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881f-c104c781cb27/sist-en-10245-5-2012)

[https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881f-](https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881f-c104c781cb27/sist-en-10245-5-2012)

[c104c781cb27/sist-en-10245-5-2012](https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881f-c104c781cb27/sist-en-10245-5-2012)

**Ta slovenski standard je istoveten z: EN 10245-5:2011**

---

**ICS:**

|           |                                      |  |
|-----------|--------------------------------------|--|
| 25.220.60 | Organske prevleke                    | Organic coatings                       |
| 77.140.65 | Jeklene žice, jeklene vrvi in verige | Steel wire, wire ropes and link chains |

**SIST EN 10245-5:2012**

**en,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 10245-5:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881f-c104c781cb27/sist-en-10245-5-2012>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 10245-5**

October 2011

ICS 25.220.60; 77.140.65

English Version

**Steel wire and wire products - Organic coatings on steel wire -  
Part 5: Polyamide coated wire**

Fils et produits tréfilés en acier - Revêtements organiques  
sur fils d'acier - Partie 5: Fils à revêtement de polyamide

Stahldraht und Drahterzeugnisse - Organische  
Beschichtungen auf Stahldraht - Teil 5: Polyamid-  
beschichteter Draht

This European Standard was approved by CEN on 17 September 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 10245-5:2012](https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881fc104c781cb27/sist-en-10245-5-2012)

<https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881fc104c781cb27/sist-en-10245-5-2012>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: Avenue Marnix 17, B-1000 Brussels**

## Contents

Page

|  |   |
|--|---|
| Foreword.....  | 3 |
| Introduction .....   | 4 |
| 1 Scope .....  | 4 |
| 2 Normative references .....   | 5 |
| 3 Terms and definitions .....  | 5 |
| 4 Methods of application and classes of Polyamide (PA6) coatings .....                   | 6 |
| 5 Requirements and testing methods for the Polyamide (PA6) coating material .....        | 6 |
| 5.1 Requirements .....   | 6 |
| 5.1.1 General.....   | 6 |
| 5.1.2 The Polyamide (PA6) organic coating composition.....                               | 6 |
| 5.1.3 Polyamide (PA6) organic coating material consistency.....                          | 6 |
| 5.2 Test methods.....  | 7 |
| 6 Requirement and test on the Polyamide (PA6) coating on wire .....                      | 7 |
| 6.1 Requirements .....   | 7 |
| 6.2 Test methods.....  | 7 |
| 7 Performance requirements and testing methods for Polyamide (PA6) coatings on wire..... | 8 |
| 7.1 Performance requirements .....   | 8 |
| 7.2 Test methods for performance appraisal .....   | 8 |
| 8 Retests .....  | 8 |
| 9 Inspection and quality assurance .....   | 8 |
| Bibliography .....   | 9 |

iTech STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 10245-5:2012  
<https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881f-c104c781cb27/sist-en-10245-5-2012>

## Foreword

This document (EN 10245-5:2011) has been prepared by Technical Committee ECISS/TC 106 "Wire rod and wires", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2012, and conflicting national standards shall be withdrawn at the latest by April 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This standard is made up of the following parts:

— *Part 1: General Rules;*

— *Part 2: PVC finished wire;*

— *Part 3: PE coated wire;*

— *Part 4: Polyester coated wire;*

— *Part 5: Polyamide coated wire;*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## Introduction

This European Standard for organic coatings for steel wire covers the requirements of a general nature and applies also to coatings for which no specific requirements have been established in the subsequent parts of this standard.

The subsequent parts of this standard deal more specifically with clearly defined coatings or groups of coatings. These coatings may have their own particular methods of application and their individual requirements which are specified in these parts of this standard, in other standards or in manufacturers data sheets.

Because the standard specifies requirements and tests not only for the coating but also for the coating material, it has proved not practical to put all the requirements in one clause and all the tests in another one. Following structure has been chosen in order to limit complexity and to facilitate the use.

In writing this series of standards consideration has been given to the nomenclature and transformation of organic coating materials as applied to steel wire products. These organic coating materials may, on application to wire and by their integration into the finished wire product, change their characteristics and properties.

This standard specifies characteristics and tests not only for the organic coating but also for the coating materials both before and after their application to steel wire and wire products. In addition it specifies the requirements for performance levels and testing methods on organic coating material, which have become an integral and permanent part of the finished wire product. Therefore it has proven not to be practical to put all requirements in one clause and all the tests in another one.

To aid continuity and in order to limit complexity, the following structure has been chosen for this standard:

- **Clause 4** deals with the characteristics and testing methods of organic coating material as supplied by the manufacturer for the purposes of its application to the wire product.

Tests described in this section are intended to be carried out by the organic coating material manufacturer or the applicator **before** the coating operation.

- **Clause 5** relates to the characteristics and testing methods for the “organic coating” when the organic coating material has been applied to and has become an integral part of the finished wire. Consequently tests are intended to be in the main carried out by the coating “applicators”.
- **Clause 6** defines the performance requirements and testing methods on the “organic coating” of the finished wire product, and where this is not possible, tests will be carried out on “coated” panels.

## 1 Scope

Complementary to EN 10245-1, this European Standard specifies the characteristics and requirements for steel wire and wire products coated with Polyamide (PA6).

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10021, *General technical delivery conditions for steel products*

EN 10245-1:2008, *Steel wire and wire products — Organic coatings on steel wires — Part 1: General rules*

EN ISO 527 (all parts), *Plastics — Determination of tensile properties*

EN ISO 1183-1, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method (ISO 1183-1:2004)*

EN ISO 1183-2, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method (ISO 1183-2:2004)*

EN ISO 1183-3, *Plastics — Methods for determining the density of non-cellular plastics — Part 3: Gas pycnometer method (ISO 1183-3:1999)*

EN ISO 2039-2, *Plastics — Determination of hardness — Part 2: Rockwell hardness (ISO 2039-2:1987)*

EN ISO 2813, *Paints and varnishes — Determination of specular gloss of non-metallic paint films at 20°, 60° and 85° (ISO 2813:1994, including Technical Corrigendum 1:1997)*

EN ISO 3668, *Paints and varnishes — Visual comparison of the colour of paints (ISO 3668:1998)*

EN ISO 4892-1, *Plastics — Methods of exposure to laboratory light sources — Part 1: General guidance (ISO 4892-1:1999)*

EN ISO 4892-2, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc lamps (ISO 4892-2:2006)*

EN ISO 4892-3, *Plastics — Methods of exposure to laboratory light sources — Part 3: Fluorescent UV lamps (ISO 4892-3:2006)*

ISO 4582, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 10245-1:2008 and the following apply.

### 3.1

#### **polyamide coating**

PA6a coating on wire and wire products made from organic coating material consisting primarily of polyamide (PA6) obtained by various polymerisation process

NOTE The coating material may also contain plasticizers, pigments, stabilisers, lubricants and other substances. The coating material is in the form of powder or granules.

**EN 10245-5:2011 (E)****4 Methods of application and classes of Polyamide (PA6) coatings**

The organic coating material shall be applied from granules by extrusion or from powders by the fluidised bed method or powder spraying.

Polyamide (PA6) coatings are classified on the basis of their method of application: either by extrusion or by fluidised bed or powder spraying and on the basis of their degree of adherence to the base wire.

- **Class 1a:** Wire with a Polyamide (PA6) coating applied by direct extrusion onto the base wire.
- **Class 1b:** Wire with Polyamide (PA6) coating applied by extrusion and made to adhere to the base wire by the use of a primer which may be thermally cured or by the use of organic glues.
- **Class 2a:** Polyamide (PA6) powder material applied by thermal fusion or electrostatic spray directly on the base wire.
- **Class 2b:** Wire that has been pretreated with a primer, thermally cured and then covered with a Polyamide (PA6) powder applied thermally or electrostatically.

**5 Requirements and testing methods for the Polyamide (PA6) coating material****5.1 Requirements****5.1.1 General**

The requirements for the coating material are summarized in Table 1.

**5.1.2 The Polyamide (PA6) organic coating composition**

The composition shall be agreed between manufacturer and the applicator and shall take account of the latter's method of application. However the Polyamide (PA6) organic coating material shall fulfil the requirements of this standard.

The processing of the Polyamide (PA6) coating material shall be at the manufacturer's discretion.

**5.1.3 Polyamide (PA6) organic coating material consistency**

The manufacturer shall ensure that the organic coating material composition and its characteristics remain constant from batch to batch and unchanged from that as agreed at the time of ordering. The processing of the Polyamide (PA6) coating material shall be at the manufacturer's discretion.

The manufacturer shall immediately notify the applicator of any subsequent change in the type and quantity of the constituent parts of the composition once this has been agreed between the two parties. At the request of the supplier/purchaser the presence of certain elements may be limited. In any case, the compound shall be cadmium free.



## 5.2 Test methods

The tests shall be performed in accordance with EN 10245-1 and Table 1 below.

**Table 1 — Requirements and testing methods for Polyamide (PA6) coating material**

| Characteristics  | Requirements               | Test methods           |
|--|----------------------------|------------------------|
| Density  | $\leq 1,15 \text{ g/cm}^3$ | EN ISO 1183-1 to -3    |
| Hardness Rockwell scale M  | Max 82                     | EN ISO 2039-2          |
| Tensile strength <sup>a</sup>  | Min. 30 MPa                | EN ISO 527 (all parts) |
| Elongation <sup>a</sup>  | Min. 200 %                 | EN ISO 527 (all parts) |
| <sup>a</sup> After conditioning in climatic chamber for 48 h at 23 °C +/- 2 °C and R.H.= 50 %. |                            |                        |

## 6 Requirement and test on the Polyamide (PA6) coating on wire

### 6.1 Requirements

The coating requirements are summarized in Table 2.

### 6.2 Test methods

Unless otherwise specified in this Part 5 the test methods shall be in accordance with EN 10245-1.

An overview of the test methods is given in Table 2.

<https://standards.iteh.ai/catalog/standards/sist/e8c9ff9c-dcd0-44cb-881f-c104c781cb27/sist-en-10245-5-2012>

**Table 2 — Requirements and testing methods for Polyamide (PA6) coating on wire**

| Characteristics   | Requirements                       |        | Test methods  |
|---|------------------------------------|--------|---|
| Appear  | see EN 10245-1                     |        | Visual - With the naked eye   |
| Colour  | see product standard <sup>a</sup>  |        | EN ISO 3668   |
| Gloss   | see product standard <sup>a</sup>  |        | EN ISO 2813   |
| Coating thickness   | see product standard               |        | EN 10245-1  |
| Concentricity of the coating  | 60% minimum                        |        | EN 10245-1  |
| Adherence <sup>b</sup>  | PA6 class 1a                       | 1-3    | EN 10245-1  |
|   | PA6 class 1b or 2b                 | 0 or 1 |   |
|   | PA6 class 2a                       | 3 or 4 |   |
| Performance after accelerated artificial light exposure <sup>c</sup>  | See product standards <sup>a</sup> |        | EN ISO 4892-1<br>Xenon arc: EN ISO 4892-2<br>QUV (A) or QUV (B) light:<br>EN ISO 4892-3 |
| <sup>a</sup> In the absence of a product specification the requirements shall be agreed at the time of enquiry and order.     |                                    |        |   |
| <sup>b</sup> For Class 1a, a minimum pull out resistance of the plastic coating can be specified or agreed with the customer. |                                    |        |   |
| <sup>c</sup> ISO samples of material of PA6 coating can be used as in Table 1.  |                                    |        |   |