



Designation: D 1613 – 03

Standard Test Method for Acidity in Volatile Solvents and Chemical Intermediates Used in Paint, Varnish, Lacquer, and Related Products¹

This standard is issued under the fixed designation D 1613; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This test method covers the determination of total acidity as acetic acid, in concentrations below 0.05 %, in organic compounds and hydrocarbon mixtures used in paint, varnish, and lacquer solvents and diluents. It is known to be applicable to such mixtures as low molecular weight saturated and unsaturated alcohols, ketones, ethers, esters, hydrocarbon diluents, naphtha, and other light distillate petroleum fractions.

1.2 For purposes of determining conformance of an observed value or a calculated value using this test method to relevant specifications, test result(s) shall be rounded off “to the nearest unit” in the last right-hand digit used in expressing the specification limit, in accordance with the rounding-off method of Practice E 29.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 For specific hazard information and guidance consult supplier’s Material Safety Data Sheet.

1.5 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of whoever uses this standard to consult and establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

D 770 Specification for Isopropyl Alcohol²

¹ This test method is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.35 on Solvents, Plasticizers, and Chemical Intermediates.

Current edition approved Oct. 1, 2003. Published October 2003. Originally approved in 1964. Last previous edition approved in 2002 as D 1613 – 02.

² Annual Book of ASTM Standards, Vol 06.04.

D 1193 Specification for Reagent Water³

E 200 Practice for Preparation, Standardization, and Storage of Standard and Reagent Solutions for Chemical Analysis⁴

E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications⁵

3. Summary of Test Method

3.1 The specimen is mixed with either an equal volume of water or an equal volume of alcohol, and titrated with aqueous sodium hydroxide solution to the phenolphthalein end point.

4. Significance and Use

4.1 This test method is useful for determining low levels of acidity, below 0.05 %, in organic compounds and hydrocarbon mixtures. The total acidity is calculated as acetic acid or milligrams of sodium hydroxide per gram of sample.

4.2 Acidity may be present as a result of contamination, decomposition during storage or distribution, or manufacture. This test method may be used in assessing compliance with a specification.

5. Apparatus

5.1 Buret, 10-mL, graduated in 0.05-mL subdivisions.

5.2 Erlenmeyer Flask, 250-mL capacity.

6. Purity of Reagents

6.1 Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such

³ Annual Book of ASTM Standards, Vol 11.01.

⁴ Annual Book of ASTM Standards, Vol 15.05.

⁵ Annual Book of ASTM Standards, Vol 14.02.

*A Summary of Changes section appears at the end of this standard.