



SLOVENSKI STANDARD
SIST ISO 9239-1:1998/Cor.2:1999
01-september-1999

DfYg_i gj`cXn]j UbUc[Yb^E`JcXcfUj bc`ýf^Yb^Yd`Ua YbUdc`dcj fý]b]`HJb]`cV`c[`E`%XY. `üf^Yb^Yd`Ua YbUdf]gYj UbYa `j]fi `j`ý][U!`HY b] b]`dcdfUj Y_`&

Reaction to fire tests — Horizontal surface spread of flame of floor-covering systems — Part 1:Flame spread using a radiant heat ignition source - Technical corrigendum 2

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: **ISO 9239-1:1997/Cor 2:1998**

SIST ISO 9239-1:1998/Cor 2:1999
<https://standards.iteh.ai/catalog/standards/sist/11a3699f-baf4-44c-ac2e-4b1ac19b63c8/sist-iso-9239-1-1998-cor-2-1999>

ICS:

13.220.40	Sposobnost vžiga in obnašanje materialov in proizvodov pri gorenju	Ignitability and burning behaviour of materials and products
59.080.60	Tekstilne talne obloge	Textile floor coverings
97.150	Netekstilne talne obloge	Non-textile floor coverings

SIST ISO 9239-1:1998/Cor.2:1999 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 9239-1:1998/Cor.2:1999](https://standards.iteh.ai/catalog/standards/sist/f1a3699f-baf4-4f4c-ae2e-4b1ac19b63c8/sist-iso-9239-1-1998-cor-2-1999)

<https://standards.iteh.ai/catalog/standards/sist/f1a3699f-baf4-4f4c-ae2e-4b1ac19b63c8/sist-iso-9239-1-1998-cor-2-1999>



INTERNATIONAL STANDARD ISO 9239-1:1997
TECHNICAL CORRIGENDUM 2

Published 1998-07-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Reaction to fire tests — Horizontal surface spread of flame of floor-covering systems —

Part 1:

Flame spread using a radiant heat ignition source

TECHNICAL CORRIGENDUM 2

Essais de réaction au feu — Propagation superficielle horizontale d'une flamme sur des revêtements de sol —

Partie 1: Propagation de flamme utilisant une source de chaleur radiante

RECTIFICATIF TECHNIQUE 2

STANDARD PREVIEW
(standards.iteh.ai)

Technical Corrigendum 2 to International Standard ISO 9239-1:1997 was prepared by Technical Committee ISO/TC 92, Fire safety, Subcommittee SC 1, Reaction to fire.

Page 25

Replace table B.1 with the following table. (Repeatability and reproducibility values have been increased by a factor of 10.)

Table B.1 — Repeatability and reproducibility of critical radiant flux at extinguishment

Material	Mean m (kW/m ²)	Repeatability		Reproducibility	
		r	r/m (%)	R	R/m (%)
Polyamide Carpet	4,2	1,5	36	1,6	38
Polyester Carpet	3,1	1,7	55	2,2	71
Polypropylene Carpet	3,0	1,4	47	1,8	60
Wool Carpet	8,0	2,1	26	3,1	39
PVC Flooring	10,9	0,7	6	1,1	10

ICS 13.220.40; 59.080.60; 97.150

Ref. No. ISO 9239-1:1997/Cor.2:1998(E)