INTERNATIONAL

Designation: D 2665 – 02a^{€1}

An American National Standard

Standard Specification for Poly(Vinyl Chloride) (PVC) Plastic Drain, Waste, and Vent Pipe and Fittings¹

This standard is issued under the fixed designation D 2665; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

 ϵ^1 Note—Table 1, Tolerance on Avg. Column, was editorially corrected in April 2002.

1. Scope

- 1.1 This specification covers requirements and test methods for materials, dimensions and tolerances, pipe stiffness, crush resistance, impact resistance, hydrostatic burst resistance, and solvent cement for poly(vinyl chloride) plastic drain, waste, and vent pipe and fittings. A form of marking is also included. Plastic which does not meet the material requirements specified in Section 5 is excluded. Installation procedures are given in the Appendix.
- 1.2 The values stated in inch-pound units are to be regarded as the standard. The metric equivalents of inch-pound units given in parentheses may be approximate.
- 1.3 The text of this specification references notes, footnotes, and appendixes which provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the specification.
- 1.4 The following safety hazards caveat pertains only to the test methods portion, Section 7, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 ASTM Standards:
- D 618 Practice for Conditioning Plastics for Testing²
- D 1599 Test Method for Resistance to Short-Time Hydraulic Pressure of Plastic Pipe, Tubing, and Fittings³
- D 1600 Terminology for Abbreviated Terms Relating to Plastics²

- D 1784 Specification for Rigid Poly(Vinyl Chloride) (PVC) Compounds and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds²
- D 2122 Test Method for Determining Dimensions of Thermoplastic Pipe and Fittings³
- D 2412 Test Method for Determination of External Loading Characteristics of Plastic Pipe by Parallel-Plate Loading³
- D 2444 Test Method for Determination of the Impact Resistance of Thermoplastic Pipe and Fittings by Means of a Tup (Falling Weight)³
- D 2564 Specification for Solvent Cements for Poly(Vinyl Chloride) (PVC) Plastic Piping Systems³
- D 3311 Specification for Drain, Waste, and Vent (DWV) Plastic Fittings Patterns³
- D 4396 Specification for Rigid Poly(Vinyl Chloride) (PVC) and Chlorinated Poly(Vinyl Chloride) (CPVC) Compounds for Plastic Pipe and Fittings Used in Nonpressure Applications³
- F 402 Practice for Safe Handling of Solvent Cements, Primers, and Cleaners Used for Joining Thermoplastic Pipe and Fittings³
- F 412 Terminology Relating to Plastic Piping Systems³
- F 1498 Specification for Taper Pipe Threads 60° for Thermoplastic Pipe and Fittings³
- F 1866 Specification for Poly (Vinyl Chloride) (PVC) Plastic Schedule 40 Drainage and DWV Fabricated Fittings³
- F 2135 Specification for Molded Drain, Waste, and Vent-(DWV) Short-Pattern Plastic Fittings²

3. Terminology

3.1 *Definitions*—Definitions are in accordance with Terminology F 412F 412, and abbreviations are in accordance with Terminology D 1600D 1600, unless otherwise specified.

4. Significance and Use

4.1 The requirements of this specification are intended to provide pipe and fittings suitable for the drainage and venting of sewage and certain other liquid wastes.

¹ This specification is under the jurisdiction of ASTM Committee F17 on Plastic Piping Systems and is the direct responsibility of Subcommittee F17.63 on DWV. Current edition approved Sept. 10, 2002 Published November 2002. Originally published as D 2665 – 68. Last previous edition D 2665 – 02.

² Annual Book of ASTM Standards, Vol 08.01.

³ Annual Book of ASTM Standards, Vol 08.04.

NOTICE: This standard has either been superseded and replaced by a new version or withdrawn. Please contact ASTM International (www.astm.org) for the latest information. D 2665 – 02a^{c1}

Note 1—Industrial waste disposal lines should be installed only with the specific approval of the cognizant building code authority since chemicals not commonly found in drains and sewers and temperatures in excess of $180^{\circ}F$ ($82.2^{\circ}C$) may be encountered.

5. Materials

- 5.1 Basic Materials—The pipe shall be made of virgin PVC compounds meeting or exceeding the requirements of Class 12454 as defined in Specification D 1784D 1784. The fittings shall be made of virgin PVC compounds meeting or exceeding the requirements of Class 12454 as defined in Specification D 1784 D 1784 or Class 11432 as defined in Specification D 4396.D 4396These plastics contain stabilizers, lubricants, and pigments.
- 5.2 Rework Material—The manufacturer shall use only his own clean pipe or fitting rework material and the pipe or fittings produced shall meet all the requirements of this specification.
- 5.3 Solvent Cement—The solvent cement used to join pipe and fittings made to this specification shall meet the requirements of Specification D 2564D 2564.

6. Requirements Requirements

- 6.1 General—The pipe and fittings shall be homogeneous throughout and free of visible cracks, holes, foreign inclusions, or other injurious defects. The pipe shall be as uniform as commercially practicable in color, opacity, density, and other physical properties.
- 6.1.1 The requirements in this section are intended only for use as quality control tests, not as simulated service tests.

- 6.2 Dimensions and Tolerances:
- 6.2.1 *Method*—All dimensions shall be determined in accordance with Test Method D 2122D 2122.
 - 6.2.2 Dimensions:
- 6.2.2.1 The outside diameter and wall thicknesses of pipe shall meet the requirements of Table 2. The pipe shall be in either 10 or 20-ft (3.05 or 6.1-m) lengths, unless otherwise specified, with an allowable tolerance of $\pm 1/2$, ± 0 in. (± 13 , ± 0 mm).
- 6.2.2.2 The patterns, dimensions, and laying lengths of fittings, including adaptors, shall meet the requirements of Specification D 3311D 3311 and Table 1.
- 6.2.2.3 The patterns, dimensions, and laying lengths of Short-Pattern fittings shall meet the requirements of Specification F 2135.F 2135
- 6.2.2.4 The spigot dimensions of fittings shall meet the requirements of Table 2.
- 6.2.2.5 For all fittings having taper pipe threads, threads shall conform to Specification F 1498F 1498 and be gaged in accordance with 7.5. Fittings of nominal sizes not given in Specification F 1498F 1498 shall not have threads.
- 6.2.2.6 Fabricated DWV fittings shall comply with F 1866F 1866.
 - 6.3 Pipe Stiffness, Deflection Load and Flattening:
- 6.3.1 *Pipe*—The minimum pipe stiffness at 5 % deflection shall be in accordance with Table 3. The pipe shall deflect by 60 % of the nominal outside diameter (flattening) without cracking, rupture, or other visible evidence of failure when tested in accordance with 7.4.

TABLE 1 Dimensions and Tolerances for Fitting Sockets for PVC Plastic Drain, Waste and Vent Pipe Fittings

Nominal Pipe Size	A Socket Entrance Diameter			B Socket Bottom Diameter			C Socket	E Wall	Internal Threads	
									Outside	Thread
	Average	Tolerance on Avg.	Out-of -Roundness	Average	Tolerance 4 on Avg.	Out-of -Roundness	Depth, min 60e43e	thickness min. ^A 7cb234/astm-	Diameter of Hub, M. min.	length min.
		_	,		in. (mm)					
11/4	1.675 (42.54)	+0.010/-0.005 (+0.25/-0.13)	0.024 (0.61)	1.655 (42.04)	±0.005 (±0.13)	0.024 (0.61)	0.687 (17.44)	0.156 (3.96)	1.871 (47.52)	0.687 (17.44)
11/2	1.915 (48.64)	+0.010/-0.005 (+0.25/-0.13)	0.024 (0.61)	1.895 (48.13)	±0.005 (±0.13)	0.024 (0.61)	0.687 (17.44)	0.156 (3.96)	2.127 (54.03)	0.687 (17.44)
2	2.390 (60.71)	+0.010/-0.005 (+0.25/-0.13)	0.024 (0.61)	2.370 (60.20)	±0.005 (±0.13)	0.024 (0.61)	0.750 (19.05)	0.156 (3.96)	2.634 (66.90)	0.750 (19.05)
3	3.520 (89.41)	+0.010/-0.005 (+0.25/-0.13)	0.030 (0.76)	3.495 (88.77)	+0.005/-0.010 (+0.13/-0.25)	0.030 (0.76)	1.500 (38.10)	0.219 (5.56)	3.841 (97.56)	1.187 (30.15)
4	4.520 (114.8)	+0.010/-0.005 (+0.25/-0.13)	0.030 (0.76)	4.495 (114.2)	+0.005/-0.010 (+0.13/-0.25)	0.030 (0.76)	1.750 (44.45)	0.250 (6.35)	4.907 (124.6)	1.28 (32.54)
6	6.647 (168.8)	+0.015/-0.010 (+0.38/-0.25)	0.060 (1.52)	6.614 (168.0)	±0.010 (±0.25)	0.060 (1.52)	3.000 (76.20	0.281 (7.14)	7.203 (183.0)	1.500 (38.10)
8	8.655 (219.8)	+0.030/-0.000 (+0.76/-0.00)	0.090 (2.29)	8.610 (218.7)	+0.030/-0.000 (+0.76/-0.00)	0.090 (2.29)	4.000 (101.6)	0.328 (8.33)	В	В
10	10.780 (273.8)	+0.025/-0.020 (+0.64/-0.51)	0.120 (3.05)	10.735 (272.7)	±0.020 (±0.51)	0.120 (3.04)	5.000 (127.0)	0.365 (9.28)	В	В
12	12.780 (324.6)	+0.030/-0.025 (+0.76/-0.64)	0.150 (3.81)	12.735 (323.5)	±0.020 (±0.51)	0.150 (3.81)	6.000 (152.4)	0.406 (10.3)	В	В

AThe wall thickness is a minimum value except that a ±10% variation resulting from core shift is allowable. In such case, the average of the two opposite wall thicknesses shall equal or exceed the value shown in the table

^BNot applicable for these nominal sizes.

TABLE 2 Dimensions and Tolerances for Outside Diameters and Thicknesses of PVC Plastic Drain, Waste, and Vent Pipe

		Outside Diameter	Wall Thickness			
Nominal Pipe Size	Average	Tolerance on Average	Out-of-Roundness (maximum minus minimum)	Minimum	Tolerance	
in. (mm)						
11/4	1.660 (42.16)	±0.005 (0.13)	0.024 (0.61)	0.140 (3.56)	+0.020 (0.51) -0.000	
1½	1.900 (48.26)	±0.006 (0.15)	0.024 (0.61)	0.145 (3.68)	+0.020 (0.51) -0.000	
2	2.375 (60.33)	±0.006 (0.15)	0.024 (0.61)	0.154 (3.91)	+0.020 (0.51) -0.000	
3	3.500 (88.90)	±0.008 (0.20)	0.030 (0.76)	0.216 (5.49)	+0.026 (0.66) -0.000	
4	4.500 (114.30)	±0.009 (0.23)	0.100(2.54)	0.237 (6.02)	+0.028 (0.71) -0.000	
6	6.625 (168.28)	±0.011 (0.28)	0.100 (2.54)	0.280 (7.11)	+0.034 (0.86) -0.000	
8	8.625 (219.08)	±0.015 (0.38)	0.150 (3.81)	0.322 (8.18)	+0.000 +0.039 (0.99) -0.000	
10	10.750 (273.05)	±0.015 (0.38)	0.150 (3.81)	0.365 (9.27)	+0.044 (1.12) -0.000	
12	12.750 (323.85)	±0.015 (0.38)	0.150 (3.81)	0.406 (10.31)	+0.000 +0.049 (1.24) -0.000	
14	14.000 (355.6)	±0.015 (±0.38)	0.200 (5.08)	0.437 (11.1)	+0.053 (1.35)	
16	16.000 (406.4)	±0.019 (±0.48)	0.320 (8.13)	0.500 (12.7)	-0.000 +0.060 (1.52) -0.000	

TABLE 3 Pipe Stiffness Requirements for PVC DWV Pipe^A

Nominal Pipe Size, in.	Pipe Stiffness Factor, min, psi (kPa)
11/4 11/2	1400 (9650) 1010 (6960)
2	600 (4140)
3 4	510 (3520) 310 (2140)
6	150 (1030)
8 10	100 (690) 78 (530)
12	63 (430) ASTM D2663
https://standa14 ls.iteh.ai/cata	alog/standa 60 (415) /93964f42-79 60 (415)

^A Measured at 5 % deflection.

6.3.1.1 *Pipe Stiffness (PS)*—Three specimens shall be tested. If all three meet the PS requirement, the sample meets the PS requirement. If one or two fail, additional testing shall be conducted in accordance with 6.3.1.2. If all three fail, the sample does not meet the PS requirement.

6.3.1.2 Pipe Stiffness and Lower Confidence Limit—In the event that one or two of the specimens tested in 6.3.1 fail to meet the minimum PS requirement, the average pipe stiffness of eleven specimens shall meet or exceed the minimum requirement given in Table 3. The 99 % lower confidence limit (LCL) shall be within 15 % of the average value. The LCL shall be calculated using the Student's "t" distribution, with N-1 degrees of freedom, where N is the number of specimens. The critical t value shall be used to at least three significant digits. Alternatively, if the LCL exceeds the minimum PS requirement in Table 3, but is not within 15 % of the average, the sample meets the requirements of the pipe stiffness testing. The eleven specimens include the three tested under 6.3.1, and

an additional eight with rotation by 35°, as specified in Test Method D 2412D 2412, continuing throughout the remaining specimens.

6.3.1.3 The LCL based on testing eleven specimens is calculated as follows:

LCL = (avg PS) -
$$\{2.76(\text{std. dev.})/\sqrt{(N)}\}\$$
 (1)

where:

$$(avg PS) = [\Sigma(PS_i)]/$$
 (2)

(std. dev.) =
$$\left[\frac{\sum PS^2 - (\sum PS)^2 / N}{N - I} \right]^{1/2}$$

N = 11

6.3.1.4 The 15 % requirement is calculated as follows:

$$(Avg - LCL)/(Avg) \times 100 \le 15\%$$
(3)

Note 2—The 5 % deflection criterion, which was arbitrarily selected for testing convenience, should not be considered as a limitation with respect to in-use deflection. The engineer is responsible for establishing the acceptable deflection.

6.3.2 *Fittings*—Individual fittings unassembled shall withstand a minimum load of 750 lbf/ft (11 kN/m) of centerline length without cracking or other visible evidence of failure when tested in accordance with 7.4.

6.4 Minimum Hydrostatic Burst Pressure— When tested at 73°F (23°C) in accordance with Test Method D 1599D 1599, the minimum burst pressure of pipe shall be in accordance with Table 4, and the minimum burst pressure of fittings shall be 200 psi (1.4 MPa). Test three specimens of pipe or three fittings; all shall meet the requirements.

Note 3—The minimum burst pressure requirements for DWV fittings