



Designation: D 961 – 86 (Reapproved 2001)

Standard Specification for Dehydrated Castor Oil¹

This standard is issued under the fixed designation D 961; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers a drying oil made from castor oil that has been treated to remove the elements of water. Two types of dehydrated castor oil are covered: unbodied and Z-3 bodied.

NOTE 1—Other types of bodied dehydrated castor oil are commercially available but are not covered by this specification.

2. Referenced Documents

2.1 ASTM Standards:

- D 445 Test Method for Kinematic Viscosity of Transparent and Opaque Liquids (and the Calculation of Dynamic Viscosity)²
- D 555 Guide for Testing Drying Oils³
- D 1475 Test Method for Density of Liquid Coatings, Inks, and Related Products⁴
- D 1544 Test Method for Color of Transparent Liquids (Gardner Color Scale)⁴
- D 1545 Test Method for Viscosity of Transparent Liquids by Bubble Time Method³
- D 1639 Test Method for Acid Value of Organic Coating Materials³
- D 1640 Test Methods for Drying, Curing, or Film Formation of Organic Coatings at Room Temperature³
- D 1955 Test Method for Gel Time of Drying Oils³
- D 1959 Test Method for Iodine Value of Drying Oils and Fatty Acids³
- D 1962 Test Method for Saponification Value of Drying

- Oils, Fatty Acids, and Polymerized Fatty Acids³
- D 1963 Test Method for Specific Gravity of Drying Oils, Varnishes, Resins, and Related Materials at 25/25°C³
- D 2090 Test Method for Clarity and Cleanness of Paint and Ink Liquids³
- E 1 Specification for ASTM Thermometers⁵

3. Properties

3.1 Dehydrated castor oil shall conform to the requirements prescribed in Table 1.

4. Test Methods

4.1 The properties enumerated in this specification shall be determined in accordance with the appropriate methods given in Table 1 with the following exceptions:

4.1.1 *Gel Time*—Determine the gel time in accordance with Test Method D 1955 but with the following changes:

4.1.1.1 Use an ASTM Partial Immersion Thermometer having a range from 20 to 760°F and conforming to the requirements for Thermometer 3F as prescribed in Specification E 1.

4.1.1.2 Heat the bath to 600 ± 1°F (315 ± 0.5°C), insert the tubes containing the oil in the bath, maintain the bath at 600 ± 1°F for the duration of the test, and

4.1.1.3 Raise the glass rods a fraction of an inch at 1-min intervals after 125 min in the case of the unbodied oil or after 25 min in the case of the bodied oil.

4.1.2 *Iodine Value*—Use the procedure described in Method D 1959, to determine the iodine value, except that the specimen weights shall be 0.11 to 0.13 g of oil.

4.2 The significance of and comments on the referenced methods are discussed in Guide D 555.

5. Keywords

5.1 castor oil; dehydrated; dehydrated castor oil

¹ This specification is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D 01.32 on Drying Oils.

Current edition approved March 27, 1986. Published May 1986. Originally published as D 961 – 48 T. Last previous edition D 961 – 80.

² *Annual Book of ASTM Standards*, Vol 05.01.

³ *Annual Book of ASTM Standards*, Vol 06.03.

⁴ *Annual Book of ASTM Standards*, Vol 06.01.

⁵ *Annual Book of ASTM Standards*, Vol 14.03.