



Designation: D 962 – 81 (Reapproved 1999)

# Standard Specification for Aluminum Powder and Paste Pigments for Paints<sup>1</sup>

This standard is issued under the fixed designation D 962; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers four types and three classes of aluminum pigments for use in paints.

## 2. Referenced Documents

### 2.1 ASTM Standards:

D 480 Test Methods for Sampling and Testing of Flaked Aluminum Powders and Pastes<sup>2</sup>

E 34 Test Methods for Chemical Analysis of Aluminum and Aluminum Base Alloys<sup>3</sup>

## 3. Classification

### 3.1 Type I—Leafing Aluminum Pigment Powder:

3.1.1 *Class A, Fine*—Maximum of 0.1 % retained on a No. 325 (45- $\mu$ m) sieve.

3.1.2 *Class B, Medium*—Maximum of 1.5 % retained on a No. 325 (45- $\mu$ m) sieve.

3.1.3 *Class C, Coarse*—Maximum of 20 % retained on a No. 325 (45- $\mu$ m) sieve.

### 3.2 Type II—Leafing Aluminum Pigment Paste:

3.2.1 *Class A, Fine*—Maximum of 0.1 % retained on a No. 325 (45- $\mu$ m) sieve.

3.2.2 *Class B, Medium*—Maximum of 1.0 % retained on a No. 325 (45- $\mu$ m) sieve.

3.2.3 *Class C, Coarse*—Maximum of 15 % retained on a No. 325 (45- $\mu$ m) sieve.

3.3 *Type III—Nonleafing Aluminum Pigment Powder* (Note):

3.3.1 *Class A, Fine*—Maximum of 1.5 % retained on a No. 325 (45- $\mu$ m) sieve.

3.3.2 *Class B, Medium*—Maximum of 6.0 % retained on a No. 325 (45- $\mu$ m) sieve.

3.3.3 *Class C, Coarse*—Maximum of 20 % retained on a No. 325 (45- $\mu$ m) sieve.

### 3.4 Type IV—Nonleafing Aluminum Pigment Paste (Note 1):

3.4.1 *Class A, Fine*—Maximum of 0.1 % retained on a No. 325 (45- $\mu$ m) sieve.

3.4.2 *Class B, Medium*—Maximum of 1.0 % retained on a

No. 325 (45- $\mu$ m) sieve.

3.4.3 *Class C, Coarse*—Maximum of 11.0 % retained on a No. 325 (45- $\mu$ m) sieve.

NOTE 1—The particle size characteristics of the Type 3 and Type 4 pigments of the same class do not correspond with each other; in the case of Types 1 and 2 they do.

## 4. Composition and Properties

4.1 *Aluminum Pigment Powder (Type 1, Leafing and Type 3, Nonleafing)*—The aluminum pigment powder shall consist of commercially pure aluminum in the form of fine, polished flakes, and a suitable fatty lubricant. It shall contain no filler or extender pigments.

4.2 *Aluminum Pigment Paste (Type 2, Leafing and Type 4, Nonleafing)*—The aluminum pigment paste shall consist of commercially pure aluminum in the form of fine, polished flakes, and a suitable fatty lubricant combined with a volatile thinner. It shall contain no filler or extender pigments.

4.3 The aluminum pigments, powder, and paste of both leafing and nonleafing types shall conform to the requirements given in Table 1.

4.4 The paint made from the powder or paste shall be free-flowing and shall give a continuous coating at least equal in smoothness, luster, and general appearance to that of a reference sample mutually agreed upon by the purchaser and the seller.

4.5 The aluminum pigments, powder and paste of both leafing and nonleafing types, stored in unopened original packages within 6 months after shipment shall pass all tests applicable to the respective type and class as described in Test Methods D 480.

## 5. Test Methods and Sampling

5.1 Sampling and tests shall be conducted in accordance with Test Methods D 480. Since several of the methods are empirical and the results are affected by the method, the specified procedures should be closely followed.

## 6. Packaging

6.1 Aluminum paste should be packaged in a polyvent container that can be safely vented in case of pressure build-up.

## 7. Keywords

7.1 aluminum powder; flake; leafing; nonleafing; paste; polishing lubricant

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Oct. 30, 1981. Published December 1981. Originally published as D962 – 48 T. Last previous edition D962 – 66 (1973).

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 06.03.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 03.05.