

SLOVENSKI STANDARD

SIST EN 12915-1:2009

01-maj-2009

Nadomešča:

SIST EN 12915-1:2003

SIST EN 12915-1:2003/AC:2006

**Izdelki, ki se uporabljajo za pripravo pitne vode - Aktivno oglje v zrnih - 1. del:
Sveže aktivno oglje v zrnih**

Products used for the treatment of water intended for human consumption - Granular
activated carbon - Part 1: Virgin granular activated carbon

iTeh STANDARD PREVIEW
(standards.iten.si)
Produkte zur Aufbereitung von Wasser für den menschlichen Gebrauch - Granulierte
Aktivkohle - Teil 1: Frische granulierte Aktivkohle

<http://standards.iten.si/catalog/standards/sist/c0c48-bc-04e1-4b1b-9b97-b61988c519a/sist-en-12915-1-2009>
Produits chimiques utilisés pour le traitement de l'eau destinée à la consommation
humaine - Charbon actif en grains - Partie 1: Charbon actif en grain vierge

Ta slovenski standard je istoveten z: EN 12915-1:2009

ICS:

13.060.20	Pitna voda	Drinking water
71.100.80	Kemikalije za čiščenje vode	Chemicals for purification of water

SIST EN 12915-1:2009

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12915-1:2009

<https://standards.iteh.ai/catalog/standards/sist/c0c48cbc-04ed-4bbb-9b97-b61f988c519a/sist-en-12915-1-2009>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 12915-1

March 2009

ICS 71.100.80

Supersedes EN 12915-1:2003

English Version

**Products used for the treatment of water intended for human
consumption - Granular activated carbon - Part 1: Virgin
granular activated carbon**

Produits chimiques utilisés pour le traitement de l'eau
destinée à la consommation humaine - Charbon actif en
grains - Partie 1: Charbon actif en grains vierge

Produkte zur Aufbereitung von Wasser für den
menschlichen Gebrauch - Granulierte Aktivkohle - Teil 1:
Frische granulierte Aktivkohle

This European Standard was approved by CEN on 1 February 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/c0c48c0c-04ed-4bbb-9b97-b61f988c519a/sist-en-12915-1-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Description	5
4.1 Identification.....	5
4.2 Commercial forms	6
5 Physical properties.....	6
5.1 Appearance	6
5.2 Particle size distribution	6
5.3 Wettability	7
5.4 Bulk density packed	7
5.5 Mechanical strength	7
6 Chemical properties	7
6.1 General.....	7
6.2 Purity criteria.....	7
7 Specific properties.....	8
8 Test methods.....	8
8.1 Sampling	8
8.2 Analysis	8
9 Labelling, transportation and storage	15
9.1 Means of delivery.....	15
9.2 Risk and safety labelling according to the EU directives.....	15
9.3 Transportation regulations and labelling.....	16
9.4 Marking	16
9.5 Storage.....	16
Annex A (informative) General information on granular activated carbon	17
A.1 Origin	17
A.2 Composition	17
A.3 Hydraulic characteristics	18
A.4 Use	19
A.5 Rules for safe handling and use	19
A.6 Emergency procedures	20
Bibliography.....	21

iTeh STANDARD PREVIEW
 (standards.iteh.ai)

SIST EN 12915-1:2009
<https://standards.iteh.ai/catalog/standards/sist/c0c48cbc-04ed-4bbb-9b97-b61f988c519a/sist-en-12915-1-2009>

Foreword

This document (EN 12915-1:2009) has been prepared by Technical Committee CEN/TC 164 “Water supply”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2009, and conflicting national standards shall be withdrawn at the latest by September 2009.

This document supersedes EN 12915-1:2003.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This European Standard consists of two parts, Part 1 is concerned with virgin granular activated carbon and Part 2 gives requirements for reactivated granular activated carbon.

Differences between this edition and EN 12915-1:2003 are editorial to harmonize the text with other standards in this series.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

SIST EN 12915-1:2009

<https://standards.iteh.ai/catalog/standards/sist/c0c48cbc-04ed-4bbb-9b97-b61f988c519a/sist-en-12915-1-2009>

Introduction

In respect of potential adverse effects on the quality of water intended for human consumption, caused by the product covered by this European Standard:

- a) this European Standard provides no information as to whether the product may be used without restriction in any of the Member States of the EU or EFTA;
- b) it should be noted that, while awaiting the adoption of verifiable European criteria, existing national regulations concerning the use and/or the characteristics of this product remain in force.

NOTE Conformity with this European Standard does not confer or imply acceptance or approval of the product in any of the Member States of the EU or EFTA. The use of the product covered by this European Standard is subject to regulation or control by National Authorities.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12915-1:2009

<https://standards.iteh.ai/catalog/standards/sist/c0c48cbc-04ed-4bbb-9b97-b61f988c519a/sist-en-12915-1-2009>

1 Scope

This part of EN 12915 is applicable to virgin granular activated carbon used for treatment of water intended for human consumption. It describes the characteristics of virgin granular activated carbon and specifies the requirements and the corresponding test methods for virgin granular activated carbon. It gives information on its use in water treatment.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12901:1999, *Products used for treatment of water intended for human consumption - Inorganic supporting and filtering materials – Definitions*

EN 12902, *Products used for treatment of water intended for human consumption - Inorganic supporting and filtering materials - Methods of test*

EN ISO 3696, *Water for analytical laboratory use – Specification and test methods (ISO 3696:1987)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12901:1999 and the following apply.

3.1

virgin activated carbon

freshly manufactured activated carbon that has not been used and has not been reactivated

3.2

wettability

ability of granular activated carbon to be wetted when in contact with water, determined by measuring the quantity of material that sinks in water under specified conditions

4 Description

4.1 Identification

4.1.1 Chemical name(s)

Carbon.

4.1.2 Synonym or common names

Virgin granular activated carbon, virgin activated coal, virgin activated charcoal, virgin active carbon.

4.1.3 Chemical formula

C (elementary).

EN 12915-1:2009 (E)**4.1.4 CAS Registry Number¹⁾**

7440-44-0.

4.1.5 EINECS reference²⁾

231-153-3.

4.2 Commercial forms

Granular activated carbon is a granular product; by convention not less than a mass fraction of 90 % is retained on a 180 µm aperture test sieve (see 5.2). The product can be either shaped (moulded/extruded) or irregular (non-moulded), and is available in many grades, differing in adsorption characteristics, hardness, porosity, granulometry, shape and purity.

5 Physical properties**5.1 Appearance**

The commercial product consists of black, porous granules of irregular shape or, for moulded or extruded products, in forms such as uniform cylinders, pellets or spheres.

5.2 Particle size distribution**5.2.1 General**

The particle size distribution shall be determined on samples taken at the point of manufacture. The particle size distribution shall be within the manufacturer's stated tolerance.

NOTE 1 Different applications can require different particle size ranges.

NOTE 2 The particle size can decrease during transportation and handling.

5.2.2 Irregular product

The particle size distribution shall be described by either:

a) effective size: (d_{10}) with a permitted tolerance of ± 5 %;

uniformity coefficient: (U) shall be less than 2,1;

minimum size: (d_1) with a permitted tolerance of ± 5 %;

or:

b) by particle size range and by mass of oversize and undersize particles according to application:

— the content of oversize plus undersize shall not exceed a mass fraction of 15 % and not more than a mass fraction of 5 % shall be undersize.

NOTE Other values can be necessary for certain applications.

1) Chemical Abstracts Service Registry Number.

2) European Inventory of Existing Commercial Chemical Substances.

5.2.3 Moulded/extruded product

Not more than a mass fraction of 3 % shall pass a test sieve with an aperture size as close as possible to 0,75 times the nominal particle diameter.

5.3 Wettability

The wettability shall be greater than a mass fraction of 99 %.

5.4 Bulk density packed

The bulk density packed shall be greater than or equal to 180 kg/m³.

5.5 Mechanical strength

The ball-pan hardness shall be greater than 75.

NOTE Products with a lower hardness are suitable for certain applications.

6 Chemical properties

6.1 General

Granular activated carbon is manufactured by controlled oxidation (by means of steam or chemicals) from carbonaceous raw materials including coconut, wood, peat or coal. The raw materials shall be stated by the manufacturer.

High internal porosity results in adsorptive properties and, depending on the raw material and the manufacturing process, it can have acid or basic properties. It is a reducing agent with catalytic properties. Activated carbon can react with oxidants to form carbon dioxide.

The carbon content of the commercial product does not affect adsorption characteristics.

6.2 Purity criteria

6.2.1 General

This European Standard specifies the minimum purity requirements for virgin granular activated carbon used for the treatment of water intended for human consumption. Limits are given for impurities commonly present in the product. Depending on the raw material and the manufacturing process other impurities may be present and, if so, this shall be notified to the user and when necessary to relevant authorities.

NOTE Users of this product should check the national regulations in order to clarify whether it is of appropriate purity for treatment of water intended for human consumption, taking into account raw water quality, contents of other impurities and additives used in the products not stated in the product standard.

Limits have been given for impurities and chemical parameters where these are likely to be present in significant quantities from the current production process and raw materials. If the production process or raw materials lead to significant quantities of impurities, by-products or additives being present, this shall be notified to the user.

6.2.2 Impurities and main by-products

The product shall conform to the requirements specified in Table 1.

Table 1 — Main impurities and by-products

Impurity		Limit ^a in mass fraction %
Ash	max.	15
Water ^b (at the time of packing) ^c	max.	5
Water-soluble material	max.	3
Zinc	max.	0,002
^a Expressed on a dry basis except for water content. ^b Higher or lower values can be necessary for certain applications. ^c The water content can increase after packing; e.g. during transportation		

6.2.3 Water-extractable substances

The product shall conform to the requirements specified in Table 2.

Table 2 — Water- extractable substances

Substance	Limit in µg/l in the extraction water
Arsenic (As) max.	10
Cadmium (Cd) max.	0,5
Chromium (Cr) max.	5
Mercury (Hg) max.	0,3
Nickel (Ni) max.	15
Lead (Pb) max.	5
Antimony (Sb) max.	3
Selenium (Se) max.	3
Cyanide (CN) max.	5
PAH ^a max.	0,02
^a Polycyclic Aromatic Hydrocarbons : the sum of the detected concentrations of fluoranthene, benzo(b)fluoranthene, benzo(k)fluoranthene, benzo(a)pyrene, benzo(ghi)perylene, indeno(1,2,3-cd)pyrene.	

7 Specific properties

The iodine number of the granular activated carbon shall be not less than 600 mg/g.

8 Test methods

8.1 Sampling

Prepare the laboratory sample(s) required by the relevant procedures described in EN 12902.

8.2 Analysis

8.2.1 Particle size distribution

The particle size distribution shall be determined in accordance with EN 12902.

8.2.2 Wettability

8.2.2.1 Principle

Immersion of the product in boiling water. Cooling, sedimentation and filtration of the supernatant through a sieve to determine the quantity of material that is not wetted.

8.2.2.2 Reagents

All reagents shall be of a recognized analytical grade and the water used shall conform to grade 3 in accordance with EN ISO 3696.

8.2.2.3 Apparatus

Ordinary laboratory apparatus and glassware together the following.

8.2.2.3.1 Drying oven capable of being controlled at $(150 \pm 5)^\circ\text{C}$.

8.2.2.3.2 Hotplate.

8.2.2.3.3 Wire cloth sieve, with an aperture size as close as possible to the nominal undersize of the granular activated carbon (for moulded/extruded products, 0,75 times the nominal particle diameter).

8.2.2.3.4 Balance having an accuracy of 0,1 g.

8.2.2.4 Procedure

Take a test sample of approximately 500 ml of granular activated carbon, dry at $(150 \pm 5)^\circ\text{C}$, and weigh (m_0). Bring 1 l of water to the boil in a 2 l glass beaker and add the granular activated carbon to the boiling water. Continue to boil for $10 \text{ min} \pm 30 \text{ s}$, swirling if necessary to remove carbon particles attached to the wall of the beaker. Remove from the hotplate (8.2.2.3.2) and cool to room temperature.

Carefully decant the supernatant water (approximately 500 ml), including any suspended or floating particles. Filter the supernatant through the sieve (8.2.2.3.3), collect the particles retained on the sieve and dry to constant mass at $(150 \pm 5)^\circ\text{C}$ (m_1).

8.2.2.5 Expression of results

The wettability, X_1 , expressed as a percentage mass fraction of product, is given by the following equation:

$$X_1 = \frac{100 \times (m_0 - m_1)}{m_0} \quad (1)$$

where

m_0 is the mass, in grams, of the test sample;

m_1 is the mass, in grams, of the test sample retained on the test sieve.

8.2.3 Bulk density packed

8.2.3.1 Principle

The bulk density packed of granular activated carbon is determined by measuring the volume packed by a free fall from a vibrating feeder into a 100 ml graduated cylinder and weighing the known volume.