



Designation: F 436 – 03

Standard Specification for Hardened Steel Washers¹

This standard is issued under the fixed designation F 436; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers the chemical, mechanical, and dimensional requirements for hardened steel washers for use with fasteners having nominal thread diameters of 1/4 through 4 in. These washers are intended for general-purpose mechanical and structural use with bolts, nuts, studs, and other internally and externally threaded fasteners. These washers are suitable for use with fasteners covered in Specifications A 325, A 354, A 449, and A 490.

1.2 The washers are designated by *type* denoting the material and by *style* denoting the shape.

1.2.1 The types of washers covered are:

1.2.1.1 *Type 1*—Carbon steel.

1.2.1.2 *Type 3*—Weathering steel. Atmospheric corrosion resistance and weathering characteristics are comparable to that of steels covered in Specifications A 588/A 588M and A 709/A 709M. The atmospheric corrosion resistance of these steels is substantially better than that of carbon steel with or without copper addition. See 5.1. When properly exposed to the atmosphere, these steels can be used bare (uncoated) for many applications.

1.2.2 The styles of washers covered are:

1.2.2.1 *Circular*—Circular washers in nominal bolt sizes 1/4 through 4 in. suitable for applications where sufficient space exists and angularity permits.

1.2.2.2 *Beveled*—Beveled washers are square or rectangular, in nominal sizes 1/2 through 1 1/2 in., with a beveled 1 to 6 ratio surface for use with American standard beams and channels.

1.2.2.3 *Clipped*—Clipped washers are circular or beveled for use where space limitations necessitate that one side be clipped.

NOTE 1—A complete metric companion to Specification F 436 has been developed—Specification F 436M; therefore no metric equivalents are presented in this specification.

1.2.2.4 *Extra Thick*—Extra thick washers are circular washers in nominal sizes 1/2 through 1 1/2 in., with a nominal thickness of 5/16 in. suitable for structural applications with oversized holes.

1.3 Terms used in this specification are defined in Specification F 1789 unless otherwise defined herein.

2. Referenced Documents

2.1 *ASTM Standards*:

A 153/A 153M Specification for Zinc Coating (Hot-Dip) on Iron and Steel Hardware²

A 325 Specification for Structural Bolts, Steel, Heat Treated, 120/105 ksi Minimum Tensile Strength³

A 354 Specification for Quenched and Tempered Alloy Steel Bolts, Studs, and Other Externally Threaded Fasteners³

A 449 Specification for Quenched and Tempered Steel Bolts and Studs³

A 490 Specification for Structural Bolts, Alloy Steel, Heat Treated, 150 ksi Minimum Tensile Strength³

A 588/A 588M Specification for High-Strength Low-Alloy Structural Steel with 50 ksi [345 MPa] Minimum Yield Point to 4 in. [100 mm] Thick⁴

A 709/A 709M Specification for Carbon and High-Strength Low-Alloy Structural Steel Shapes, Plates, and Bars and Quenched-and-Tempered Alloy Structural Steel Plates for Bridges⁴

A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products⁵

B 695 Specification for Coatings of Zinc Mechanically Deposited on Iron and Steel⁶

D 3951 Practice for Commercial Packaging⁷

F 606 Test Methods for Determining the Mechanical Properties of Externally and Internally Threaded Fasteners, Washers, and Rivets³

¹ This specification is under the jurisdiction of ASTM Committee F16 on Fasteners and is the direct responsibility of Subcommittee F16.02 on Steel Bolts, Nuts, Rivets, and Washers.

Current edition approved Oct. 1, 2003. Published October 2003. Originally approved in 1976. Last previous edition approved in 2002 as F 436 – 02.

² *Annual Book of ASTM Standards*, Vol 01.06.

³ *Annual Book of ASTM Standards*, Vol 01.08.

⁴ *Annual Book of ASTM Standards*, Vol 01.04.

⁵ *Annual Book of ASTM Standards*, Vol 01.03.

⁶ *Annual Book of ASTM Standards*, Vol 02.05.

⁷ *Annual Book of ASTM Standards*, Vol. 15.09.

*A Summary of Changes section appears at the end of this standard.

F 1789 Terminology for F16 Mechanical Fasteners³
 G 101 Guide for Estimating the Atmospheric Corrosion
 Resistance of Low-Alloy Steels⁸

TABLE 1 Chemical Requirements

Element	Composition, %	
	Type 1	Type 3 ^A
Phosphorus, max		
Heat analysis	0.040	0.040
Product analysis	0.050	0.045
Sulfur, max		
Heat analysis	0.050	0.050
Product analysis	0.060	0.055
Silicon		
Heat analysis	...	0.15–0.35
Product analysis	...	0.13–0.37
Chromium		
Heat analysis	...	0.45–0.65
Product analysis	...	0.42–0.68
Nickel		
Heat analysis	...	0.25–0.45
Product analysis	...	0.22–0.48
Copper		
Heat analysis	...	0.25–0.45
Product analysis	...	0.22–0.48

^A Weathering steel washers may also be manufactured from any of the steels listed in Table 2 of Specification A 325.

3. Ordering Information

3.1 Orders for hardened steel washers under this specification shall include the following:

3.1.1 ASTM designation and year of issue,

3.1.2 Quantity (number of pieces by size),

3.1.3 Type and Style (see 1.2.1 and 1.2.2),

3.1.4 *Zinc Coating*—Specify the zinc coating process required, for example, hot-dip, mechanically deposited, or no preference (see 4.3),

3.1.5 Dimensions, nominal size, and other dimensions, if modified from those covered in this specification,

3.1.6 Specify if inspection at point of manufacture is required,

3.1.7 Specify if manufacturer's certification or test reports, or both, are required, and

3.1.8 Special requirements.

4. Materials and Manufacture

4.1 Steel used in the manufacture of washers shall be produced by the open-hearth, basic-oxygen, or electric-furnace process.

4.2 Washers up to and including 1½ in. in bolt size shall be through hardened. Washers over 1½ in. may be either through hardened or carburized at the option of the manufacturer.

4.3 *Zinc Coatings, Hot-Dip and Mechanically Deposited:*

4.3.1 When zinc-coated washers are required, the purchaser shall specify the zinc coating process, for example, hot-dip, mechanically deposited, or no preference.

4.3.2 When hot-dip is specified the washers shall be zinc coated by the hot-dip process in accordance with the requirements of Class C of Specification A 153/A 153M.

4.3.3 When mechanically deposited is specified the washers shall be zinc coated by the mechanical-deposition process in accordance with the requirements of Class 50 of Specification B 695.

4.3.4 When no preference is specified, the supplier may furnish either a hot-dip zinc coating in accordance with Specification A 153/A 153M, Class C, or a mechanically deposited zinc coating in accordance with Specification B 695, Class 50. Threaded components (bolt and nuts) shall be coated by the same zinc-coating process and the supplier's option is limited to one process per item with no mixed processes in a lot.

4.4 If washers are heat treated by a subcontractor, they shall be returned to the manufacturer for testing prior to shipment to the purchaser.

5. Chemical Composition

5.1 Type 1 and Type 3 washers shall conform to the chemical composition specified in Table 1. For Type 3 see Guide G 101 for methods of estimating corrosion resistance of low alloy steels.

5.2 Product analysis may be made by the purchaser from finished material representing each lot of washers. The chemical composition shall conform to the requirements of 4.1 and 5.1.

5.3 Individual heats of steel are not identified in the finished product.

5.4 Chemical analyses shall be performed in accordance with Test Methods, Practices, and Terminology A 751.

6. Mechanical Properties

6.1 Through hardened washers shall have a hardness of 38 to 45 HRC, except when zinc-coated by the hot-dip process, in which case they shall have a hardness of 26 to 45 HRC.

6.2 Carburized washers shall be carburized to a minimum depth of 0.015 in. and shall have a surface hardness of 69 to 73 HRA or 79 to 83 HR15N, except when zinc-coated by the hot-dip process, in which case they shall have a hardness of 63 to 73 HRA or 73 to 83 HR15N.

6.3 Carburized and hardened washers shall have a minimum core hardness of 30 HRC or 65 HRA.

7. Dimensions and Tolerances

7.1 All circular and clipped circular washers shall conform to the dimensions shown in Table 2 and Table 3.


7.2 All square beveled and clipped square beveled washers shall conform to the dimensions shown in Table 3 and Table 4. In addition, rectangular beveled and clipped rectangular beveled washers shall conform to the dimensions shown in Table 3 and Table 4, except that one side may be longer than shown for the "A" dimension.

7.3 Unless otherwise stated in the inquiry or purchase order, plain (uncoated) hardened steel circular washers shall be furnished. Where corrosion-preventive treatment is required, washers shall be coated as agreed upon between the manufacturer and the purchaser.

⁸ Annual Book of ASTM Standards, Vol 03.02.

TABLE 2 Hardened Circular, Clipped Circular, and Extra-Thick Washers

NOTE 1—Tolerances are as noted in table on washer dimension tolerances.



Nominal Size	Circular and Extra Thick		Clipped Circular			
	Circular, Clipped Circular, and Extra Thick		Circular and Clipped		Extra Thick	Clipped
	Nominal Outside Diameter (OD), in.	Nominal Inside Diameter (ID), in.	Thickness (T), in.			
min			max	min	max	
1/4	0.625	0.281	0.051	0.080	...	0.219
5/16	0.688	0.344	0.051	0.080	...	0.281
3/8	0.813	0.406	0.051	0.080	...	0.344
7/16	0.922	0.469	0.051	0.080	...	0.406
1/2	1.063	0.531	0.097	0.177	0.305	0.438
9/16	1.188	0.625	0.110	0.177	0.305	0.500
5/8	1.313	0.688	0.122	0.177	0.305	0.563
3/4	1.468	0.813	0.122	0.177	0.305	0.656
7/8	1.750	0.938	0.136	0.177	0.305	0.781
1	2.000	1.125	0.136	0.177	0.305	0.875
1 1/8	2.250	1.250	0.136	0.177	0.305	1.000
1 1/4	2.500	1.375	0.136	0.177	0.305	1.094
1 3/8	2.750	1.500	0.136	0.177	0.305	1.219
1 1/2	3.000	1.625	0.136	0.177	0.305	1.313
1 3/4	3.375	1.875	0.178 ^B	0.28 ^B	0.305	1.531
2	3.750	2.125	0.178 ^B	0.28 ^B	0.305	1.750
2 1/4	4.000	2.375	0.24 ^C	0.34 ^C	0.305	2.000
2 1/2	4.500	2.625	0.24 ^C	0.34 ^C	0.313	2.188
2 3/4	5.000	2.875	0.24 ^C	0.34 ^C	0.313	2.406
3	5.500	3.125	0.24 ^C	0.34 ^C	0.313	2.625
3 1/4	6.000	3.375	0.24 ^C	0.34 ^C	0.313	2.875
3 1/2	6.500	3.625	0.24 ^C	0.34 ^C	0.313	3.063
3 3/4	7.000	3.875	0.24 ^C	0.34 ^C	0.313	3.313
4	7.500	4.125	0.24 ^C	0.34 ^C	0.313	3.500

^A Clipped edge E shall be not closer than 7/8 of the bolt diameter from the center of the washer.

^B 3/16 in. nominal.

^C 1/4 in. nominal.

Standard Standards
<https://standards.iteh.com/document/astm-f436-03>
 Document Review
 ASTM F436-03
<https://standards.iteh.com/catalog/standards/sist/71af5d5-481e-c3-c96f66068/astm-f436-03>