



SLOVENSKI STANDARD SIST EN ISO 9513:2013

01-junij-2013

Nadomešča:
SIST EN ISO 9513:2004

Kovinski materiali - Kalibracija ekstenzometrov, ki se uporabljajo pri enoosnem preskušanju (ISO 9513:2012)

Metallic materials - Verification and calibration of extensometers used in uniaxial testing (ISO 9513:2012)

Metallische Werkstoffe - Zugversuch - Teil 5: Prüfung und Kalibrierung von Längenänderungs-Messeinrichtungen für die Prüfung mit einachsiger Beanspruchung (ISO 9513:2012)

Matériaux métalliques - Matériaux métalliques - Etalonnage des extensomètres utilisés lors d'essais uniaxiaux (ISO 9513:2012)

Ta slovenski standard je istoveten z: EN ISO 9513:2012

ICS:

77.040.10 Mehansko preskušanje kovin Mechanical testing of metals

SIST EN ISO 9513:2013

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 9513:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 9513

December 2012

ICS 77.040.10

Supersedes EN ISO 9513:2002

English Version

Metallic materials - Calibration of extensometer systems used in uniaxial testing (ISO 9513:2012)

Matériaux métalliques - Étalonnage des chaînes extensométriques utilisées lors d'essais uniaxiaux (ISO 9513:2012)

Metallische Werkstoffe - Kalibrierung von Längenänderungs-Messeinrichtungen für die Prüfung mit einachsiger Beanspruchung (ISO 9513:2012)

This European Standard was approved by CEN on 14 December 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 9513:2013

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>

Foreword

This document (EN ISO 9513:2012) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee ECISS/TC 101 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2013, and conflicting national standards shall be withdrawn at the latest by June 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 9513:2002.

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
Endorsement notice

The text of ISO 9513:2012 has been approved by CEN as a EN ISO 9513:2012 without any modification.

[SIST EN ISO 9513:2013
https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013](https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 9513:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>

INTERNATIONAL STANDARD

**ISO
9513**

Third edition
2012-12-01

Metallic materials — Calibration of extensometer systems used in uniaxial testing

*Matériaux métalliques — Étalonnage des chaînes extensométriques
utilisées lors d'essais uniaxiaux*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 9513:2013](https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013)

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>



Reference number
ISO 9513:2012(E)

© ISO 2012

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 9513:2013](https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013)

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Terms and definitions	1
3 Symbols and designations	1
4 Principle	2
5 Calibration equipment	2
5.1 Calibration apparatus	2
5.2 Calibration traceability	2
6 Pre-calibration inspection	2
6.1 Objective	2
6.2 Records of the inspection	3
6.3 Identification of extensometer system elements	3
7 Measurement of extensometer gauge length	3
7.1 Fixed gauge length extensometry	3
7.2 Variable gauge length extensometry	3
7.3 Non-contacting extensometry	4
7.4 Extensometer gauge lengths established using setting gauges	4
8 Calibration process	4
8.1 Environmental considerations	4
8.2 Position of the extensometer	4
8.3 Calibration increments	4
8.4 Calibration process	6
8.5 Determination of the characteristics of the extensometer system	6
9 Classification of the extensometer system	7
9.1 Input data	7
9.2 Analysis of the data	7
9.3 Classification criteria	7
9.4 Assessment of the results	7
10 Uncertainty determination	8
10.1 Uncertainty of the calibration	8
10.2 Uncertainty budget determination	8
11 Extensometer system calibration intervals	8
12 Calibration certificate	8
12.1 Mandatory information	8
12.2 Data presentation	9
Annex A (informative) Uncertainty of measurement	10
Annex B (informative) Calibration of the calibration apparatus	15
Annex C (informative) Example of a report of the calibration of calibration apparatus	17
Annex D (informative) Examples of extensometer system configurations	20
Annex E (informative) Laser extensometry	29
Annex F (informative) Video extensometry	37
Annex G (informative) Full field strain measurement video extensometry	41
Annex H (informative) Calibration of a cross-head measurement system	43
Bibliography	44

ISO 9513:2012(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 9513 was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 1, *Uniaxial testing*.

This third edition cancels and replaces the second edition (ISO 9513:1999), which has been technically revised. It also incorporates the Technical Corrigendum ISO 9513:1999/Cor.1:2000.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 9513:2013](https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013)

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>

Introduction

This International Standard sets out criteria for the calibration of extensometer systems, covering general principles, the calibration equipment to be used, pre-calibration inspection and the measurement of gaugelength for various types of extensometer systems. Aspects of the calibration process are addressed, as are the assessment of the results, uncertainties, calibration intervals and reporting. Criteria for calibration apparatus, their calibration and grading are addressed, complemented by a Bibliography covering a number of important papers related to extensometer systems and their application ^[1] to ^[10]. Work is in progress to develop processes for dynamic extensometer calibration, however these have not reached, at the time of writing of this International Standard, the level of development appropriate for inclusion within this International Standard. For further information, refer to Reference [6].

Informative annexes address calculation of uncertainties of measurement for an extensometer system calibration (Annex A), calibration of calibration apparatus (Annex B) and an example of a calibration report (Annex C). Subsequent annexes address examples of extensometer system configurations (Annex D), laser extensometry (Annex E), video extensometry (Annex F), full field extensometry (Annex G) and calibration of a crosshead measurement system (Annex H).

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 9513:2013](https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013)

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 9513:2013](#)

<https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46fbf89c1/sist-en-iso-9513-2013>

Metallic materials — Calibration of extensometer systems used in uniaxial testing

1 Scope

This International Standard specifies a method for the static calibration of extensometer systems used in uniaxial testing, including axial and diametral extensometer systems, both contacting and non-contacting.

2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

2.1

extensometer system

equipment used to measure displacement or strain on the surface of a test piece

NOTE For the purpose of this International Standard, the term “extensometer system” includes the indicator. Some extensometers indicate strain directly (e.g. laser extensometers or digital image correlation techniques). Other extensometers indicate the change in gauge length of a test piece; this is converted into strain by dividing by the relevant gauge length.

2.2

gauge length

portion of a test piece where extension is measured

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 9513:2013](https://standards.iteh.ai/catalog/standards/sist/64207d5f-407d-471d-a5aa-8cf46bf89c1/sist-en-iso-9513-2013)

3 Symbols and designations

Symbols used throughout this International Standard are given in Table 1 together with their designation.

Table 1 — Symbols and designations

Symbol	Designation	Unit
L_e	Nominal gauge length of extensometer	mm
L'_e	Measured gauge length of extensometer	mm
l_{\max}	Maximum limit of calibration range	mm
l_{\min}	Minimum limit of calibration range	mm
l_i	Displacement indicated by extensometer	μm
l_t	Displacement given by calibration apparatus	μm
q_{L_e}	Relative gauge length error of the extensometer system	%
q_{rb}	Relative bias error of the extensometer system	%
q_b	Absolute bias error of the extensometer system	μm
r	Resolution of the extensometer system	μm

ISO 9513:2012(E)

4 Principle

The calibration of extensometer systems involves a comparison of the readings given by the extensometer with known variations in length provided by a calibration apparatus.

NOTE 1 The user can define the displacement range(s) over which the calibration is to be performed. In this way, the performance of the extensometer system can be optimized. For example, for strain-controlled low cycle fatigue, only a small portion of the operating range of the extensometer is typically used. Hence, it would be appropriate, in this case, to concentrate the calibration on the centre portion of the operating range.

The calibration process compares the known displacement from the calibration device with the output of the extensometer system. This output can range from manual readings of high precision dial gauges to the displacement indication of a transducer/electronics/data-logging system. In the latter case, the extensometer system output would include any data curve fitting applied by the electronics/data-logging system.

NOTE 2 For certain types of extensometer systems, the calibration and classification will also be dependent upon the ability of the extensometer system to define the gauge length.

5 Calibration equipment

5.1 Calibration apparatus

The calibration apparatus, which allows a known displacement l_t to be applied to the extensometer, may consist of a rigid frame with suitable coaxial spindles or other fixtures to which the extensometer can be attached. The calibration apparatus shall comprise a mechanism for moving at least one of the axial spindles together with a device for accurately measuring the change in length produced. These variations in length can be measured by, for example, an interferometer, a linear incremental encoder or gauge blocks and a comparator, or a micrometer.

NOTE Special attachments to the calibration apparatus spindles are utilized for the calibration of diametral extensometers.

The calibration apparatus should be calibrated in accordance with Annex B and should meet the performance requirements given in Table B.1.

Annex B gives a recommended calibration procedure for the calibration apparatus and details performance criteria that indicate that the apparatus is suitable for calibrating extensometer systems in accordance with this International Standard.

5.2 Calibration traceability

The calibration apparatus and the supporting equipment (such as micrometers, callipers, optical projection microscopes) shall be calibrated using standards that are traceable to the International System of Units (SI). The uncertainty associated with any measurements made by the supporting equipment shall not exceed one third of the permissible error of the extensometer system being calibrated (see Table 2). The temperature measurement instrument shall have a resolution of 0,1 °C.

6 Pre-calibration inspection

6.1 Objective

Prior to the calibration of the extensometer system it shall be inspected. This shall comprise, but not be limited to, inspection of the mechanical components for, for example, free movement, damaged parts, worn knife edges, and worn gauge length setting pins/fixtures. For extensometer systems incorporating electronic transducers, the cabling and connectors shall be examined for damage, wear, etc.

The extensometer system shall be calibrated in the as-found condition if at all possible. The results shall be assessed and, if necessary, the system shall be adjusted and re-calibrated. In this case, both data sets shall be reported.

6.2 Records of the inspection

Records of the pre-calibration inspection shall be kept, identifying the “as-found” condition of the extensometer system, when the inspection was performed and who performed it. These pre-calibration inspection records can take the form of either a written report or a completed “pro-forma” checklist.

6.3 Identification of extensometer system elements

The extensometer shall be uniquely identified. Parts that may be changed by the user during normal use of the extensometer that affect the calibration of the extensometer shall also be uniquely identified where possible. However, this requirement does not extend to clamping devices used to attach the extensometer to the test piece. These unique identifications form part of the records for the extensometer system.

7 Measurement of extensometer gauge length

7.1 Fixed gauge length extensometry

7.1.1 The measured gauge length, L'_e , of a fixed gauge length extensometer shall be determined by either direct or indirect means. In both cases, the extensometer setting pin or gauge fixture is used to set the extensometer contact points to their pre-set displacement.

NOTE Variability of the measured gauge length might be experienced due to excessive play/wear in the gauge length setting mechanism.

7.1.1.1 Direct measurement of the gauge length, L'_e , is performed between the extensometer contact points, using a calibrated measuring instrument such as a caliper or a shadowgraph/projection microscope.

7.1.1.2 Indirect measurement of the gauge length, L'_e , is performed by placing the extensometer on a soft metal test piece in such a way that the blades or points of the extensometer leave their marks. Once the extensometer is removed, the distance between the marks on the test piece shall be measured, using equipment with an accuracy consistent with the required class of extensometer.

7.1.2 The relative error on the gauge length, q_{L_e} , calculated from Formula (1) shall meet the requirements given in Table 2.

$$q_{L_e} = \frac{L'_e - L_e}{L_e} \times 100 \quad (1)$$

7.2 Variable gauge length extensometry

7.2.1 The gauge length of a variable gauge length extensometer shall be measured either directly, or indirectly.

7.2.1.1 Direct measurement of the gauge length is performed by setting the extensometer to the required gauge length using jigs, fixtures or other tools, followed by measurement between the extensometer contact points, using a calibrated measuring instrument such as a calliper or a shadowgraph/projection microscope.

7.2.1.2 Indirect measurement of the gauge length, L'_e is performed by attaching the extensometer to a soft metal test piece in such a way that the blades or points of the extensometer leave their marks. Once the extensometer is removed, the distance between the marks on the test piece is measured, using equipment with an accuracy consistent with the required class of extensometer.

7.2.2 Extensometers commonly used in creep, elevated temperature tensile or stress relaxation testing have their gauge length defined by small ridges machined on the parallel length of the test piece, to which the