



Designation: D6181 – 03

Standard Test Method for Measurement of Turbidity in Mineral Insulating Oil of Petroleum Origin¹

This standard is issued under the fixed designation D6181; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the laboratory procedure that ascertains the quantity of suspensions in insulating oils of petroleum origin using a nephelometric measurement technique to determine the fluid's turbidity. This test method is designed to reveal changes that may occur to these oils.

1.2 This test method is applicable for turbidities in the range of 0.1 to 500 Nephelometric Turbidity Units (NTU).

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- D923 Practices for Sampling Electrical Insulating Liquids
- D1533 Test Method for Water in Insulating Liquids by Coulometric Karl Fischer Titration
- D1698 Test Method for Sediments and Soluble Sludge in Service-Aged Insulating Oils
- D1889 Test Method for Turbidity of Water³
- D4652 Specification for Silicone Fluid Used for Electrical Insulation
- D5180 Test Method for Quantitative Test for Turbidity in Clear Liquids³

¹ This test method is under the jurisdiction of ASTM Committee D27 on Electrical Insulating Liquids and Gases and is the direct responsibility of Subcommittee D27.07 on Physical Test.

Current edition approved Oct. 1, 2003. Published December 2003. Originally approved in 1997. Last previous edition approved in 1997 as D6181-97. DOI: 10.1520/D6181-03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

³ Withdrawn. The last approved version of this historical standard is referenced on www.astm.org.

E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods

3. Terminology

3.1 Description of Terms Specific to This Standard:

3.1.1 *nephelometric turbidity unit (NTU), n*—intensity of light scattered by a known aqueous suspension of formazine. One NTU is the turbidity of a formazine solution produced by mixing 12.5 μg of hydrazine sulfate and 1.25 μg of hexamethylenetetramine in 1 mL of turbidity-free water. See Appendix X1 for preparation instructions.

3.1.2 *turbidity, n*—the reduction of transparency due to the presence of particulate matter.

4. Summary of Test Method

4.1 The turbidity is determined by a calibrated, ratio turbidimeter, which measures scattered light at 0.5π rad (90°) or 0.5 and 1.5π rad (90 and 270°) angles to the incident beam. These instruments cannot be calibrated accurately in terms of absolute turbidity except in the case of fluids having uniform-size particles that are less than approximately one fifth of the wave length of the incident light. Standards have been prepared by thoroughly mixing suitable amounts of finely divided titanium dioxide into partially polymerized polystyrene. Alternatively, suspension of formazine has been used as a turbidity standard, formed by reacting hydrazine sulfate and hexamethylenetetramine under carefully controlled conditions.⁴ Calibrated commercial standards in sealed tubes also are available.

4.2 The test specimen is placed in the cell and its turbidity is measured. The turbidimeter measures the light scattered by suspended solids dispersed within the test specimen. Accuracy and sensitivity of the method is ensured by measuring the turbidity at a wavelength of light where there is little or no absorption of the light by the test specimen. Use of a narrow bandwidth of light reduces interference that may be inherent to oxidized insulating oils. The narrow bandwidth is achieved through the use of an optical filter to provide light at 600 nm with a 40 nm bandwidth.

⁴ For information, see Chevalier, P., "Formazine Standard for Turbidity," Brasserie, Vol 152, 1959, pp. 132–133.

4.3 This test method is recommended only for mineral insulating oils and is not intended to be used on other fluids.

5. Significance and Use

5.1 This test method uses a ratio turbidimetric optical system to measure the turbidity of insulating oils relative to turbidity standards. Cloudiness or turbidity is attributed to matter whose diameter is approximately 20 % of the wavelength of the incident light. Increasing turbidity signifies increasing transformer fluid contamination, either from external sources or internal chemical reactions (such as oxidation) that produce fine particulate matter. Other turbidity sources, such as water droplets or gas bubbles, are not of interest in this evaluation of insulating oils. The elimination of these interferences is described in 6.2 and 6.6. This test method quantifies changes which may not be apparent to the unaided human eye.

6. Interferences

6.1 The changed color of the test specimen, as a result of the oxidation process, may cause light absorption at the wave length of the turbidity measurement. This interference is minimized by using light of a narrow bandwidth, which is not absorbed by the test specimen.

6.2 Gas bubbles that are entrained in the test specimen will interfere. If gas bubbles are apparent, measurement should be delayed until all bubbles disappear. This usually will require several minutes.

6.3 Scratches on the test specimen cell can increase the stray light of the optical system resulting in positive interference when performing ultra-low turbidity measurements. The selection of high optical grade cells and coating the outside of the cells with a thin layer of silicone will eliminate this interference.

6.4 The use of matched test specimen cells that are inserted into the measurement instrument in a consistent orientation will result in consistent measurements.

6.5 The turbidity of the sample can be influenced by the temperature of the sample. The test specimen, therefore, always should be analyzed at room temperature between 20 to 30°C.

6.6 When cloudiness in the oil test specimen is visible to the naked eye, it should be tested first for excessive water content in accordance with Test Methods D1533. If excessive water is confirmed present, a new sample should be obtained for turbidity testing. Moisture contained in the test specimen cells may generate a two-phased test specimen. As a precaution, dry test specimen cells by placing them upright, with caps removed, in an oven at 105°C for 1 h.

7. Apparatus

7.1 *Turbidimeter and Cells*,⁵ a ratioing turbidimeter equipped with a 600 nm interference filter assembly having the following characteristics:

Center Wavelength	600 ± 6 nm
Band Width	40 ± 8 nm

⁵ A suitable turbidimeter and accessories are obtainable from Hach Company, P.O. Box 389, Loveland, CO 80539.

(Warning—In this application, the test specimens are often highly colored with products of oxidation. This color will interfere with the turbidity measurements. This interference is the result of the absorption of energy by the colored sample for instruments whose light source emits a broad spectrum of visible radiation. The above wavelength conditions have been found to minimize this interference and provide the most reliable turbidity measurement.)

7.2 *Volumetric Flasks*, Class A, 2 × 100 mL, 1 × 200 mL and 1 × 1 L.

7.3 *Volumetric Pipets*, Class A, 5 mL and 25 mL.

7.4 *Filtration Equipment*, membrane filter equipment with membranes having a pore size of 0.2 µm or less.

7.5 *Degassing Equipment*, such as an ultrasonic bath.

7.6 *Oiling Cloth*, a soft, lint-free cotton cloth for removing excess silicone from the test specimen cell.

8. Reagents

8.1 *Water*, deionized water that has been filtered through a 0.2 µm or smaller membrane filter and free of turbidity.

8.2 *Formazine*, primary stock standard solution with a turbidity of 4000 NTU (see Appendix X1 for preparation of formazine solution).

8.3 *Silicone Oil*, a silicone fluid meeting Specification D4652.

8.4 *Turbidity Standards*, as an alternative to turbidity standard preparation, stable turbidity standards are available from most laboratory supply companies.

9. Sampling

9.1 Insulating oils for this test should be sampled in accordance with Test Method D923.

10. Procedure

10.1 Calibrate the turbidimeter according to the manufacturer’s directions. Use the calibration standards of 0, 20.0, 200 and 500 NTU prepared as directed in Table 1 from the 4000 NTU stock solution. Calibrate turbidimeter quarterly or as needed.

10.2 Wash test specimen cells with a solvent that will dissolve oil, such as petroleum ether, and remove all oil residues. Wash cells again with water and detergent. Rinse cells three times with filtered, deionized water.

10.3 Place test specimen cells with opening upright and caps removed in an oven at 105°C for 1 h. Cool in a desiccator. Cap immediately when cool to prevent cell contamination.

TABLE 1 Preparation of Calibration Solutions

Calibration Standard Concentration (NTU)	Volumetric Flask to Be Used	Volumetric Pipet to Be Used	Dilution mL Stock Formazine by Filtered Water
Blank	n/a	n/a	none
20.0 NTU	1 L	5.00 mL	5.00 mL to 1 L
200 NTU	100 mL	5.00 mL	5.00 mL to 100 mL
500 NTU	200 mL	25.0 mL	25.0 mL to 200 mL