



SLOVENSKI STANDARD

SIST EN 1563:2012

01-februar-2012

Nadomešča:

SIST EN 1563:1998

SIST EN 1563:1998/A1:2003

SIST EN 1563:1998/A2:2005

Livarstvo - (Siva) litina s kroglastim grafitom

Founding - Spheroidal graphite cast irons

Gießereiwesen - Gusseisen mit Kugelgraphit

Fonderie - Fontes à graphite sphéroïdal

STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/f76f8fb1-d962-4383-ae9e-230706ecbb8a/sist-en-1563-2012>

Ta slovenski standard je istoveten z: EN 1563:2011

ICS:

77.080.10

Železo

Irons

SIST EN 1563:2012

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1563:2012

<https://standards.iteh.ai/catalog/standards/sist/f76f8fb1-d962-4383-ac9e-230706ecbb8a/sist-en-1563-2012>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1563

December 2011

ICS 77.080.10

Supersedes EN 1563:1997

English Version

Founding - Spheroidal graphite cast irons

Fonderie - Fontes à graphite sphéroïdal

Gießereiwesen - Gusseisen mit Kugelgraphit

This European Standard was approved by CEN on 12 November 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

SIST EN 1563:2012

<https://standards.iteh.ai/catalog/standards/sist/f76f8fb1-d962-4383-ae9e-230706ecbb8a/sist-en-1563-2012>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Designation	6
5 Order information	7
6 Manufacture.....	7
7 Requirements	7
7.1 General.....	7
7.2 Ferritic to pearlitic spheroidal graphite cast irons.....	8
7.3 Solid solution strengthened ferritic spheroidal graphite cast irons	11
8 Sampling	12
8.1 General.....	12
8.2 Cast samples	13
8.3 Samples cut from a casting	14
9 Test methods.....	19
9.1 Tensile test	19
9.2 Impact test	20
9.3 Hardness test	21
9.4 Graphite structure examination	21
10 Retests	21
10.1 Need for retests.....	21
10.2 Test validity	22
10.3 Non-conforming test results	22
10.4 Heat treatment of samples and castings	22
11 Inspection documentation	22
Annex A (informative) Additional information on solid solution strengthened ferritic spheroidal graphite cast irons.....	23
Annex B (informative) Guidance values for mechanical properties measured on test pieces machined from samples cut from the castings	27
Annex C (informative) Guidance values for hardness.....	29
Annex D (informative) Nodularity	31
Annex E (informative) Additional information on mechanical and physical properties	32
Annex F (informative) Fracture toughness, impact energy and ductility of spheroidal graphite cast irons	34
Annex G (normative) Sectioning procedure for cast samples	38
Annex H (informative) Comparison of spheroidal graphite cast iron material designations according to EN 1560 [1] and ISO/TR 15931 [24].....	39
Annex I (informative) Un-notched impact test.....	40
Annex J (informative) Significant technical changes between this European Standard and the previous edition	42
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EC Directive 97/23/EC	44
Bibliography	45

ITeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1563:2012

<https://standards.iteh.ai/catalog/standards/sist/176f8fb1-d962-4383-ac9e-230706ecbb8a/sist-en-1563-2012>

Foreword

This document (EN 1563:2011) has been prepared by Technical Committee CEN/TC 190 “Foundry technology”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2012, and conflicting national standards shall be withdrawn at the latest by June 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1563:1997.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive 97/23/EC, see informative Annex ZA, which is an integral part of this document.

Within its programme of work, Technical Committee CEN/TC 190 requested CEN/TC 190/WG 7 “Spheroidal graphite, silicon molybdenum and austempered ductile iron” to revise EN 1563:1997.

Annex J provides details of significant technical changes between this European Standard and the previous edition.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

The properties of spheroidal graphite cast irons depend on their structure.

Spheroidal graphite cast irons covered by this European Standard are divided in two groups:

- 1) ferritic to pearlitic spheroidal graphite cast irons which were in the previous standard;
- 2) solid-solution strengthened ferritic spheroidal graphite cast irons which were not in the previous standard.

The two groups present specific properties, for example:

- the ferritic grades of the first group present the highest impact energy;
- the pearlite containing grades are more suitable for wear resistance applications;
- the solid-solution strengthened ferritic grades present for an equivalent tensile strength a higher proof strength and a higher elongation than that of the ferritic to pearlitic grades;
- a significant property of these solid-solution strengthened ferritic grades is the reduced hardness variation resulting in an improved machinability.

The mechanical properties of the material can be evaluated on machined test pieces prepared from:

- separately cast samples;
- side-by-side cast samples;
- cast-on samples;
- samples cut from a casting.

The material grade is defined by mechanical properties measured on machined test pieces prepared from cast samples.

If hardness or un-notched impact energy are a requirement of the purchaser as being important for the application, then Annex C or Annex I provide means for its determination.

It is well known that tensile properties and hardness of spheroidal graphite cast irons are interrelated. When considered by the purchaser as being important for the application, both tensile and hardness properties may be specified.

Further technical data on spheroidal graphite cast irons is given in Annexes A, E and F.

In this European Standard a new designation system by number, as established in EN 1560:2011 [1], is given.

NOTE This designation system by number is based on the structure and rules of EN 10027-2 [2] and so corresponds with the European numbering system for steel and other materials.

Some spheroidal graphite cast iron grades can be used for pressure equipment.

The permitted material grades of spheroidal graphite cast iron for pressure applications and the conditions for their use are given in specific product or application standards.

For the design of pressure equipment, specific design rules apply.

Annex ZA gives information relating to the conformance of permitted spheroidal graphite cast iron grades to the Pressure Equipment Directive 97/23/EC.

1 Scope

This European Standard defines the grades and the corresponding requirements for spheroidal graphite cast irons.

This European Standard specifies 2 groups of spheroidal graphite cast iron grades by a classification based on mechanical properties measured on machined test pieces prepared from cast samples. The first group deals with ferritic to pearlitic grades. The second group deals with solid-solution strengthened ferritic grades.

This European Standard does not cover technical delivery conditions for iron castings (see EN 1559-1 [3] and EN 1559-3 [4]).

This European Standard does not cover all aspects of:

- ausferritic spheroidal graphite cast irons which are specified in EN 1564 [5];
- low alloyed ferritic spheroidal graphite cast irons which are specified in EN 16124 [6];
- austenitic cast irons which are specified in EN 13835 [7];
- spheroidal graphite cast irons used for pipes, fittings and their joints which are the subject of EN 545 [8], EN 598 [9] and EN 969 [10];
- the grades of spheroidal graphite cast iron as specified in EN 545 which are used for products such as industrial valves, non industrial manually operated shut-off valves and flanges and their joints, which are the subject of the applicable European product standards.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 764-5:2002, *Pressure Equipment — Part 5: Compliance and Inspection — Documentation of Materials*

EN 10204:2004, *Metallic products — Types of inspection documents*

EN ISO 148-1:2010, *Metallic materials — Charpy impact test — Part 1: Test method (ISO 148-1:2009)*

EN ISO 945-1:2008, *Microstructure of cast irons — Part 1: Graphite classification by visual analysis (ISO 945-1:2008)*

EN ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method (ISO 6506-1)*

EN ISO 6892-1:2009, *Metallic materials — Tensile testing — Part 1: Method of test at ambient temperature (ISO 6892-1:2009)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

spheroidal graphite cast iron

cast material, iron, carbon and silicon-based, the carbon being present mainly in the form of spheroidal graphite particles

NOTE Spheroidal graphite cast iron is also known as ductile iron, and less commonly as nodular iron.

EN 1563:2011 (E)**3.2****ferritic to pearlitic spheroidal graphite cast iron**

spheroidal graphite cast iron with a matrix containing ferrite or pearlite or a combination of both

NOTE Pearlite can be partially or totally replaced by bainite or tempered martensite in grades having higher strength

3.3**solid-solution strengthened ferritic spheroidal graphite cast iron**

spheroidal graphite cast iron with a matrix mainly consisting of ferrite, solution strengthened mainly by silicon

3.4**graphite spheroidizing treatment**

operation that brings the liquid iron into contact with a substance to produce graphite in the predominantly spheroidal (nodular) form during solidification

NOTE This operation is often followed by a second one called inoculation.

3.5**cast sample**

quantity of material cast to represent the cast material, including separately cast sample, side by side cast sample and cast-on sample

3.6**separately cast sample**

sample cast in a separate sand mould under representative manufacturing conditions and material grade

3.7**side-by-side cast sample**

sample cast in the mould alongside the casting, with a joint running system

3.8**cast-on sample**

sample attached directly to the casting

SIST EN 1563:2012
<https://standards.iteh.ai/catalog/standards/sist/f76f8fb1-d962-4383-ae9e-230706ecbb8a/sist-en-1563-2012>

3.9**relevant wall thickness**

wall thickness representative of the casting, defined for the determination of the size of the cast samples to which the mechanical properties apply

4 Designation

The material shall be designated either by symbol or by number as given in Tables 1, 2 or 3.

In the case of samples cut from the casting the letter C is added at the end of the designation by symbol.

NOTE The comparison of EN 1563 grade designations with the grades from the ISO standard for spheroidal graphite cast iron, ISO 1083:2004 [11], is given in Annex H.

5 Order information

The following information shall be supplied by the purchaser:

- a) the number of this European Standard;
- b) the designation of the material;
- c) the relevant wall thickness;
- d) any special requirements.

All requirements shall be agreed between the manufacturer and the purchaser by the time of acceptance of the order (e.g. technical delivery conditions according to EN 1559-1 and EN 1559-3).

6 Manufacture

The method of producing spheroidal graphite cast irons and their chemical composition shall be left to the discretion of the manufacturer who shall ensure that the requirements of this European Standard are met for the material grade specified in the order.

- ferritic to pearlitic spheroidal graphite cast irons.
For these grades, the level of the mechanical properties is determined by the ferrite to pearlite ratio. This ratio is normally adjusted by alloying with pearlite stabilising elements or, less commonly, by heat treatment.
- solid-solution strengthened ferritic spheroidal graphite cast irons.
For these grades, the level of the mechanical properties is determined by the extent of solid solution strengthening of the ferritic matrix. This extent is normally governed by the silicon content.

NOTE For spheroidal graphite cast irons to be used in special applications, the chemical composition and heat treatment may be the subject of an agreement between the manufacturer and the purchaser.

All agreements between the manufacturer and the purchaser shall be made by the time of the acceptance of the order.

7 Requirements

7.1 General

The property values apply to spheroidal graphite cast irons cast in sand moulds or moulds of comparable thermal behaviour. Subject to amendments to be agreed upon in the order, they can apply to castings obtained by alternative methods.

The material designation is based on the minimum mechanical properties obtained in cast samples with a thickness or diameter of 25 mm. The designation is irrespective of the type of cast sample.

Mechanical properties are wall thickness dependant as shown in Tables 1, 2 and 3. For relevant wall thicknesses more than 200 mm, the manufacturer and the purchaser shall agree on the minimum values to be obtained and the type and size of the cast sample.

NOTE Tensile testing requires sound test pieces in order to guarantee pure uni-axial stress during the test.

EN 1563:2011 (E)**7.2 Ferritic to pearlitic spheroidal graphite cast irons****7.2.1 Test pieces machined from cast samples****7.2.1.1 Tensile properties**

The mechanical properties of ferritic to pearlitic spheroidal graphite cast iron test pieces shall be as specified in Table 1.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1563:2012](https://standards.iteh.ai/catalog/standards/sist/f76f8fb1-d962-4383-ae9e-230706ecbb8a/sist-en-1563-2012)

<https://standards.iteh.ai/catalog/standards/sist/f76f8fb1-d962-4383-ae9e-230706ecbb8a/sist-en-1563-2012>

Table 1 — Mechanical properties measured on test pieces machined from cast samples for ferritic to pearlitic grades

Material designation		Relevant wall thickness	0,2 % proof strength	Tensile strength	Elongation
Symbol	Number	t mm	$R_{p0,2}$ MPa min	R_m MPa min	A % min
EN-GJS-350-22-LT ^a	5.3100	$t \leq 30$	220	350	22
		$30 < t \leq 60$	210	330	18
		$60 < t \leq 200$	200	320	15
EN-GJS-350-22-RT ^b	5.3101	$t \leq 30$	220	350	22
		$30 < t \leq 60$	220	330	18
		$60 < t \leq 200$	210	320	15
EN-GJS-350-22	5.3102	$t \leq 30$	220	350	22
		$30 < t \leq 60$	220	330	18
		$60 < t \leq 200$	210	320	15
EN-GJS-400-18-LT ^a	5.3103	$t \leq 30$	240	400	18
		$30 < t \leq 60$	230	380	15
		$60 < t \leq 200$	220	360	12
EN-GJS-400-18-RT ^b	5.3104	$t \leq 30$	250	400	18
		$30 < t \leq 60$	250	390	15
		$60 < t \leq 200$	240	370	12
EN-GJS-400-18	5.3105	$t \leq 30$	250	400	18
		$30 < t \leq 60$	250	390	15
		$60 < t \leq 200$	240	370	12
EN-GJS-400-15	5.3106	$t \leq 30$	250	400	15
		$30 < t \leq 60$	250	390	14
		$60 < t \leq 200$	240	370	11
EN-GJS-450-10	5.3107	$t \leq 30$ $30 < t \leq 60$ $60 < t \leq 200$	310 to be agreed upon between the manufacturer and the purchaser	450	10
EN-GJS-500-7	5.3200	$t \leq 30$	320	500	7
		$30 < t \leq 60$	300	450	7
		$60 < t \leq 200$	290	420	5
EN-GJS-600-3	5.3201	$t \leq 30$	370	600	3
		$30 < t \leq 60$	360	600	2
		$60 < t \leq 200$	340	550	1
EN-GJS-700-2	5.3300	$t \leq 30$	420	700	2
		$30 < t \leq 60$	400	700	2
		$60 < t \leq 200$	380	650	1
EN-GJS-800-2	5.3301	$t \leq 30$	480	800	2
		$30 < t \leq 60$ $60 < t \leq 200$	to be agreed upon between the manufacturer and the purchaser		
EN-GJS-900-2	5.3302	$t \leq 30$	600	900	2
		$30 < t \leq 60$ $60 < t \leq 200$	to be agreed upon between the manufacturer and the purchaser		

NOTE The mechanical properties of test pieces machined from cast samples may not reflect exactly the properties of the casting itself. Values for tensile properties of the casting are given in Annex B for guidance.

^a LT for low temperature.

^b RT for room temperature.

EN 1563:2011 (E)

7.2.1.2 Impact energy

The impact energy values given in Table 2 for room temperature (RT) and low temperature (LT) applications, if applicable, shall only be determined if specified by the purchaser by the time of acceptance of the order.

NOTE The use of impact energy is currently being reassessed regarding its limited relevance as a measure of resistance to brittle fracture in castings subject to application loads. Annex F gives information about fracture toughness, impact energy and ductility.

Table 2 — Minimum impact energy values measured on V-notched test pieces machined from cast samples for ferritic grades of the ferritic to pearlitic group

Material designation		Relevant wall thickness t mm	Minimum impact energy values					
			J					
			Room temperature (23 ± 5) °C		Low temperature (– 20 ± 2) °C		Low temperature (– 40 ± 2) °C	
Symbol	Number		Mean value (3 tests)	Individual value	Mean value (3 tests)	Individual value	Mean value (3 tests)	Individual value
EN-GJS-350-22-LT	5.3100	$t \leq 30$	—	—	—	—	12	9
		$30 < t \leq 60$	—	—	—	—	12	9
		$60 < t \leq 200$	—	—	—	—	10	7
EN-GJS-350-22-RT	5.3101	$t \leq 30$	17	14	—	—	—	—
		$30 < t \leq 60$	17	14	—	—	—	—
		$60 < t \leq 200$	15	12	—	—	—	—
EN-GJS-400-18-LT	5.3103	$t \leq 30$	—	—	12	9	—	—
		$30 < t \leq 60$	—	—	12	9	—	—
		$60 < t \leq 200$	—	—	10	7	—	—
EN-GJS-400-18-RT	5.3104	$t \leq 30$	14	11	—	—	—	—
		$30 < t \leq 60$	14	11	—	—	—	—
		$60 < t \leq 200$	12	9	—	—	—	—

NOTE The mechanical properties of test pieces machined from cast samples may not reflect exactly the properties of the casting itself.

7.2.2 Test pieces machined from samples cut from a casting

If applicable, the manufacturer and the purchaser shall agree on:

- the location(s) on a casting where the sample(s) shall be taken;
- the mechanical properties that shall be measured;
- the minimum values, or allowable range of values, for these mechanical properties (for information, see Annex B).

NOTE 1 The properties of castings may not be uniform, depending on the complexity of the castings and variation in their section thickness.

NOTE 2 Mechanical properties for test pieces cut from a casting are affected not only by material properties (subject of this European Standard) but also by the local casting soundness (not subject of this standard).

7.2.3 Hardness

Brinell hardness and its range values for the grades listed in Table 1 and 3 shall only be specified when agreed between the manufacturer and the purchaser by the time of acceptance of the order.

Information regarding hardness is given in Annex C.

7.2.4 Graphite structure

The graphite structure shall be mainly of form V and VI in accordance with EN ISO 945-1. A more precise definition may be agreed upon by the time of acceptance of the order.

NOTE Annex D gives more information on nodularity.

7.2.5 Matrix structure

Information regarding the matrix structure is given in Table E.1.

7.3 Solid solution strengthened ferritic spheroidal graphite cast irons

7.3.1 Test pieces machined from cast samples

The mechanical properties of solid solution strengthened ferritic spheroidal graphite cast iron test pieces shall be as specified in Table 3.

Table 3 — Mechanical properties measured on test pieces machined from cast samples for solid solution strengthened ferritic grades

Material designation		Relevant wall thickness	0,2 % proof strength	Tensile strength	Elongation
Symbol	Number	t mm	$R_{p0,2}$ MPa min	R_m MPa min	A % min
EN-GJS-450-18	5.3108	$t \leq 30$	350	450	18
		$30 \leq t \leq 60$	340	430	14
		$t > 60$	to be agreed upon between the manufacturer and the purchaser		
EN-GJS-500-14	5.3109	$t \leq 30$	400	500	14
		$30 \leq t \leq 60$	390	480	12
		$t > 60$	to be agreed upon between the manufacturer and the purchaser		
EN-GJS-600-10	5.3110	$t \leq 30$	470	600	10
		$30 \leq t \leq 60$	450	580	8
		$t > 60$	to be agreed upon between the manufacturer and the purchaser		

NOTE The mechanical properties of test pieces machined from cast samples may not reflect exactly the properties of the casting itself. Values for tensile properties of the casting are given in Annex B for guidance.