
**Rubber, vulcanized or thermoplastic —
Determination of indentation hardness —
Part 1:
Durometer method (Shore hardness)**

*Caoutchouc vulcanisé ou thermoplastique — Détermination de la
dureté par pénétration —
Partie 1: Méthode au duromètre (dureté Shore)*

[ISO 7619-1:2004](https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004)

[https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-
2c73069a148c/iso-7619-1-2004](https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 7619-1:2004

<https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle and choice of durometer type	1
4 Apparatus	2
5 Test piece	5
6 Conditioning	5
7 Procedure	5
8 Calibration and checking	6
9 Test report	6
Bibliography	8

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 7619-1:2004](https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7619-1 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*, Subcommittee SC 2, *Testing and analyses*.

This first edition of ISO 7619-1, together with ISO 7619-2, cancels and replaces ISO 7619:1997, which has been technically revised as follows in respect of the durometer method now covered exclusively by Part 1:

- a specified pressure-foot area has been introduced;
- a test time of 3 s replaces the formerly specified "within 1 s", giving a more accurate value, as the hardness value drops significantly during the first few seconds;
- a test time of 15 s has been introduced for TPE materials, as the hardness value continues to decrease over a longer period of time than for vulcanized rubber, this test time being the same as that specified for plastics in ISO 868 [1];
- the AO scale for soft materials has been added;
- the AM scale for thin samples has been added;
- the use of stands is described in more detail;
- changes of tolerances, etc. have been made to improve precision.

ISO 7619 consists of the following parts, under the general title *Rubber, vulcanized or thermoplastic — Determination of indentation hardness*:

- *Part 1: Durometer method (Shore hardness)*
- *Part 2: IRHD pocket meter method*

Introduction

The hardness of rubber, as measured by the durometer or the IRHD pocket meter, is a complex response to an applied indentation. The measurement will depend upon

- a) the elastic modulus of the rubber,
- b) the viscoelastic properties of the rubber,
- c) the thickness of the test piece,
- d) the geometry of the indenter,
- e) the pressure exerted,
- f) the rate of increase of pressure, and
- g) the interval at which the hardness is recorded.

Because of these factors, it is inadvisable to relate results using a durometer directly to IRHD values, although correlations have been established for some individual rubbers or compounds.

NOTE ISO 48^[2] specifies hardness measurements for determination of hardness between 10 IRHD and 100 IRHD. Further information on the relation between the durometer values and IRHD values is given in the literature ^{[5], [6], [7]}.

[ISO 7619-1:2004](https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 7619-1:2004

<https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004>

Rubber, vulcanized or thermoplastic — Determination of indentation hardness —

Part 1: Durometer method (Shore hardness)

1 Scope

This part of ISO 7619 specifies a method for determining the indentation hardness (Shore hardness) of vulcanized or thermoplastic rubber using durometers with the following scales:

- the A scale for rubbers in the normal hardness range;
- the D scale for rubbers in the high hardness range;
- the AO scale for rubbers in the low hardness range and cellular rubbers;
- the AM scale for thin rubber test pieces in the normal hardness range.

2 Normative references

ISO 7619-1:2004

<https://standards.iteh.ai/catalog/standards/sist/73fd879-2dca-4de3-8719-2c73069a148c/iso-7619-1-2004>

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 23529, *Physical test methods — Preparation and conditioning of test pieces and preferred test conditions*¹⁾

3 Principle and choice of durometer type

The measured property is the penetration of a specified indenter forced into the material under specified conditions.

When using durometers, the scale should be chosen as follows.

- For values less than 20 with Type D durometer: Type A.
- For values less than 20 with Type A durometer: Type AO.
- For values over 90 with Type A durometer: Type D.
- For thin test pieces (less than 6 mm thick): Type AM.

1) To be published. (Revision of ISO 471:1995)

4 Apparatus

4.1 Durometer Types A, D and AO

These durometers consist of the components specified in 4.1.1 to 4.1.5.

4.1.1 Pressure foot

The pressure foot for Types A and D shall have a diameter of $18 \text{ mm} \pm 0,5 \text{ mm}$ and a central hole of diameter $3 \text{ mm} \pm 0,1 \text{ mm}$. For Type AO, the pressure foot shall have a minimum area of 500 mm^2 with a $5,4 \text{ mm} \pm 0,2 \text{ mm}$ central hole. The tolerances on the dimension of the centre hole and the requirement for the size of the pressure foot only apply to instruments used on a stand.

4.1.2 Indentor

The indentor shall be formed from a hardened steel rod of $1,25 \text{ mm} \pm 0,15 \text{ mm}$ diameter to the shape and dimension shown in Figure 1, for Type A durometers, and Figure 2 for Type D durometers. Type AO durometers shall have a round indentor with a radius of $2,5 \text{ mm} \pm 0,02 \text{ mm}$ according to Figure 3.

4.1.3 Indicating device

This is a device for allowing the extent of protrusion of the point of the indentor beyond the face of the pressure foot to be read. It shall be calibrated directly in terms of units ranging from 0 for the maximum protrusion of $2,50 \text{ mm} \pm 0,02 \text{ mm}$ to 100 for zero protrusion obtained by placing the pressure foot and indentor in firm contact with a suitable flat hard surface.

4.1.4 Calibrated spring

This shall be used to apply a force, F , expressed in millinewtons, to the indentor in accordance with one of the following equations.

— For durometer Type A:

$$F = 550 + 75 H_A$$

where H_A is the hardness reading taken from a Type A durometer.

— For durometer Type D:

$$F = 445 H_D$$

where H_D is the hardness reading taken from a Type D durometer.

— For durometer Type AO:

$$F = 550 + 75 H_{AO}$$

where H_{AO} is the hardness reading taken from a Type AO durometer.

4.1.5 Automatic timing device (optional)

The timer shall be automatically activated when the pressure foot is in contact with the test piece, and shall indicate the end of the test time or lock the test value at its completion. Use of a timing device for the test time improves precision. When used in a stand, the time tolerance shall be $\pm 0,3 \text{ s}$.

4.2 Durometer Type AM

This durometer consists of the components specified in 4.2.1 to 4.2.5.

4.2.1 Pressure foot

The pressure foot shall have a diameter of $9 \text{ mm} \pm 0,3 \text{ mm}$ and a central hole of diameter $1,19 \text{ mm} \pm 0,03 \text{ mm}$.

4.2.2 Indentor

The indentor shall be formed from a hardened steel rod of $0,79 \text{ mm} \pm 0,025 \text{ mm}$ diameter to the shape and dimension shown in Figure 4.

4.2.3 Indicating device

This is a device for allowing the extent of protrusion of the point of the indentor beyond the face of the pressure foot to be read. It shall be calibrated directly in terms of units ranging from 0 for the maximum protrusion of $1,25 \text{ mm} \pm 0,01 \text{ mm}$ to 100 for zero protrusion obtained by placing the pressure foot and indentor in firm contact with a suitable flat hard surface.

4.2.4 Calibrated spring

To shall be used to apply a force, F , expressed in millinewtons, to the indentor in accordance with the equation:

$$F = 324 + 4,4 H_{AM}$$

where H_{AM} is the hardness reading taken from a Type AM durometer.

4.2.5 Automatic timing device (optional)

The timer shall be automatically activated when the pressure foot is in contact with the test piece, and shall indicate the end of the test time or lock the test value at its completion. Use of a timing device for the test time improves precision. When used in a stand, the time tolerance shall be $\pm 0,3 \text{ s}$.

4.3 Stand

Better precision is obtained by using a stand with a weight centred on the axis of the indentor to apply the pressure foot to the test piece. Durometer Types A, D and AO may be used either as pocket meters by hand, or mounted on a stand. Durometer Type AM shall always be mounted on a stand.

4.3.1 General

The operating stand shall be capable of supporting the durometer pressure-foot surface parallel to the test piece support table.

4.3.2 Operating speed

The stand shall be capable of applying the test piece to the indentor, or vice versa, without shock, at a maximum speed of $3,2 \text{ mm/s}$.