



SLOVENSKI STANDARD
SIST ISO 18920:2011

01-julij-2011

Upodobitveni materiali - Procesirani fotografski refleksijski natisi - Shranjevanje

Imaging materials - Processed photographic reflection prints - Storage practices

Matériaux pour image - Tirages photographiques traités par réflexion - Directives pour l'archivage

(standards.iteh.ai)

Ta slovenski standard je istoveten z: ISO 18920:2000

<https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011>

ICS:

37.040.20	Fotografski papir, filmi in fotografske plošče. Filmski zvitki	Photographic paper, films and cartridges
-----------	--	--

SIST ISO 18920:2011

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 18920:2011

<https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011>

INTERNATIONAL
STANDARD

ISO
18920

First edition
2000-07-15

**Imaging materials — Processed
photographic reflection prints — Storage
practices**

*Matériaux pour image — Tirages photographiques traités par réflexion —
Directives pour l'archivage*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 18920:2011](https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011)

[https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-
ed982e3412a2/sist-iso-18920-2011](https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011)



Reference number
ISO 18920:2000(E)

© ISO 2000

ISO 18920:2000(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 18920:2011](https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011)

<https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Enclosures and containers.....	3
5 Storage housings.....	4
6 Storage rooms.....	4
7 Environmental conditions.....	5
8 Fire-protective storage (see annex H)	7
9 Print identification, handling, and inspection (see annexes E, F and I).....	8
Annex A (informative) Numbering system for related International Standards.....	9
Annex B (informative) Humidity during storage	10
Annex C (informative) Temperature during storage.....	11
Annex D (informative) Temperature/relative humidity relationship	12
Annex E (informative) Historic records for photographic prints.....	13
Annex F (informative) Distinction between storage (record) copies and work (reference) copies	14
Annex G (informative) Air-entrained and gaseous impurities	15
Annex H (informative) Fire protection	16
Annex I (informative) Silver image degradation.....	17
Bibliography	18

ISO 18920:2000(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 18920 was prepared by Technical Committee ISO/TC 42, *Photography*.

This first edition cancels and replaces the fourth edition of ISO 6051 (ISO 6051:1997), and is mainly an editorial revision.

iTeh STANDARD PREVIEW

This International Standard is one of a series of standards dealing with the physical properties and stability of imaging materials. To facilitate identification of these International Standards, they are assigned a number within the block from 18900 to 18999 (see annex A).

[SIST ISO 18920:2011](https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011)

Annexes A to I of this International Standard are for information only.

<https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011>

Introduction

Photographic and other reflection prints, including hard-copy output from digital imaging systems, have become increasingly important as documentary and pictorial reference material in archives, libraries, government, commerce and academia. This has focused attention on the importance of the preservation of such materials to ensure their longest possible life.

The stability and useful life of photographic reflection prints depend on their physical and chemical properties and the processing, as well as on the conditions under which they are stored and used. This International Standard provides recommendations on proper storage conditions and practices.

The important elements affecting the useful life of photographic reflection prints during storage are as follows:

- relative humidity and temperature of the storage environment;
- hazards of fire, water, and light exposure;
- fungal growth and other micro-organisms;
- contact with certain chemicals in solid, liquid, or gaseous form;
- physical damage.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

The extent to which the relative humidity and temperature of the storage environment, or variations of both, can be permitted to reach beyond recommended limits without producing adverse effects will depend upon the duration of exposure, biological conditions conducive to fungal growth, and the accessibility of the atmosphere to the print surfaces.

The term “archival” is no longer used to express longevity or stability in International Standards on imaging materials since it has been interpreted to have many meanings, ranging from preserving documents “forever”, which is unattainable, to temporary storage of actively used materials.

This International Standard defines two levels of recommended storage conditions: medium-term and extended-term. Medium-term storage conditions can be used to preserve information for a minimum of 10 years. Extended-term storage conditions shall be used when it is desired to preserve information for as long as possible, and these conditions will prolong the life of all prints, even those not optimized for permanence.

The space requirements and costs for establishing and operating the two levels of storage conditions (medium-term and extended-term) differ significantly. Furthermore, the specified limits of temperature and relative humidity for both sets of storage conditions may not be realizable due to budgetary constraints, energy considerations, climatic conditions, building construction, etc. However, it must be recognized that any deviation from the specified conditions will reduce the effectiveness of the storage environment. If such deviation is unavoidable, the lowest possible storage temperature should be provided. In any event, the best preservation of prints will be attained with extended-term storage conditions.

The recommendations of this International Standard for the storage of photographic reflection prints encompass the following:

- storage enclosures, housing, and rooms;
- atmospheric and environmental conditions;
- fire protection;

ISO 18920:2000(E)

— handling and inspection procedures.

With the exception of fire and associated hazards that are sufficiently common to warrant inclusion of protective measures, this International Standard does not pertain to means or methods for protecting photographic reflection prints against natural or man-made catastrophes.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 18920:2011](https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011)

<https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011>

Imaging materials — Processed photographic reflection prints — Storage practices

1 Scope

1.1 This International Standard specifies dark storage conditions, storage facilities, and procedures for the handling and inspection of photographic reflection prints of all types and sizes.

1.2 This International Standard is applicable to photographic reflection prints on the following opaque supports:

- fibre-base paper;
- RC (resin coated) paper;
- plastic films (polyester, cellulose acetate, etc.).

1.2.1 This International Standard is applicable to the following black-and-white silver gelatin prints:

- wet-processed, including those that have been chemically treated to improve the permanence of the silver image and/or to modify its colour (e.g. with gold, selenium or sulfur formulations);
- diffusion transfer (e.g. Polaroid and Fuji Photo Film instant prints¹⁾);
- stabilization-processed (which contain the silver image as well as invisible, chemically stabilized silver halides);
- heat-processed.

1.2.2 This International Standard is applicable to the following multicolour and monochrome photographic prints:

- chromogenic, washed and stabilized;
- silver dye bleach;
- dye transfer;
- diffusion transfer (e.g. Polaroid and Fuji Photo Film instant prints¹⁾, peel-apart or integral);
- pigmented gelatin (carbon, carbro, etc.).

1.2.3 This International Standard is applicable to black-and-white and colour photographic reflection prints made with the following systems:

- thermal dye transfer (commonly referred to as dye sublimation);

1) Polaroid and Fuji Photo Film instant prints are examples of suitable products available commercially. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of these products.

ISO 18920:2000(E)

- thermal wax transfer;
- electrophotographic;
- ink jet;
- diazo.

1.3 Recommendations for storage of photographic films are given in ISO 18911 and for storage of processed photographic plates in ISO 18918. Print material on translucent film supports intended to be viewed primarily by transmitted light should be stored in accordance with ISO 18911.

1.4 This International Standard is applicable to medium-term and extended-term storage conditions as defined in clause 3.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 14523:1999, *Photography — Processed photographic materials — Photographic activity test for enclosure materials*.

ISO 18902:—²⁾, *Imaging materials — Processed films, plates and papers — Filing enclosures and storage containers*.

ISO 18911:—²⁾, *Imaging materials — Processed safety photographic films — Storage practices*.

ISO 18918:2000, *Imaging materials — Processed photographic plates — Storage practices*.

3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

3.1 archival medium

recording material that can be expected to retain information forever, so that such information can be retrieved without significant loss when properly stored

NOTE There is, however, no such material and it is not a term to be used in International Standards or system specifications.

3.2 extended-term storage conditions

storage conditions suitable for the preservation of recorded information having a permanent value

2) To be published.

3.3**fire-protective storage**

facility designed to protect records against excessive temperatures, water and other fire-fighting agents, and steam developed by insulation of safes or caused by the extinguishing of fires and collapsing structures

3.4**fire-resistant vaults**

fire-resistant vaults as defined in appropriate national standards and regulations [1, 2]³⁾

3.5**insulated record containers (Class 150)**

insulated record containers (Class 150) as defined in appropriate national standards and regulations [3, 4]

3.6**life expectancy****LE**

length of time that information is predicted to be acceptable in a system at 21 °C and 50 % RH

3.7**medium-term storage conditions**

storage conditions suitable for the preservation of recorded information for a minimum of 10 years

3.8**storage container**

box or can used to store prints

3.9**storage enclosure**

any item in close or direct contact with recording material such as folders, envelopes, sleeves, albums and mats

3.10**storage housing**

physical structure supporting materials and their enclosures

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 18920:2011](https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011)

<https://standards.iteh.ai/catalog/standards/sist/9b8d9587-b19d-46e6-a8d9-ed982e3412a2/sist-iso-18920-2011>

NOTE It may consist of drawers, racks, shelves or cabinets.

4 Enclosures and containers

All enclosures and containers used for medium-term and extended-term storage shall meet the requirements of ISO 18902 and ISO 14523. This includes enclosures and containers that are in either direct or indirect contact with the prints. Photographic reflection prints may be stored in envelopes or sleeves of paper or plastic, file folders, folding cartons, boxes, and albums, or may be matted. Photographic reflection prints should be protected from unnecessary light exposure, especially colour and diazo prints which shall not be exposed at all.

Generally, prints smaller than 28 cm × 36 cm in size may be stored vertically, but shall be placed between rigid supports to minimize slumping and curling. Prints 28 cm × 36 cm or larger should be stored horizontally, unless mounted on rigid supports. Stacks of horizontal prints should be less than 5 cm high to prevent excessive pressure on prints at the bottom.

Multiple prints, stored within an enclosure or container, shall be oriented with the emulsion sides against back sides, never emulsion against emulsion.

³⁾ The numbers in square brackets refer to references listed in the bibliography.