

SLOVENSKI STANDARD

SIST EN 10028-4:2009

01-september-2009

BUXca Yý U.

SIST EN 10028-4:2003

SIST EN 10028-4:2003/AC:2006

D`cý Uj`Y_`Yb]`JnXY_`JnUhU bYdcgcXY!`("XY.`>Y_`UZ`Y[]fUbUn`b]`Ya žg
gdYVJZVfUb]a]`Uglbcgla]`df]`b]n_`l `Ya dYfUi fU

Flat products made of steels for pressure purposes - Part 4: Nickel alloy steels with specified low temperature properties

iTeh STANDARD PREVIEW

Flacherzeugnisse aus Druckbehälterstählen - Teil 4: Nickellegierte kaltzähe Stähle
[\(standards.iteh.ai\)](http://standards.iteh.ai/)

Produits plats en aciers pour appareils à pression - Partie 4: Aciers alliés au nickel avec caractéristiques spécifiées à basse température

[SIST EN 10028-4:2009
http://standards.iteh.ai/catalog/standards/sist/en/ed1166b8-5d46-471f-a6ca-31653fc6372a/sist-en-10028-4-2009](http://standards.iteh.ai/catalog/standards/sist/en/ed1166b8-5d46-471f-a6ca-31653fc6372a/sist-en-10028-4-2009)

Ta slovenski standard je istoveten z: **EN 10028-4:2009**

ICS:

77.140.30	Jekla za uporabo pod tlakom	Steels for pressure purposes
77.140.50	Ú[[z æm̄ \ ^} æk å^ \ æ\] [ã å^ \ ã	Flat steel products and semi-products

SIST EN 10028-4:2009

en,fr,de

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

SIST EN 10028-4:2009

<https://standards.iteh.ai/catalog/standards/sist/ed1166b8-5d46-471f-a6ca-31653fc6372a/sist-en-10028-4-2009>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 10028-4

June 2009

ICS 77.140.30; 77.140.50

Supersedes EN 10028-4:2003

English Version

**Flat products made of steels for pressure purposes - Part 4:
 Nickel alloy steels with specified low temperature properties**

Produits plats en aciers pour appareils à pression - Partie
 4: Aciers alliés au nickel avec caractéristiques spécifiées à
 basse température

Flacherzeugnisse aus Druckbehälterstählen - Teil 4:
 Nickellegierte kaltzähe Stähle

This European Standard was approved by CEN on 14 May 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 10028-4:2009](#)

<https://standards.iteh.ai/catalog/standards/sist/ed1166b8-5d46-471f-a6ca-31653fc6372a/sist-en-10028-4-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION
 COMITÉ EUROPÉEN DE NORMALISATION
 EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Dimensions and tolerances on dimensions	4
5 Calculation of mass	4
6 Classification and designation	4
6.1 Classification	4
6.2 Designation	4
7 Information to be supplied by the purchaser	4
7.1 Mandatory information	4
7.2 Options	5
7.3 Example for ordering	5
8 Requirements	5
8.1 Steelmaking process	5
8.2 Delivery condition	5
8.3 Chemical composition	5
8.4 Mechanical properties	SIST EN 10028-4:2009 6
8.5 Surface condition https://standards.itech.ai/catalog/standards/sist/ed1166b8-5d46-471f-acaa-31653fc6372a/sist-en-10028-4-2009	9
8.6 Internal soundness	9
9 Inspection	9
9.1 Types of inspection and inspection documents	9
9.2 Tests to be carried out	9
9.3 Retests	9
10 Sampling	9
11 Test methods	9
12 Marking	9
Annex A (informative) Guidelines for heat treatment	10
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EU Directive 97/23/EC	11
Bibliography	12

Foreword

This document (EN 10028-4:2009) has been prepared by Technical Committee ECISS/TC 22 "Steels for pressure purposes - Qualities", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2009, and conflicting national standards shall be withdrawn at the latest by December 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10028-4:2003.

This European Standard consists of the following parts, under the general title *Flat products made of steels for pressure purposes*:

- Part 1: General requirements
- Part 2: Non-alloy and alloy steels with specified elevated temperature properties
iTeh STANDARD PREVIEW
(standards.iteh.ai)
- Part 3: Weldable fine grain steels, normalized
- Part 4: Nickel alloy steels with specified low temperature properties
- Part 5: Weldable fine grain steels, thermomechanically rolled
[SIST EN 10028-4:2009](#)
http://standards.iteh.ai/standard/SIST-EN-10028-4-2009-1166b8-5d46-471f-a6ca-31653fc6372a/sist-en-10028-4-2009
- Part 6: Weldable fine grain steels, quenched and tempered
- Part 7: Stainless steels

NOTE The clauses marked by two points (••) contain information relating to agreements that may be made at the time of enquiry and order.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive 97/23/EC.

For relationship with EU Directive 97/23/EC, see informative Annex ZA, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

EN 10028-4:2009 (E)

1 Scope

This European Standard specifies requirements for flat products for pressure equipment made of nickel alloy steels as specified in Table 1.

The requirements and definitions of EN 10028-1:2007 + A1:2009 also apply.

NOTE Once this European Standard is published in the EU Official Journal (OJEU) under Directive 97/23/EC, presumption of conformity to the Essential Safety Requirements (ESRs) of Directive 97/23/EC is limited to technical data of materials in this European Standard (Part 1 and this Part 4 of the series) and does not presume adequacy of the material to a specific item of equipment. Consequently, the assessment of the technical data stated in this material standard against the design requirements of this specific item of equipment to verify that the ESRs of Directive 97/23/EC are satisfied, needs to be done.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10028-1:2007 + A1:2009, *Flat products made of steels for pressure purposes – Part 1: General requirements*

EN 10204:2004, *Metallic products – Types of inspection documents*

iTeh STANDARD PREVIEW (standards.iteh.ai)

For the purposes of this document, the terms and definitions given in EN 10028-1:2007 + A1:2009 apply.

SIST EN 10028-4:2009

<https://standards.iteh.ai/catalog/standards/sist/ed1166b8-5d46-471f-a6ca-33f333f333f3>

4 Dimensions and tolerances on dimensions

See EN 10028-1:2007 + A1:2009.

5 Calculation of mass

See EN 10028-1:2007 + A1:2009,

6 Classification and designation

6.1 Classification

In accordance with EN 10020, all steel grades covered by this document are alloy special steels.

6.2 Designation

See EN 10028-1:2007 + A1:2009.

7 Information to be supplied by the purchaser

7.1 Mandatory information

See EN 10028-1:2007 + A1:2009.

7.2 Options

A number of options are specified in this European Standard and listed below. Additionally the relevant options of EN 10028-1:2007 + A1:2009 apply. If the purchaser does not indicate a wish to implement any of these options at the time of enquiry and order, the products shall be supplied in accordance with the basic specification (see also EN 10028-1:2007 + A1:2009).

- 1) delivery condition other than that specified in Table 3 (see 8.2.2);
- 2) delivery of products in the untreated condition (see 8.2.3);
- 3) specification of a minimum impact energy of 40 J (see NOTE to 8.4 and Table 4);
- 4) mid thickness test pieces for the impact test (see Clause 10);
- 5) verification of impact energy for longitudinal test pieces (see Clause 11).

7.3 Example for ordering

10 plates with nominal dimensions, thickness = 50 mm, width = 2 000 mm, length = 10 000 mm, made of a steel grade with the name 15NiMn6 and the number 1.6228 as specified in EN 10028-4, to be delivered with inspection document 3.1 as specified in EN 10204.

10 plates – 50 x 2000 x 10 000 – EN 10028-4 15NiMn6 – Inspection document 3.1

iTeh STANDARD PREVIEW
or
(standards.iteh.ai)

10 plates – 50 x 2000 x 10 000 – EN 10028-4 1.6228 – Inspection document 3.1.

SIST EN 10028-4:2009

8 Requirements <https://standards.iteh.ai/catalog/standards/sist/ed1166b8-5d46-471f-a6ca-31653fc6372a/sist-en-10028-4-2009>

8.1 Steelmaking process

See EN 10028-1:2007 + A1:2009.

8.2 Delivery condition

8.2.1 The delivery condition shall be noted in the inspection document.

8.2.2 Unless otherwise agreed at the time of enquiry and order, the products covered by this document shall be supplied in the usual delivery conditions specified in Table 3.

8.2.3 If so agreed at the time of enquiry and order, the products may be supplied in the untreated condition.

In these cases, the specified tests shall be carried out on test pieces in the usual delivery condition as given in Table 3.

NOTE Testing in a simulated heat treated condition does not discharge the processor from the obligation of providing proof of the specified properties in the finished product.

8.3 Chemical composition

8.3.1 The requirements of Table 1 shall apply for the chemical composition according to the cast analysis.

8.3.2 The product analysis shall not deviate from the specified values for the cast analysis as specified in Table 1 by more than the values given in Table 2.

Table 1 — Chemical composition (cast analysis) ^a

Steel grade		% by mass									
Steel name	Steel number	C max.	Si max.	Mn	P max.	S max.	Al _{total} min.	Mo max.	Nb max.	Ni	V max.
11MnNi5-3	1.6212	0,14	0,50	0,70 to 1,50	0,025	0,010	0,020	—	0,05	0,30 ^b to 0,80	0,05
13MnNi6-3	1.6217	0,16	0,50	0,85 to 1,70	0,025	0,010	0,020	—	0,05	0,30 ^b to 0,85	0,05
15NiMn6	1.6228	0,18	0,35	0,80 to 1,50	0,025	0,010	—	—	—	1,30 to 1,70	0,05
12Ni14	1.5637	0,15	0,35	0,30 to 0,80	0,020	0,005	—	—	—	3,25 to 3,75	0,05
X12Ni5	1.5680	0,15	0,35	0,30 to 0,80	0,020	0,005	—	—	—	4,75 to 5,25	0,05
X8Ni9	1.5662	0,10	0,35	0,30 to 0,80	0,020	0,005	—	0,10	—	8,5 to 10,0	0,05
X7Ni9	1.5663	0,10	0,35	0,30 to 0,80	0,015	0,005	—	0,10	—	8,5 to 10,0	0,01

^a Elements not listed in this Table shall not be intentionally added to the steel without the agreement of the purchaser except for finishing the cast. All appropriate measures shall be taken to prevent the addition from scrap or other materials used in steelmaking of these elements which may adversely affect the mechanical properties and usability. The content of Cr + Cu + Mo shall not exceed 0,50 %.

^b For product thicknesses ≤ 40 mm, a minimum nickel content of 0,15 % is permitted.

Table 2 — Permissible product analysis tolerances on the limiting values given in Table 1 for the cast analysis

Element	Specified value in the cast analysis (according to Table 1) % by mass	Permissible deviation ^a of the product analysis % by mass
C	$\leq 0,18$ SIST EN 10028-4:2009	+ 0,02
Si	$\leq 0,50$ https://standards.iteh.ai/catalog/standards/sist/ed1166b8-5d46-471f-abca-3165346372/arsist-en-10028-4-2009 $\leq 1,00$	+ 0,05
Mn	$> 1,00$ to $\leq 1,70$	$\pm 0,05$
P	$\leq 0,015$	+ 0,003
	$> 0,015$ to $\leq 0,025$	+ 0,005
S	$\leq 0,010$	+ 0,003
Al	$\geq 0,020$	- 0,005
Mo	$\leq 0,10$	+ 0,03
Nb	$\leq 0,05$	+ 0,01
Ni	$\leq 0,85$ $> 0,85$ to $\leq 3,75$ $> 3,75$ to $\leq 10,0$	$\pm 0,05$ $\pm 0,07$ $\pm 0,10$
V	$\leq 0,05$	+ 0,01

^a If several product analyses are carried out on one cast, and the contents of an individual element determined lie outside the permission range of the chemical composition specified for the cast analysis, then it is only allowed to exceed the permissible maximum value or fall short of the permissible minimum value, but not both for one cast.

8.4 Mechanical properties

The values given in Tables 3 and 4 (see also EN 10028-1:2007 + A1:2009 and clause 10) shall apply.

NOTE Optionally, for steel grades 11MnNi5-3, 13MnNi6-3, 15NiMn6, 12Ni14 and X12Ni5, a minimum impact energy value of 40 J may be specified for temperatures where lower minimum values are specified (see Table 4, footnote d).

Table 3 — Mechanical properties at room temperature

Steel grade		Usual delivery condition ^{a,b} (Heat treatment symbol)	Product thickness <i>t</i> mm	Yield strength <i>R_{eh}</i> MPa min.	Tensile strength <i>R_m</i> MPa	Elongation after fracture <i>A</i> % min.
Steel name	Steel number					
11MnNi5-3	1.6212	+N (+NT)	≤ 30	285	420 to 530	24
			30 < <i>t</i> ≤ 50	275		
			50 < <i>t</i> ≤ 80	265		
13MnNi6-3	1.6217	+N (+NT)	≤ 30	355	490 to 610	22
			30 < <i>t</i> ≤ 50	345		
			50 < <i>t</i> ≤ 80	335		
15NiMn6	1.6228	+N or +NT or +QT	≤ 30	355	490 to 640	22
			30 < <i>t</i> ≤ 50	345		
			50 < <i>t</i> ≤ 80	335		
12Ni14	1.5637	+N or +NT or +QT	≤ 30	355	490 to 640	22
			30 < <i>t</i> ≤ 50	345		
			50 < <i>t</i> ≤ 80	335		
X12Ni5	1.5680	+N or +NT or +QT	≤ 30	390	530 to 710	20
X8Ni9 +NT640 ^a	1.5662 +NT640 ^a	+N plus +NT SIST EN 10028-4:2009 https://standards.iteh.ai/catalog/standards/sisted1166b8-5d46471fa6ca- 1653fc6372a/sist-en-10028-4-2009	30 < <i>t</i> ≤ 50	380		
			≤ 30	490	640 to 840	18
			30 < <i>t</i> ≤ 50	480		
X8Ni9 +QT640 ^a	1.5662 +QT640 ^a	+QT	≤ 30	490		
			30 < <i>t</i> ≤ 50	480		
X8Ni9 +QT680 ^a	1.5662 +QT680 ^a	+QT ^c	≤ 30	585	680 to 820	18
			30 < <i>t</i> ≤ 50	575		
X7Ni9	1.5663	+QT ^c	≤ 30	585	680 to 820	18
			30 < <i>t</i> ≤ 50	575		

^a +N: normalized; +NT: normalized and tempered; +QT: quenched and tempered; +NT640/+QT640/+QT680: Heat treatment variant with minimum tensile strength of 640 MPa or 680 MPa.

^b For temperatures and cooling conditions, see Table A.1.

^c For product thickness < 15 mm, delivery conditions +N plus +NT are also applicable.