

Designation: D 1092 – 99

Standard Test Method for Measuring Apparent Viscosity of Lubricating Greases¹

This standard is issued under the fixed designation D 1092; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This test method has been adopted for use by government agencies to replace Method 306 of Federal Test Method Standard No. 791b.

1. Scope

1.1 This test method covers measurement, in poises, of the apparent viscosity of lubricating greases in the temperature range from -54 to 38° C (-65 to 100° F). Measurements are limited to the range from 25 to 100 000 P at 0.1 s⁻¹ and 1 to 100 P at 15 000 s⁻¹.

Note 1—At very low temperatures the shear rate range may be reduced because of the great force required to force grease through the smaller capillaries. Precision has not been established below 10 s^{-1} .

1.2 This standard uses inch-pound units as well as SI (acceptable metric) units. The values stated first are to be regarded as standard. The values given in parentheses are for information only. The capillary dimensions in SI units in Fig. A1.1 and Fig. A1.2 are standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

<u>ASTM D109</u>

2.1 ASTM Standards: 5.1 Apparent

D 88 Test Method for Saybolt Viscosity²

- D 217 Test Methods for Cone Penetration of Lubricating $\ensuremath{\mathsf{Grease}}^3$
- D 3244 Practice for Utilization of Test Data to Determine Conformance with Specifications⁴

3. Terminology

3.1 Definitions:

² Annual Book of ASTM Standards, Vol 04.04.

3.1.1 *apparent viscosity,* n—of a lubricating grease is the ratio of shear stress to shear rate calculated from Poiseuille's equation, and is measured in poises (see 10.1).

3.1.2 *capillary*, n—For the purpose of this method, a capillary is any right cylindrical tube having a length to diameter ratio of 40 to 1.

3.1.3 *shear rate*, *n*—the rate at which a series of adjacent layers of grease move with respect to each other; proportional to the linear velocity of flow divided by the capillary radius, and is thus expressed as reciprocal seconds.

4. Summary of Test Method

4.1 The sample is forced through a capillary by means of a floating piston actuated by the hydraulic system. From the predetermined flow rate and the force developed in the system, the apparent viscosity is calculated by means of Poiseuille's equation. A series of eight capillaries and two pump speeds are used to determine the apparent viscosity at sixteen shear rates. The results are expressed as a log-log plot of apparent viscosity versus shear rate.

5. Significance and Use /astm-d1092-99

5.1 Apparent viscosity versus shear rate information can be useful in predicting pressure drops in grease distribution systems under steady-state flow conditions at constant temperature.

6. Apparatus

6.1 The assembled pressure viscometer consists of four major divisions, the power system, the hydraulic system, the grease system (described in the annex and shown in Fig. 1), and a bath of optional design. Fig. 2 is a photograph of the first three divisions as commonly used at room temperature. This form of the apparatus can be used with a cylindrical insulated tank 178 mm (7 in.) in diameter and 508 mm (20 in.) deep. The bath medium may be kerosene or alcohol cooled manually with dry ice. Alternatively the grease system, the grease and hydraulic system, or all three major divisions can be built into any liquid or air bath that will cover the temperature range and maintain the grease at test temperature $\pm 0.25^{\circ}$ C ($\pm 0.5^{\circ}$ F).

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This test method is under the jurisdiction of ASTM Committee D-2 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D 02.G on Lubricating Grease.

Current edition approved Nov. 10, 1999. Published November 1999. Originally published as D 1092 – 50 T. Last previous edition D 1092 – 93.

³ Annual Book of ASTM Standards, Vol 05.01.

⁴ Annual Book of ASTM Standards, Vol 05.02.

🖽 D 1092 – 99



FIG. 1 Schematic Drawing of Apparatus



FIG. 2 Photograph of Apparatus

7. Sampling

7.1 A single filling of the grease cylinder requires about 0.223 kg ($\frac{1}{2}$ lb) of grease which is the minimum size sample.

NOTE 2-It is possible for an experienced operator to complete the 16 single determinations with a single filling. However, some samples reach the equilibrium pressure slowly, making it advisable to have a sample of several pounds available.

7.2 Generally no special preparation of the sample is nec-

Note 3-The apparatus works the samples to some extent as they pass through the capillary. Somewhat better precision is obtained if they are previously worked as described in Test Methods D 217. Working of some greases may cause aeration.

NOTE 4—It is desirable to filter some greases through a 60-mesh screen to prevent plugging the No. 8 capillary.

8. Calibration and Standardization

8.1 To calibrate the hydraulic system, remove the grease cylinder and replace it with a needle valve. Select a hydraulic oil of about 2000 cSt (2000 mm²/s) viscosity at the test temperature. Fill the system with hydraulic oil and circulate the oil until it is free of air bubbles. At atmospheric pressure, quickly place a 60-mL Saybolt receiving flask (Test Method D 88), under the outlet and start a timer. Determine the delivery time for 60 mL and calculate the flow rate in cubic centimetres per second assuming 1 mL equal to 1 cm³. Repeat this observation at 500, 1000, 1500 psi (3.45, 6.89, 10.4 MPa) and at sufficient pressures above 1500 psi to develop a calibration curve of the type as shown in Fig. 3. The developed curve of the type is used to correct flow rates when grease is dispensed. Repeat the calibration at intervals to determine if wear is changing the pump flow.

8.2 An alternative procedure for the calibration of the hydraulic system is the measurement of the rate of flow of the test grease. To cover the desired range of shear rates, flow rates over an approximate range of pressure are determined. Any suitable means of measuring the rate of grease flow may be used.

9. Procedure

9.1 Charge the sample so as to reduce inclusion of air to a minimum. Soft greases may be poured into the cylinder or