

Designation: D 1101 - 97a

Standard Test Methods for Integrity of Adhesive Joints in Structural Laminated Wood Products for Exterior Use¹

This standard is issued under the fixed designation D 1101; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The integrity of adhesive joints for structural laminated wood members, such as laminated arches and beams, should be at least equal to that of the wood. Because initial strength tests generally are not an adequate measure of integrity of adhesive joints under severe service conditions, a test that simulates the effects of exterior exposure has been devised to evaluate adhesive joints in structural laminated wood members intended for this type of service.

1. Scope

- 1.1 These test methods cover an accelerated means of measuring the resistance to delamination of structural laminated wood members intended for exterior service.
- 1.2 These test methods are not intended as substitutes or replacements for the more severe test of resistance to delamination in Specification D 2559, which is used to qualify adhesives for structural laminated wood products for use under exterior (wet-use) exposure conditions under industry standard ANSI/AITC A190.1-1992.
- 1.3 Two test methods are included. Choice of test method depends on purpose of the test and available time to complete.
- 1.3.1 *Test Method A*—This test requires 3 days to complete and is a method for determining the suitability of adhesives and manufacturing techniques and equipment for production of joints adequate for exterior service.
- 1.3.2 Test Method B—This test requires approximately $12\frac{1}{2}$ h. (If excessive delamination occurs, the cycle is repeated). It is a quality-control type test for examining adhesive joint quality.
- 1.4 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.
- 1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:
- D 907 Terminology of Adhesives²
- D 2559 Specification for Adhesives for Structural Laminated Wood Products for Use Under Exterior (Wet Use) Exposure Conditions²

3. Terminology

- 3.1 *Definitions*—Many terms in these test methods are defined in Terminology D 907.
- 3.1.1 glulam, n—synonym for structural-glued-laminated timber
- 3.1.2 structural-glued-laminated timber, n—an engineered stress-rated product of a timber laminating plant comprising assemblies of specially selected and prepared wood laminations securely bonded together with adhesives, with the following characteristics: (1) the grain of all laminations is approximately parallel longitudinally; and (2) the laminations may be comprised of pieces end-joined to form any length, of pieces placed or glued edge-to-edge to make wider ones or of pieces bent to curved form during gluing. (Synonym glulam) ANSI/AITC A190.1-1992. American National Standard for Wood Products, Structural Glued Laminated Timber (Edited to conform with ASTM format)
 - 3.2 Definitions of Terms Specific to This Standard:
- 3.2.1 laminated wood, n—the fabricated product resulting from the bonding of two or more laminations, with each lamination made from one or more pieces bonded either lengthwise, edgewise, or both, and all with the direction of the grain essentially parallel, to form a larger piece such as a structural member.

¹ These test methods are under the jurisdiction of ASTM Committee D 14 on Adhesives and are the direct responsibility of Subcommittee D14.30 on Wood Adhesives.

Current edition approved Sept. 10, 1997. Published May 1998. Originally published as D 1101 - 81. Last previous edition D 1101 - 97.

² Annual Book of ASTM Standards, Vol 15.06.