
**Watch-cases and accessories —
Gold alloy coverings —**

Part 2:

**Determination of fineness, thickness,
corrosion resistance and adhesion**

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Boîtes de montres et leurs accessoires — Revêtements d'alliage d'or —

*Partie 2: Détermination du titre, de l'épaisseur, de la résistance à la
corrosion et de l'adhérence*

ISO 3160-2:2003

<https://standards.iteh.ai/catalog/standards/sist/46922067-0b7f-4640-af9f-50899c0640cb/iso-3160-2-2003>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 3160-2:2003](https://standards.iteh.ai/catalog/standards/sist/46922067-0b7f-4640-af9f-50899c0640cb/iso-3160-2-2003)

<https://standards.iteh.ai/catalog/standards/sist/46922067-0b7f-4640-af9f-50899c0640cb/iso-3160-2-2003>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

| | |
|--|----|
| Foreword | iv |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 2 |
| 4 General | 2 |
| 5 Determination of fineness | 2 |
| 6 Determination of contents | 2 |
| 7 Determination of thickness | 3 |
| 8 Determination of the corrosion resistance | 4 |
| 9 Adhesion test | 7 |
| Annex A (normative) Method of obtaining a sample of gold alloy covering | 8 |
| Annex B (normative) Description of the main tests for determination of the thickness of gold alloy coverings | 10 |
| Bibliography | 12 |

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 3160-2:2003](https://standards.iteh.ai/catalog/standards/sist/46922067-0b7f-4640-af9f-50899c0640cb/iso-3160-2-2003)

<https://standards.iteh.ai/catalog/standards/sist/46922067-0b7f-4640-af9f-50899c0640cb/iso-3160-2-2003>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 3160-2 was prepared by Technical Committee ISO/TC 114, *Horology*, Subcommittee SC 6, *Precious metal coverings*.

This third edition cancels and replaces the second edition (ISO 3160-2:1992), which has been technically revised.

ISO 3160 consists of the following parts, under the general title *Watch-cases and accessories — Gold alloy coverings*:

- *Part 1: General requirements*
- *Part 2: Determination of fineness, thickness, corrosion resistance and adhesion*
- *Part 3: Abrasion resistance tests of a type of coating on standard gauges*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/46922067-0b7f-4640-af9f-50899c0640cb/iso-3160-2-2003>

Watch-cases and accessories — Gold alloy coverings —

Part 2:

Determination of fineness, thickness, corrosion resistance and adhesion

1 Scope

This part of ISO 3160 specifies methods to determine fineness, thickness, corrosion resistance and adhesion for gold alloy coverings on watch-cases and accessories, including bracelets when they are permanently attached to the case.

The tests apply only to significant surfaces.

This part of ISO 3160 applies to all gold alloy coverings specified in ISO 3160-1.

iTeh STANDARD PREVIEW

2 Normative references (standards.iteh.ai)

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1463:—¹⁾, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 2177, *Metallic coatings — Measurement of coating thickness — Coulometric method by anodic dissolution*

ISO 3160-1, *Watch-cases and accessories — Gold alloy coverings — Part 1: General requirements*

ISO 3497, *Metallic coatings — Measurement of coating thickness — X-ray spectrometric methods*

ISO 3543, *Metallic and non-metallic coatings — Measurement of thickness — Beta backscatter method*

ISO 3868, *Metallic and other non-organic coatings — Measurement of coating thicknesses — Fizeau multiple-beam interferometry method*

ISO 4524-1, *Metallic coatings — Test methods for electrodeposited gold and gold alloy coatings — Part 1: Determination of coating thickness*

ISO 4524-5, *Metallic coatings — Test methods for electrodeposited gold and gold alloy coatings — Part 5: Adhesion tests*

ISO 4538, *Metallic coatings — Thioacetamide corrosion test (TAA test)*

1) To be published. (Revision of ISO 1463:1982)

ISO 3160-2:2003(E)

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*

ISO 11426, *Determination of gold in gold jewellery alloys — Cupellation method (fire assay)*

ISO 12687, *Metallic coatings — Porosity tests — Humid sulfur (flowers of sulfur) test*

ISO 14647, *Metallic coatings — Determination of porosity in gold coatings on metal substrates — Nitric acid vapour test*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 significant surface
that part of the surface which is to receive the gold alloy covering and which is essential to the appearance and serviceability of the component

NOTE When there is no agreement between the supplier and customer, a significant surface is considered to be any surface which can be touched by a 5 mm diameter ball.

4 General

In the context of this part of ISO 3160, the term "corrosion" includes tarnishing and oxidation, as well as surface penetration and the effects of the penetration of corrosive agents into gaps in the surface protection.

It is generally required that, except where specified to the contrary, gold-alloy-covered surfaces should not have suffered any damage after each of the proposed tests. In practice, however, this condition is never strictly fulfilled and certain minor changes are observed, especially at the edges of the gold-covered parts. Consequently, interpretation of the results requires a certain amount of common sense and, if necessary, agreement between the supplier and customer. The presence of such almost inevitable faults makes it impossible to sell the tested item as new. In this respect, the tests are therefore to be considered to be destructive.

The test methods apply to all gold alloy coverings specified in ISO 3160-1.

5 Determination of fineness

If the fineness is measured on a gold alloy covering which is separated from the base metal, the method used to separate the gold alloy covering from the base metal shall not affect the fineness of the gold covering to a significant extent.

For multilayer coverings, the covering content measured is the mean content, which shall be a minimum of 585/1 000, in accordance with ISO 3160-1.

The method of separation of the sample is specified in Annex A.

6 Determination of contents

Any of the following methods shall be used for the determination of contents:

- a) chemical analysis by reduction in an aqueous solution of, for example, sulfur dioxide or any other suitable reducing agent;

- b) analysis by:
- 1) cupellation (fire test) as specified in ISO 11426,
 - 2) atomic absorption spectrometry,
 - 3) spectrophotometry,
 - 4) X-ray spectrometry as specified in ISO 3497,
 - 5) plasma emission spectrometry (ICP method);
- c) touchstone method (only to be used to evaluate the approximate fineness);
- d) any other physico-chemical method.

Any method used shall be capable of giving an indication of fineness to within an accuracy of 50 parts per thousand.

In the event of arbitration, the reference method is that of analysis by cupellation (fire test) specified in ISO 11426.

7 Determination of thickness

Any of the following test methods for the determination of the thickness of gold alloy coatings shall be used, provided a measuring accuracy of $\pm 10\%$ is guaranteed:

- a) the microsection method specified in ISO 1463 for a thickness of $5\ \mu\text{m}$ (-20%) and above (local thickness);
<https://standards.iteh.ai/catalog/standards/sist/46922067-0b7f-4640-a19f-108120211516/iso-3160-2:2003>
- b) the dissolution method and chemical analysis for any thickness of gold alloy covering (average thickness) specified in ISO 4524-1;
- c) dissolution and measurement by the micrometer method specified in ISO 1463;
- d) the beta-ray backscatter method specified in ISO 3543;
- e) the X-ray spectrometric method (fluorescence) specified in ISO 3497;
- f) the coulometric method (coulometric method by anodic dissolution) specified in ISO 2177;
- g) the fizeau multiple-beam interferometry method specified in ISO 3868;
- h) the scanning electron microscope method specified in ISO 9220^[6];
- i) any other physical-chemical method which can guarantee accuracy.

In the event of arbitration, the microsection method specified in ISO 1463 shall be used (local thickness).

8 Determination of the corrosion resistance

8.1 Forms of corrosion

The various forms of corrosion which appear on a gold-alloy-covered article may be divided into three groups.

- a) Corrosion of the base metal at points where there are gaps in the covering: electrochemical cells may act at these points and accelerate penetration, and also at the boundary between the covering and the base metal.
- b) Attack caused by saline agents or possibly by mildly acidic agents (contact with perspiration, packaging, leathers or certain plastics): the products of corrosion may be of various colours, i.e. orange, violet, blue, green or brown.
- c) Attack caused by sulfur-containing agents (atmospheric hydrogen sulfide, vulcanized rubber, etc.): such agents may also attack the base metal at points where there are gaps in the protective covering. In addition, they cause changes in the surface colouring, which may even turn matt and black.

The proposed tests make it possible for these various effects to be distinguished to a certain extent. Gold alloy coverings shall be resistant in all the environments described below. According to the nature of the article, the supplier may, with the agreement of the customer, determine the number of items to be submitted to each test.

The development of corrosion is closely allied to the relative humidity of the ambient environment.

8.2 Sampling and preparation

ITeCh STANDARD PREVIEW
(standards.iteh.ai)

8.2.1 General

According to the nature of the article, the supplier may, with the agreement of the customer, determine the number of items to be submitted to each test and the test conditions. The test conditions shall be stated in the test report.

The tests for determination of the corrosion resistance are applicable to finished items in the condition in which they are supplied to customers. They can also be applied during manufacture, but any interpretation of results shall take into account the form which the item will take when in its final condition.

8.2.2 Test of finished items (ready-for-use condition)

If the item to be tested is delivered in the ready-for-use condition, no cleaning operation shall be carried out. It is well known that residues remaining after insufficient rinsing have a considerable effect on tarnishing. It is necessary for the item to be tested in the condition in which it will be received by the customer.

8.2.3 Test of coating process (without passivation treatment)

When testing the quality of the coating on significant surfaces, care shall be taken to avoid any unusual influence. The sample shall be completely cleaned, first by the use of a water-based detergent, then in a mixture of distilled water and ethanol or isopropanol. Degreasing in a chlorinated solvent is insufficient.

8.2.4 Non-significant surfaces

The non-significant surfaces of the object shall be coated with a lacquer or a covering which is sufficiently resistant to prevent any attack on the protected metal throughout the duration of the test.

8.3 Continuity of the covering (porosity test)

8.3.1 General

In practice, for the porosity test, it is recommended that account be taken of the tests given in ISO 10308^[7].

8.3.2 Test for a copper-containing base metal with or without nickel, and die-cast zinc-based alloys

8.3.2.1 Test vessel

Use a suitable closed vessel, made of glass or acid-resistant plastic, and expose the sample to the corrosive atmosphere on all sides.

8.3.2.2 Test solution

The solution shall be of the following composition:

- acetic acid: [CH_3COOH , $\rho_{20} = 1,048 \text{ g/cm}^3$ to $1,052 \text{ g/cm}^3$, $\geq 99,0 \%$ (m/m)]: 50 % (m/m);
- deionized water: 50 % (m/m).

The vessel shall be filled with this solution to a height of about 10 mm. The walls of the vessel shall be lined with thick white blotting paper which dips into the liquid.

8.3.2.3 Position of the sample

The sample shall be suspended on a glass hook at a distance of at least 30 mm from the liquid and the walls of the vessel.

8.3.2.4 Temperature during the test

The temperature during the test shall be $(23 \pm 2) \text{ }^\circ\text{C}$.

8.3.2.5 Duration of the test

The duration of the test shall be 24 h.

8.3.2.6 Criteria

When observed, the sample shall not reveal to the naked eye either green droplets or accumulations of green deposits anywhere on the significant surface. On die-cast zinc-based alloys, no white deposit shall appear.

8.3.3 Test a ferrous base metal

8.3.3.1 Test vessel

The test shall be carried out in a suitable closed vessel made of glass or acid-resistant plastic, in which the sample is exposed to a corrosive atmosphere on all sides.

8.3.3.2 Test mixture

The mixture shall have the following composition:

- crystalline sodium metabisulfite ($\text{Na}_2\text{S}_2\text{O}_5$ p.a. ACS, synonyms: sodium pyrosulfite, sodium disulfite): 45 % (m/m);
- deionized water: 55 % (m/m).