



SLOVENSKI STANDARD

SIST EN 14294:2010

01-maj-2010

Nadomešča:
SIST EN 14294:2005

Lepila za usnjene in obutvene materiale - Izdelava lepljenih preskušancev s postopki direktnega podplatenja

Adhesives for leather and footwear materials - Preparation of bonded test pieces by moulding-on processes

Klebstoffe für Leder und Schuhwerkstoffe - Herstellung von Verbund-Proben nach dem Anformverfahren

STANDARD PREVIEW
(standards.iteh.ai)

Adhésifs pour cuir et matériaux de la chaussure - Préparation d'éprouvettes collées par moulage direct sur tige

<https://standards.iteh.ai/catalog/standards/sist/31fa542-4311-4a1b-9c8-07a27d60f3ce/sist-en-14294-2010>

Ta slovenski standard je istoveten z: EN 14294:2010

ICS:

61.060	Obuvala	Footwear
83.180	Lepila	Adhesives

SIST EN 14294:2010 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14294:2010

<https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d60f3ce/sist-en-14294-2010>

EUROPEAN STANDARD

EN 14294

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2010

ICS 83.180

Supersedes EN 14294:2004

English Version

Adhesives for leather and footwear materials - Preparation of bonded test pieces by moulding-on processes

Adhésifs pour cuir et matériaux de la chaussure -
Préparation d'éprouvettes collées par moulage direct sur
tige

Klebstoffe für Leder und Schuhwerkstoffe - Herstellung von
Verbund-Proben nach dem Anformverfahren

This European Standard was approved by CEN on 28 December 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 14294:2010](https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d603ce/sist-en-14294-2010)

<https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d603ce/sist-en-14294-2010>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
Introduction	4
1 Scope	5
2 Normative references	5
3 Terms and definitions	5
4 Procedure	6
5 Adhesives and materials	6
6 Apparatus	7
7 Test pieces	8
8 Preparation of moulded-on assemblies	9
9 Test report	13

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 14294:2010

<https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d60f3ce/sist-en-14294-2010>

Foreword

This document (EN 14294:2010) has been prepared by Technical Committee CEN/TC 193 “Adhesives”, the secretariat of which is held by AENOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2010, and conflicting national standards shall be withdrawn at the latest by August 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 14294:2004.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 14294:2010](https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d60f3ce/sist-en-14294-2010)

<https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d60f3ce/sist-en-14294-2010>

Introduction

EN 15307 and EN 1392 specify methods of testing and evaluation of adhesives for leather and footwear materials in "stuck-on" assemblies. Most footwear produced in Europe is manufactured using stuck-on processes, but a significant proportion is produced by "moulding-on" processes such as vulcanising, injection moulding and reaction moulding.

This document specifies the preparation of bonded test pieces by moulding-on processes. The form and dimensions of the test pieces produced allows testing according to the test methods specified in EN 1392, and evaluation of the bond strength obtained according to EN 15307.

This document therefore complements the above mentioned series of documents, and together they allow the simulation, testing and evaluation of almost all bonds occurring in common footwear constructions.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 14294:2010](https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d60f3ce/sist-en-14294-2010)

<https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-07a27d60f3ce/sist-en-14294-2010>

1 Scope

This European Standard specifies procedures for the preparation of test pieces comprising adhesive coated leather or other footwear upper material onto which a soling material is moulded directly. The procedures described simulate direct vulcanising of rubber, injection moulding of thermoplastics and reaction moulding of polyurethane.

The prepared test pieces are suitable for the test procedures described in EN 1392, to meet the requirements of EN 15307.

SAFETY STATEMENT— Persons using this document should be familiar with the normal laboratory practice, if applicable. This document does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user to establish appropriate safety and health practices and to ensure compliance with any regulatory conditions.

ENVIRONMENTAL STATEMENT— It is understood that some of the material permitted in this standard may have negative environmental impact. As technological advantages lead to acceptable alternatives for these materials, they will be eliminated from this standard to the extent possible.

At the end of the test, the user of the standard should take care to carry out an appropriate disposal of the wastes, according to local regulation.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 923:2005, *Adhesives — Terms and definitions* SIST EN 14294:2010

<https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8->

EN 1392:2006, *Adhesives for leather and footwear materials — Solvent-based and dispersion adhesives — Testing of bond strength under specified conditions* https://standards.iteh.ai/catalog/standards/sist/31f1a542-4311-4a1b-9cf8-

EN 15307, *Adhesives for leather and footwear materials — Sole-upper bonds — Minimum strength requirements*

EN ISO 868, *Plastics and ebonite — Determination of indentation hardness by means of a durometer (Shore hardness) (ISO 868:2003)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 923:2005 and EN 1392:2006 and the following apply.

3.1
moulding-on process
process for soling footwear in which the soling material is directly moulded onto the bottom of the shoe in a mould closed by the shoe upper or other footwear component

NOTE The other footwear component can be an outsole or midsole onto which another soling layer is to be moulded.

3.2
vulcanising
moulding process in which uncured rubber is inserted or extruded into the mould and is shaped and crosslinked by heat and pressure

EN 14294:2010 (E)**3.3****injection moulding**

moulding process in which molten thermoplastic material is injected into the mould and sets on cooling

3.4**reaction moulding**

moulding process in which reactive chemicals are poured or injected into the mould and polymerise and crosslink by chemical reaction

4 Procedure

The surface of the leather, other footwear upper material or other footwear component material used is treated in a manner specific to the nature of the material. Strips of specified length and width are cut from the treated material.

One or more of these strips are coated with adhesive and attached, with the bonding surface uppermost, to the bottom plate of a mould. Soling material is introduced to fill the mould and allowed to cure or set as appropriate to produce an assembly of soling bonded to upper material.

The moulded assembly, and test pieces cut from it, are stored under specified conditions before testing.

5 Adhesives and materials**5.1 Footwear adhesives**

The adhesive used shall be identified in the report, in particular note name and/or designation, manufacturer, date of manufacture or supply and/or lot number, main polymer and colour. For two-part adhesives the nature of the crosslinking agent and the mixing ratio of the components shall be identified.

Reference footwear test adhesives are one- or two-part adhesives with specified properties (e.g. Test adhesive CR 1, Test adhesive CR 2, Test adhesive PU 1, Test adhesive PU 2, Test adhesive PUD 1, Test adhesive PUD 2). If a reference footwear test adhesive in accordance with EN 15307 is used, record its designation in the report.

NOTE For direct vulcanising processes, and injection moulding processes with styrene-butadiene-styrene thermoplastic rubber (SBSR), special types of adhesive are required.

5.2 Footwear materials**5.2.1 General**

Identify all footwear materials used in the report.

5.2.2 Upper materials (or other footwear materials)

Record the name and/or designation, manufacturer, date of manufacture or supply and type of leather, other footwear upper material (or other footwear material) used. For leathers list colour, thickness and type of tannage (if known). If reference test material Leather 1 is used in accordance with EN 15307, record its designation.

5.2.3 Soling moulding materials**5.2.3.1 General**

The soling moulding material required depends on the moulding-on process to be simulated.

5.2.3.2 Direct vulcanising materials

Record the name and/or designation, manufacturer, date of manufacture or supply, colour, polymer base and Shore hardness in accordance with EN ISO 868 of the material used.

NOTE Uncured compounds of acrylonitrile-butadiene (nitrile) rubber (NBR) or styrene-butadiene rubber (SBR) are mainly used.

5.2.3.3 Injection moulding materials

Record the name and/or designation, manufacturer, date of manufacture or supply, colour, polymer base and Shore hardness in accordance with EN ISO 868 of the material used.

NOTE PVC compounds or styrene-butadiene-styrene thermoplastic rubber (SBSR) compounds are mainly used.

5.2.3.4 Reaction moulding materials

Record the name and/or designation, manufacturer, date of manufacture or supply, colour, chemical nature of the reactive constituents and the catalysts used, if any.

NOTE Polyurethane chemicals are mainly used, consisting of a prepolymer and a resin which are mixed in the appropriate proportions before moulding. If a catalyst is also required, this can be added to the resin prior to the weighing out of the constituents.

6 Apparatus

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6.1 General

The items required depend on the types of material used and the type of moulding-on process.

6.2 Cutting knife, sharp for cutting test pieces in accordance with 7.1. The angle between the inner and outer cutting surface shall be approximately 20°.

6.3 Adhesive applicator, brush, roller or coating machine for applying a uniform coat of the adhesive under test.

6.4 Platen press, a heated platen press suitable for direct vulcanisation of rubber, capable of:

- maintaining platen temperatures of (105 ± 5) °C for the bottom platen and (180 ± 5) °C for the top platen;
- applying a pressure up to 5 MPa to the mould.

6.5 Rectangular mould, of approximate dimensions 150 mm × 100 mm × 5 mm for direct vulcanisation. The wall of the mould base should include a 10 mm wide shelf all round, half way up, to accept excess rubber displaced from the cavity.

6.6 Surface pyrometer, suitable for measuring the operating temperatures of the press platens.

6.7 Oven, capable of maintaining a temperature of (75 ± 5) °C to pre-heat the rubber prior to moulding.

6.8 Gloves, heat resistant, suitable for handling the hot mould.

6.9 Injection moulding machine, fitted with a mould of approximate dimensions 150 mm × 100 mm × 5 mm for the preparation of flat test plaques. A commercial single station low pressure screw injection moulder is suitable.

6.10 Mould, for polyurethane reaction moulding, having:

- flat rigid base with a rectangular cavity of approximate dimensions 300 mm × 200 mm × 6,5 mm;