

TECHNICAL SPECIFICATION

**ISO/TS
17226**

**IULTCS/
IUC 19**

First edition
2003-08-15

Leather — Chemical tests — Determination of formaldehyde content

Cuir — Essais chimiques — Détermination de la formaldéhyde

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[ISO/TS 17226:2003](https://standards.iteh.ai/catalog/standards/sist/1fdbeb37-e3af-4f21-a246-251133bc6a59/iso-ts-17226-2003)

<https://standards.iteh.ai/catalog/standards/sist/1fdbeb37-e3af-4f21-a246-251133bc6a59/iso-ts-17226-2003>



Reference number
ISO/TS 17226:2003(E)
IULTCS/IUC 19

© ISO 2003

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TS 17226:2003](#)

<https://standards.iteh.ai/catalog/standards/sist/1fd1beb37-e3af-4f21-a246-251133bc6a59/iso-ts-17226-2003>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Preparation and standardisation of formaldehyde stock solution	1
4 Chromatographic HPLC method	2
5 Colourimetric method	5
6 Expression of results	8
7 Test report	8
Annex A (informative) Precision	9

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/TS 17226:2003](https://standards.iteh.ai/catalog/standards/sist/1fd1beb37-e3af-4f21-a246-251133bc6a59/iso-ts-17226-2003)

<https://standards.iteh.ai/catalog/standards/sist/1fd1beb37-e3af-4f21-a246-251133bc6a59/iso-ts-17226-2003>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

In other circumstances, particularly when there is an urgent market requirement for such documents, a technical committee may decide to publish other types of normative document:

- an ISO Publicly Available Specification (ISO/PAS) represents an agreement between technical experts in an ISO working group and is accepted for publication if it is approved by more than 50 % of the members of the parent committee casting a vote;
- an ISO Technical Specification (ISO/TS) represents an agreement between the members of a technical committee and is accepted for publication if it is approved by 2/3 of the members of the committee casting a vote.

ISO/TS 17226:2003

An ISO/PAS or ISO/TS is reviewed after three years in order to decide whether it will be confirmed for a further three years, revised to become an International Standard, or withdrawn. If the ISO/PAS or ISO/TS is confirmed, it is reviewed again after a further three years, at which time it must either be transformed into an International Standard or be withdrawn.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO/TS 17226 was prepared by the Chemical Test Commission of the International Union of Leather Technologists and Chemists Societies (IUC Commission, IULTCS) in collaboration with the European Committee for Standardization (CEN) Technical Committee CEN/TC 289, *Leather*, the secretariat of which is held by UNI, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement). This method is technically similar to the method in IUC 19 which was declared an official method at the IULTCS Delegates meeting on 31st May 2003 in Cancun, Mexico. This edition differs slightly in the text compared with IUC 19.

Leather — Chemical tests — Determination of formaldehyde content

1 Scope

This Technical Specification includes two methods for the determination of free and released formaldehyde in leathers. One method (Section 5) is relatively simple with regard to the laboratory equipment (colourimetric method), while the other (Section 4) needs more sophisticated equipment (HPLC method). The second method is selective and not sensitive to coloured extracts.

The formaldehyde content is taken to be the quantity of formaldehyde contained in a water extract from the leather.

The two analytical methods should give similar trends but not necessarily the same absolute result.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2418:2002, Leather - Chemical, physical and mechanical and fastness tests - Sampling location

ISO 2419:2002, Leather - Physical and mechanical tests - Sample preparation and conditioning

ISO 3696:1987, Water for analytical laboratory use - Specification and test methods

ISO 4044:1977, Leather - Preparation of chemical test samples

3 Preparation and standardisation of formaldehyde stock solution

3.1 Reagents

Unless otherwise stated only analytical grade chemicals are to be used. The water must be demineralised, grade 3 in accordance with ISO 3696. All solutions are aqueous solutions.

3.1.1 Formaldehyde solution, approx. 37 %;

3.1.2 0,05 M iodine solution, (i.e. 12,68 g iodine per l);

3.1.3 2M sodium hydroxide;

3.1.4 1,5 M sulphuric acid;

3.1.5 0,1 M sodium thiosulphate solution;

3.1.6 1 % starch solution, (i.e. 1 g in 100 ml water).

3.2 Procedure for the determination of formaldehyde in the stock solution

5 ml of the formaldehyde solution (3.1.1) is pipetted into a 1 000 ml volumetric flask which contains approximately 100 ml demineralised water and is subsequently filled with demineralised water up to the mark. This solution is the formaldehyde stock solution.

From this solution, 10 ml is pipetted into a 250 ml Erlenmeyer flask and mixed with 50 ml iodine solution (3.1.2) and sodium hydroxide (3.1.3) is added until it turns yellow. It is allowed to settle for 15 min ± 1 min at 18 °C to 26 °C and then 50 ml of sulphuric acid (3.1.4) is added while swirling.

After addition of 2 ml of starch solution (3.1.6), the excess iodine is titrated with sodium thiosulphate (3.1.5) until the colour changes. Three individual determinations shall be made. A blank solution is titrated in the same manner.

$$C_{FA} = \frac{(V_0 - V_1) \times c_1 \times M_{FA}}{2}$$

C_{FA} = concentration of the formaldehyde stock-solution, in mg / 10 ml;

V_0 = titre of the thiosulphate solution for the blank solution, in ml;

V_1 = titre of the thiosulphate solution for the sample solution, in ml;

M_{FA} = molecular weight of formaldehyde, 30,08 g/mol;

c_1 = concentration of the thiosulphate solution, M.

4 Chromatographic HPLC method

4.1 Principle

The process is selective. Formaldehyde is separated and quantified as a derivative from other aldehydes and ketones by liquid chromatography. Detected is the free-formaldehyde and formaldehyde which is hydrolysed during extraction to yield free-formaldehyde.

The sample is eluted with water at 40 °C. The eluate is mixed with 2,4 dinitrophenylhydrazine, whereby aldehydes and ketones react to give the respective hydrazines. These are separated by means of a reversed-phase HPLC method, detected at 350 nm and quantified.

4.2 Chemicals

Unless otherwise stated only analytical grade chemicals are to be used. The water must be demineralised, grade 3 in accordance with ISO 3696. All solutions are aqueous solutions.

4.2.1 0,1% sodium dodecylsulphonate (detergent), 1 g in 1 000 ml water;

4.2.2 0,3 % DNPH (2,4 Dinitrophenylhydrazine) in conc. o-Phosphoric acid (85 %). (DNPH recrystallised from 25 % acetonitrile in water);

4.2.3 Acetonitrile.

4.3 Apparatus

4.3.1 Strainer with glass fibre filter, GF8 (or glass filter strainer G 3, diameter 70 - 100 mm);

4.3.2 Water bath, thermostatically controlled to $40\text{ }^{\circ}\text{C} \pm 0,5\text{ }^{\circ}\text{C}$, fitted with a flask shaker or stirrer;

4.3.3 Thermometer, with $0,1\text{ }^{\circ}\text{C}$ graduations over the range $20\text{ }^{\circ}\text{C}$ to $50\text{ }^{\circ}\text{C}$;

4.3.4 HPLC system with UV detection, 350 nm;

4.3.5 Membrane filter, polyamide, $0,45\text{ }\mu\text{m}$;

4.3.6 Analytical balance weighing to an accuracy of 0,1 mg.

4.4 Process for the determination of formaldehyde in leather

4.4.1 Sampling and preparation of samples

If possible sample in accordance with ISO 2418:2002 and grind the leather in accordance with ISO 4044:1977. If sampling in accordance with ISO 2418 is not possible (e.g. leathers from finished products like shoes, garments) details about sampling have to be given together with the test report.

Condition the ground test sample in accordance with ISO 2419:2002, prior to weighing.

4.4.2 Extraction of formaldehyde

$2\text{ g} \pm 0,1\text{ g}$ leather are weighed into a 100 ml Erlenmeyer flask. 50 ml of the detergent solution (4.2.1) (pre-warmed to $40\text{ }^{\circ}\text{C}$) is added and the flask is closed with a glass stopper (see Note). The content of the flask is stirred or shaken smoothly at $40\text{ }^{\circ}\text{C} \pm 0,5\text{ }^{\circ}\text{C}$ in a water bath (4.3.2) for $60\text{ min} \pm 2\text{ min}$. The warm extract solution is immediately filtered by vacuum through a glass fibre filter (4.3.1) into a flask. The filtrate, in a closed flask, is cooled down to room temperature ($18\text{ }^{\circ}\text{C}$ to $26\text{ }^{\circ}\text{C}$).

NOTE The leather/solution ratio shall not be modified. Extraction and analysis should be performed within the same working day.

4.4.3 Reaction with DNPH

In a 10 ml volumetric flask pipette 4,0 ml of acetonitrile (4.2.3), a 5,0 ml aliquot of the filtered eluate and 0,5 ml of DNPH solution (4.2.2). The volumetric flask is filled with demineralised water up to the mark and shaken briefly by hand to mix the components. Allow to stand at least 60 min, but not more than a maximum of 180 min. After filtration through a membrane filter (4.3.5) the sample is chromatographed. If the concentration is out of the calibration range smaller aliquots shall be taken. (Standard additions procedure is recommended).

4.4.4 HPLC conditions (recommendation)

Flow rate: 1,0 ml/min

Mobile phase: acetonitrile / water, 60:40

Separation column: Merck 100, CH 18,2 (highly coated, 12 % C)+ precolumn (1 cm, RP18)

UV detection wavelength: 350 nm

Injection volume: 20 µl

4.4.5 Calibration of HPLC

0,5 ml of the formaldehyde stock solution (3.2), with an exactly known formaldehyde content, is pipetted into a 500 ml volumetric flask, pre-filled with approximately 100 ml water, mixed, filled with water to the mark, and again mixed. (Content approx. 2 µg formaldehyde /ml).

This solution is the standard solution.

In each of six 10 ml volumetric flasks, add 4 ml acetonitrile (4.2.3) and then add a concentration series of 0,5; 1,0; 2,0; 3,0; 4,0; 5,0 ml respectively of the standard solution. Immediately upon addition of the formaldehyde solution, each flask shall be mixed and 0,5 ml DNPH solution (4.2.2) added. Fill the flasks up to the mark with demineralised water and mix. After at least 60 min and not more than 180 min, the samples shall be chromatographed after filtration through a membrane filter. The calibration is effected through plotting a graph of the formaldehyde derivative peak area versus the concentration in µg/10 ml.

4.4.6 Calculation of the formaldehyde content in leather samples

$$C_F = \frac{C_s \times F}{E_W}$$

iTeh STANDARD PREVIEW

C_F concentration of formaldehyde in the sample in mg/kg rounded to 0,01 mg/kg;

C_S concentration of formaldehyde obtained from the calibration graph in µg/10 ml;

F dilution factor; <https://standards.iteh.ai/catalog/standards/sist/1fdbeb37-e3af-4f21-a246-251133bc6a59/iso-ts-17226-2003>

E_W quantity of leather weighed in g.

4.4.7 Spiking - determination of recovery rate

4 ml acetonitrile are pre-filled into a 10 ml volumetric flask and an aliquot of 2,5 ml of the filtrate, obtained as described in section 4.4.2, added. An accurately determined volume of the formaldehyde standard solution is then added to give an almost equal concentration to that found in the sample.

This solution is further treated analogous to the description under 4.4.5 and C_{S2} determined analogous to section 4.4.3. Carry out the determination in duplicate and report the mean and individual values in the test report.

$$RR = \frac{2 \times (C_{S2} - C_S) \times 100}{2 \times C_{FA1}}$$

C_{S2} = Concentration of formaldehyde obtained from the calibration graph in µg/10 ml;

C_S = Concentration of formaldehyde in the non-spiked sample in µg/10 ml;

C_{FA1} = Spiked quantity of formaldehyde in µg/10 ml;

RR = Recovery rate in percent, rounded to 0,1 %.

5 Colourimetric method

5.1 Scope

The formaldehyde content is taken to be the quantity of formaldehyde contained in the water extract of the leather under the conditions described below referred to the weighed quantity of leather.

This process is not absolutely selective. Detected is not only the free formaldehyde but also the formaldehyde which is hydrolysed during extraction to yield free formaldehyde.

5.2 Principle

The leather sample is eluted with water at 40 °C. The eluate is treated with acetylacetone, whereby formaldehyde reacts to give a yellow compound (3,5-diacetyl-1,4-dihydrolutidine). The absorbance of this compound is measured at 412 nm. The amount of formaldehyde corresponding to the absorbance value for the test specimen is obtained from a calibration curve prepared under identical conditions.

5.3 Chemicals

Unless otherwise stated only analytically pure chemicals are to be used. The water must be demineralised, grade 3 in accordance with ISO 3696. All solutions are aqueous solutions.

5.3.1 0,1% sodium dodecylsulphonate (detergent), 1 g in 1 000 ml water;

5.3.2 150 g ammonium acetate + 3 ml glacial acetic acid + 2 ml acetylacetone (pentane - 2,4 -dione, CAS 123-54-6) in 1 000 ml water. Prepare fresh daily and keep in a dark place (it is sensitive to light);

5.3.3 150 g ammonium acetate + 3 ml glacial acetic acid in 1 000 ml water;

5.3.4 5 g dimedone in 1 000 ml water (dimedone = Methone = 5,5'-Dimethyl-1,3-cyclohexanedione, CAS 126-81-8).

NOTE It is reported that dimedone can not be readily dissolved in pure water. In such cases dimedone can be dissolved in a small amount of ethanol and then made up to volume with water.

5.4 Apparatus

The same apparatus as in 4.3 above.

5.4.1 Spectrophotometer with suitable cells capable of measuring absorbance at 412 nm. The recommended cell path length is 20 mm.

5.5 Preparation and standardisation of formaldehyde stock solution

The same procedure as in Section 3 above.

5.6 Procedure for determination of formaldehyde in leather

5.6.1 Sampling and preparation of samples

If possible sample in accordance with ISO 2418 and grind the leather in accordance with ISO 4044:1977. If sampling in accordance with ISO 2418 is not possible (e.g. leathers from finished products like shoes, garments) details about sampling have to be given together with the test report.

Condition the ground test sample in accordance with ISO 2419, prior to weighing.