



Designation: D 1119 – 00

## Standard Test Method for Percent Ash Content of Engine Coolants and Antirusts<sup>1</sup>

This standard is issued under the fixed designation D 1119; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reappraisal.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method covers the determination of ash content after ignition of commercial engine coolants and antirusts, as packaged or after use.

1.2 Some commercial antirusts are solid products. This procedure applies only to liquid products.

1.3 The values stated in SI units are to be regarded as the standard.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. A specific precautionary statement is given in Note 1.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:

D 1176 Test Method for Sampling and Preparing Aqueous Solutions of Engine Coolants or Antirusts for Testing Purposes<sup>2</sup>

D 3306 Specification for Ethylene Glycol Base Engine Coolant for Automobile and Light Duty Service<sup>2</sup>

### 3. Terminology

#### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *ash, n*—the components of an engine coolant not removed by ignition at 750°C.

### 4. Summary of Test Method

4.1 To determine the ash content, the antirust or coolant is weighed, evaporated or charred, and finally ignited at a strong heat.

### 5. Significance and Use

5.1 This test method is designed to aid in identifying types of coolants and antirusts. While the ash is primarily due to the

inorganic inhibitors used, it is not a measure of the total inhibitor concentration because of the loss of organic inhibitors.

5.2 An ash content greater than that stated in Specification D 3306 may indicate a salt-based product.

### 6. Apparatus

6.1 *Crucible*, high-silica glass, porcelain, or platinum of 50-mL capacity, equipped with cover.

### 7. Procedure

7.1 Ignite the crucible and cover over a Meker burner for 5 min and allow to cool to room temperature in a desiccator; then weigh to the nearest 0.1 mg.

NOTE 1—**Warning:** When handling a hot crucible use proper caution and safety equipment such as safety glasses, gloves, tongs, etc.

7.2 Weigh  $20 \pm 0.1$  g of well-mixed antirust or coolant (Note 2 and Note 3), including all phases, into the crucible. Sample in accordance with Test Method D 1176. Record the weight of the sample to the nearest 0.1 mg.

NOTE 2—The weight of sample taken is suitable for most commercial products. If there is reason to believe that the ash content may be high, the sample size may be decreased to  $5$  or  $10 \pm 0.1$  g.

7.3 Place the covered crucible in a cool small sand bath in a vented hood. Raise the temperature by any convenient means until the liquid is evaporated. If the sample ignites, remove the heat source until the burning ceases; then reapply the heat.

NOTE 3—**Caution:** Many types of coolant and antirust have tendencies to spatter upon heating, with consequent loss of sample and erroneous results. All precautions consistent with good laboratory practice should be followed.

NOTE 4—**Warning:** Avoid inhalation of the fumes.

7.4 When the crucible appears dry, transfer the crucible to a support over a Meker-type burner. Ignite strongly at red heat until all carbonaceous material disappears from both crucible and cover. The crucible cover may be removed and carefully ignited, directly if desired, taking care to avoid losing any material deposited on the underside of the cover. Place the crucible and cover, with contents, in a desiccator to cool. When they have cooled to room temperature, weigh the crucible, cover, and contents (ash) to the nearest 0.1 mg. Proceed to 7.6.

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D15 on Engine Coolants and is the direct responsibility of Subcommittee D15.04 on Chemical Properties.

Current edition approved Sept. 10, 2000. Published December 2000. Originally published as D 1119 – 50. Last previous edition D 1119 – 96.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 15.05.