



Designation: D 5077 – 90 (Reapproved 2003)

Standard Terminology Relating to Electrostatic Discharge (ESD) Packaging Materials¹

This standard is issued under the fixed designation D 5077; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 The terms and definitions in this standard are related to Electrostatic Discharge (ESD) Packaging Materials and ESD Protective Materials.

2. Referenced Documents

2.1 ASTM Standards:²

D 996 Terminology Relating to Packaging and Distribution Environments

2.2 EIA Standard:

EIA-541 Packaging Material Standards for ESD, Sensitive Items³

3. Terminology

antistatic agent—a chemical compound which, when impregnated or formulated into or topically applied to a primary material or substrate, gives the primary material antistatic properties. See **antistatic property**.

antistatic property—the prevention of triboelectric charge generation by effectively minimizing the production of a static charge when materials are separated from another surface.

DISCUSSION—The forword of EIA-541 states, “‘Antistatic’ no longer refers to a resistivity range ... ‘Antistatic’ refers to a material’s ability to resist triboelectric charge generation. A material’s antistatic propensity depends upon the nature of the material itself and the material with which it is in contact along with the means of surface separation. The antistatic property is not a dependent function of material resistivity. Material resistivity is an intrinsic property used to define its degree of conductivity without regard to other materials.”

conductor—a substance or body that allows a flow of electric current to pass continuously along it or through it when a sufficient voltage is applied across any two points.

dielectric breakdown—a threshold effect in a dielectric medium where, at some electric field strength across the medium, bound electrons become unbound and travel through the medium as a current. In solid media, the region of the current path is permanently damaged. The unit of measurement is usually volts per unit of thickness.

electrically continuous surface—a surface that is electrically conductive in that current can be passed at an applied voltage between any two points of its physical surface.

electrical overstress (EOS)—overstress which may be due to ESD or the operation of items beyond their electrical specifications.

electromagnetic shield—a screen or other housing placed around a device or circuit to reduce the effects on them from both electric and magnetic fields.

electrostatic discharge—the transfer of electrostatic charge between bodies at different electrostatic potentials.

electrostatic discharge (ESD) protective—a property of materials capable of one or more of the following:

preventing the generation of static electricity.

dissipating electrostatic charges over its surface or volume.

providing shielding from ESD or electrostatic fields.

electrostatic discharge sensitive (ESDS)—a property of items in which they are inherently sensitive (ESDS) susceptible to either catastrophic failure or latent damage when exposed to sources of ESD. Items are often categorized as to their levels of sensitivity but in all cases require some means of ESD protective packaging and handling.

electrostatic shield—a barrier or enclosure that prevents the penetration of an electrostatic field.

DISCUSSION—An electrostatic shield may not offer much protection against the effects of an electromagnetic field. Electromagnetic shields, however, are good electrostatic shields.

ground—a metallic connection with the earth to establish zero potential.

DISCUSSION—The ground is the voltage reference point in a circuit. There may or may not be an actual connection to earth, but it is understood that a point in the circuit said to be at ground potential could be connected to earth without disturbing the operation of the circuit in any way. Grounds that can be used for static control work stations

¹ This terminology is under the jurisdiction of ASTM Committee D10 on Packaging and is the direct responsibility of Subcommittee D10.13 on Interior Packaging.

Current edition approved June 29, 1990. Published August 1990.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard’s Document Summary page on the ASTM website.

³ Available from the Electronic Industries Association, 2001 Eye St., N.W., Washington, DC 20006.

include metal water pipes, any power ground, or any large metal structural member of a building, vessel hull, etc. (See **grounding**.)

grounding—connecting to ground or to a conductor that is grounded.

insulator (electric)—a device having high electrical resistance and used for supporting or separating conductors to prevent undesired flow of current from them to other objects. (Also known as electrical insulator.)

ionization—the process by which neutral atoms or molecules, such as air, acquire a positive or negative charge.

packaging—See Terminology D 996.

DISCUSSION—The term packaging as used in this context should not be confused with the term as it is used in the electronics industry where it describes the assembly, black box enclosure, or physical encasing of microelectronic devices.

surface resistivity, ρ_s —the surface resistivity of a material is the ratio of the potential gradient parallel to the current along its surface to the current per unit width of the surface.

DISCUSSION—Surface resistivity of a material is numerically equal to the surface resistance between two electrodes forming opposite sides of a square. The size of the square is immaterial.

volume resistivity, ρ_v —the volume resistivity of a material is the ratio of the potential gradient parallel to the current in the material to the current density.

DISCUSSION—In the metric system, volume resistivity of an electrical insulating material in ohm-cm is numerically equal to the volume resistance in ohms between opposite faces of a 1-cm cube of the material. (Volume resistivity in $\Omega \cdot m$ has a value of $1/100$ of the value in $\Omega \cdot cm$.)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

(<https://standards.iteh.ai>)
Document Preview

ASTM D5077-90(2003)

</catalog/standards/astm/7a1b0c0e-66c7-456d-8497-70c96b2b217c/astm-d5077-90-2003>