
**Aluminium oxide used for the production
of primary aluminium — Determination of
attrition index**

*Oxyde d'aluminium utilisé pour la production de l'aluminium primaire —
Détermination de l'index d'attrition*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 17500:2006](https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006)

<https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17500:2006

<https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6fa6f0e/iso-17500-2006>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Principle.....	1
4 Apparatus	1
5 Sample handling and preparation.....	3
5.1 Reference alumina	3
5.2 Test sample	3
6 Procedure	3
6.1 Flow calibration.....	3
6.2 Attrition procedure for test sample and reference alumina	6
6.3 Particle size distribution analysis.....	6
7 Calculation and reporting of results.....	6
8 Precision.....	7
9 Quality control.....	7
10 Test report	7
Annex A (informative) Results of test programme	8
Bibliography	9

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17500 was prepared by Technical Committee ISO/TC 226, *Materials for the production of primary aluminium*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 17500:2006

<https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006>

Introduction

This International Standard is based on Australian method, AS 2879.10-2003, *Alumina — Determination of attrition index*.

The Attrition Index reference material ASCRM 025 was released in December 2003 by SAI Global, along with a Technical Report on its preparation (TR 2.25-2003). These are available from SAI through their website:

<http://www.standards.com.au/>

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 17500:2006

<https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 17500:2006

<https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006>

Aluminium oxide used for the production of primary aluminium — Determination of attrition index

1 Scope

This International Standard specifies a procedure for the determination of the attrition index of smelter-grade alumina.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2926:2005, *Aluminium oxide used for the production of primary aluminium — Particle size analysis for the range 45 µm to 150 µm — Method using electroformed sieves*

AS 2879.6-1995, *Alumina — Determination of the mass distribution of particle sizes using electroformed sieves*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3 Principle

<https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006>

A test portion is attrited using a high velocity gas jet under controlled conditions using the attrition index apparatus. Flow in the apparatus is calibrated to a reference alumina. The particle size distribution is measured before and after attrition. The attrition index is the relative percentage decrease in the + 45 µm fraction under specific test conditions.

4 Apparatus

4.1 Attrition index apparatus.

A typical assembled apparatus is shown in Figure 1 which consists of:

a) Column

Stainless steel, aluminium and glass columns of length 1 500 mm to 1 600 mm and inside diameter 25 mm have been tested and found to be suitable. To minimize dust carryover, columns with larger-diameter upper sections are also suitable. A column of reduced overall length (700 mm) and upper diameter 64 mm has also been found to be suitable. In any case, modified columns shall maintain the 25 mm ID for a minimum of 200 mm from the orifice plate. Also, they shall be constructed with a smooth tapered transition between sections, to ensure that alumina is not held up in the upper section of the column. Columns may also be provided with a timed automated rapper to facilitate rapping the column [see 6.2 f)].

b) Orifice plate and assembly

The orifice plate assembly holds and seals the orifice plate ¹⁾ centrally to the base of the column. The orifice plate has a circular aperture of (400 ± 15) μm diameter cut through a hard material. A typical orifice plate and its correct orientation is shown in Figure 2.

Flow variations caused by minor dimensional variations between orifice plates are overcome by calibration with a reference alumina.

c) Dust filter and assembly

The dust filter assembly holds and seals the dust filter to the top of the column. Ideally the assembly should enclose the filter to allow subsequent flow measurement to the atmosphere, so that the flow can be monitored to ensure that it is maintained for the test period.

NOTE A cellulose Soxhlet thimble, with an internal diameter of 43 mm and length of 123 mm, has been found to be a suitable filter.

d) Flow measurement and control equipment

The flow measurement and control equipment shall include components to measure and control the airflow, to within 0,1 l/min, at the operating flows (typically 5 l/min to 8 l/min).

4.2 Balance.

Analytical balance capable of weighing 100 g to the nearest 0,01 g.

4.3 Particle sizing apparatus.

Electroformed sieves and apparatus as specified in ISO 2926:2005. For an alternative sizing technique, see Note to 6.3.

[ISO 17500:2006](https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006)

4.4 Sample splitter.

<https://standards.iteh.ai/catalog/standards/sist/54599a2a-c926-42f4-9db7-44e8fe6f0e/iso-17500-2006>

To provide representative portions, a rotary splitter is preferred.

4.5 Dried air or nitrogen supply.

A regulated system capable of supplying stable pressures, typically in the range 400 kPa to 800 kPa.

4.6 Sample containers.

Capable of being sealed and with a volume of between 60 ml and 125 ml.

4.7 Reference alumina.

With a certified attrition index value.

NOTE A suitable reference material is available from Standards Australia — (ASCRM 025 series).

1) A suitable orifice plate is obtainable from Societe des Filieres Balloffet, 13 rue de l'Industrie, BP 18, 01151 Lagnieu Cedex, France. This information is given for the convenience of users of this International Standard and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.

5 Sample handling and preparation

5.1 Reference alumina

The reference alumina shall be split into 50 g to 60 g portions for attrition index and particle size analysis.

5.2 Test sample

The test sample shall be equilibrated to the laboratory atmosphere for a minimum of 2 h in a layer of maximum thickness 5 mm. Then the sample shall be split into 50 g to 60 g portions for attrition index and particle size analysis. Immediately after splitting, place the sample in containers (4.6) and seal.

6 Procedure

6.1 Flow calibration

The calibrated flow rate (F_c) required to produce the reference attrition index value shall be determined using several portions of reference alumina. F_o shall be subsequently used for the analysis of test samples. The procedure to determine F_o shall be as follows:

- a) Determine the percent + 45 μm size fraction of the unattrited reference alumina in accordance with 6.3. Perform this determination in triplicate. The mean of the three determinations is used in the calculation of the attrition index for all calibration portions.
- b) Weigh out six 50 g \pm 0,5 g portions of the reference alumina, using the balance (4.2), and record the actual mass to the nearest 0,01 g (m_1).
- c) Attrite the first of the six portions of the reference alumina in accordance with 6.2 c) to i), and determine the percent + 45 μm size fraction of the attrited material. Use a nominal exit flow rate within the range of 5 l/min to 8 l/min.
- d) Calculate the attrition index of this first portion of reference alumina according to Clause 7.
- e) Using this initial result, attrite three further portions of the reference alumina at different flow rates, determine the percent + 45 μm size fraction of each portion and calculate each portion's attrition index. Choose these flow rates such that:
 - 1) the determined attrition index values are greater and less than the recommended reference value; and
 - 2) the difference between the minimum and maximum flow rate is at least 1,0 l/min, but less than 3,0 l/min.
- f) Plot attrition index versus flow rate for these four portions and include a linear trend line of best fit. Add y-axis error bars of 5 % relative to the data points. If an error bar for a data point does not cross the trend line then repeat the analysis for that flow rate. Use the chart to determine the calibrated flow rate (F_c) required to obtain the attrition index of the reference alumina. Figure 3 shows an example of a typical calibration.

NOTE The attrition index has been shown not to be a linear function of flow, however linearity is assumed for the narrow range of flow rates used for calibration.

- g) Using the remaining two portions, repeat the attrition procedure [6.2 c) to i)] in duplicate at the calibrated flow rate. Determine the percent + 45 μm size fraction of each portion and calculate each portion's attrition index. The average of these results should produce the reference attrition index value \pm 0,8. If this value is not obtained, then the apparatus shall be checked and the calibration repeated.