

SLOVENSKI STANDARD

SIST EN 1555-3:2010

01-december-2010

Nadomešča:

SIST EN 1555-3:2003

SIST EN 1555-3:2003/A1:2005

Cevni sistemi iz polimernih materialov za oskrbo s plinastimi gorivi - Polietilen (PE) - 3. del: Fitingi

Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE) - Part 3: Fittings

Kunststoff-Rohrleitungssysteme für die Gasversorgung - Polyethylen (PE) - Teil 3: Formstücke

Systèmes de canalisations en plastique pour la distribution de combustibles gazeux - Polyéthylène (PE) - Partie 3: Raccords

Ta slovenski standard je istoveten z: EN 1555-3:2010

ICS:

83.140.30	Cevi, fittingi in ventili iz polimernih materialov	Plastics pipes, fittings and valves
91.140.40	Sistemi za oskrbo s plinom	Gas supply systems

SIST EN 1555-3:2010

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1555-3:2010

<https://standards.iteh.ai/catalog/standards/sist/511c1954-ff5c-452c-b593-b9437683fd84/sist-en-1555-3-2010>

EUROPEAN STANDARD

EN 1555-3

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2010

ICS 23.040.45; 91.140.40

Supersedes EN 1555-3:2002

English Version

Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE) - Part 3: Fittings

Systèmes de canalisations en plastique pour la distribution
de combustibles gazeux - Polyéthylène (PE) - Partie 3:
Raccords

Kunststoff-Rohrleitungssysteme für die Gasversorgung -
Polyethylen (PE) - Teil 3: Formstücke

This European Standard was approved by CEN on 30 July 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 1555-3:2010](https://standards.iteh.ai/catalog/standards/sist/511c1954-f5c-452c-b593-b9437683fd84/sist-en-1555-3-2010)

<https://standards.iteh.ai/catalog/standards/sist/511c1954-f5c-452c-b593-b9437683fd84/sist-en-1555-3-2010>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	4
Introduction	5
1 Scope	6
2 Normative references	6
3 Terms and definitions, symbols and abbreviations	8
4 Material	9
4.1 PE Compound	9
4.2 Material for non-polyethylene parts	9
4.2.1 General.....	9
4.2.2 Metal parts	9
4.2.3 Elastomers.....	9
4.2.4 Other materials.....	9
5 General characteristics	10
5.1 Appearance	10
5.2 Colour	10
5.3 Design	10
5.4 Appearance of factory made joints.....	10
5.5 Electrical characteristics for electrofusion fittings.....	10
6 Geometrical characteristics.....	11
6.1 Measurement of dimensions	11
6.2 Dimensions of electrofusion socket fittings.....	11
6.2.1 Diameters and lengths of electrofusion sockets.....	11
6.2.2 Wall thicknesses	12
6.2.3 Out-of-roundness of the bore of a fitting (at any point).....	13
6.2.4 Spigots.....	13
6.2.5 Other dimensions	13
6.3 Dimensions of electrofusion saddle fittings.....	13
6.4 Dimensions of spigot end fittings.....	14
6.4.1 Diameters and lengths	14
6.4.2 Wall thickness of the fusion end.....	16
6.4.3 Wall thickness of the fitting body	16
6.4.4 Other dimensions	17
6.5 Dimensions of mechanical fittings	17
6.5.1 General.....	17
6.5.2 Mechanical fittings with polyethylene spigot ends.....	17
6.5.3 Mechanical fittings with polyethylene electrofusion sockets.....	17
6.5.4 Threads	17
7 Mechanical characteristics	17
7.1 General.....	17
7.2 Requirements	18
7.3 Performance requirements	20
8 Physical characteristics.....	20
8.1 Conditioning.....	20
8.2 Requirements	20
9 Performance requirements	21
10 Marking	21
10.1 General.....	21
10.2 Minimum required marking of fittings	21

10.3	Additional marking	22
10.4	Fusion system recognition.....	22
11	Delivery conditions	22
Annex A	(informative) Examples of typical terminal connection for electrofusion fittings	23
Annex B	(normative) Short-term pressure test method	25
B.1	Principle.....	25
B.2	Apparatus	25
B.3	Test piece	25
B.4	Procedure	25
B.5	Test report.....	26
Annex C	(normative) Tensile test for fitting/pipe assemblies	27
C.1	Principle.....	27
C.2	Apparatus	27
C.3	Test piece	27
C.4	Procedure	27
C.5	Test report.....	27
Bibliography	29

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 1555-3:2010](https://standards.iteh.ai/catalog/standards/sist/511c1954-f5c-452c-b593-b9437683fd84/sist-en-1555-3-2010)

<https://standards.iteh.ai/catalog/standards/sist/511c1954-f5c-452c-b593-b9437683fd84/sist-en-1555-3-2010>

EN 1555-3:2010 (E)**Foreword**

This document (EN 1555-3:2010) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2011, and conflicting national standards shall be withdrawn at the latest by March 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1555-3:2002.

EN 1555 consists of the following parts:

- EN 1555-1, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*;
- EN 1555-2, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes*;
- EN 1555-3, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 3: Fittings* (this standard);
- prEN 1555-4, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 4: Valves*;
- EN 1555-5, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 5: Fitness for purpose of the system*;
- CEN/TS 1555-7, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 7: Guidance for assessment of conformity*.

NOTE EN 12007-2:2000 [1] prepared by CEN/TC 234 "Gas infrastructure" deals with the recommended practice for installation of plastics pipes system in accordance with EN 1555 (all parts).

System Standards are based on the results of the work being undertaken in ISO/TC 138 "Plastics pipes, fittings and valves for the transport of fluids", which is a Technical Committee of the International Organization for Standardization (ISO).

They are supported by separate standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and on recommended practice for installation.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

Introduction

The System Standard, of which this is Part 3, specifies the requirements for a piping system and its components made from polyethylene (PE) and which is intended to be used for the supply of gaseous fuels.

Requirements and test methods for material and components, other than fittings, are specified in EN 1555-1, EN 1555-2 and prEN 1555-4 [9].

Characteristics for fitness for purpose are covered in EN 1555-5. CEN/TS 1555-7 [2] gives guidance for assessment of conformity. Recommended practice for installation is given in EN 12007-2:2000 [1] prepared by CEN/TC 234.

This part of EN 1555 covers the characteristics of fittings.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 1555-3:2010](https://standards.iteh.ai/catalog/standards/sist/511c1954-ff5c-452c-b593-b9437683fd84/sist-en-1555-3-2010)

<https://standards.iteh.ai/catalog/standards/sist/511c1954-ff5c-452c-b593-b9437683fd84/sist-en-1555-3-2010>

EN 1555-3:2010 (E)**1 Scope**

This part of EN 1555 specifies the characteristics of fusion fittings made from polyethylene (PE) as well as of mechanical fittings for piping systems in the field of the supply of gaseous fuels.

It also specifies the test parameters for the test methods referred to in this standard.

In conjunction with Parts 1, 2, 4 and 5 of EN 1555, it is applicable to PE fittings, their joints and to joints with components of PE and other materials intended to be used under the following conditions:

- a) a maximum operating pressure, MOP, up to and including 10 bar ¹⁾;
- b) an operating temperature of 20 °C as reference temperature.

NOTE 1 For other operating temperatures, derating coefficients should be used; see EN 1555-5.

EN 1555 (all parts) covers a range of maximum operating pressures and gives requirements concerning colours and additives.

NOTE 2 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

This European Standard is applicable for fittings of the following types:

- c) electrofusion socket fittings;
- d) electrofusion saddle fittings;
- e) spigot end fittings (for butt fusion using heated tools and electrofusion socket fusion);
- f) mechanical fittings.

ITeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/511c1954-f5c-452c-b593-b9437683fd84/sist-en-1555-3-2010>

The fittings can e.g. be in the form of couplers, equal and reduced tees, reducers, bends or caps.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 682:2002, *Elastomeric Seals — Materials requirements for seals used in pipes and fittings carrying gas and hydrocarbon fluids*

EN 1555-1:2010, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*

EN 1555-2, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes*

EN 1555-5, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 5: Fitness for purpose of the system*

EN 1716, *Plastics piping systems — Polyethylene (PE) tapping tees — Test method for impact resistance of an assembled tapping tee*

1) 1 bar = 0,1 MPa.

- EN 10226-1, *Pipe threads where pressure tight joints are made on the threads — Part 1: Taper external threads and parallel internal threads — Dimensions, tolerances and designation*
- EN 10226-2, *Pipe threads where pressure tight joints are made on the threads — Part 2: Taper external threads and taper internal threads — Dimensions, tolerances and designation*
- EN 12117, *Plastics piping systems — Fittings, valves and ancillaries — Determination of gaseous flow rate/pressure drop relationships*
- EN ISO 228-1:2000, *Pipe threads where pressure-tight joints are not made on the threads — Part 1: Dimensions, tolerances and designation (ISO 228-1:2000)*
- EN ISO 1133, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics (ISO 1133:2005)*
- EN ISO 1167-1:2006, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method (ISO 1167-1:2006)*
- EN ISO 1167-4, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 4: Preparation of assemblies (ISO 1167-4:2007)*
- EN ISO 3126, *Plastics piping systems — Plastics components — Determination of dimensions (ISO 3126:2005)*
- ISO 10838-1 ²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 1: Metal fittings for pipes of nominal outside diameter less than or equal to 63 mm*
- ISO 10838-2 ²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 2: Metal fittings for pipes of nominal outside diameter greater than 63 mm*
- ISO 10838-3 ²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 3: Thermoplastic fittings for pipes of nominal outside diameter less than or equal to 63 mm*
- ISO 11357-6:2008, *Plastics — Differential scanning calorimetry (DSC) — Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)*
- ISO 13950, *Plastics pipes and fittings — Automatic recognition systems for electrofusion joints*
- ISO 13951:2001, *Plastics piping systems — Test method for the resistance of polyolefin pipe/pipe or pipe/fitting assemblies to tensile loading*
- ISO 13953, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint*
- ISO 13954, *Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm*
- ISO 13955, *Plastics pipes and fittings — Crushing decohesion test for polyethylene (PE) electrofusion assemblies*
- ISO/FDIS 13956, *Plastics pipes and fittings — Determination of cohesive strength — Evaluation of ductility of fusion joint interface by tear test*

2) Under revision.

EN 1555-3:2010 (E)**3 Terms and definitions, symbols and abbreviations**

For the purposes of this document, the terms and definitions, symbols and abbreviations given in EN 1555-1:2010 and the following apply.

3.1 electrofusion socket fitting
polyethylene (PE) fitting which contains one or more integral heating elements, that are capable of transforming electrical energy into heat to realise a fusion joint with a spigot end or a pipe

3.2 electrofusion saddle fitting
polyethylene (PE) fitting which contains one or more integral heating elements, that are capable of transforming electrical energy into heat to realise a fusion joint onto a pipe

3.2.1 tapping tee
electrofusion saddle fitting (top loading or wrap round) which contains an integral cutter, to cut through the wall of the main pipe which remains in the body of the tapping tee after installation

3.2.2 branch saddle
electrofusion saddle fitting (top loading or wrap round) which requires an ancillary cutting tool for drilling a hole in the adjoining main pipe

3.3 mechanical fitting
fitting, that generally includes a compression part to provide pressure integrity, leaktightness and resistance to end loads, for assembling polyethylene (PE) pipe to another PE pipe or any other element of the piping system

iTeh STANDARD PREVIEW

(standard.itteh.ai)

SIST EN 1555-3:2010

NOTE 1 A pipe-supporting sleeve providing a permanent support for a polyethylene (PE) pipe to prevent creep in the pipe wall under radial compressive forces, is applicable. The metallic parts of the fitting can be assembled to metallic pipes by screw-threads, compression joints, welded or flanged connections, including PE flanges. In some cases the supporting sleeve at the same time constitutes a grip ring.

NOTE 2 The fitting can allow either a dismantable or permanently assembled joint.

NOTE 3 The mechanical fitting can be supplied for field assembly or pre-assembled by the manufacturer.

3.4 spigot end fitting
polyethylene (PE) fitting where the outside diameter of the spigot end is equal to the nominal outside diameter, d_n , of the corresponding pipe

3.5 voltage regulation
control of energy supplied, during the fusion process of an electrofusion fitting, by means of the voltage parameter

3.6 intensity regulation
control of energy supplied, during the fusion process of an electrofusion fitting, by means of the current parameter

4 Material

4.1 PE Compound

The PE compound from which the fittings are made shall conform to EN 1555-1.

The stress bearing parts shall only be made from virgin material conforming to EN 1555-1.

4.2 Material for non-polyethylene parts

4.2.1 General

All components shall conform to the relevant EN standard(s). Alternative standards may be applied in cases where the suitable EN standard(s) do not exist. In all cases fitness for purpose of the components shall be demonstrated.

The materials and the constituent elements used in making the fitting (including elastomers and any metal parts as may be used) shall be as resistant to the external and internal environments as the other elements of the piping system and shall have a life expectancy under the following conditions at least equal to that of the PE pipes conforming to EN 1555-2 with which they are intended to be used:

- a) during storage;
- b) under the effect of the gas conveyed therein;
- c) with respect to the service environment and operating conditions.

The requirements for the level of material performance of non-polyethylene parts shall be at least as stringent as that of the PE compound for the piping system. Reprocessed materials shall not be used for stress bearing polymeric parts.

Other materials used in fittings in contact with the PE pipe shall not adversely affect pipe performance or initiate stress cracking.

NOTE Clause 4.2 does not apply to non-stress bearing fitting parts.

4.2.2 Metal parts

All metal parts susceptible to corrosion shall be adequately protected, providing this is necessary for the durability and function of the system.

When dissimilar metallic materials are used which can be in contact with moisture, steps shall be taken to avoid the possibility of galvanic corrosion.

4.2.3 Elastomers

Elastomeric seals shall conform to EN 682:2002.

Other sealing materials are permitted if suitable for gas service.

4.2.4 Other materials

Greases or lubricants shall not exude onto fusion areas, and shall not affect the long-term performance of fitting materials.

EN 1555-3:2010 (E)**5 General characteristics****5.1 Appearance**

When viewed without magnification, the internal and external surfaces of fittings shall be smooth, clean and shall have no scoring, cavities and other surface defects to an extent that would prevent conformity to this standard.

No component of the fitting shall show any signs of damage, scratches, pitting, bubbles, blisters, inclusions or cracks to an extent that would prevent conformity of the fittings to the requirements of this standard.

5.2 Colour

The colour of the PE parts of fittings shall be either black, yellow, or orange.

5.3 Design

The design of the fitting shall be such that, when assembling the fitting onto the pipe or other component, electrical coils and/or seals are not displaced.

5.4 Appearance of factory made joints

The internal and external surfaces of the pipe and fitting after fusion jointing, examined visually without magnification, shall be free from melt exudation outside the confines of the fitting, apart from that which may be declared acceptable by the fitting manufacturer or used deliberately as a fusion marker.

Any melt exudation shall not cause wire movement in electrofusion fittings such that it leads to short-circuiting, when jointed in accordance with the manufacturer's instructions. There shall be no excessive creasing of the internal surfaces of the adjoining pipes.

<https://standards.iteh.ai/catalog/standards/sist/511c1954-f5c-452c-b593-b94276827384/sist-en-1555-3-2010>

5.5 Electrical characteristics for electrofusion fittings

The electrical protection that shall be provided by the fusion process depends on the voltage and the current used and on the characteristics of the electricity power source.

For voltages greater than 25 V, direct human contact with energized parts shall not be possible when the fitting is in the fusion cycle during assembly in accordance with the instructions of the manufacturers of the fittings and of the assembly equipment, as applicable.

NOTE 1 The fitting is during the fusion process part of an electrical system as defined in EN 60335-1 [3], HD 60364-1 [4] and IEC 60449 [5].

The tolerance on the electrical resistance of the fitting at 23 °C shall be stated by the manufacturer. The resistance shall be between nominal resistance (-10%) and nominal resistance (+10%) + 0,1 Ω.

NOTE 2 0,1 Ω is the assumed value of the contact resistance.

The surface finish of the terminal pins shall allow a minimum contact resistance in order to satisfy the resistance tolerance requirements.

NOTE 3 See Annex A, for examples of typical electrofusion terminal connections.