



SLOVENSKI STANDARD

SIST EN 1555-5:2010

01-december-2010

Nadomešča:
SIST EN 1555-5:2003

Cevni sistemi iz polimernih materialov za oskrbo s plinastimi gorivi - Polietilen (PE) - 5. del: Ustreznost sistema namenu

Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE) - Part 5: Fitness for purpose of the system

Kunststoff-Rohrleitungssysteme für die Gasversorgung - Polyethylen (PE) - Teil 5: Gebrauchstauglichkeit des Systems

Systèmes de canalisations en plastique pour la distribution de combustibles gazeux - Polyéthylène (PE) - Partie 5: Aptitude à l'emploi du système

Ta slovenski standard je istoveten z: EN 1555-5:2010

ICS:

83.140.30	Cevi, fittingi in ventili iz polimernih materialov	Plastics pipes, fittings and valves
91.140.40	Sistemi za oskrbo s plinom	Gas supply systems

SIST EN 1555-5:2010

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 1555-5:2010

<https://standards.iteh.ai/catalog/standards/sist/4a31254c-2dca-4bfb-ad73-427ccb11c9d8/sist-en-1555-5-2010>

EUROPEAN STANDARD

EN 1555-5

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2010

ICS 23.040.01; 91.140.40

Supersedes EN 1555-5:2002

English Version

Plastics piping systems for the supply of gaseous fuels - Polyethylene (PE) - Part 5: Fitness for purpose of the system

Systèmes de canalisations en plastique pour la distribution
de combustibles gazeux - Polyéthylène (PE) - Partie 5:
Aptitude à l'emploi du système

Kunststoff-Rohrleitungssysteme für die Gasversorgung -
Polyethylen (PE) - Teil 5: Gebrauchstauglichkeit des
Systems

This European Standard was approved by CEN on 30 July 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 1555-5:2010](https://standards.iteh.ai/catalog/standards/sist/4a31254c-2dca-4bfb-ad73-427ccb11c9d8/sist-en-1555-5-2010)

<https://standards.iteh.ai/catalog/standards/sist/4a31254c-2dca-4bfb-ad73-427ccb11c9d8/sist-en-1555-5-2010>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

	Page
Foreword.....	3
Introduction	4
1 Scope.....	5
2 Normative references	5
3 Terms and definitions	6
4 Fitness for purpose.....	7
4.1 Method of preparation of assemblies for testing	7
4.1.1 General.....	7
4.1.2 Butt fusion joints.....	7
4.1.3 Electrofusion jointing	7
4.1.4 Mechanical joints	7
4.2 Requirements for fitness for purpose	7
4.2.1 General.....	7
4.2.2 Fitness for purpose of butt fusion joints.....	8
4.2.3 Fitness for purpose for electrofusion joints	9
4.2.4 Fitness for purpose for mechanical joints	10
4.3 Conditioning.....	10
4.4 Requirements	10
4.5 Retest in case of failure at 80 °C	11
5 Design coefficient	12
Annex A (informative) Derating coefficients for operating temperatures	13
Annex B (normative) Rapid crack propagation (RCP) resistance of pipe at temperature less than 0 °C	14
Bibliography.....	15

Foreword

This document (EN 1555-5:2010) has been prepared by Technical Committee CEN/TC 155 "Plastics piping systems and ducting systems", the secretariat of which is held by NEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2011 and conflicting national standards shall be withdrawn at the latest by March 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 1555-5:2002.

EN 1555 consists of the following parts:

- EN 1555-1, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*;
- EN 1555-2, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes*;
- EN 1555-3, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 3: Fittings*;
- prEN 1555-4, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 4: Valves*;
- EN 1555-5, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 5: Fitness for purpose of the system (this standard)*;
- CEN/TS 1555-7, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 7: Guidance for assessment of conformity*.

System Standards are supported by separate standards on test methods to which references are made throughout the System Standard.

The System Standards are consistent with general standards on functional requirements and on recommended practice for installation.

NOTE EN 12007-2:2000 [1] prepared by CEN/TC 234 "Gas infrastructure" deals with the recommended practice for installation of plastics pipes system in accordance with EN 1555 (all parts).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

EN 1555-5:2010 (E)**Introduction**

The System Standard, of which this is Part 5, specifies the requirements of a piping system and its components made from polyethylene (PE) and which is intended to be used for the supply of gaseous fuels.

Requirements and test methods for material and components are specified in EN 1555-1, EN 1555-2, EN 1555-3 and prEN 1555-4.

CEN /TS 1555-7 [2] gives guidance for assessment of conformity. Recommended practice for installation is given in EN 12007-2:2000 [1] prepared by CEN /TC 234.

This part of EN 1555 covers the characteristics of fitness for purpose of the system.

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

SIST EN 1555-5:2010

<https://standards.iteh.ai/catalog/standards/sist/4a31254c-2dca-4bfb-ad73-427ccb11c9d8/sist-en-1555-5-2010>

1 Scope

This part of EN 1555 specifies requirements of fitness for purpose of the polyethylene (PE) piping system in the field of the supply of gaseous fuels.

It specifies the definitions of electrofusion, butt fusion and mechanical joints.

It specifies the method of preparation of test piece joints, and the tests to be carried out on these joints for assessing the fitness for purpose of the system under normal and extreme conditions.

It specifies the test parameters for the test methods referred to in this standard.

In conjunction with Parts 1 to 4 of EN 1555, it is applicable to PE pipes, fittings, valves, their joints and to joints with components of other materials intended to be used under the following conditions:

- a) a maximum operating pressure, MOP, up to and including 10 bar ¹⁾;
- b) an operating temperature of 20 °C as reference temperature.

NOTE 1 For other operating temperatures, derating coefficients should be used, see Annex A.

EN 1555 (all parts) covers a range of maximum operating pressures and gives requirements concerning colours and additives.

NOTE 2 It is the responsibility of the purchaser or specifier to make the appropriate selections from these aspects, taking into account their particular requirements and any relevant national regulations and installation practices or codes.

2 Normative references

SIST EN 1555-5:2010

<https://standards.iteh.ai/catalog/standards/sist/4a31254c-2dca-4bfb-ad73-7c9e11d55016/555-5-2010>

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1555-1:2010, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 1: General*

EN 1555-2:2010, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 2: Pipes*

EN 1555-3, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 3: Fittings*

prEN 1555-4, *Plastics piping systems for the supply of gaseous fuels — Polyethylene (PE) — Part 4: Valves*

EN ISO 1167-1:2006, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 1: General method (ISO 1167-1:2006)*

EN ISO 1167-2, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 2: Preparation of pipe test pieces (ISO 1167-2:2006)*

EN ISO 1167-4, *Thermoplastics pipes, fittings and assemblies for the conveyance of fluids — Determination of the resistance to internal pressure — Part 4: Preparation of assemblies (ISO 1167-4:2007)*

1) 1 bar = 0,1 MPa.

EN 1555-5:2010 (E)

EN ISO 13477, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Small-scale steady-state test (S4 test) (ISO 13477:2008)*

EN ISO 13478, *Thermoplastics pipes for the conveyance of fluids — Determination of resistance to rapid crack propagation (RCP) — Full scale test (FST) (ISO 13478:2007)*

ISO 10838-1²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 1: Metal fittings for pipes of nominal outside diameter less than or equal to 63 mm*

ISO 10838-2²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 2: Metal fittings for pipes of nominal outside diameter greater than 63 mm*

ISO 10838-3²⁾, *Mechanical fittings for polyethylene piping systems for the supply of gaseous fuels — Part 3: Thermoplastics fittings for pipes of nominal outside diameter less than or equal to 63 mm*

ISO 11413:2008, *Plastics pipes and fittings — Preparation of test piece assemblies between a polyethylene (PE) pipe and an electrofusion fitting*

ISO 11414:2009, *Plastics pipes and fittings — Preparation of polyethylene (PE) pipe/pipe or pipe/fitting test piece assemblies by butt fusion*

ISO 13953, *Polyethylene (PE) pipes and fittings — Determination of the tensile strength and failure mode of test pieces from a butt-fused joint*

ISO 13954, *Plastics pipes and fittings — Peel decohesion test for polyethylene (PE) electrofusion assemblies of nominal outside diameter greater than or equal to 90 mm*

ISO 13955, *Plastics pipes and fittings — Crushing decohesion test for polyethylene (PE) electrofusion assemblies*

ISO/FDIS 13956, *Plastics pipes and fittings — Determination of cohesive strength — Evaluation of ductility of fusion joint interface by tear test*

3 Terms and definitions

For the purposes of this document, the terms and definitions, symbols and abbreviations given in EN 1555-1:2010 and the following definition apply.

3.1 mechanical joint
joint made by assembling a PE pipe with a fitting that generally includes a compression part to provide for pressure integrity, leaktightness and resistance to end loads

NOTE A support sleeve inserted into the pipe bore should be used to provide a permanent support for the PE pipe to prevent creep in the pipe wall under radial compressive forces. The metallic part of this fitting can be assembled to a metallic pipe by screw threads, compression joints, welded or brazed flanges or by other means.

²⁾ These standards are under revision.

4 Fitness for purpose

4.1 Method of preparation of assemblies for testing

4.1.1 General

The joints shall be made by using pipes conforming to EN 1555-2, fittings conforming to EN 1555-3 or valves conforming to prEN 1555-4.

Test pieces for pressure test shall be closed with pressure-tight, end-load-bearing end caps, plugs or flanges which shall be provided with connections for the entry of water and release of air.

The peelable layer of peelable layer pipe shall be removed in the area of the joint prior to jointing.

4.1.2 Butt fusion joints

PE pipes, spigot end fittings and valves intended to be used for jointing by butt fusion shall be prepared and assembled in accordance with ISO 11414. The conditions for the preparation of the joints are given in 4.2.2.1 for the assessment of fitness for purpose under normal conditions and in 4.2.2.2 for the assessment of fitness for purpose under extreme conditions.

4.1.3 Electrofusion jointing

PE pipes, fittings and valves intended to be used for jointing by electrofusion shall be prepared and assembled in accordance with ISO 11413. The conditions for the preparation of the joints are given in 4.2.3.1 for the assessment of fitness for purpose under normal conditions and in 4.2.3.2 for the assessment of fitness for purpose under extreme conditions.

For joints with electrofusion saddle fittings, the electrofusion saddle fitting shall be fused to the pipe, while it is pneumatically pressurized to the allowable maximum operating pressure. The pipe shall be cut immediately after the manufacturer prescribed cooling time has elapsed.

NOTE These joints with electrofusion saddle fitting should be prepared taking into consideration national safety regulations.

For straight equal electrofusion socket fittings (couplers) test joints on selected diameters out of the product range shall be prepared with a gap of $0,05d_n$ between the pipe end and the maximum theoretical depth of penetration of the fitting, where for diameters greater than 225 mm the adjoining pipes shall be arranged to provide the maximum angular deflection possible for the fitting, limited to $1,5^\circ$.

4.1.4 Mechanical joints

For mechanical joints the assembly of the PE pipe and the fitting shall be prepared in accordance with ISO 10838-1, ISO 10838-2 or ISO 10838-3, as applicable.

4.2 Requirements for fitness for purpose

4.2.1 General

When tested in accordance with the test methods as specified in Table 5 using the indicated parameters, fittings shall have mechanical characteristics conforming to the requirements given in Table 5, as applicable to the following types of joints:

- (A) electrofusion socket fittings;
- (B) electrofusion saddle fitting;