



SLOVENSKI STANDARD SIST EN ISO 898-2:2012

01-julij-2012

Nadomešča:

SIST EN 20898-2:1996

SIST EN ISO 898-6:1996

Mehanske lastnosti veznih elementov, narejenih iz ogljikovega jekla in jeklene zlitine - 2. del: Matice z določenimi razredi trdnosti - Grobi in fini navoj (ISO 898-2:2012)

Mechanical properties of fasteners made of carbon steel and alloy steel - Part 2: Nuts with specified property classes - Coarse thread and fine pitch thread (ISO 898-2:2012)

Mechanische Eigenschaften von Verbindungselementen aus Kohlenstoffstahl und legiertem Stahl - Teil 2: Muttern mit festgelegten Festigkeitsklassen - Regelgewinde und Feingewinde (ISO 898-2:2012)

Caractéristiques mécaniques des éléments de fixation en acier au carbone et en acier allié - Partie 2: Écrous de classes de qualité spécifiées - Filetages à pas gros et filetages à pas fin (ISO 898-2:2012)

Ta slovenski standard je istoveten z: EN ISO 898-2:2012

ICS:

21.060.20 Matice Nuts

SIST EN ISO 898-2:2012 en,fr

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 898-2:2012](#)

<https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338fffd3ed78/sist-en-iso-898-2-2012>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 898-2

March 2012

ICS 21.060.20

Supersedes EN 20898-2:1993, EN ISO 898-6:1995

English Version

Mechanical properties of fasteners made of carbon steel and alloy steel - Part 2: Nuts with specified property classes - Coarse thread and fine pitch thread (ISO 898-2:2012)

Caractéristiques mécaniques des éléments de fixation en acier au carbone et en acier allié - Partie 2: Écrous de classes de qualité spécifiées - Filetages à pas gros et filetages à pas fin (ISO 898-2:2012)

Mechanische Eigenschaften von Verbindungselementen aus Kohlenstoffstahl und legiertem Stahl - Teil 2: Muttern mit festgelegten Festigkeitsklassen - Regelgewinde und Feingewinde (ISO 898-2:2012)

This European Standard was approved by CEN on 14 March 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[SIST EN ISO 898-2:2012](https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338fffd3ed78/sist-en-iso-898-2-2012)

<https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338fffd3ed78/sist-en-iso-898-2-2012>

Foreword

This document (EN ISO 898-2:2012) has been prepared by Technical Committee ISO/TC 2 "Fasteners" in collaboration with Technical Committee CEN/TC 185 "Fasteners" the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2012, and conflicting national standards shall be withdrawn at the latest by September 2012.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 20898-2:1993, EN ISO 898-6:1995.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

iTeh STANDARD PREVIEW
Endorsement notice
(standards.iteh.ai)

The text of ISO 898-2:2012 has been approved by CEN as a EN ISO 898-2:2012 without any modification.

SIST EN ISO 898-2:2012

<https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338fffd3ed78/sist-en-iso-898-2-2012>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 898-2:2012

<https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338fffd3ed78/sist-en-iso-898-2-2012>

INTERNATIONAL STANDARD

ISO
898-2

Third edition
2012-03-15

Mechanical properties of fasteners made of carbon steel and alloy steel —

Part 2:

Nuts with specified property classes — Coarse thread and fine pitch thread

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Caractéristiques mécaniques des éléments de fixation en acier au
carbone et en acier allié —*

*Partie 2. Écrous de classes de qualité spécifiées — Filetages à pas
gros et filetages à pas fin*

[SIST EN ISO 898-2:2012](https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338ffd3ed78/sist-en-iso-898-2-2012)

<https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338ffd3ed78/sist-en-iso-898-2-2012>



Reference number
ISO 898-2:2012(E)

© ISO 2012

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 898-2:2012

<https://standards.iteh.ai/catalog/standards/sist/549651ea-82fb-4ea5-afa1-338fffd3ed78/sist-en-iso-898-2-2012>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2012

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents	Page
Foreword	iv
1 Scope	1
2 Normative references	2
3 Symbols	2
4 Designation systems	2
4.1 Designation of nut styles	2
4.2 Designation of property classes	2
4.3 Ranges of nominal diameters in relation to nut style and property class	3
5 Design of bolt and nut assemblies	3
6 Materials	4
7 Mechanical properties	5
8 Inspection	8
8.1 Manufacturer's inspection	8
8.2 Supplier's inspection	8
8.3 Purchaser's inspection	8
9 Test methods	9
9.1 Proof load test	9
9.2 Hardness test	11
9.3 Surface integrity inspection	13
10 Marking	13
10.1 General	13
10.2 Identification mark of the manufacturer	13
10.3 Marking of property classes	13
10.4 Identification	14
10.5 Marking of left-hand thread	15
10.6 Marking of packages	15
Annex A (informative) Design principles of nuts	16
Annex B (informative) Thread dimensions for the test mandrel	19
Bibliography	21

ISO 898-2:2012(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 898-2 was prepared by Technical Committee ISO/TC 2, *Fasteners*, Subcommittee SC 12, *Fasteners with metric internal thread*.

This third edition cancels and replaces the second edition (ISO 898-2:1992) and ISO 898-6:1994, which have been technically revised.

ISO 898 consists of the following parts, under the general title *Mechanical properties of fasteners made of carbon steel and alloy steel*:

- Part 1: Bolts, screws and studs with specified property classes — Coarse thread and fine pitch thread
- Part 2: Nuts with specified property classes — Coarse thread and fine pitch thread
- Part 5: Set screws and similar threaded fasteners with specified hardness classes — Coarse thread and fine pitch thread
- Part 7: Torsional test and minimum torques for bolts and screws with nominal diameters 1 mm to 10 mm¹⁾

1) It is intended that, upon revision, the main element of the title of Part 7 will be aligned with the main element of the title of Part 1.

Mechanical properties of fasteners made of carbon steel and alloy steel —

Part 2: Nuts with specified property classes — Coarse thread and fine pitch thread

1 Scope

This part of ISO 898 specifies mechanical and physical properties of nuts with coarse thread and fine pitch thread made of carbon steel and alloy steel when tested at an ambient temperature range of 10 °C to 35 °C.

Nuts conforming to the requirements of this part of ISO 898 are evaluated at that ambient temperature range. It is possible that they do not retain the specified mechanical and physical properties at elevated and/or lower temperatures.

NOTE 1 Nuts conforming to the requirements of this part of ISO 898 have been used in applications ranging from –50 °C to +150 °C. It is the responsibility of users to consult an experienced fastener materials expert for temperatures outside the range of –50 °C to +150 °C and up to a maximum temperature of +300 °C to determine appropriate choices for a given application.

NOTE 2 Information for the selection and application of steels for use at lower and elevated temperatures is given for instance in EN 10269, ASTM F2281 and in ASTM A320/A320M.

This part of ISO 898 is applicable to nuts:

- a) made of carbon steel or alloy steel;
- b) with coarse thread $M5 \leq D \leq M39$, and fine pitch thread $M8 \times 1 \leq D \leq M39 \times 3$;
- c) with triangular ISO metric thread according to ISO 68-1;
- d) with diameter/pitch combinations according to ISO 261 and ISO 262;
- e) with specified property classes, including proof load;
- f) with different nut styles: thin nuts, regular nuts and high nuts;
- g) with minimum height $m \geq 0,45D$;
- h) with a minimum outside diameter or width across flats $s \geq 1,45D$ (see Annex A);
- i) able to mate with bolts, screws and studs with property classes according to ISO 898-1.

For hot dip galvanized nuts, see ISO 10684.

This part of ISO 898 does not specify requirements for properties such as:

- prevailing torque properties (see ISO 2320);
- torque/clamp force properties (see ISO 16047 for test method);
- weldability;
- corrosion resistance.

ISO 898-2:2012(E)

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 6157-2, *Fasteners — Surface discontinuities — Part 2: Nuts*

ISO 6506-1, *Metallic materials — Brinell hardness test — Part 1: Test method*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 6508-1, *Metallic materials — Rockwell hardness test — Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)*

ISO 6892-1, *Metallic materials — Tensile testing — Part 1: Method of test at room temperature*

ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 16426, *Fasteners — Quality assurance system*

3 Symbols

For the purposes of this document, the following symbols apply.

D nominal thread diameter of the nut, in millimetres

d_h hole diameter of the grip, in millimetres

F load, in newtons

h thickness of the grip, in millimetres

m height of the nut, in millimetres

P pitch of the thread, in millimetres

s width across flats, in millimetres

4 Designation systems

4.1 Designation of nut styles

This part of ISO 898 specifies requirements for three styles of nuts according to their height:

- style 2: high nut with minimum height $m_{\min} \approx 0,9D$ or $m_{\min} > 0,9D$; see Table A.1;
- style 1: regular nut with minimum height $m_{\min} \geq 0,8D$; see Table A.1;
- style 0: thin nut with minimum height $0,45D \leq m_{\min} < 0,8D$.

4.2 Designation of property classes

4.2.1 General

The marking and labelling of nuts with property classes shall be as specified in Clause 10 for only those nuts which meet all applicable requirements of this part of ISO 898.