



Designation: C 365 – 03

## Standard Test Method for Flatwise Compressive Properties of Sandwich Cores<sup>1</sup>

This standard is issued under the fixed designation C 365; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### 1. Scope

1.1 This test method covers the determination of the compressive strength and modulus of sandwich cores. These properties are usually determined for design purposes in a direction normal to the plane of facings as the core would be placed in a structural sandwich construction. The test procedures pertain to compression in this direction in particular, but also can be applied with possible minor variations to determining compressive properties in other directions.

1.2 The values stated in SI units are to be regarded as the standard. The inch-pound units given may be approximate.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

E 4 Practices for Force Verification of Testing Machines

### 3. Significance and Use

3.1 The flatwise compressive strength and modulus are fundamental mechanical properties of sandwich cores that are used in designing sandwich panels. Deformation data can be obtained, and from a complete load-deformation curve it is possible to compute the compressive stress at any load (such as compressive stress at proportional limit load or compressive strength at maximum load) and to compute the effective modulus of the core.

3.2 This test method provides a standard method of obtaining the flatwise compressive strength and modulus for sandwich panel design and research and development.

### 4. Apparatus

4.1 *Testing Machine*, capable of maintaining a controlled loading rate and indicating the load with an accuracy of  $\pm 1\%$  of the indicated value. The accuracy of the test machine shall be verified in accordance with Practices E 4.

4.2 *Spherical Bearing Block*, preferably of the suspended, self-aligning type.

4.3 *Deflectometer or Compressometer*, capable of measuring the displacement with a precision of at least  $\pm 1\%$ . Bonded resistance strain gages are not usually considered satisfactory because of their stiffness. The reinforcing effect of bonding these gages to some cores leads to large errors in measurement of strains. Also, using the test machines cross-head travel reading is not satisfactory as large modulus errors can result. A transducer and rod setup as shown in Fig. 1 and Fig. 2 have been found to work satisfactorily. Here a small hole is drilled in the center of the specimen and in the bottom loading platen, and a transducer rod is inserted that contacts the upper loading platen.

4.4 *Micrometer, Gage, or Caliper*, capable of measuring accurately to 0.025 mm (0.001 in.).

### 5. Test Specimens

5.1 Test specimens shall be of core or of sandwich construction and shall be of square or circular cross section having areas not exceeding 10 000 mm<sup>2</sup> (16 in.<sup>2</sup>), but not less than the following minimum areas for various types of cores:

5.1.1 For continuous cores, such as balsa wood and foams, the minimum cross-sectional area shall be 625 mm<sup>2</sup> (1 in.<sup>2</sup>).

5.1.2 For open-celled cores, such as honeycomb, having cells less than 6 mm ( $\frac{1}{4}$  in.) the minimum cross-sectional area shall be 2500 mm<sup>2</sup> (4 in.<sup>2</sup>) and for cells 6 mm ( $\frac{1}{4}$  in.) or greater the minimum cross-sectional area shall be 5800 mm<sup>2</sup> (9 in.<sup>2</sup>).

5.2 The height of the specimen shall be as agreed upon by the purchaser and the seller.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D30 on Composite Materials and is the direct responsibility of Subcommittee D30.09 on Sandwich Construction.

Current edition approved Dec. 1, 2003. Published December 2003. Originally approved in 1955. Last previous edition approved in 2000 as C 365 – 00.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.