

SLOVENSKI STANDARD

oSIST prEN ISO 5659-2:2011

01-junij-2011

Polimerni materiali - Nastajanje dima - 2. del: Določanje optične gostote s preskusom v eni preskusni komori (ISO/DIS 5659-2:2011)

Plastics - Smoke generation - Part 2: Determination of optical density by a single-chamber test (ISO/DIS 5659-2:2011)

Kunststoffe - Rauchentwicklung - Teil 2: Bestimmung der optischen Dichte durch Einkammerprüfung (ISO/DIS 5659-2:2011)

Plastiques - Production de fumée - Partie 2: Détermination de la densité optique par un essai en enceinte unique (ISO/DIS 5659-2:2011)

Ta slovenski standard je istoveten z: prEN ISO 5659-2

<https://standards.iteh.ai/catalog/standards/sist/2b99b0ec-2ce7-428a-853b-060f7c536e4d/sist-en-iso-5659-2-2014>

ICS:

13.220.40	Sposobnost vžiga in obnašanje materialov in proizvodov pri gorenju	Ignitability and burning behaviour of materials and products
83.080.01	Polimerni materiali na splošno	Plastics in general

oSIST prEN ISO 5659-2:2011

en,fr

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN ISO 5659-2

March 2011

ICS 83.080.01; 13.220.40

Will supersede EN ISO 5659-2:2006

English Version

Plastics - Smoke generation - Part 2: Determination of optical density by a single-chamber test (ISO/DIS 5659-2:2011)

Plastiques - Production de fumée - Partie 2: Détermination de la densité optique par un essai en enceinte unique (ISO/DIS 5659-2:2011)

Kunststoffe - Rauchentwicklung - Teil 2: Bestimmung der optischen Dichte durch Einkammerprüfung (ISO/DIS 5659-2:2011)

This draft European Standard is submitted to CEN members for parallel enquiry. It has been drawn up by the Technical Committee CEN/TC 249.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
---------------	---

iTeh Standards (<https://standards.iteh.ai>) Document Preview

SIST EN ISO 5659-2:2014

<https://standards.iteh.ai/catalog/standards/sist/2b99b0ec-2ce7-428a-853b-060f7c536e4d/sist-en-iso-5659-2-2014>

Foreword

This document (prEN ISO 5659-2:2011) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics" the secretariat of which is held by NBN.

This document is currently submitted to the parallel Enquiry.

This document will supersede EN ISO 5659-2:2006.

Endorsement notice

The text of ISO/DIS 5659-2:2011 has been approved by CEN as a prEN ISO 5659-2:2011 without any modification.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN ISO 5659-2:2014](https://standards.iteh.ai/catalog/standards/sist/2b99b0ec-2ce7-428a-853b-060f7c536e4d/sist-en-iso-5659-2-2014)

<https://standards.iteh.ai/catalog/standards/sist/2b99b0ec-2ce7-428a-853b-060f7c536e4d/sist-en-iso-5659-2-2014>



DRAFT INTERNATIONAL STANDARD ISO/DIS 5659-2

ISO/TC 61/SC 4

Secretariat: BSI

Voting begins on
2011-03-03Voting terminates on
2011-08-03

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Plastics — Smoke generation —

Part 2:

Determination of optical density by a single-chamber test

*Plastiques — Production de fumée —**Partie 2: Détermination de la densité optique par un essai en enceinte unique*

[Revision of second edition (ISO 5659-2:2006)]

ICS 13.220.40; 83.080.01

iTeh Standards
(<https://standards.iteh.ai>)

ISO/CEN PARALLEL PROCESSING

This draft has been developed within the International Organization for Standardization (ISO), and processed under the **ISO-lead** mode of collaboration as defined in the Vienna Agreement.

This draft is hereby submitted to the ISO member bodies and to the CEN member bodies for a parallel five-month enquiry.

Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month approval vote in ISO and formal vote in CEN.

In accordance with the provisions of Council Resolution 15/1993 this document is circulated in the English language only.

Conformément aux dispositions de la Résolution du Conseil 15/1993, ce document est distribué en version anglaise seulement.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

RECIPIENTS OF THIS DRAFT ARE INVITED TO SUBMIT, WITH THEIR COMMENTS, NOTIFICATION OF ANY RELEVANT PATENT RIGHTS OF WHICH THEY ARE AWARE AND TO PROVIDE SUPPORTING DOCUMENTATION.

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh Standards (<https://standards.iteh.ai>) Document Preview

SIST EN ISO 5659-2:2014

<https://standards.iteh.ai/catalog/standards/sist/2b99b0ec-2ce7-428a-853b-060f7c536e4d/sist-en-iso-5659-2-2014>

Copyright notice

This ISO document is a Draft International Standard and is copyright-protected by ISO. Except as permitted under the applicable laws of the user's country, neither this ISO draft nor any extract from it may be reproduced, stored in a retrieval system or transmitted in any form or by any means, electronic, photocopying, recording or otherwise, without prior written permission being secured.

Requests for permission to reproduce should be addressed to either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Reproduction may be subject to royalty payments or a licensing agreement.

Violators may be prosecuted.

Contents

Page

Foreword.....	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principles of the test	2
5 Suitability of a material for testing.....	3
6 Specimen construction and preparation.....	3
7 Apparatus and ancillary equipment.....	5
8 Test environment.....	17
9 Setting-up and calibration procedures.....	17
10 Test procedure.....	20
11 Expression of results	23
12 Precision.....	24
13 Test report	24
Annex A (normative) Calibration of heat flux meter.....	25
Annex B (informative) Variability in the specific optical density of smoke measured in the single-chamber test	26
Annex C (informative) Determination of mass optical density.....	28
Annex D (informative) Precision data from tests on intumescent materials	33
Annex E (informative) Guidance on optical density testing	36
Bibliography.....	43

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 5659-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 4, *Burning behaviour*.

This third edition cancels and replaces the second edition (ISO 5659-2:2006), which has been technically revised. It also replaces ISO 5659-1:1996, which has been withdrawn.

ISO 5659 consists of the following parts, under the general title *Plastics — Smoke generation*:

[— *Part 1: Guidance*]

— *Part 2: Determination of optical density by a single chamber test*

— *Part 3: Determination of dynamic optical density by a dynamic flow test*

Introduction

Fire is a complex phenomenon: its development and effects depend upon a number of interrelated factors. The behaviour of materials and products depends upon the characteristics of the fire, the method of use of the materials and the environment in which they are exposed (see also ISO/TR 3814 and ISO 13943).

A test such as is specified in this part of ISO 5659 deals only with a simple representation of a particular aspect of the potential fire situation, typified by a radiant heat source, and it cannot alone provide any direct guidance on behaviour or safety in fire. A test of this type may, however, be used for comparative purposes or to ensure the existence of a certain quality of performance (in this case, smoke production) considered to have a bearing on fire behaviour generally. It would be wrong to attach any other meaning to results from this test.

The term “smoke” is defined in ISO 13943 as a visible suspension of solid and/or liquid particles in gases resulting from incomplete combustion. It is one of the first response characteristics to be manifested and should almost always be taken into account in any assessment of fire hazard as it represents one of the greatest threats to occupants of a building or other enclosure, such as a ship or train, on fire.

The responsibility for the preparation of ISO 5659 was transferred during 1987 from ISO/TC 92 to ISO/TC 61 on the understanding that the scope and applicability of the standard for the testing of materials should not be restricted to plastics but should also be relevant to other materials where possible, including building materials.

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

SIST EN ISO 5659-2:2014

<https://standards.iteh.ai/catalog/standards/sist/2b99b0ec-2ce7-428a-853b-060f7c536e4d/sist-en-iso-5659-2-2014>

Plastics — Smoke generation —

Part 2:

Determination of optical density by a single-chamber test

1 Scope

1.1 This part of ISO 5659 specifies a method of measuring smoke production from the exposed surface of specimens of essentially flat materials, composites or assemblies not exceeding 25 mm in thickness when placed in a horizontal orientation and subjected to specified levels of thermal irradiance in a closed cabinet with or without the application of a pilot flame. This method of test is applicable to all plastics and may also be used for the evaluation of other materials (e.g. rubbers, textile-coverings, painted surfaces, wood and other materials).

1.2 It is intended that the values of optical density determined by this test be taken as specific to the specimen or assembly material in the form and thickness tested, and are not to be considered inherent, fundamental properties.

1.3 The test is intended primarily for use in research and development and fire safety engineering in buildings, trains, ships, etc. and not as a basis for ratings for building codes or other purposes. No basis is provided for predicting the density of smoke that may be generated by the materials upon exposure to heat and flame under other (actual) exposure conditions. This test procedure excludes the effect of irritants on the eye.

NOTE This test procedure addresses the loss of visibility due to smoke density, which generally is not related to irritancy potency (see Annex E).

1.4 It is emphasized that smoke production from a material varies according to the irradiance level to which the specimen is exposed. In making use of the results of this method, it should be borne in mind that the results are based on exposure to the specific irradiance levels of 25 kW/m² and 50 kW/m².

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 5659. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 5659 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 13943, *Fire safety — Vocabulary*

3 Terms and definitions

For the purposes of this part of ISO 5659, the terms and definitions given in ISO 13943 and the following apply.

3.1

assembly

fabrication of materials and/or composites

NOTE 1 Sandwich panels are an example of an assembly.

NOTE 2 The assembly may include an air gap.

3.2

composite

ISO/DIS 5659-2

combination of materials which are generally recognized in building construction as discrete entities

NOTE Coated or laminated materials are examples of composites.

3.3

essentially flat surface

surface which does not deviate from a plane by more than 1 mm

3.4

exposed surface

surface of the product subjected to the heating conditions of the test

3.5

irradiance

radiant flux incident on an infinitesimal element of the surface containing the point divided by the area of that element

3.6

material

basic single substance or uniformly dispersed mixture

NOTE Metal, stone, timber, concrete, mineral fibre, polymers are examples.

3.7

mass optical density

MOD

measure of the degree of opacity of smoke in terms of the mass loss of the material

3.8

optical density of smoke

D

measure of the degree of opacity of smoke, taken as the negative common logarithm of the relative transmission of light

3.9

product

material, composite or assembly about which information is required

<https://standards.iteh.ai/catalog/standards/sist/2b99b0ec-2ce7-428a-853b-060f7c536e4d/sist-en-iso-5659-2-2014>

3.10

specific optical density

D_s

optical density multiplied by a factor which is calculated by dividing the volume of the test chamber by the product of the exposed area of the specimen and the path length of the light beam

NOTE See 11.1.1.

3.11

specimen

representative piece of the product to be tested together with any substrate or surface coating.

NOTE The specimen may include an air gap.

3.12

intumescent material

dimensionally unstable material, developing a carbonaceous expanded structure of thickness > 10 mm during the test, with the cone heater 25 mm from the specimen

4 Principles of the test

Specimens of the product are mounted horizontally within a chamber and exposed to thermal radiation on their upper surfaces at selected levels of constant irradiance up to 50 kW/m².

The smoke evolved is collected in the chamber, which also contains photometric equipment. The attenuation of a light beam passing through the smoke is measured. The results are reported in terms of specific optical density.