
**Welding consumables — Tubular cored
electrodes for gas-shielded and non-gas-
shielded metal arc welding of high-
strength steels — Classification**

*Produits consommables pour le soudage — Fils-électrodes fourrés pour
le soudage à l'arc avec ou sans gaz de protection des aciers à haute
résistance — Classification*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 18276:2005](https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005)

<https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18276:2005

<https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope.....	1
2 Normative references	1
3 Classification.....	2
4 Symbols and requirements	4
4.1 Symbol for the product/process.....	4
4.2 Symbol for tensile properties of all-weld metal	4
4.3 Symbol for impact properties of all-weld metal	4
4.4 Symbol for chemical composition of all-weld metal	5
4.5 Symbol for type of electrode core or the usability characteristics of the electrodes.....	8
4.6 Symbol for shielding gas	9
4.7 Symbol for welding position	9
4.8 Symbol for hydrogen content of deposited metal	10
4.9 Symbol for conditions of post-weld heat treatment.....	10
4.10 Rounding-off procedure.....	10
5 Mechanical tests	10
5.1 Preheating and interpass temperatures.....	11
5.2 Pass sequence	12
5.3 Post-weld heat treatment (PWHT) condition.....	12
6 Chemical analysis.....	13
7 Fillet weld test	13
8 Retest	14
9 Technical delivery conditions.....	14
10 Examples of designations.....	14
Annex A (informative) Classification systems.....	16
Annex B (informative) Description of composition designations for electrodes in the classification system based upon tensile strength and average impact energy of 27 J	19
Annex C (informative) Description of types of electrode core in the classification system based upon yield strength and average impact energy of 47 J.....	20
Annex D (informative) Descriptions of types of usability characteristics in the classification system based upon tensile strength and average impact energy of 27 J	21
Annex E (informative) Notes on hydrogen content.....	23

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18276 was prepared by Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 3, *Welding consumables*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 18276:2005](https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005)

<https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005>

Introduction

This International Standard proposes a classification system for tubular cored electrodes in terms of the tensile properties, impact properties, chemical composition of the all-weld metal, type of electrode core, shielding gas and welding position. The ratio of yield strength to tensile strength of the weld metal is generally higher than that of the parent metal. Users should note that matching weld metal yield strength to parent metal yield strength will not necessarily ensure that the weld metal tensile strength matches that of the parent metal. Where the application requires matching tensile strength, therefore, selection of the consumable should be made by reference to column 3 of Table 1A or Table 1B.

It should be noted that the mechanical properties of all-weld metal test specimens used to classify tubular cored electrodes will differ from those obtained with production joints because of differences in welding procedure such as electrode size, width of weave, welding position and parent metal composition.

The classification in accordance with system A is mainly based on EN 12535:2000, *Welding consumables — Tubular cored electrodes for gas shielded metal arc welding of high strength steels — Classification*. The classification in accordance with system B is mainly based upon standards used around the Pacific Rim.

Requests for official interpretation of any aspect of this International Standard should be directed to the Secretariat of ISO/TC 44/SC 3 via the user's national standardization body. A complete listing of these bodies can be found at <<http://www.iso.org>>.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 18276:2005](https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005)

<https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 18276:2005

<https://standards.iteh.ai/catalog/standards/sist/06e43d10-84a2-4f8b-ab61-3427dcd1b94c/iso-18276-2005>

Welding consumables — Tubular cored electrodes for gas-shielded and non-gas-shielded metal arc welding of high-strength steels — Classification

1 Scope

This International Standard specifies requirements for classification of tubular cored electrodes with or without a gas shield for metal arc welding of high-strength steels in the as-welded condition or in the post-weld heat-treated condition with a minimum yield strength higher than 550 MPa or a minimum tensile strength higher than 590 MPa. One tubular cored electrode can be tested and classified with different shielding gases, if used with more than one.

This document is a combined specification providing classification utilizing a system based upon the yield strength and an average impact energy of 47 J of the all-weld metal, or utilizing a system based upon the tensile strength and an average impact energy of 27 J of the all-weld metal.

- 1) Subclauses and tables which carry the suffix letter “A” are applicable only to tubular cored electrodes classified under the system based upon the yield strength and an average impact energy of 47 J of the all-weld metal given in this International Standard.
- 2) Subclauses and tables which carry the suffix letter “B” are applicable only to tubular cored electrodes classified under the system based upon the tensile strength and an average impact energy of 27 J of the all-weld metal given in this International Standard.
- 3) Subclauses and tables which do not have either the suffix letter “A” or the suffix letter “B” are applicable to all tubular cored electrodes classified under this International Standard.

It is recognized that the operating characteristics of tubular cored electrodes can be modified by the use of pulsed current but, for the purposes of this International Standard, pulsed current is not used for determining the electrode classification.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 31-0:1992, *Quantities and units — Part 0: General principles*

ISO 544, *Welding consumables — Technical delivery conditions for welding filler materials — Type of product, dimensions, tolerances and markings*

ISO 3690, *Welding and allied processes — Determination of hydrogen content in ferritic steel arc weld metal*

ISO 6847, *Welding consumables — Deposition of a weld metal pad for chemical analysis*

ISO 6947:1990, *Welds — Working positions — Definitions of angles of slope and rotation*

ISO 13916, *Welding — Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature*

ISO 14175:1997, *Welding consumables — Shielding gases for arc welding and cutting*

ISO 14344, *Welding and allied processes — Flux and gas shielded electrical welding processes — Procurement guidelines for consumables*

ISO 15792-1:2000, *Welding consumables — Test methods — Part 1: Test methods for all-weld metal test specimens in steel, nickel and nickel alloys*

ISO 15792-3, *Welding consumables — Test methods — Part 3: Classification testing of positional capacity and root penetration of welding consumables in a fillet weld*

3 Classification

Classification designations are based upon two approaches to indicate the tensile properties and the impact properties of the all-weld metal obtained with a given electrode. The two designation approaches include additional designators for some other classification requirements, but not all, as will be clear from the following subclauses. In most cases, a given commercial product can be classified under both systems. Then either or both classification designations can be used for the product.

The classification includes all-weld metal properties obtained with a tubular cored electrode and appropriate shielding gas combination as given below. With the exception of the symbol for welding position, which is based on ISO 15792-3, the classification of gas-shielded tubular cored electrodes is based on an electrode size of 1,2 mm or, if this size is not manufactured, the next larger diameter manufactured, and the classification of self-shielded tubular cored electrodes is based on a diameter of 2,4 mm or the largest diameter manufactured if less than 2,4 mm.

ISO 18276:2005

3.1A Classification by yield strength and 47 J impact energy

The classification designation is divided into nine parts:

- 1) the first part (T) indicates a tubular cored electrode;
- 2) the second part gives a symbol indicating the strength and elongation of the all-weld metal in the as-welded or post-weld heat-treated condition (see Table 1A);
- 3) the third part gives a symbol indicating the impact properties of the all-weld metal (see Table 2);
- 4) the fourth part gives a symbol indicating the chemical composition of the all-weld metal (see Table 3A);

3.1B Classification by tensile strength and 27 J impact energy

The classification designation is divided into nine parts:

- 1) the first part (T) indicates a tubular cored electrode;
- 2) the second part gives a symbol indicating the strength and elongation of the all-weld metal in either the as-welded or the post-weld heat-treated condition (see Table 1B);
- 3) the third part gives a symbol indicating the impact properties of the all-weld metal (see Table 2). The symbol "U", added as an optional supplemental designator at or near the end of the complete tubular cored electrode designation, indicates that the deposit meets an average optional requirement of 47 J at the designated Charpy test temperature;
- 4) the fourth part gives a symbol indicating the usability characteristics of the electrode (see Table 4B);

- | | |
|--|--|
| <p>5) the fifth part gives a symbol indicating the type of electrode core (see Table 4A);</p> <p>6) the sixth part gives a symbol indicating the shielding gas (see 4.6 and 4.6A);</p> <p>7) the seventh part gives a symbol indicating the welding position (see Table 5A);</p> <p>8) the eighth part gives a symbol indicating the hydrogen content of the deposited metal (see Table 6);</p> <p>9) the ninth part gives a symbol indicating the post-weld heat treatment if this is applied (see 4.9A).</p> | <p>5) the fifth part gives a symbol indicating the welding position (see Table 5B);</p> <p>6) the sixth part gives a symbol indicating the shielding gas (see 4.6 and 4.6B);</p> <p>7) the seventh part gives a symbol indicating whether the classification tests were conducted in the as-welded condition (A) or the post-weld heat-treated condition (P);</p> <p>8) the eighth part gives a symbol indicating the chemical composition of the all-weld metal (see Table 3B);</p> <p>9) the ninth part gives a symbol indicating the hydrogen content of the deposited metal (see Table 6).</p> |
|--|--|

Electrodes may be classified under any number of classifications for either or both the as-welded and post-weld heat-treated condition.

In both systems, the electrode classification shall include all the compulsory section and may include the optional section, as outlined below.

3.2A Compulsory and optional sections in the classification by yield strength and 47 J impact energy

a) Compulsory section

This section includes the symbols for the type of product, the strength and elongation, the impact properties, the chemical composition, the type of electrode core, the shielding gas and the post-weld heat treatment, i.e. the symbols defined in 4.1, 4.2, 4.3A, 4.4, 4.5A, 4.6 and 4.9A.

b) Optional section

This section includes the symbols for the welding positions for which the electrode is suitable and the symbol for hydrogen content, i.e. the symbols defined in 4.7 and 4.8.

3.2B Compulsory and optional sections in the classification by tensile strength and 27 J impact energy

a) Compulsory section

This section includes the symbols for the type of product, the strength and elongation in the as-welded condition or post-weld heat-treated condition, the welding positions for which the electrode is suitable, the usability characteristics, the shielding gas, the impact properties and the chemical composition, i.e. the symbols defined in 4.1, 4.2, 4.3B, 4.4, 4.5B, 4.6, 4.7 and 4.9B.

b) Optional section

This section includes the symbol "U" to indicate that the weld metal will have an average of 47 J impact energy at the classification test temperature and the symbol for hydrogen content, i.e. the symbol "U" defined in 4.3B and the symbols defined in 4.8.

The full designation (see Clause 10) shall be used on packages and in the manufacturer's literature and data sheets.

4 Symbols and requirements

4.1 Symbol for the product/process

The symbol for the tubular cored electrodes used in the metal arc welding process is the letter T.

4.2 Symbol for tensile properties of all-weld metal

The symbol in Table 1A or 1B indicates the yield strength, tensile strength and elongation of the all-weld metal, determined in accordance with Clause 5.

Table 1A — Symbol for tensile properties of all-weld metal (classification by yield strength and 47 J impact energy)

Symbol	Minimum yield strength ^a	Tensile strength	Minimum elongation ^b
	MPa	MPa	%
55	550	640 to 820	18
62	620	700 to 890	18
69	690	770 to 940	17
79	790	880 to 1 080	16
89	890	940 to 1 180	15

^a For yield strength, the lower yield (R_{el}) is used when yielding occurs, otherwise the 0,2% proof strength ($R_{p0,2}$) is used.

^b Gauge length is equal to five times the test specimen diameter.

Table 1B — Symbol for tensile properties of all-weld metal (classification by tensile strength and 27 J impact energy)

Symbol	Minimum yield strength ^a	Tensile strength	Minimum elongation ^b
	MPa	MPa	%
59	490	590 to 790	16
62	530	620 to 820	15
69	600	690 to 890	14
76	680	760 to 960	13
78	680	780 to 980	13
83	745	830 to 1 030	12

^a For yield strength, the lower yield (R_{el}) is used when yielding occurs, otherwise the 0,2% proof strength ($R_{p0,2}$) is used.

^b Gauge length is equal to five times the test specimen diameter.

4.3 Symbol for impact properties of all-weld metal

4.3A Classification by yield strength and 47 J impact energy

The symbols in Table 2 indicate the temperature at which an impact energy of 47 J is achieved under the conditions given in Clause 5. Three test specimens shall be tested. Only one individual value may be lower than 47 J but not lower than 32 J.

4.3B Classification by tensile strength and 27 J impact energy

The symbols in Table 2 indicate the temperature at which an impact energy of 27 J is achieved in the as-welded condition or in the post-weld heat-treated condition under the conditions given in Clause 5. Five test specimens shall be tested. The lowest and highest values obtained shall be disregarded. Two of the three remaining values shall be greater than the specified 27 J level, one of the three may be lower but shall not be less than 20 J. The average of the three remaining values shall be at least 27 J. Three test specimens shall be tested when the optional symbol “U” is used to indicate that the weld deposit will meet a minimum impact energy of 47 J at the test temperature. The impact value shall be determined by the average of the three test specimens. The average of the three values shall be 47 J or greater.

When an all-weld metal has been classified for a certain temperature, it automatically covers any higher temperature in Table 2.

Table 2 — Symbol for impact properties of all-weld metal

Symbol	Temperature for minimum average impact energy of 47 J ^a or 27 J ^b °C
Z	No requirements
A ^a or Y ^b	+ 20
0	0
2	– 20
3	– 30
4	– 40
5	– 50
6	– 60
7	– 70
8	– 80

^a Classification by yield strength and 47 J impact energy (see 4.3A).
^b Classification by tensile strength and 27 J impact energy (see 4.3B).

(standards.iteh.ai)

4.4 Symbol for chemical composition of all-weld metal

The symbols in Table 3A or Table 3B indicate the chemical composition of the all-weld metal, determined in accordance with Clause 6.

Table 3A — Symbol for chemical composition of all-weld metal (classification by yield strength and 47 J impact energy)

Symbol	Chemical composition, % (by mass) ^{a, b}									
	C	Mn	Si	P	S	Ni	Cr	Mo	V	
Z	Any other agreed composition									
MnMo	0,03 to 0,10	1,4 to 2,0	0,90	0,020	0,020	0,3	0,2	0,3 to 0,6	0,05	
Mn1Ni	0,03 to 0,10	1,4 to 2,0	0,90	0,020	0,020	0,6 to 1,2	0,2	0,2	0,05	
Mn1,5Ni	0,03 to 0,10	1,1 to 1,8	0,90	0,020	0,020	1,3 to 1,8	0,2	0,2	0,05	
Mn2,5Ni	0,03 to 0,10	1,1 to 2,0	0,90	0,020	0,020	2,1 to 3,0	0,2	0,2	0,05	
1NiMo	0,03 to 0,10	1,4	0,90	0,020	0,020	0,6 to 1,2	0,2	0,3 to 0,6	0,05	
1,5NiMo	0,03 to 0,10	1,4	0,90	0,020	0,020	1,2 to 1,8	0,2	0,3 to 0,7	0,05	
2NiMo	0,03 to 0,10	1,4	0,90	0,020	0,020	1,8 to 2,6	0,2	0,3 to 0,7	0,05	
Mn1NiMo	0,03 to 0,10	1,4 to 2,0	0,90	0,020	0,020	0,6 to 1,2	0,2	0,3 to 0,7	0,05	
Mn2NiMo	0,03 to 0,10	1,4 to 2,0	0,90	0,020	0,020	1,8 to 2,6	0,2	0,3 to 0,7	0,05	
Mn2NiCrMo	0,03 to 0,10	1,4 to 2,0	0,90	0,020	0,020	1,8 to 2,6	0,3 to 0,6	0,3 to 0,6	0,05	
Mn2Ni1CrMo	0,03 to 0,10	1,4 to 2,0	0,90	0,020	0,020	1,8 to 2,6	0,6 to 1,0	0,3 to 0,6	0,05	

^a Single values shown in the table are maximum values.

^b Cu ≤ 0,3, Nb ≤ 0,05