

---

---

**Resistance welding — Weldability —**

Part 1:

**Assessment of weldability for resistance  
spot, seam and projection welding of  
metallic materials**

**iTeh STANDARD PREVIEW**  
*Soudage par résistance — Soudabilité —*

*(standard in preparation)*  
*Partie 1: Évaluation de la soudabilité pour le soudage par résistance  
par points, à la molette et par bossages des matériaux métalliques*

ISO 18278-1:2004

<https://standards.iteh.ai/catalog/standards/sist/0392bf90-fb8d-41fb-99d3-48de6b0bcf0a/iso-18278-1-2004>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 18278-1:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/0392bf90-fb8d-41fb-99d3-48de6b0bcf0a/iso-18278-1-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 18278-1 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

Throughout the text of this document, read “...this European Standard...” to mean “...this International Standard...”.

[ISO 18278-1:2004](http://www.iso.org/iso/18278-1-2004)

ISO 18278 consists of the following parts, under the general title *Resistance welding — Weldability*:

- *Part 1: Assessment of weldability for resistance spot, seam and projection welding of metallic materials*
- *Part 2: Alternative procedures for the assessment of sheet steels for spot welding*

## Contents

	page
Foreword.....	v
1 Scope .....	1
2 Normative references .....	1
3 Terms and definitions .....	2
4 Test procedures .....	2
4.1 General.....	2
4.2 Basic test procedures .....	3
4.2.1 Determination of the ability to make a weld.....	3
4.2.2 Determination of the ability to continue making welds .....	3
4.2.3 Determination of the weld properties .....	4
4.3 Additional tests .....	5
4.3.1 General.....	5
4.3.2 Hold time sensitivity procedure .....	5
5 Further weld properties.....	5
6 Test report .....	6
Bibliography .....	7

iTeh STANDARD PREVIEW

(standards.iteh.ai)

ISO 18278-1:2004

<https://standards.iteh.ai/catalog/standards/sist/0392b190-fb8d-411b-99d3-48dc6b0bcfd2/iso-18278-1-2004>

## Foreword

This document (EN ISO 18278-1:2004) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2005, and conflicting national standards shall be withdrawn at the latest by May 2005.

This standard consists of the following parts:

- Part 1: Assessment of weldability for resistance spot, seam and projection welding of metallic materials;
- Part 2: Alternative procedures for the assessment of sheet steels for spot welding.

This document includes a Bibliography.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

ISO 18278-1:2004  
<https://standards.iteh.ai/catalog/standards/sist/0392bf90-fb8d-41fb-99d3-48de6b0bcf0a/iso-18278-1-2004>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 18278-1:2004

<https://standards.iteh.ai/catalog/standards/sist/0392bf90-fb8d-41fb-99d3-48de6b0bcf0a/iso-18278-1-2004>

## 1 Scope

This document recommends procedures for determining the generic weldability for resistance spot, seam and projection welding of metallic materials.

This procedure is applicable for the assessment of the weldability of uncoated/coated steels, stainless steels and non-ferrous alloys such as aluminium, titanium, magnesium and nickel and their alloys of single thickness lower than or equal to 5 mm.

The weldability of metallic materials in resistance welding is defined in terms of:

- the ability to make the weld in the first place;
- the ability to continue making welds;
- the ability of the weld to withstand the imposed service stresses.

The procedures recommended in this standard can be used to:

- compare the weldability of different metallic materials;
- compare the welding response of particular welding equipment and allow comparisons between different equipment and determine the influence of the static/dynamic properties of different welding equipment;
- determine the weldability of a material when any welding configuration is changed e.g. electrode material and/or shape, water cooling requirements etc.;
- investigate the effect of welding parameters such as welding current, weld time, electrode force or complex welding schedules including pulse welding, current stepping etc. on weldability.

<https://standards.iteh.ai/catalog/standards/sist/0392bf90-fb8d-41fb-99d3-48de6b0bcf0a/iso-18278-1-2004>

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN ISO 8166, *Resistance welding — Procedure for the evaluation of the life of spot welding electrodes using constant machines settings (ISO 8166:2003)*.

EN ISO 14270, *Specimen dimensions and procedure for mechanized peel testing resistance spot, seam and embossed projection welds (ISO 14270:2000)*.

EN ISO 14271, *Vickers hardness testing of resistance spot, projection and seam welds (low load and microhardness) (ISO 14271:2000)*.

EN ISO 14272, *Specimen dimensions and procedure for cross tension testing resistance spot and embossed projection welds (ISO 14272:2000)*.

EN ISO 14273, *Specimen dimensions and procedure for shear testing resistance spot, seam and embossed projection welds (ISO 14273:2000)*.

EN ISO 14327, *Resistance welding — Procedures for determining the weldability lobe for resistance spot, projection and seam welding (ISO 14327:2004)*.

## ISO 18278-1:2004(E)

EN ISO 14329:2003, *Resistance welding — Destructive tests of welds — Failure types and geometric measurements for resistance spot, seam and projection welds (ISO 14329:2003)*.

EN ISO 15609-5, *Specification and qualification of welding procedures for metallic materials — Welding procedure specification — Part 5: Resistance welding (ISO 15609-5:2004)*.

EN ISO 15614-12, *Specification and qualification of welding procedures for metallic materials — Welding procedure test — Part 12: Spot, seam and projection welding (ISO 15614-12:2004)*.

EN ISO 18278-2:2004, *Resistance welding — Weldability — Part 2: Alternative procedures for the assessment of sheet steels for spot welding (ISO 18278-2:2004)*.

ISO 669:2000, *Resistance welding — Resistance welding equipment — Mechanical and electrical requirements*.

ISO/DIS 14373, *Resistance welding — Procedure for spot welding of uncoated and coated low carbon steels*.

ISO/DIS 16432, *Resistance welding — Procedure for projection welding of uncoated and coated low carbon steels using embossed projection(s)*.

ISO/DIS 16433, *Resistance welding — Procedure for seam welding of uncoated and coated low carbon steels*.

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 669:2000, EN ISO 14329:2003 and EN ISO 18278-2:2004 and the following apply.

#### 3.1

##### **ability to make a weld**

characteristic of a component defined by the available welding current range

#### 3.2

##### **ability to continue making welds**

estimation of the electrode life as defined by the number of welds which can be made before the need for re-dressing or changing of the welding electrodes

#### 3.3

##### **service stresses**

as used in this context, applies not only to static and dynamic loading, but also includes stresses imposed by environmental conditions such as corrosion, humidity, low, elevated or fluctuating temperatures etc.

### 4 Test procedures

#### 4.1 General

Test procedures can be sub-divided into two groups as follows:

- those which are considered basic to an understanding of weldability. Such tests shall be carried out to assess the weldability of the material;
- those tests which provide additional information to any basic evaluation of a material. Such tests may be carried out depending on the end application.

Acceptance criteria for each test will depend on the requirements of the product being welded and shall be specified before commencing the test programme. The type of failure shall be determined according to EN ISO 14329.



The procedure for spot welding on uncoated and coated low carbon and high strength steels shall be used in accordance with ISO/DIS 14373, for seam welding in accordance with ISO/DIS 16433 and for projection welding with ISO/DIS 16432. Other welding procedures shall be also be specified, if necessary.

## 4.2 Basic test procedures

### 4.2.1 Determination of the ability to make a weld

For the determination of the ability to make a weld a weldability lobe shall be determined according to procedures as specified in EN ISO 14327.

The purpose of this procedure is to provide information on suitable weld settings and the welding current range which can be used to give acceptable welds as defined within precise limits.

The weldability lobe is influenced by:

- the electrical and mechanical characteristics of the welding equipment;
- welding parameters;
- the electrical, mechanical and physical properties of the material being welded;
- the welding configuration used;
- the electrode material and design of the welding electrode;
- the test specimen or component being welded.

### 4.2.2 Determination of the ability to continue making welds

For the determination of the ability to continue making welds the electrode life test determined at constant machine settings according to EN ISO 8166 shall be used.

The purpose of this test is to provide an indication of the number of acceptable welds which can be made from a pair of welding electrodes before the need to re-dress or change the electrodes.

If current stepping programs or pulse welding procedures are used, the test procedure shall be modified to take into account any necessary changes arising from the use of such welding schedules.

Factors which determine the value of electrode life include:

- electrode material and design;
- type of welding equipment;
- the electrical and mechanical characteristics of the welding equipment;
- welding conditions;
- welding rate;
- water cooling arrangements;
- transformer/electrode configuration;
- material being welded;
- shape of the test specimen or component being welded;