



Designation: C637 – 98a (Reapproved 2003)

Standard Specification for Aggregates for Radiation-Shielding Concrete¹

This standard is issued under the fixed designation C637; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers special aggregates for use in radiation-shielding concretes in which composition or high specific gravity, or both, are of prime consideration.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following precautionary caveat pertains only to the test method portion, Section 8, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

C33 Specification for Concrete Aggregates

C127 Test Method for Density, Relative Density (Specific Gravity), and Absorption of Coarse Aggregate

C128 Test Method for Density, Relative Density (Specific Gravity), and Absorption of Fine Aggregate

C131 Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine

C136 Test Method for Sieve Analysis of Fine and Coarse Aggregates

C535 Test Method for Resistance to Degradation of Large-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine

C638 Descriptive Nomenclature of Constituents of Aggregates for Radiation-Shielding Concrete

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.41 on Pre-placed Aggregate Concrete for Radiation Shielding.

Current edition approved Dec. 1, 2003. Published December 1998. Originally approved in 1969. Last previous edition approved in 1998 as C637 – 98a. DOI: 10.1520/C0637-98AR03.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3. Classification

3.1 Aggregates covered by this specification include:

3.1.1 Natural mineral aggregates of either high density or high fixed water content, or both. These include aggregates that contain or consist predominately of materials such as barite, magnetite, hematite, ilmenite, and serpentine.

3.1.2 Synthetic aggregates such as iron, steel, ferrophosphorus and boron frit or other boron compounds (see Descriptive Nomenclature C638).

3.1.3 Fine aggregate consisting of natural or manufactured sand including high-density minerals. Coarse aggregate may consist of crushed ore, crushed stone, or synthetic products, or combinations or mixtures thereof.

4. Composition and Specific Gravity

4.1 Table 1 gives data on chemical composition and specific gravity of aggregate materials covered by this specification.

4.2 The purchaser shall specify the minimum specific gravity for each size and type of aggregate.

4.2.1 *Uniformity of Specific Gravity*—The bulk specific gravity (saturated surface-dry) of successive shipments of aggregate shall not differ by more than 3 % from that of the sample submitted for source approval tests. The average specific gravity of the total shipment shall be equal to or greater than the specified minimum.

4.3 The purchaser shall specify the minimum fixed water content of hydrous ores. If the design temperature, T , is different from that given in 8.1.3.5, the purchaser shall specify the value of T .

4.3.1 *Uniformity of Fixed Water Content*—For hydrous aggregates the fixed water content of successive shipments of aggregate shall not be less than 95 % of the specified minimum value. The average fixed water content of the total shipment shall be equal to or exceed the specified minimum value.

5. Aggregate Grading

5.1 *Sieve Analysis*—Fine and coarse aggregates for conventionally placed concrete shall be graded within the limits given in Specification C33, except that with the approval of the

TABLE 1 Composition and Specific Gravity of Aggregates Covered by This Specification

Predominant Constituent	Class of Material	Chemical Composition of Principal Constituent ^A	Specific Gravity of Available Aggregates
Serpentine ^B	crushed stone, hydrous silicate	Mg ₃ Si ₂ O ₅ (OH) ₄	2.4 to 2.65
Limonite ^C	crushed stone, hydrous iron ore	(HFeO ₂) _x (H ₂ O) _y	3.4 to 3.8
Goethite ^C	crushed stone, hydrous iron ore	HFeO ₂	3.5 to 4.5
Barite	gravel or crushed stone	BaSO ₄	4.0 to 4.4
Ilmenite	crushed stone, iron ore	FeTiO ₃	4.2 to 4.8
Hematite	crushed stone, iron ore	Fe ₂ O ₃	4.6 to 5.2
Magnetite	crushed stone, iron ore	FeFe ₂ O ₄	4.6 to 5.2
Iron	manufactured from iron/steel	Fe	6.5 to 7.5
Ferrophosphorous ^D	synthetic	Fe _n P	5.8 to 6.3
Boron Frit ^E	synthetic	B ₂ O ₃ , Al ₂ O ₃ , SiO ₂ , CaO	2.6 to 2.8
Boron Carbide	synthetic	B ₄ C, B ₂ O ₃ , C	2.5
Calcium Boride	synthetic	C ₂ B ₆ , C	2.5

^A When it is necessary to minimize the production of long-lived secondary radiation in the shield, or to avoid using materials having inherent radioactivity, the purchaser should specify limits on the contents of objectionable elements.

^B The fixed water content of serpentine ranges from 10 to 13 percent by weight.

^C The fixed water content of limonite and goethite ranges from 8 to 12 percent by weight.

^D Ferrophosphorous when used in Portland cement concrete will generate flammable and possibly toxic gases which can develop high pressures if confined. See Clendenning, T. G., Kellam, B., and MacInnis, C., "Hydrogen Evolution from Ferrophosphorous Aggregate in Portland Cement Concrete," *Journal of the American Concrete Institute*, No. 12, December 1968. (*Proceedings*, Vol 65, pp. 1021–1028), and Mather, Bryant, discussion of Davis, Harold S., "Concrete for Radiation Shielding—In Perspective," and closure by author in "Concrete for Nuclear Reactors," *Journal of the American Concrete Institute* SP-34, Vol 1, 1972, pp. 11–13.

^E The fixed water content of boron frit is less than 0.5 %.

purchaser, as much as 20 % of the material passing the 9.5-mm (3/8 -in.) sieve may also pass the 150-µm (No. 100) sieve, with up to 10 % passing the 75-µm (No. 200) sieve if the material passing the 75-µm (No. 200) sieve is essentially free of clay or shale.

5.1.1 Fine and coarse aggregates for preplaced aggregate concrete shall be graded according to the requirements of [Table 2](#) and as follows:

Specific Gravity of Fine Aggregate	Grading of Aggregate	
	Coarse Aggregate	Fine Aggregate
Up to 3.0	Grading 1	Grading 1
Greater than 3.0	Grading 1	Grading 2
Full range	Grading 2	Grading 2

TABLE 2 Grading Requirements for Coarse and Fine Aggregates for Preplaced Aggregate Concrete

Sieve Size	Percentage Passing	
	Grading 1 For 37.5-mm (1½ -in.) Nominal Maximum Size Aggregate	Grading 2 For 25-mm (1-in.) Nominal Maximum Size Aggregate
Coarse Aggregate		
50-mm (2-in.)	100	...
37.5-mm (1½ in.)	95 to 100	100
25.0-mm (1-in.)	40 to 80	95 to 100
19.0-mm (¾ in.)	20 to 45	40 to 80
12.5-mm (½-in.)	0 to 10	0 to 15
9.5-mm (¾-in.)	0 to 2	0 to 2
Fine Aggregate		
2.36-mm (No. 8)	100	...
1.18-mm (No. 16)	95 to 100	100
600-µm (No. 30)	55 to 80	75 to 95
300-µm (No. 50)	30 to 55	45 to 65
150-µm (No. 100)	10 to 30	20 to 40
75-µm (No. 200)	0 to 10	0 to 10
Fineness modulus	1.30 to 2.10	1.00 to 1.60

5.1.2 When boron frit is used as part of the fine aggregate, the grading shall be such that 100 % passes the 4.75-mm (No. 4) sieve and not more than 5 % passes the 600-µm (No. 30) sieve.

5.2 *Fineness Modulus*—If the fineness modulus of the fine aggregate varies more than 0.2 from the value corresponding to that of the sample submitted for acceptance, the fine aggregate shall be rejected unless suitable adjustments are made in concrete proportions to compensate for the difference in grading.

6. Deleterious Substances

6.1 Fine and coarse aggregates shall meet the requirements of [Specification C33](#).

6.2 Boron frit shall not contain more than 2.0 % of water soluble material.

NOTE 1—This limit is based on concrete mixtures containing no more than 300 kg/m³ (500 lb/yd³) of boron frit.

7. Abrasion Resistance of Coarse Aggregate

7.1 Coarse aggregate shall have an abrasion loss not greater than 50 % when tested in accordance with [Test Method C131](#), or [Test Method C535](#), as applicable. Coarse aggregate failing to meet this requirement may be used, provided it can be shown that it produces satisfactory strengths in concrete of the proportions selected for the work.

8. Methods of Sampling and Testing

8.1 Sample and test the aggregates in accordance with the methods cited in [Specification C33](#) as applicable, except as follows:

8.1.1 *Specific Gravity*—Determine the bulk specific gravity (saturated surface-dry basis) of fine aggregate in accordance with [Test Method C128](#), and of coarse aggregate in accordance with [Test Method C127](#), except that the weight of the test sample for fine and coarse aggregate shall be approximately the specified weight multiplied by the ratio: