



SLOVENSKI STANDARD

SIST ISO 4516:2004

01-december-2004

Kovinske in druge anorganske prevleke - Preskusi mikrotrdote po Vickersu in Knoopu

Metallic and other inorganic coatings -- Vickers and Knoop microhardness tests

Revêtements métalliques et autres revêtements inorganiques -- Essais de microdureté Vickers et Knoop

ITeH STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: **ISO 4516:2002**
<https://standards.iteh.ai/catalog/standards/sist/2b565905-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004>

ICS:

25.220.40 Kovinske prevleke Metallic coatings

SIST ISO 4516:2004 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 4516:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004>

INTERNATIONAL STANDARD

**ISO
4516**

Second edition
2002-06-15

Metallic and other inorganic coatings — Vickers and Knoop microhardness tests

*Revêtements métalliques et autres revêtements inorganiques — Essais de
microdureté Vickers et Knoop*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 4516:2004](https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004)

[https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-
ba6ec42edc8c/sist-iso-4516-2004](https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004)



Reference number
ISO 4516:2002(E)

© ISO 2002

ISO 4516:2002(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 4516:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Principle.....	1
4 Symbols and designations	2
5 Apparatus	2
6 Factors affecting measurement accuracy.....	5
7 Measuring procedure	9
8 Test report	11
Bibliography	12

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 4516:2004](https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004)

<https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004>

ISO 4516:2002(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4516 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 2, *Test methods*.

This second edition cancels and replaces the first edition (ISO 4516:1980), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 4516:2004](https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004)

<https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004>

Metallic and other inorganic coatings — Vickers and Knoop microhardness tests

1 Scope

This International Standard describes the application of the Vickers and Knoop micro-indentation tests for determining the microhardness of metallic and other inorganic coatings. This method is applicable where indenter forces generally need to be below 10 N such as for electrodeposited coatings, autocatalytic coatings, sprayed coatings and anodic coatings on aluminium. It is applicable to measurements normal to the coated surface as described in 7.4 and to measurements on cross-sections as described in 7.3.

NOTE 1 Attention is drawn to ISO 4545, ISO 6507-1, ISO 6507-2 and ISO 6507-3, which describe Knoop and Vickers hardness testing of metallic materials. Other International Standards for instrumental indentation testing, the verification of microindentation testing instruments and for the verification of reference blocks to be used with such instruments are currently being developed (e.g. ISO 14577 Parts 1 to 4).

NOTE 2 Usually for hardness measurements of coating test forces in the microhardness range in accordance with ISO 6507-1 are used. However since the largest possible test force should be selected, test forces of the low force and hardness ranges may also be used.

(standards.iteh.ai)

2 Normative references

SIST ISO 4516:2004

<https://standards.iteh.ai/catalog/standards/sist/2b565903-127e-4042-b42c->

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 1463, *Metallic and oxide coatings — Measurement of coating thickness — Microscopical method*

ISO 6507-1, *Metallic materials — Vickers hardness test — Part 1: Test method*

ISO 9002, *Quality systems — Model for quality assurance in production, installation and servicing*

3 Principle

A testing instrument slowly lowers an indenter vertically on to the test surface and holds it there for a specified time under a specified load (see 6.2). The tolerance of the applied test force is within 1 % of that specified.

An indenter is forced into the coating and the diagonal(s) of the indentation left in the surface after removal of the indenter is measured using a microscope. The indenter is applied such that the resultant indentation does not contain artefacts of the loading apparatus or procedure but rather is characteristic of the coating.

A number, known as the Vickers or Knoop hardness number, is derived from this measurement using the symbols and designations given in clause 4.

ISO 4516:2002(E)

4 Symbols and designations

Vickers and Knoop hardnesses are denoted respectively by the symbols HV and HK preceded by the hardness value and followed by:

- a) a number representing the test force (force in newtons multiplied by proportionality factor 0,102) (see Table 1);
- b) the application time of test force, in seconds, if different from the time specified in 6.3.

EXAMPLE 1 640 HV 0,1: Vickers hardness of 640 determined using a test force of 0,980 7 N applied for between 10 s and 15 s.

EXAMPLE 2 640 HK 0,1/20: Knoop hardness of 640 determined using a test force of 0,980 7 N applied for 20 s.

Table 1 — Symbols and designations

Symbol	Measuring unit	Designation	
		Vickers	Knoop
F	Force: N	Test force: N	Test force: N
d	Diagonal measurement: μm	Arithmetic mean of the two separately measured diagonals $d = \frac{d_1 + d_2}{2}$	Length of longer diagonal
HV and HK	—	Vickers hardness number = $(0,102 F)/A_V = 189,1 \times 10^6 F/d^2$	Knoop hardness number = $(0,102 F)/A_K = 1\,451,4 \times 10^6 F/d^2$
A_V	mm^2	Sloping surface area of indentation (contact area)	
A_K	mm^2		Projected area of the indentation
t	μm	Coating thickness	Coating thickness
s	—	Standard deviation $s = \sqrt{\frac{(\overline{\text{HV}} - \text{HV})^2}{(n-1)}}$	Standard deviation $s = \sqrt{\frac{(\overline{\text{HK}} - \text{HK})^2}{(n-1)}}$
N	—	Number of measurements	Number of measurements
$\overline{\text{HV}}$ and $\overline{\text{HK}}$	—	$\overline{\text{HV}} = \Sigma \text{HV}/n$	$\overline{\text{HK}} = \Sigma \text{HK}/n$
V	%	Coefficient of variation $V = 100s/\overline{\text{HV}}$	Coefficient of variation $V = 100s/\overline{\text{HK}}$

5 Apparatus

5.1 Testing instrument, to perform the task described in clause 3.


5.2 Indenters

5.2.1 Form and dimensions

5.2.1.1 Vickers indenter


The indenter consists of a diamond in the form of a right pyramid with a square base (see Figure 1). The angle at the vertex between opposite faces shall be $136^\circ \pm 0,5^\circ$. This angle shall have been verified with a 2-circle goniometer of appropriate accuracy. The relation between the diagonals d_1 and d_2 and the depth of the indentation, h , is approximately 7:1.

The four faces shall be equally inclined to the axis of the indenter (within $0,5^\circ$) and shall meet at a point; any line of junction (offset) between two opposite faces shall not exceed $0,5 \mu\text{m}$. The usual shape of the point is shown in Figure 2 as it would appear under high magnification.



a Offset

SIST ISO 4516:2004
<https://standards.iteh.ai/standards/ISO/4516/2004/27e-4042-b42c-ba6ec42edc8c/sist-iso-4516-2004>
Figure 1 — Vickers indenter



a Maximum offset $0,5 \mu\text{m}$

Figure 2 — Vickers indenter offset

5.2.1.2 Knoop indenter

The indenter consists of a diamond tipped right pyramid with a rhomboid base (see Figure 3). The angles at the vertex shall be $172,5^\circ \pm 0,3^\circ$ and $130^\circ \pm 0,3^\circ$. These angles shall have been verified with a 2-circle goniometer of appropriate accuracy. The four faces shall be equally inclined to the axis of the indenter (within $0,5^\circ$) and shall meet at a point; any line of junction (offset) between two opposite faces shall not exceed $1,0 \mu\text{m}$. The usual shape of the point as it would appear under high magnification is shown in Figure 4. The relation between the long diagonal and the depth of the indentation is approximately 30:1.