



Designation: D2899 – 03

## Standard Practice for Establishing Allowable Stresses for Round Timber Piles<sup>1</sup>

This standard is issued under the fixed designation D2899; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This practice contains procedures for establishing allowable stresses for round timber piles starting with clear wood strength properties.

1.2 Stresses established under this practice are applicable to piles conforming to the quality, straightness, spiral grain, knot, check, shake, and split provisions of Specification D25.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

D25 Specification for Round Timber Piles

D245 Practice for Establishing Structural Grades and Related Allowable Properties for Visually Graded Lumber

D2555 Practice for Establishing Clear Wood Strength Values

### 3. Terminology

3.1 *Definitions:*

3.1.1 *allowable stress*—the numeric value of pile strength that is appropriate for use in structural analysis.

3.1.2 *end-bearing*—compression-parallel-to-the-grain stress resulting when pile load is not carried to the soil through skin friction.

3.1.3 *load sharing*—the distribution of load in proportion to pile stiffness. This results in piles that perform as a group reducing effects of between-pile variability and increasing system reliability over that of piles which perform independently.

3.1.4 *skin friction*—the interaction between the pile surface and the soil which serves to distribute load either away from or into a pile. A positive skin friction refers to pile loads distributed to the soil. Negative skin friction distributes load to the pile when soil strata subside or consolidate.

3.2 *Symbols:*

$C_{cp}$  = adjustment for small clear compression perp for annual ring orientation (1/1.67)

$C_{ct}$  = conditioning factor

$C_{dol}$  = adjustment for duration of load and factor of safety

$C_d$  = adjustment for density applied for Douglas fir and Southern pine only

$C_{fs}$  = combined adjustment for form and size (= 0.97)

$C_g$  = adjustment for grade characteristics applied to all species including bending (0.75), compression (0.93), and shear (0.50)

$C_h$  = adjustment for height in the tree (= 0.96 if softwoods and = 1.0 for hardwoods)

$C_{hv}$  = adjustment for height and for reduced variability ( $MOR = 0.91$  for softwoods, 1.05 for hardwoods,  $C// = 0.91$  for softwoods, 1.05 for hardwoods, Shear = 0.99 for softwoods, 1.03 for hardwoods)

$C_{ls}$  = load sharing adjustment (structural engineers option)

$C_s$  = size adjustment

$C_v$  = adjustment for shear deflection in calculation for bending modulus of elasticity (= 1.06)

$D$  = diameter of a round timber pile

$E$  = clear wood unseasoned average modulus of elasticity from Test Methods D2555

$MOE$  = modulus of elasticity (average)

$F_{\beta}$  = allowable stress for stress designated by the subscript  $\beta$

$F_c$  = allowable compression stress for pile tips

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee D07 on Wood and is the direct responsibility of Subcommittee D07.04 on Pole and Pile Products.

Current edition approved Oct. 1, 2003. Published December 2003. Originally approved in 1970 as D2899 – 70 T. Last previous edition approved in 2001 as D2899 – 01. DOI: 10.1520/D2899-03.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For Annual Book of ASTM Standards volume information, refer to the standard's Document Summary page on the ASTM website.

$f_{c05}$  = small clear lower 5 % exclusion compression strength in accordance with Test Methods **D2555**

$f_{i05}$  = lower 5 % exclusion value for stress “x” determined using the green, small clear strength and standard deviation values reported in Test Methods **D2555**

$\beta$  = stress value subscripts,  $c$  = compression parallel,  $cp$  = compression perpendicular,  $b$  = bending,  $v$  = shear

#### 4. Significance and Use

4.1 This practice is intended for use by associations, technical societies and other groups that develop national design standards and use recommendations for round timber piles.

4.2 In using allowable stresses established under this practice, factors specific to each end use which may affect the performance of the pile system shall be considered. Such factors include the location of the critical section, the bearing capacity of the soil, the ability of the pile to withstand driving forces and conditions of service.

### PRINCIPLES INVOLVED IN ESTABLISHING ALLOWABLE STRESSES

#### 5. Species

5.1 This practice applies to any species of piles for which clear wood strength values are given in Test Methods **D2555**.

5.2 Where pile allowable stress is to be established for a combination of species and/or regions, clear wood values assigned to such combinations are based on the grouping criteria given in Section 5 of Test Methods **D2555**.

#### 6. Clear Wood Properties

6.1 Information on average properties and their variation given in Test Methods **D2555** apply to small, clear, straight-grained wood in the green condition under short-term loading.

6.2 Round timber piles having minimum tip diameters of 5 in. or larger are considered by this practice to be comparable to sawn timbers: General adjustment factors used to establish allowable stress for such timbers under Practice **D245** also are applied to piles.

6.3 For the properties of bending strength (modulus of rupture), compression strength parallel to the grain and horizontal shear strength, clear-wood 5 % -exclusion values calculated from Test Methods **D2555** are divided by the adjustment factors given in Table 10 of Practice **D245** to obtain basic values for these properties from which pile allowable stress is established. The adjustment factors for the three strength properties include a reduction for normal duration of load and a factor of safety.

6.4 For the properties of modulus of elasticity and compression perpendicular to grain at 0.04-in. deformation, clear wood average values from Test Methods **D2555** are divided by the adjustment factors for these properties given in Table 10 of Practice **D245** to obtain basic values from which pile allowable stress for these properties also are established. The modulus of elasticity factor is a shear deflection adjustment. The compression perpendicular to grain factor is an adjustment to account for limiting ring position.

#### 7. Pile Variability

7.1 Standard deviations given in Test Methods **D2555** and used to calculate 5 % exclusion values include both variability in properties between trees and variability in properties occurring within the cross section and along the length of an individual tree.

7.2 For round timber piles, only the between tree component of variance is applicable. Clear wood 5 % exclusion values applied to piles are adjusted to account for this reduced variability.

#### 8. Minimum Tip and Critical Section Properties

8.1 Average clear wood properties given in Test Methods **D2555** represent volume weighted average whole tree values where the average property is that associated with material occurring between heights of 8 and 16 ft. For softwood species, clear wood strength properties generally decrease as the height location in the tree increases.

8.2 For compression parallel to grain, the minimum strength of the pile occurs at the pile tip, or at a minimum diameter of 5 in. For bending and shear strengths, the critical section of the pile is assumed to occur at a point 10 ft above the pile tip. In terms of location in the tree, both of these sections occur at heights in the tree which are appreciably greater than the heights associated with the whole tree average property values. Therefore clear wood average properties obtained from Test Methods **D2555** must be reduced to account for this height effect when establishing compression parallel to grain, bending, shear and modulus of elasticity design stresses for piles made with softwood species.

#### 9. Density

9.1 Specification **D25** requires the outer 50 % of the radius at the pile tip to have an average rate of growth of at least 6 rings per inch and an average summerwood content of not less than 33.3 %. Piles with less than 6 rings per inch are acceptable if the average summerwood content in the outer 50 % of the pile tip radius is 50 % or more.

9.2 Practice **D245** provides for the classification of Douglas fir and southern pine sawn lumber meeting growth rate and summerwood content requirements similar to those in Specification **D25** as dense material. The properties of such lumber, except shear, are increased to account for the increased strength and stiffness associated with limiting the occurrence of low density material.

9.3 Increases for density applicable to Douglas fir and southern pine lumber also are applicable to piles of the same species. The increase for density in compression parallel to grain applicable to lumber must be adjusted when applied to piles to account for the inner core of the pile tip that is not required to meet the density provisions.

#### 10. Form and Size

10.1 The average bending strength of round wood sections based on standard beam formulas is greater than that of matched rectangular sections. However, the section modulus of a round beam is less (1/1.18) than that of a square beam of equivalent area by approximately the same ratio as the strength

of the round member is greater than that of the rectangular member. Round members therefore are assigned a unit strength equal to 1.18 times that based on rectangular sections when the section modulus of the circular cross section is used.

10.2 Clear wood bending stresses in Test Methods D2555 are based on tests of 2-in. deep rectangular sections. Under Practice D245, such values are adjusted for depth (*d*) by the factor  $(2/d)^{1/9}$  when applied to sawn lumber members. Based on a circular section having an area equal to that of a square section, the equivalent depth adjustment for a round member is  $(2.2568/D)^{1/9}$ .

10.3 Under standard practice, bending allowable stress for beams and stringers and post and timbers are given for a 12-in. beam depth. Values for beams exceeding 12 in. are reduced using the 1/9 power equation. The same practice is employed with round timber piles. Pile bending stresses are indexed to the diameter of a circular section having an area equal to that of a 12-in. square, or 13.5 in. Clear wood bending values are adjusted to a 13.5-in. pile diameter by the factor 0.82.

### 11. Grade

11.1 Knots in round piles reduce compression parallel to grain and bending strength properties. Limits on allowable size and spacing of knots along the pile length are given in Specification D25.

11.2 The effect of knots on pile tip strength is determined from tests of full size pile sections containing various knot sizes. Regression analyses of compression strength against knot size and specific gravity establish the effect of allowable knots on compression parallel to grain strength.

11.3 The effect of allowable knots on pile bending strength is derived assuming load-carrying capacity is reduced by the ratio of the section modulus of a wedge section occupied by the knot to the section modulus of the total circular section. The combined interaction of clear wood strength, knot size and knot location along the pile length is assessed through random products simulation assuming (1) a rectangular distribution of strength ratio, (2) a normal clear wood distribution, and (3) linear induced moment in 2-ft length segments over a 10-ft cantilever beam length from the top of the pile to the critical section.

11.4 The effect of splits, checks, and shakes on pile shear strength is considered to be the same as that on the shear strength of sawn timber.

### 12. Duration of Load

12.1 Wood strength properties are affected by the duration of the maximum applied load: the shorter the duration the

greater the maximum load that can be carried. Allowable stress for round timber piles established under this practice are short-term test values reduced to a normal load duration basis. Normal load duration represents application of a load that fully stresses a member to its design stress for a cumulative duration of approximately 10 years.

12.2 When the cumulative duration of the full maximum load is less than or more than ten years, pile allowable stress for bending, compression parallel to grain and horizontal shear shall be modified in accordance with the duration of load adjustments shown in Fig. 6 of Practice D245. Load duration adjustments greater than 1.6 shall not apply to piles preservative-treated with water-borne salts.

12.3 Duration of load adjustments are not applied to pile allowable stress for modulus of elasticity and compression perpendicular to grain based on a deformation limit.

### 13. Moisture Content

13.1 Allowable stress established by this practice applies to piles that are continuously wet or are continuously exposed to the weather.

13.2 No increase in properties for material that is partially above ground and may be partially seasoned is recognized.

### 14. Preservative Treatment

14.1 Preservative treatment by approved processes and chemicals does not significantly affect allowable stress values for round timber piles established in this practice.

14.2 Conditioning of piles by kiln drying, steaming or boiling in liquids prior to pressure treatment to facilitate penetration of preservative chemicals does affect strength properties. Reduction of allowable stress (Table 2) to account for such effects are based on compression parallel to grain tests of end-matched conditioned and unconditioned full-size pile sections.

14.3 No adjustments are made for conditioning prior to treatment of allowable stress for modulus of elasticity (*E*) and compression perpendicular to grain at 0.04-in. deformation (*F<sub>cp</sub>*).

### DERIVATION OF ALLOWABLE STRESS FOR UNTREATED PILES

### 15. Compression Parallel to Grain

15.1 Calculate compression allowable stress for pile tips using the following equation:

$$F_c = (f_{c05} C_{dol}) [C_{nv}] [C_d] [C_g] \tag{1}$$

15.2 Where the critical section in compression parallel to grain is located above the pile tip as a result of skin friction from the soil through which the pile is driven, or equivalent other effect;  $F^{1/2} c$  for softwood species may be increased by the following adjustment:

**TABLE 1 Strength and Stiffness Adjustments for Density (*d*), Grade (*g*), and Combined Duration of Load and Factor of Safety (*dol*)**

Stress Factor	Bending	Shear	Compression		MOE
			Parallel to grain	Perpendicular to grain	
$C_d^A$	1.17	1.00	1.13	1.17	1.05
$C_g$	0.75	0.50	0.93	1.00	1.00
$C_{dol-Stlwd}$	1/2.1	1/2.1	1/1.9	1.00	1.00
$C_{dol-Hrdwd}$	1/2.3	1/2.3	1/2.1	1.00	1.00

<sup>A</sup> Density adjustments apply only to Douglas fir and southern pine.

**TABLE 2 Conditioning Effects on the Strength of Round Timber**

Conditioning	Air Drying	Kiln Drying	Boulton Drying	Steaming (Normal)	Steaming (Marine)
$C_{ct}$	1.0	0.90	0.95	0.80	0.74