

SLOVENSKI STANDARD SIST EN 10223-5:2013

01-marec-2013

Nadomešča:

SIST EN 10223-5:2000

Jeklena žica in žični izdelki za ograje - 5. del: Kolenčasto in vozlasto tkana jeklena žična mreža

Steel wire and wire products for fences - Part 5: Steel wire woven hinged joint and knotted mesh fencing

Stahldraht und Erzeugnisse aus Stahldraht für Zäune Teil 5: Gelenk- und Knotengitter aus Stahldraht für Zäune (standards.iteh.ai)

Fils et produits tréfilés en acier pour clôtures (•2 Partiel 5: Grillage noué en acier pour le bétail https://standards.iteh.ai/catalog/standards/sist/24479e8c-2ba9-47f9-8eac-0bd2b8bf7698/sist-en-10223-5-2013

Ta slovenski standard je istoveten z: EN 10223-5:2012

ICS:

77.140.65 Jeklene žice, jeklene vrvi in Steel wire, wire ropes and

verige link chains

91.090 Konstrukcije zunaj stavb External structures

SIST EN 10223-5:2013 en,fr,de

SIST EN 10223-5:2013

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 10223-5:2013 https://standards.iteh.ai/catalog/standards/sist/24479e8c-2ba9-47f9-8eac-0bd2b8bf7698/sist-en-10223-5-2013

EUROPEAN STANDARD NORME EUROPÉENNE EUROPÄISCHE NORM EN 10223-5

November 2012

ICS 77.140.65

Supersedes EN 10223-5:1998

English Version

Steel wire and wire products for fencing and netting - Part 5: Steel wire woven hinged joint and knotted mesh fencing

Fils et produits tréfilés en acier pour clôtures et grillages -Partie 5: Grillage noué et grillage à raccords pivotants en acier Stahldraht und Drahterzeugnisse für Zäune und Drahtgeflechte - Teil 5: Gelenk- und Knotengitter aus Stahldraht für Zäune

This European Standard was approved by CEN on 13 October 2012.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards podies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.

SIST EN 10223-5:2013

https://standards.iteh.ai/catalog/standards/sist/24479e8c-2ba9-47f9-8eac-0bd2b8bf7698/sist-en-10223-5-2013



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

EN 10223-5:2012 (E)

Cont	tents	Page
Forew	ord	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Information to be supplied by the purchaser	6
5	Designation of hinged joint and knotted mesh fencing	6
6 6.1 6.2	ManufactureBase metalFabrication	6
7 7.1 7.1.1 7.1.2 7.2 7.2.1 7.2.2 7.3 7.4	Requirements Tensile strength Woven hinged joint fencing Knotted mesh fencing Wire diameters Woven hinged joint fencing Knotted mesh fencing Tolerances Coating Kanadards:iteh.ai	7777777
8	Sampling and testing <u>SIST EN 10223-5:2013</u>	10
9	Inspection documentation pdards, itch.ai/catalog/standards/sist/24479e8c-2ba9-47f9-8cac-	10
10 10.1 10.2	Test methods	10
11	Packaging	10
Annex	A (informative) Typical designations for hinged joint and knotted joint fencing	11

Foreword

This document (EN 10223-5:2012) has been prepared by Technical Committee ECISS/TC 106 "Wire rod and wires", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2013, and conflicting national standards shall be withdrawn at the latest by May 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 10223-5:1998.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

EN 10223 "Steel wire and wire products for fencing and netting" consists of the following parts:

- Part 1: Zinc and zinc-alloy coated steel barbed wire
- Part 2: Hexagonal steel wire netting for agricultural, insulation and fencing purposes
- (standards.iteh.ai)

 Part 3: Hexagonal steel wire mesh products for engineering purposes
- Part 4: Steel wire welded mesh fencing https://standards.iteh.a/catalog/standards/sist/24479e8c-2ba9-47f9-8eac-
- Part 5: Steel wire woven hinged joint and knotted mesh fencing
- Part 6: Steel wire chain link fencing
- Part 7: Steel wire welded panels for fencing
- Part 8: Welded mesh gabion products

According to the CEN/CENELEC Internal Regulations, the national standards organisations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

EN 10223-5:2012 (E)

1 Scope

This European Standard specifies preferred dimensions, properties and coatings of zinc and zinc alloy coated steel wire woven hinged joint and knotted mesh fencing.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10021, General technical delivery conditions for steel products

EN 10204, Metallic products — Types of inspection documents

EN 10218-1, Steel wire and wire products — General — Part 1: Test methods

EN 10218-2:2012, Steel wire and wire products — General — Part 2: Wire dimensions and tolerances

EN 10244-1:2009, Steel wire and wire products — Non-ferrous metallic coatings on steel wire — Part 1: General principles

EN 10244-2:2009, Steel wire and wire products — Non-ferrous metallic coatings on steel wire — Part 2: Zinc and zinc alloy coatings

(standards.iteh.ai)

3 Terms and definitions

SIST EN 10223-5:2013

https://standards.iteh.ai/catalog/standards/sist/24479e8c-2ba9-47f9-8eac-For the purposes of this document, the following terms and definitions apply.

3.1

knotted mesh fencing

fencing with rectangular meshes made of line and stay wires zinc or zinc alloy coated to EN 10244-1:2009 and EN 10244-2:2009, class A

The line and stay wires are connected by a hinged joint spiral knot in the case of hinge joint stock fence (see Figure 1) and by a knot in the case of knotted stock fence (see Figure 2) (except for the selvedge wire which is spiral knotted):

- The top and bottom wires of the fence may consist of a larger diameter selvedge wire.
- The rectangular mesh openings may decrease in size from the top downwards.
- The line and selvedge wire are regularly and evenly crimped between the stay wires (to aid erection of the fence)


3.2

woven joint fencing

classification relating to:

- a) strength of wire:
 - 1. strength 1 applies to fencing manufactured from low tensile wire;
 - 2. strength 2 applies to fencing manufactured from high tensile wire;

- b) nominal diameter of wires incorporated in the fence using:
 - 1. L for light (small diameter wire);
 - 2. *M* for medium (medium diameter wire);
 - 3. *H* for heavy (large diameter wire)



Key

3

line wire

- 1 selvedge wire2 stay wire4 length5 height
 - Figure 1 Example of woven hinged joint design




Figure 2 — Examples of knotted joint design

EN 10223-5:2012 (E)

4 Information to be supplied by the purchaser

The following information shall be supplied by the purchaser at the time of enquiry and order:

- a) number of this European Standard;
- b) quantity;
- c) hinged joint or knotted joint;
- d) classification (i.e. L, M or H and 1 or 2 according to Table 1);
- e) designation (see Clause 5, Table A.1 and Table A.2);
- f) length of rolls;
- g) height of roll;
- h) number of line wires and stay wire spacing;
- i) for 2M and 2H (according to Table 1) the size of selvedge wire required;
- j) coating type, zinc or zinc alloy;
- k) if uniformity of coating is to be measured;
- I) inspection documentation requirements;
- m) agreed quality characteristics for testing (see Clause 7). PREVIEW

5 Designation of hinged joint and knotted mesh fencing

SIST EN 10223-5:2013

https://standards.iteh.ai/catalog/standards/sist/24479e8c-2ba9-47thxxxyacxxy / xx
0bd2b8bf7698/sist-en-10223-5-2013

Height (in cm)

Number of line wires including selvedge

Distance between stay wires (in cm)

Figure 3

EXAMPLE 80/8/15

Typical designations of hinged joint and knotted mesh fencing are given in Table A.1 and Table A.2.

6 Manufacture

6.1 Base metal

Wires shall be manufactured from steel rod capable of achieving the tensile properties given in Tables 1 and 2.

6.2 Fabrication

The hinge joint or knotted fence shall be made from zinc or zinc-alloy coated wires which conform to EN 10244-1 and EN 10244-2.

The line and selvedge wires shall be regularly and evenly crimped between the stay wires (to aid erection of the fence).

In the case of hinge joint fencing the wires shall be twisted at least one and a half times to ensure that the hinge joints are tightly fixed. In the case of knotted joint fencing the knots shall be manufactured so that they are tightly fixed.

7 Requirements

7.1 Tensile strength

7.1.1 Woven hinged joint fencing

The tensile strength of wires shall not be less than that given in Table 1 for the classification and tensile strength required. The tensile strength range for any one batch within a type of wire shall be not more than 200 N/mm².

7.1.2 Knotted mesh fencing

The tensile strength of the wires shall be not less than that given in Table 2. The tensile strength range in any one batch within a wire type shall be not more than 200 N/mm².

7.2 Wire diameters

SIST EN 10223-5:2013

7.2.1 Woven hinged joint fencing obd2b8bf7698/sist-en-10223-5-2013

The nominal diameters of wires shall be as given in Table 1 and shall be subject to tolerance EN 10218-2:2012 (T1 – Table 1).

7.2.2 Knotted mesh fencing

The nominal diameters of wires shall be as given in Table 2 and shall be subject to tolerance EN 10218-2:2012 (T1 - Table 1).

7.3 Tolerances

The tolerance on roll width is ± 25 mm.

The maximum variation in any individual vertical or horizontal spacing shall be no more than \pm 5 mm from the nominal stated by the manufacturer.

NOTE Rolls are usually supplied with either 150 or 300 mm spacing between verticals, but other spacing may be arranged by agreement.

7.4 Coating

The zinc or zinc alloy coating of wire shall be tested in accordance with EN 10244-2:2009 complying with class A for Zn coatings and class B for Zn95/Al5 alloys (for similar service life), adherence and where specified, the uniformity of the coating