



Designation: D 1241 – 00

Standard Specification for Materials for Soil-Aggregate Subbase, Base, and Surface Courses¹

This standard is issued under the fixed designation D 1241; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification covers the quality and grading of the following materials for use in the construction of subbase, base, and surface courses: sand-clay mixtures; gravel; stone or slag screenings; sand; crusher-run coarse aggregate consisting of gravel, crushed stone, or slag combined with soil mortar; or any combination of these materials. The requirements are intended to cover only materials having normal or average specific gravity, absorption, and gradation characteristics. Where other materials are to be used, appropriate limits suitable to their use must be specified.

1.2 The following precautionary caveat pertains only to the Test Methods portion, Section 9, of this specification. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards:*
- C 117 Test Method for Material Finer than 75- μm (No. 200) Sieve in Mineral Aggregates by Washing²
 - C 131 Test Method for Resistance to Degradation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine²
 - C 136 Test Method for Sieve Analysis of Fine and Coarse Aggregates
 - D 75 Practice for Sampling Aggregates³
 - D 420 Guide to Site Characterization for Engineering, Design, and Construction Purposes⁴

¹ This specification is under the jurisdiction of ASTM Committee D18 on Soil and Rock and is the direct responsibility of Subcommittee D18.08 on Special and Construction Control Tests.

Current edition approved Nov. 10, 2000. Published February 2001. Originally issued 1952. Replaces D556, D557, D1241 – 64 T. Last previous edition D 1241 – 68 (1994) ^{ϵ 1}.

² *Annual Book of ASTM Standards*, Vol 04.02.

³ *Annual Book of ASTM Standards*, Vol 04.03.

⁴ *Annual Book of ASTM Standards*, Vol 04.08.

D 421 Practice for Dry Preparation of Soil Samples for Particle-Size Analysis and Determination of Soil Constants⁴

D 653 Terminology Relating to Soil, Rock, and Contained Fluids⁴

D 3740 Practice for Minimum Requirements for Agencies Engaged in the Testing and/or Inspection of Soil and Rock as Used in Engineering Design and Construction⁴

D 4318 Test Method for Liquid Limit, Plastic Limit, and Plasticity Index of Soils⁴

3. Terminology

3.1 For definitions of terms in this standard, refer to Terminology D 653.

4. Types

4.1 The following types of mixtures are specified:

4.1.1 *Type I*—Mixtures consisting of stone, gravel, or slag with natural or crushed sand and fine mineral particles passing a No. 200 (75- μm) sieve and conforming to the requirements of Table 1 for Gradation A, B, C, or D.

4.1.2 *Type II*—Mixtures consisting of natural or crushed sand with fine mineral particles passing a No. 200 (75- μm) sieve, with or without stone, gravel, or slag, and conforming to the requirements of Table 1 for Gradation E or F.

5. General Requirements

5.1 *Coarse Aggregate*—Coarse aggregate retained on a No. 10 (2.00-mm) sieve, for use in Type I and Type II mixtures, shall consist of hard, durable particles or fragments of stone, gravel, sand, or slag; materials that break up when alternately frozen and thawed or wetted and dried shall not be used. Coarse aggregate shall have a percentage of wear, by the Los Angeles Abrasion (Test Method) test, of not more than 50.

NOTE 1—A higher or lower percentage of wear may be specified by the engineer, depending upon the materials available for the work.

5.2 *Fine Aggregate*—Fine aggregate passing a No. 10 (2.00-mm) sieve, for use in Type I and Type II mixtures, shall consist of natural or crushed sand and fine mineral particles passing the No. 200 (75- μm) sieve. The fraction passing the

*A Summary of Changes section appears at the end of this standard.