



Designation: D 5793 – 03

## Standard Test Method for Binding Sites per Unit Length or Width of Pile Yarn Floor Coverings<sup>1</sup>

This standard is issued under the fixed designation D 5793; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This test method describes the measurement of the number of binding sites per unit length or width of machine-made, woven, knitted, and tufted pile yarn floor covering both before and after adhesive backing application.

1.2 The values stated in SI units are to be regarded as the standard for all measurements. The inch-pound values provided are for information purposes only.

1.3 Determination of the number of binding sites per unit length or width of pile floor covering previously was contained within Test Methods D 418.

NOTE 1—For user convenience, Subcommittee D13.21 has subdivided Test Method D 418 into separate standards, of which this test method is one.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

### 2. Referenced Documents

- 2.1 *ASTM Standards:*<sup>2</sup>
- D 123 Terminology Relating to Textiles
  - D 418 Test Methods of Testing Pile Yarn Floor Covering Construction
  - D 1776 Practice for Conditioning and Testing Textiles
  - D 1909 Table of Commercial Moisture Regains for Textile Fibers
  - D 2904 Practice for Interlaboratory Testing of a Textile Test Method that Produces Normally Distributed Data

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D13 on Textiles and is the direct responsibility of Subcommittee D13.21 on Pile Yarn Floor Coverings.

Current edition approved Oct. 1, 2003. Published November 2003. Originally approved in 1995. Last previous edition approved in 1995 as D 5793 – 95.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

D 2906 Practice for Statements of Precision and Bias of Textiles

D 5684 Terminology Relating to Pile Floor Coverings

E 122 Practice for Calculating Sample Size to Estimate With a Specified Tolerable Error, the Average Characteristic of a Lot Process

### 3. Terminology

3.1 For definitions of pile yarn floor covering related terms used in this test method, refer to Terminology D 5684.

3.2 For definitions of other textile terms used in this test method, refer to Terminology D 123.

### 4. Summary of Test Method

4.1 The length of pile floor covering containing 40 binding sites is measured in either the lengthwise or widthwise direction as required and the number of binding sites per unit length is calculated.

### 5. Significance and Use

5.1 This test method is useful in quality and cost control during manufacture. Both appearance and performance of pile yarn floor coverings can be affected by the number of binding sites per length and width.

5.2 This test method is considered satisfactory for acceptance testing of commercial shipments because current estimates of between-laboratory precision are acceptable and the method is used extensively in the trade for acceptance testing.

5.2.1 If there are differences of practical significance between reported test results for two laboratories (or more), comparative tests should be performed to determine if there is statistical bias between them using competent statistical assistance. As a minimum, use test samples for such comparative tests that are as homogeneous as possible, drawn from the same lot of material as the samples that resulted in the disparate results during initial testing, and that are randomly assigned in equal numbers to each laboratory for testing. The test results from the laboratories should be compared using a statistical test for unpaired data at a probability level chosen prior to the testing series. If a bias is found either its cause must be found

and corrected, or future test results for that material must be adjusted in consideration of the know bias.

## 6. Apparatus

6.1 *Shears or Clippers*, capable of shearing close enough to the backing to leave a stubble of no more than 1.3 mm (0.05 in.).

6.2 *Scale or Tape*, metal, graduated in 1 mm (0.05 in.) and at least 10 % longer than the distance being measured.

6.3 *Location Markers*, two, such as straight pins.

## 7. Sampling Units and Test Specimens

### 7.1 Sampling Units:

7.1.1 *Uncoated Floor Covering*—The basic sampling unit of uncoated floor covering is a production roll.

7.1.2 *Coated Floor Covering*—The basic sampling unit of coated floor covering is a shipping roll. The number of shipping rolls obtained from each production roll ranges from one to over ten.

7.2 Take a lot sample as directed in Practice E 122 when statistical knowledge of the product variability and test method precision is available, and decision has been made on the maximum deviation that can be tolerated between the estimate to be made from the sample and the result that would be obtained by measuring every sampling unit of the lot. Otherwise the number of sampling units in a lot sample and the use of the test results obtained from the individual test samples shall be in accordance with the manufacturer's quality control program or with the specification agreed to by the purchaser and the supplier.

7.3 A test sample shall consist of a full width section of floor covering cut from one end of each roll in the lot sample and shall be at least 100 mm (4 in.) longer than the specimens required for the tests being conducted. Do not cut a test sample of coated floor covering from a seam end of a production roll.

### 7.4 Test Specimens:

7.4.1 The test specimens shall be large enough to include 44 binding sites in each direction.

7.4.2 This test method may be nondestructive since the measurements may be made on the test specimens without cutting the test specimens from the test sample.

7.4.3 A test specimen is a designated area of a test sample that may be marked on or cut from the test sample as directed in the test method. For test samples 3000 mm (118 in.) wide or wider, three test specimens are required, one at each edge no nearer to the edge than 5 % of the total floor covering width and one in the middle portion of the test sample. For test samples at least 1500 mm (60 in.) wide but less 3000 mm (118 in.), take two test specimens, one at each edge no nearer to the edge than 5 % of the total floor covering width. For test samples less than 1500 mm wide (60 in.), take one specimen, from the middle.

7.4.4 Where it is known that systematic variations in a floor covering characteristic may occur in bands 460 mm (18 in.) or more in width, as with modular pattern device having separate controls or adjustments for each module, take test specimens from the middle of each band.

7.4.5 When a full width test sample is not available, take a specimen as directed in 7.4.3 and state in the report the width available and the number of test specimens taken.

7.5 A test result is the average of the measurements made on a set of test specimens as described in 7.4.3, 7.4.4, or 7.4.5. In these methods, directions are given only for obtaining a test result from one test sample. The value representative of the lot being sampled will be the average of the test results for all the test samples in the lot sample.

## 8. Conditioning

8.1 Condition the test specimens or the test sample as directed in Practice D 1776 in the at standard atmosphere for testing textiles ( $21 \pm 1^\circ\text{C}$  ( $70 \pm 2^\circ\text{F}$ ) at  $65 \pm 2\%$  relative humidity) for 12 h or until the mass changes no more than 0.1 % in 2 h.

8.2 If the fiber in any layer of the backing has a commercial regain of over 5 %, the specimen may be conditioned before measuring. Commercial moisture regains for textile fibers are listed in Table D 1909.

## 9. Procedure

9.1 If the binding sites are visible from the back, place the test specimen face down on a flat surface; otherwise, place the test specimen back down and shear the pile close to the backing to reveal the binding sites. Select a line of binding sites in the direction to be counted.

9.1.1 Handle uncoated floor coverings carefully to avoid distortion of binding sites of coated floor covering after treating with reagents and removing the secondary backing.

9.2 Select a distinguishing feature found at each binding site.

NOTE 2—It is not necessary to define precisely the boundaries of a binding site; only to use the same distinguishing feature in every binding site being counted in a particular specimen. For tufted floor covering, a distinguishing feature is the needle hole separating two adjacent binding sites. For woven floor covering, it may be a filling yarn appearing once on the back for every binding site.

9.3 Locate the zero point at this distinguishing feature of one binding site with a marker.

9.4 Count 40 complete binding sites from this marker and insert another marker at this distinguishing feature of the 40th site.

NOTE 3—Some pile yarn floor coverings exhibit non-straight line binding sites; therefore, counting is facilitated by counting on the back side of the specimen.

9.5 Measure the length,  $L$ , between the marked binding sites with the graduated scale or tape, reading to the nearest 1 mm (0.05 in.).

9.6 Make one measurement on each of the test specimens or specimen areas.

## 10. Calculation

10.1 For each measurement calculate the number of binding sites per unit length (or width) to the nearest 0.1 sites/length (width) using Eq 1.

$$N = 40/L \quad (1)$$