
**Plastics — Determination of permanganate
absorption number of caprolactam —
Spectrometric method**

*Plastiques — Détermination de l'indice d'absorption de permanganate du
caprolactame — Méthode spectrométrique*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8660:2002

<https://standards.iteh.ai/catalog/standards/sist/f51f550-0a4d-48b0-bbc7-9220e35c15ad/iso-8660-2002>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8660:2002

<https://standards.iteh.ai/catalog/standards/sist/f51f550-0a4d-48b0-bbc7-9220e35c15ad/iso-8660-2002>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Term and definition	1
3 Principle	1
4 Reagents	1
5 Apparatus	2
6 Sample	3
7 Procedure	3
8 Calculation	4
9 Precision	4
10 Test report	6

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 8660:2002](https://standards.iteh.ai/catalog/standards/sist/ff51f550-0a4d-48b0-bbc7-9220e35c15ad/iso-8660-2002)

<https://standards.iteh.ai/catalog/standards/sist/ff51f550-0a4d-48b0-bbc7-9220e35c15ad/iso-8660-2002>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 8660 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

This second edition cancels and replaces the first edition (ISO 8660:1988), which has been technically revised.

ITEH STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/f51f550-0a4d-48b0-bbc7-9220e35c15ad/iso-8660-2002>

Introduction

The permanganate index, expressed as the permanganate absorption number (PAN), defines the stability of a caprolactam sample to potassium permanganate in a buffered neutral aqueous solution and is a measure of the purity of the caprolactam in relation to the presence of oxidizable impurities, e.g. unsaturated caprolactams.

Permanganate in a neutral aqueous solution is a strong oxidizing agent, capable of oxidizing the impurities in caprolactam. The determination of the permanganate absorption number is based on measurement of the absorbance of a 3 % (by mass) aqueous caprolactam solution at a wavelength of 420 nm. The measurement is carried out 10 min after adding a potassium permanganate solution of 0,002 mol/l. To correct for the oxidation of water, a blank determination is carried out.

In general, the oxidation reaction with unsaturated organic compounds is faster than with saturated organic compounds. Unsaturated caprolactam is oxidized at a faster rate than saturated caprolactam. The reaction speed depends upon the reducing agent and, in addition to other experimental conditions, strongly on the pH of the solution. The majority of the unsaturated impurities in caprolactam are considered to react within a period of 10 min. The reaction does not end there, however, as the oxidation of slowly oxidizing compounds, e.g. caprolactam, will continue.

The amount of manganese dioxide generated during the reaction is determined at a wavelength of 420 nm. The contribution of caprolactam at this wavelength in the method described here is less than 0,2 % of the total absorbance.

The method is sensitive to external factors and therefore needs to be followed closely. The results obtained with the method in this edition of ISO 8660 are approximately 11 % lower than those obtained with ISO 8660:1988. The difference is due to buffering of the test solution and the blank at pH 7,0. Buffering the solution at a pH of 7,0 results in a significantly higher precision of the method, as fluctuations caused by the acidity/alkalinity of the sample are eliminated.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 8660:2002

<https://standards.iteh.ai/catalog/standards/sist/fb51f550-0a4d-48b0-bbc7-9220e35c15ad/iso-8660-2002>

Plastics — Determination of permanganate absorption number of caprolactam — Spectrometric method

WARNING — This International Standard may involve hazardous chemicals, materials or operations. This standard does not purport to address the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish proper safety and health practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies a spectrometric method for the determination of the permanganate absorption number of caprolactam for industrial use. The permanganate absorption number is a measure of the oxidizable impurities in caprolactam, determined in a buffered neutral aqueous medium under fixed conditions.

The method is applicable to purified caprolactam (and intermediates in the caprolactam purification process) with an alkalinity or acidity lower than 0,50 mmol/kg and a PAN value of up to 35.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

2 Term and definition

For the purposes of this International Standard, the following term and definition apply.

[ISO 8660:2002](#)

2.1 permanganate absorption number PAN

<https://standards.iteh.ai/catalog/standards/sist/f51f550-0a4d-48b0-bbc7-9220e35c15ad/iso-8660-2002>

index based on measurement of the absorbance at 420 nm of a 3 % (by mass) buffered neutral aqueous caprolactam solution in comparison with a blank consisting of buffered water, after addition of a standard solution of potassium permanganate, $c = 0,002$ mol/l, to each and allowing each to stand for 10 min, the absorbance being measured in a cell of pathlength 5 cm

NOTE The PAN is the difference between the absorbance of the test solution and that of the blank, multiplied by 100/3 for a glass cell of pathlength 5 cm.

3 Principle

Equal amounts of potassium permanganate are added to a buffered caprolactam test solution and to a blank consisting of buffered water. After a reaction time of 10 min, the absorbance at a wavelength of 420 nm of the caprolactam test solution and the blank are compared in glass cells with a pathlength of 5 cm.

4 Reagents

During the analysis, use only reagents of recognized analytical grade or of the grade specified.

4.1 Sulfuric acid, p.a., 95 % (by mass) to 97 % (by mass).

4.2 Hydrochloric acid, p.a., 37 % (by mass).

4.3 Oxalic acid dihydrate, $c = 0,1$ mol/l.

4.4 Millipore-Q (or double-distilled) water.

4.5 pH 7,0 buffer salt, exclusively composed of potassium dihydrogen phosphate (40,30 %) and disodium hydrogen phosphate (59,70 %). The salt shall not contain impurities that influence the PAN analysis.

Some commercially available buffer salts contain impurities and/or preservatives which influence the PAN analysis. The suitability of a commercially available buffer salt shall always be tested by comparing the PAN results obtained with this buffer salt with those obtained with a buffer salt made of analytically pure components. The maximum storage time of a commercially available buffer salt or the pure components shall never be exceeded.

4.6 pH 7,0 buffer solution.

Dissolve 3,3 g of the buffer salt (4.5) in Millipore-Q water (4.4) in a 500 ml volumetric flask and make up to the mark with Millipore-Q water. This solution shall be discarded 6 months after preparation (or sooner if any sediment is noticed).

4.7 PAN water.

Add 2,5 ml/l of buffer solution (4.6) to a small quantity of Millipore-Q water in a 1 l volumetric flask, make up to the mark with Millipore-Q water and degas with helium (4.11). Prepare a fresh solution daily. The PAN value of a blank determination shall be $< 0,67$.

4.8 Potassium permanganate, solid, p.a.

4.9 Potassium permanganate stock solution, $c = 0,020$ mol/l.

Store in a brown bottle in the dark. Prepare a fresh solution every 4 weeks. Check the solution every day for manganese dioxide deposit on the walls of the bottle (see the note to 7.1). If any deposit is observed, the solution shall be discarded.

4.10 Potassium permanganate solution, $c = 0,002$ mol/l.

Store in brown bottle in the dark. Prepare a fresh solution weekly from the 0,020 mol/l potassium permanganate solution (4.9). Before use check the solution for manganese dioxide deposit on the walls of the bottle. If any deposit is observed, the solution shall be discarded.

4.11 Helium.

5 Apparatus

Ordinary laboratory apparatus and additionally:

5.1 Spectrometer, suitable for monochromatic analyses at 420 nm, bandwidth ≤ 2 nm.

5.2 Glass cells, pathlength 5 cm.

5.3 Water bath, capable of being maintained at $25,0 \text{ }^\circ\text{C} \pm 0,5 \text{ }^\circ\text{C}$.

5.4 Stopwatch, accurate to at least 0,5 s.

5.5 Glassware, extremely clean and suitable for PAN analyses (see 7.1).

NOTE Disposable syringes and other plastic devices are not suitable because of the extraction capacity of caprolactam. Additives extracted from plastic devices such as syringes have a negative effect on the PAN determination.

5.6 Pipette, made of glass (e.g. a Pasteur pipette), chemically clean (see 7.1).

NOTE Plastic pipettes are not suitable (see note to 5.5).

6 Sample

Caprolactam samples shall be stored in chemically clean, preferably glass, containers. If plastic flasks or containers are used, contact with hot, liquid caprolactam shall be avoided. Caprolactam solutions shall not be stored in plastic containers and any contact with e.g. plastic stoppers shall be avoided (see 5.5).

Samples can consist of pure solid caprolactam or caprolactam solutions. The preferred sample is a solution containing 50 % (by mass) of caprolactam in Millipore-Q water.

NOTE Sampling of pure liquid caprolactam may result in an increase in the PAN value, as a result of oxidation of caprolactam in the presence of air.

7 Procedure

7.1 Cleaning of the glassware

Glassware used for the first time in PAN analysis shall be cleaned successively with

- concentrated sulfuric acid (4.1),
- tap water,
- concentrated hydrochloric acid (4.2),
- Millipore-Q water (4.4).

Glassware used for PAN analysis shall be used for that purpose only and shall be cleaned at least once every 6 months using the above procedure.

Glassware shall be rinsed with tap water (3 times) immediately after the analysis, followed by rinsing 3 times with Millipore-Q water (4.4). Glassware shall be stored closed.

NOTE If the glassware is not rinsed immediately after the analysis, manganese dioxide will settle on the inside surface of the glass. Manganese dioxide catalyses the reaction and has a negative effect on the PAN determination. Manganese dioxide can be removed from the glassware by rinsing with oxalic acid (4.3).

7.2 Purity of the PAN water

Check the PAN water (4.7) by carrying out a blank determination in accordance with 7.3 and calculate its PAN value (see clause 8). If the PAN value is $< 0,67$, the PAN water is acceptable.

For e.g. production control, the blank determination carried out to check the PAN water should preferably be combined with a determination carried out on a control sample. Analysis of further samples should only be carried out if both the blank and the control sample meet the specifications.

If the PAN value of the PAN water is $> 0,67$, repeat the blank determination with a freshly prepared 0,002 mol/l solution of potassium permanganate (4.10) and, if necessary, a fresh 0,020 mol/l stock solution of potassium permanganate (4.9).

If the PAN value is still $> 0,67$, purify the Millipore-Q water by dissolving 1 g of potassium permanganate (4.8) in each litre of Millipore-Q water, storing the solution for 24 h and then distilling with a 600 mm Vigreux column, collecting the first three-quarters of the solution to distill over. Use this purified Millipore-Q water to prepare a fresh solution of PAN water.

If the PAN water still does not meet the specification of $< 0,67$ PAN units (for a glass cell of 5 cm in length, this corresponds to an absorbance of 0,020), the potassium permanganate may be contaminated with manganese dioxide or the PAN water may have too high an impurity content.