NOTICE: This standard has either been superseded and replaced by a new version or discontinued. Contact ASTM International (www.astm.org) for the latest information.



Designation: D 1272 – 56 (Reapproved 1997)^{€1}

Standard Specification for Pentachlorophenol¹

This standard is issued under the fixed designation D 1272; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

 ϵ^1 Note—The AWPA address was updated editorially in October 1997.

1. Scope

1.1 This specification covers dry pentachlorophenol for use in the preservative treatment of wood.

2. Referenced Documents

2.1 ASTM Standards:

This specification is identical in substance with the Standards for Pentachlorophenol in Section 1 of the American Wood-Preservers' Association Standard for Oil-Borne Preservatives (P8-77). Acknowledgement is made to the American Wood Preservatives (preservation for its dayalament of the subject matter equared in D 1274 Test Methods for Chemical Analysis of Pentachlorophenol²

2.2 Other Standard:

AWPA P8 Standards for Oil-Borne Preservatives³

3. Composition and Properties

3.1 Dry pentachlorophenol shall conform to the following requirements:

Chlorinated phenols, min, %	95
Sodium hydroxide insoluble matter, max, %	1
Freezing point, min, °C	174

4. Chemical Analysis

4.1 The material shall be analyzed in accordance with Methods D 1274.

5. Keywords

5.1 pentachlorophenol; preservative

² Annual Book of ASTM Standards, Vol 04.10.

Wood-Preservers' Association for its development of the subject matter covered in ³ Available from American Wood-Preservers' Association, 3246 Fall Creek Highway, Suite 190, Granbury, TX 76049.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

¹ This specification is under the jurisdiction of the ASTM Committee D-7 on Wood and is the direct responsibility of Subcommittee D07.06 on Treatments for Wood Products.

Current edition effective Sept. 10, 1956. Originally issued 1953. Replaces D 1272–53T.