



SLOVENSKI STANDARD
SIST HD 22.1 S2:1998/A13:1998
01-februar-1998

**Rubber insulated cables of rated voltages up to and including 450/750 V - Part 1:
General requirements - Amendment A13**

Rubber insulated cables of rated voltages up to and including 450/750 V -- Part 1:
General requirements

Gummi-isolierte Leitungen mit Nennspannungen bis 450/750 V -- Teil 1: Allgemeine
Anforderungen

Conducteurs et câbles isolés au caoutchouc, de tension assignée au plus égale à
450/750 V -- Partie 1: Prescriptions générales

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/902d671d-e874-4266-8dd4-3d9adab61fa7/sist-hd-22-1-s2-1998-a13-1998>

Ta slovenski standard je istoveten z: HD 22.1 S2:1992/A13:1992

ICS:

29.060.20 Kabli Cables

SIST HD 22.1 S2:1998/A13:1998 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST HD 22.1 S2:1998/A13:1998

<https://standards.iteh.ai/catalog/standards/sist/902d671d-e874-4266-8dd4-3d9adab61fa7/sist-hd-22-1-s2-1998-a13-1998>



HARMONIZATION DOCUMENT

REPUBLIKA SLOVENIJA
 MINISTRSTVO ZA ZNANOST IN TEHNOLOGIJO
 Urad RS za standardizacijo in meroslovje
 LJUBLJANA

HD 22.1 S2/A13

DOCUMENT D'HARMONISATION

HARMONISIERUNGSDOKUMENT

SIST..... HD 22.1 S2/A13
 PREVZET PO METODI RAZGLASITVE

-02- 1998

November 1992

UDC 621.315.211.2.027.475-777.1/.2-777.6.001.2.002.2.001.4(083.71)
 (083.73)621.315.616

Descriptors: see HD 22.1 S2:1992

ENGLISH VERSION

Rubber insulated cables of rated voltages
 up to and including 450/750 V
 Part 1: General requirements

Conducteurs et câbles isolés
 au caoutchouc, de tension
 assignée au plus égale à 450/750 V
 Première partie: Prescriptions
 générales

Isolierte Starkstromleitungen
 mit einer Isolierung aus Gummi
 mit Nennspannungen bis 450/750 V
 Teil 1: Allgemeine Anforderungen

iTeh STANDARD PREVIEW

This amendment modifies the Harmonization Document HD 22.1 S2:1992. It was approved by CENELEC on 1992-09-15. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for implementation of this amendment on a national level.

Up-to-date lists and bibliographical references concerning national implementation may be obtained on application to the Central Secretariat or to any CENELEC member.

This amendment exists in three official versions (English, French and German).

CENELEC members are the national electrotechnical committees of Austria, Belgium, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
 Comité Européen de Normalisation Electrotechnique
 Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B-1050 Brussels

© 1992 Copyright reserved to CENELEC members

Ref. No. HD 22.1 S2:1992/A13:1992 E

FOREWORD

Following a decision taken by CENELEC Technical Committee TC 20 some supplementary common modifications to the International Standard IEC 245-1:1980 were submitted to the CENELEC Unique Acceptance Procedure (UAP) in November 1991 for acceptance as an amendment to HD 22.1 S2.

The text of the draft was approved by CENELEC as amendment A13 to HD 22.1 S2 on 15 September 1992.

The following dates were fixed:

- latest date of announcement
of the amendment at national level (doa) 1993-03-01
- latest date of publication of
a harmonized national standard (dop) 1993-09-01
- latest date of withdrawal of
conflicting national standards (dow) 1993-09-01

For products which have complied with HD 22.1 S2:1992 and its amendments before 1993-09-01, as shown by the manufacturer or by a certification body, this previous standard may continue to apply for production until 1994-09-01.

SIST HD 22.1 S2:1998/A13:1998

[https://standards.iteh.ai/catalog/standards/sist/902d671d-e874-4266-](https://standards.iteh.ai/catalog/standards/sist/902d671d-e874-4266-8dd4-3d9adab011a7/sist-hd-22-1-s2-1998-a13-1998)

[8dd4-3d9adab011a7/sist-hd-22-1-s2-1998-a13-1998](https://standards.iteh.ai/catalog/standards/sist/902d671d-e874-4266-8dd4-3d9adab011a7/sist-hd-22-1-s2-1998-a13-1998)



CLAUSE 2: DEFINITIONS

Add new sub-clause:

2.1.5 Polyolefin based cross-linked compound or other equivalent synthetic compound having a low level of emission of corrosive gases

A crosslinked compound in which the polymer is a polyolefin or equivalent synthetic non-halogenated polymer providing a compound which, when burned, has low emission of corrosive gases and is suitable for use in cables which, when burned, have low emission of smoke.

SUB-CLAUSE 4.2.2: SINGLE CORE NON-SHEATHED CABLES

Amend first sentence to read:

For cable types H07G (Part 7, Clause 2) and H07Z (Part 9, Clause 2 and 3) the following mono-colours are recognised:

TABLE I

Delete existing table and insert attached to include EI 5

SUB-CLAUSE 5.2.1 MATERIAL

Insert new lines:

Type EI 5 for cables insulated with polyolefin-based cross-linked compound having a low level of emission of corrosive gases and which is suitable for use in cables which, when burned, have low emission of smoke.

AND
90°C for compound EI 5.

TABLE III

Insert new section as follows:

1	2	3	4	5	6	7	8
Ref. No.	Test	Unit	Rated voltage of cables			Test method described in	
			300/300V	300/500V	450/750V	HD	Clause
4.	<u>Measurement of insulation resistance</u>					22.2	2.4.1
4.1	Test conditions						
	- length of sample from the previous voltage test (ref. 2 or 3)	m	-	5	5		
	- minimum period of immersion in hot water	h	-	2	2		
	- temperature of the water	°C	-	****	****		
4.2	Results to be obtained	MΩ	-	****	****		

**** See tables in the particular specifications (Part 9)

TABLE I

Requirements for the non-electrical test for cross-linked insulation

1	2	3	4	5	6	7	8	9
Ref. No.	Test	Unit	Type of compound				Test method described in	
			EI 2	EI 3	EI 4	EI 5	HD	Clause
1.	Tensile strength and elongation at break							
1.1	Properties in the state as delivered						505.1.1	9.1
1.1.1	Values to be obtained for the tensile strength: - median, min.	N/mm ²	5.0	6.5	5.0	10.0		
1.1.2	Values to be obtained for the elongation at break: - median, min.	%	150	200	200	125		
1.2	Properties after ageing in air oven						505.1.2	8.1
1.2.1	Ageing conditions: 2) 4) - temperature - duration of treatment	°C	200 ± 3	150 ± 3	100 ± 2	135 ± 2		
			10x24	10x24	7x24	7x24		
1.2.2	Value to be obtained for the tensile strength: - median, min. - variation 1) max.	N/mm ² %	4.0 -	- ± 30	4.2 ± 25	- ± 30		
1.2.3	Values to be obtained for the elongation at break: - median, min. - variation 1) max.	% %	120 -	- ± 30	200 ± 25	- ± 30		
1.3	(Spare)							
1.4	Properties after ageing in the oxygen bomb for seven days						505.1.2	8.3
1.4.1	Ageing conditions: - temperature - duration of treatment	°C h	- -	- -	70 ± 1 7x24	- -		
1.4.2	Value to be obtained for the tensile strength: - median, min. - variation 1) max.	N/mm ² %	- -	- -	- ± 25	- -		
1.4.3	Values to be obtained for the elongation at break: - median, min. - variation 1) max.	% %	- -	- -	- ± 25	- -		

TABLE I
(continued)

1	2	3	4	5	6	7	8	9
Ref. No.	Test	Unit	Type of compound				Test method described in	
			EI 2	EI 3	EI 4	EI 5	HD	Clause
1.5	Properties after ageing in the air bomb						505.1.2	8.2
1.5.1	Ageing conditions							
	- temperature	°C	-	150±2	-	-		
	- duration of treatment	h	-	7x24	-	-		
1.5.2	Values to be obtained for the tensile strength							
	- median, min	N/mm ²	-	6.0	-	-		
1.5.3	Values to be obtained for the elongation at break							
	- variation, max	%	-	-30(3)	-	-		
2.	Hot set test						505.2.1	9
2.1	Conditions of treatment							
	- temperature	°C	250±3	200±3	200±3	200±3		
	- time under load	min	15	15	15	15		
	- mechanical stress	N/cm ²	20	20	20	20		
2.2	Test requirements							
	- max. elongation under load	%	100	100	100	100		
	- max. elongation after unloading	%	25	25	25	25		
3.	Pressure test at high temperature						505.3.1	8
3.1	Test conditions							
	- force exerted by blade							
	- K value :		-	1.0	-	1.0		
	- duration of heating under load 5)	h	-	0.5	-	4or6		
	- temperature	°C	-	150±2	-	100±2		
3.2	Result to be obtained							
	- median of the depth of penetration	%	-	50	-	50		
	max							

TABLE I
(continued)

1	2	3	4	5	6	7	8	9
Ref. No.	Test	Unit	Type of compound				Test method described in	
			EI 2	EI 3	EI 4	EI 5	HD	Clause
4.	Ozone resistance test							
	Method A							
	Test conditions						505.2.1	8
	- test temperature	°C	-	-	25 ± 2	25 ± 2		
	- test duration	h	-	-	24	24		
	- ozone concentration	ppm	-	-	250 to 300	250 to 300		
	Method B						22.2	7.3
	- test temperature	°C	-	-				
	- test duration	h	-	-	40 ± 2	40 ± 2		
	- ozone concentration	pphm	-	-	72	72		
					200 ± 50	200 ± 50		
5.	Low temperature tests							
5.1	Bending test						505.1.4	8.1
5.1.1	Test conditions							
	- temperature	°C	-	-				
	- period of application of low temperature					-15 ± 2	505.1.4	8.1.4 and 8.1.5
5.1.2	Result to be obtained		-	-				
5.2	Elongation test					No cracks	505.1.4	8.3
5.2.1	Test conditions							
	- temperature	°C	-	-				
	- period of application of low temperature		-	-		-15 ± 2	505.1.4	8.3.4 and 8.3.5
						**		
5.2.2	Result to be obtained							
	- elongation without break (min)	%	-	-		30		
5.3	Impact test						505.1.4	8.5
5.3.1	Test conditions							
	- temperature	°C	-	-				
	- period of application of low temperature		-	-		-15 ± 2	505.1.4	8.5.5
	- mass of hammer		-	-		**	505.1.4	8.5.4
5.3.2	Result to be obtained		-	-		**	505.1.4	8.5.6